

First edition
2013-11-15

Corrected version
2014-11-01

**Paints and varnishes — Methods of
exposure to laboratory light sources —
Part 3:
Fluorescent UV lamps**

*Peintures et vernis — Méthodes d'exposition à des sources lumineuses
de laboratoire —*

Partie 3: Lampes fluorescentes UV

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 16474-3:2013

<https://standards.iteh.ai/catalog/standards/sist/855c6583-b06d-466b-9731-6f743c937796/iso-16474-3-2013>



Reference number
ISO 16474-3:2013(E)

© ISO 2013

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 16474-3:2013

<https://standards.iteh.ai/catalog/standards/sist/855c6583-b06d-466b-9731-6f743c937796/iso-16474-3-2013>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2013

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	2
5 Apparatus	3
5.1 Laboratory light source.....	3
5.2 Test chamber.....	6
5.3 Radiometer.....	6
5.4 Black-standard/black-panel thermometer.....	6
5.5 Wetting and humidity.....	7
5.6 Specimen holders.....	7
5.7 Apparatus to assess changes in properties.....	7
6 Test specimens (panels)	7
6.1 General.....	7
6.2 Preparation and coating.....	8
6.3 Drying and conditioning.....	8
6.4 Thickness of coating.....	8
6.5 Number of test panels.....	8
7 Test conditions	8
7.1 Radiation.....	8
7.2 Temperature.....	8
7.3 Relative humidity of chamber air.....	9
7.4 Condensation and spray cycles.....	9
7.5 Complex cycles with dark periods.....	9
7.6 Sets of exposure conditions.....	9
8 Procedure and mounting of the test specimens	10
8.1 General.....	10
8.2 Exposure.....	10
8.3 Measurement of radiant exposure.....	11
8.4 Determination of changes in properties after exposure.....	11
9 Test report	11
Annex A (informative) Spectral distribution of radiation for typical fluorescent UV lamps	12
Bibliography	16

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information \(standards.iteh.ai\)](http://Foreword - Supplementary information (standards.iteh.ai))

The committee responsible for this document is ISO/TC 35, *Paints and varnishes*, Subcommittee SC 9, *General test methods for paints and varnishes*.

This first edition of ISO 16474-3, together with ISO 16474-1 cancels and replaces ISO 11507:2007, which has been technically revised.

ISO 16474 consists of the following parts, under the general title *Paints and varnishes — Methods of exposure to laboratory light sources*:

- *Part 1: General guidance*
- *Part 2: Xenon-arc lamps*
- *Part 3: Fluorescent UV lamps*
- *Part 4: Open-flame carbon-arc lamps*

This corrected version of ISO 16474-3:2013 incorporates the following corrections.

- In 7.4, “method B” has been replaced by “method A, cycle No. 2”.
- In 7.6, “(method A)” has been replaced by “(method A, cycle No. 1)” and “(method B)” has been replaced by “(method A, cycle No. 2)”.

Introduction

Coatings of paints, varnishes and similar materials (subsequently referred to simply as coatings) are exposed to laboratory light sources, in order to simulate in the laboratory the ageing processes which occur during natural weathering or behind window glass.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 16474-3:2013

<https://standards.iteh.ai/catalog/standards/sist/855c6583-b06d-466b-9731-6f743c937796/iso-16474-3-2013>

iTeh STANDARD PREVIEW **(standards.iteh.ai)**

ISO 16474-3:2013

<https://standards.iteh.ai/catalog/standards/sist/855c6583-b06d-466b-9731-6f743c937796/iso-16474-3-2013>

Paints and varnishes — Methods of exposure to laboratory light sources —

Part 3: Fluorescent UV lamps

1 Scope

This part of ISO 16474 specifies methods for exposing coatings to fluorescent UV lamps, heat and water in apparatus designed to reproduce the weathering effects that occur when materials are exposed in actual end-use environments to daylight, or to daylight through window glass.

The coatings are exposed to different types of fluorescent UV lamps under controlled environmental conditions (temperature, humidity and/or water). Different types of fluorescent UV lamp may be used to meet all the requirements for testing different materials.

Specimen preparation and evaluation of the results are covered in other ISO documents for specific materials.

General guidance is given in ISO 16474-1.

NOTE Fluorescent UV lamp exposures for plastics are described in ISO 4892-3.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1514, *Paints and varnishes — Standard panels for testing*

ISO 2808, *Paints and varnishes — Determination of film thickness*

ISO 4618, *Paints and varnishes — Terms and definitions*

ISO 9370, *Plastics — Instrumental determination of radiant exposure in weathering tests — General guidance and basic test method*

ISO 16474-1, *Paints and varnishes — Methods of exposure to laboratory light sources — Part 1: General guidance*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 4618 and the following apply.

3.1

radiant exposure

H

amount of radiant energy to which a test panel has been exposed

Note 1 to entry: Radiant exposure is given by the equation $H = \int E \cdot dt$

where

H is the radiant exposure, in joules per square metre;

E is the irradiance, in watts per square metre;

t is the exposure time, in seconds

Note 2 to entry: If the irradiance E is constant throughout the whole exposure time, the radiant exposure H is given simply by the product of E and t .

4 Principle

4.1 Fluorescent UV lamps, when properly maintained, can be used to simulate the spectral irradiance of daylight in the ultraviolet (UV) region of the spectrum.

4.2 Specimens are exposed to various levels of UV radiation, heat and moisture (see [4.4](#)) under controlled environmental conditions.

4.3 The exposure conditions may be varied by selection of:

- a) the type of fluorescent lamp (spectral power distribution);
- b) the irradiance level;
- c) the temperature during the UV exposure;
- d) the relative humidity of the chamber air during the light and dark exposures, when test conditions requiring control of humidity are used;

NOTE Commercial fluorescent UV lamp devices mostly do not provide means of relative humidity control.

- e) the type of wetting (see [4.4](#));
- f) the wetting temperature and cycle;
- g) the timing of the UV/dark cycle.

4.4 Wetting is usually produced by condensation of water vapour onto the exposed specimen surface or by spraying the test specimens with demineralized/deionized water.

4.5 The procedure(s) may include measurement of the irradiance and the radiant exposure in the plane of the specimen.

4.6 It is recommended that a similar material of known performance (a control) be exposed simultaneously with the test specimens to provide a standard for comparative purposes.

4.7 Intercomparison of results obtained from specimens exposed in different apparatus or to different types of lamp should not be made unless an appropriate statistical relationship has been established between the different types of equipment for the material to be tested.

5 Apparatus

5.1 Laboratory light source

5.1.1 Fluorescent UV lamps are fluorescent lamps in which radiant emission in the ultraviolet region of the spectrum, i.e. below 400 nm, makes up at least 80 % of the total light output. There are three types of fluorescent UV lamp used in this part of ISO 16474:

- Type 1A (UVA-340) fluorescent UV lamp: These lamps have a radiant emission below 300 nm of less than 1 % of the total light output, have an emission peak at 343 nm, and are more commonly identified as UVA-340 for simulation of daylight from 300 nm to 340 nm (see [Table 1](#), column [A.1](#)). [Figure A.1](#) is a graph of spectral irradiance from 250 nm to 400 nm of a typical type 1A (UVA-340) fluorescent lamp compared to daylight.
- Type 1B (UVA-351) fluorescent UV lamp: These lamps have a radiant emission below 310 nm of less than 1 % of the total light output, have a peak emission at 353 nm, and are more commonly identified as UVA-351 for simulation of the UV portion of daylight behind window glass (see [Table 2](#)). [Figure A.2](#) is a graph of spectral irradiance from 250 nm to 400 nm of a typical type 1B (UVA-351) fluorescent UV lamp compared to daylight filtered by window glass.
- Type 2 (UVB-313) fluorescent UV lamp: These lamps are more commonly identified as UVB-313 and have a radiant emission below 300 nm that is more than 10 % of the total output and a peak emission at 313 nm (see [Table 3](#)). [Figure A.3](#) is a graph of the spectral irradiance from 250 nm to 400 nm of two typical type 2 (UVB-313) fluorescent lamps compared to daylight. Type 2 (UVB-313) lamps may be used only by agreement between the parties concerned. Such agreement shall be stated in the test report.

NOTE 1 Type 2 (UVB-313) lamps have a spectral distribution of radiation which peaks near the 313 nm mercury line and might emit radiation down to $\lambda = 254$ nm, which can initiate ageing processes that never occur in end-use environments.

NOTE 2 The solar spectral irradiance for a number of different atmospheric conditions is described in CIE No. 85.[2] The benchmark daylight used in this part of ISO 16474 is from CIE No. 85:1989, Table 4.

5.1.2 Unless otherwise specified, type 1A (UVA-340) fluorescent UV lamps or corresponding type 1A fluorescent UV lamp combinations shall be used to simulate the UV part of daylight (see [Table 4](#), method A). Unless otherwise specified, type 1B (UVA-351) lamps shall be used to simulate the UV part of daylight through window glass (see [Table 4](#), method B).

5.1.3 Fluorescent lamps age significantly with extended use. If an automatic irradiance control system is not used, follow the apparatus manufacturer's instructions on the procedure necessary to maintain the desired irradiance.

5.1.4 Irradiance uniformity shall be in accordance with the requirements specified in ISO 16474-1. Requirements for periodic repositioning of specimens when irradiance within the exposure area is less than 90 % of the peak irradiance are described in ISO 16474-1.

Table 1 — Relative ultraviolet spectral irradiance for type 1A lamps for daylight UV (method A) ^{a, b}

Spectral pass-band	Minimum ^c	CIE No. 85:1989, Table 4 ^{d,e}	Maximum ^c
(λ = wavelength in nm)	%	%	%
$\lambda < 290$		0	0,1
$290 \leq \lambda \leq 320$	5,9	5,4	9,3
$320 < \lambda \leq 360$	60,9	38,2	65,5
$360 < \lambda \leq 400$	26,5	56,4	32,8

^a This table gives the irradiance in the given passband, expressed as a percentage of the total irradiance between 290 nm and 400 nm. To determine whether a specific type 1A (UVA-340) lamp meets the requirements of this table, the spectral irradiance from 250 nm to 400 nm shall be measured. Typically, this is done in 2 nm increments. The total irradiance in each passband is then summed and divided by the total irradiance between 290 nm and 400 nm.

^b The minimum and maximum limits for type 1A (UVA-340) lamps in this table are based on more than 60 spectral irradiance measurements with type 1A (UVA-340) lamps from different production lots and of various ages.^[3] The spectral irradiance data are for lamps within the ageing recommendations of the apparatus manufacturer. As more spectral irradiance data become available, minor changes in the limits are possible. The minimum and maximum limits are at least three sigma from the mean for all the measurements. The range of the relative irradiance of fluorescent UV lamp combinations is determined by radiation measurements at about 50 locations within the exposure area recommended by the apparatus manufacturer.

^c The minimum and maximum columns will not necessarily sum to 100 % because they represent the minima and maxima for the measurement data used. For any individual spectral irradiance distribution, the percentages calculated for the pass-bands in this table will sum to 100 %. For any individual type 1A (UVA-340) fluorescent lamp, the calculated percentage in each pass-band shall fall within the minimum and maximum limits given. Test results can be expected to differ between exposures using type 1A (UVA-340) lamps in which the spectral irradiance differs by as much as that allowed by the tolerances. Contact the manufacturer of the fluorescent UV apparatus for specific spectral irradiance data for the type 1A (UVA-340) lamp used.

^d The data from CIE No. 85:1989, Table 4, is the global solar irradiance on a horizontal surface for an air mass of 1,0, an ozone column of 0,34 cm at STP, 1,42 cm of precipitable water vapour and a spectral optical depth of aerosol extinction of 0,1 at 500 nm. These data are provided for reference purposes only and are intended to serve as a target.

^e For the solar spectrum represented by CIE No. 85:1989, Table 4, the UV irradiance (290 nm to 400 nm) is 11 % and the visible irradiance (400 nm to 800 nm) is 89 %, expressed as a percentage of the total irradiance from 290 nm to 800 nm. Because the primary emission of fluorescent UV lamps is concentrated in the 300 nm to 400 nm pass-band, there are limited data available for the visible light emission of fluorescent UV lamps. The percentages of UV irradiance and visible irradiance on specimens exposed in fluorescent UV apparatus might vary due to the number of specimens being exposed and their reflectance properties.

Table 2 — Relative ultraviolet spectral irradiance for type 1B (UVA 351) lamps for daylight behind window glass (method B) ^{a, b}

Spectral pass-band	Minimum ^c	CIE No. 85:1989, Table 4, plus effect of window glass ^{d,e}	Maximum ^c
(λ = wavelength in nm)	%	%	%
$\lambda < 300$		0	0,2
$300 \leq \lambda \leq 320$	1,1	≤ 1	3,3
$320 < \lambda \leq 360$	60,5	33,1	66,8
$360 < \lambda \leq 400$	30,0	66,0	38,0

^a This table gives the irradiance in the given pass-band, expressed as a percentage of the total irradiance between 290 nm and 400 nm. To determine whether a specific type 1B (UVA-351) lamp meets the requirements of this table, the spectral irradiance from 250 nm to 400 nm shall be measured. Typically, this is done in 2 nm increments. The total irradiance in each pass-band is then summed and divided by the total irradiance between 290 nm and 400 nm.

^b The minimum and maximum limits given in this table are based on 21 spectral irradiance measurements with type 1B (UVA-351) lamps from different production lots and of various ages. [3] The spectral irradiance data are for lamps within the ageing recommendations of the apparatus manufacturer. As more spectral irradiance data become available, minor changes in the limits are possible. The minimum and maximum limits are at least three sigma from the mean for all the measurements.

^c The minimum and maximum columns will not necessarily sum to 100 % because they represent the minima and maxima for the measurement data used. For any individual spectral irradiance distribution, the percentages calculated for the pass-bands in this table will sum to 100 %. For any individual type 1B (UVA-351) fluorescent lamp, the calculated percentage in each pass-band shall fall within the minimum and maximum limits given. Test results can be expected to differ between exposures using type 1B (UVA-351) lamps in which the spectral irradiance differs by as much as that allowed by the tolerances. Contact the manufacturer of the fluorescent UV apparatus for specific spectral irradiance data for the type 1B (UVA-351) lamp used.

^d The data from CIE No. 85:1989, Table 4, plus the effect of window glass was determined by multiplying the CIE No. 85:1989, Table 4 data by the spectral transmittance of typical 3-mm-thick window glass (see ISO 16474-2, Annex A). These data are provided for reference purposes only and are intended to serve as a target.

^e For the solar spectrum represented by CIE No. 85:1989, Table 4, plus window glass data, the UV irradiance from 300 nm to 400 nm is typically about 9 % and the visible irradiance (400 nm to 800 nm) is typically about 91 %, expressed as a percentage of the total irradiance from 300 nm to 800 nm. Because the primary emission of fluorescent UV lamps is concentrated in the 300 nm to 400 nm passband, there are limited data available for the visible light emission of fluorescent UV lamps. The percentages of UV irradiance and visible irradiance on specimens exposed in fluorescent UV apparatus might vary due to the number of specimens being exposed and their reflectance properties.