# INTERNATIONAL STANDARD

First edition 2012-06-01

Plastics piping systems for the supply of gaseous fuels — Unplasticized polyamide (PA-U) piping systems with fusion jointing and mechanical jointing —

Part 6:

# Code of practice for design, handling iTeh STand installation EVIEW

#### (standards itch ai) Systèmes de canalisations en matières plastiques pour la

distribution de combustibles gazeux — Systèmes de canalisations en polyamide non plastifié (PA-U) avec assemblages par soudage et https://standards.iteh.a/stemptages/mecahique8-79ec-45ad-9503-

Partie 6: Code de pratique pour la conception, la manutention



Reference number ISO 16486-6:2012(E)

# iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>ISO 16486-6:2012</u> https://standards.iteh.ai/catalog/standards/sist/51242cf2-79ee-45ad-9503f908705a6dcb/iso-16486-6-2012



#### **COPYRIGHT PROTECTED DOCUMENT**

#### © ISO 2012

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office Case postale 56 • CH-1211 Geneva 20 Tel. + 41 22 749 01 11 Fax + 41 22 749 09 47 E-mail copyright@iso.org Web www.iso.org

Page

### Contents

Fore	word	iv
Introduction		v
1	Scope	1
2	Normative references	1
3	Terms and definitions	
4	Symbols and abbreviated terms	2
5 5.1 5.2 5.3 5.4 5.5	Design General Materials, components and jointing equipment Maximum operating pressure Assembly techniques Squeeze-off properties.	3 3 3 3 3 4 4
6 6.1 6.2 6.3 6.4 6.5	Installation Jointing procedure Training Heated-tool fusion jointing Electrofusion jointing Laying	
7 7.1 7.2 7.3 7.4	Storage, handling and transport NDARD PREVIEW General Storage (Standards.iteh.ai) Handling Transport ISO 16486-6:2012	
8 8.1 8.2 8.3	Quality control General Inspection prior to laying Inspection during laying	
Anne	ex A (normative) Derating coefficients for operating temperatures	
Bibli	ography	20

### Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 16486-6 was prepared by Technical Committee ISO/TC 138, *Plastics pipes, fittings and valves for the transport of fluids*, Subcommittee SC 4, *Plastics pipes and fittings for the supply of gaseous fuels*.

This first edition of ISO 16486-6 cancels and replaces the first edition of ISO 22621-6:2010 which has been technically revised.

ISO 16486 consists of the following parts, under the general title *Plastics piping systems for the supply of gaseous fuels* — *Unplasticized polyamide (PA-U) piping systems with fusion jointing and mechanical jointing*:

— Part 1: General

## (standards.iteh.ai)

- Part 2: Pipes
- *ISO* 16486-6:2012 *Part 3: Fittings* https://standards.iteh.ai/catalog/standards/sist/51242cf2-79ee-45ad-9503-
- f908705a6dcb/iso-16486-6-2012
- Part 5: Fitness for purpose of the system
- Part 6: Code of practice for design, handling and installation

### Introduction

Thin wall thickness unplasticized polyamide (PA-U) pipes and solvent cement joints are used typically for low pressures, while thicker wall thickness pipes and butt fusion, electrofusion or mechanical joints are typically used for high pressures.

For technical and safety reasons, it is not possible to mix the components of the two types of piping system (thin wall thickness pipes cannot be jointed by butt fusion or mechanical joints and vice versa). In particular, solvent cement joints must not be used for jointing for high pressure piping systems.

So for the time being, the standardization programme dealing with unplasticized polyamide (PA-U) piping systems for the supply of gaseous fuels is split into two series of International Standards, with one series (ISO 17467) covering piping systems the components of which are connected by solvent cement jointing and the other (ISO 16486) the components of which are connected by fusion jointing and/or mechanical jointing. When more experience will be gained from the field, it might be reasonable to merge the ISO 17467 series and the ISO 16486 series in one single series applicable to PA-U piping systems.

A similar series (ISO 17135) for fusion and mechanically jointed plasticized polyamide (PA-P) piping systems is in preparation.

# iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>ISO 16486-6:2012</u> https://standards.iteh.ai/catalog/standards/sist/51242cf2-79ee-45ad-9503f908705a6dcb/iso-16486-6-2012

# iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>ISO 16486-6:2012</u> https://standards.iteh.ai/catalog/standards/sist/51242cf2-79ee-45ad-9503f908705a6dcb/iso-16486-6-2012

### Plastics piping systems for the supply of gaseous fuels — Unplasticized polyamide (PA-U) piping systems with fusion jointing and mechanical jointing —

## Part 6: Code of practice for design, handling and installation

#### 1 Scope

This part of ISO 16486 specifies a code of practice dealing with unplasticized polyamide (PA-U) piping systems, intended to be buried outside buildings and used for the supply of gaseous fuels. It addresses the common basic principles for gas supply systems.

More detailed national standards or codes of practice might exist in the ISO member countries. This part of ISO 16486 is intended to be applied in association with those national standards or codes of practice related to the above-mentioned basic principles.

It is applicable to mains and service lines, the components of which are prepared for jointing by scraping and/or machining, and gives instructions for the design, storage, handling, transportation, laying conditions and fusion quality control of PA-U pipes and fittings up to and including 250 mm outside diameter, as well as subsequent joint testing, backfilling, pipe system testing, commissioning and decommissioning.

The jointing methods covered by this part of ISO 16486 are butt fusion jointing and electrofusion jointing. <u>ISO 16486-6:2012</u>

No special precautions are necessary for areas exposed to the influence of mining and earthquakes other than those precautions mentioned in this part of ISO 16486,486-6-2012

It is the responsibility of users of this part of ISO 16486 to take existing and new national regulations into account.

#### 2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 12162, Thermoplastics materials for pipes and fittings for pressure applications — Classification, designation and design coefficient

ISO 12176-1, Plastics pipes and fittings — Equipment for fusion jointing polyethylene systems — Part 1: Butt fusion

ISO 12176-2, Plastics pipes and fittings — Equipment for fusion jointing polyethylene systems — Part 2: Electrofusion

ISO 12176-3, Plastics pipes and fittings — Equipment for fusion jointing polyethylene systems — Part 3: Operator's badge

EN 12327, Gas supply systems — Pressure testing, commissioning and decommissioning procedures — Functional requirements

ISO 16486-1, Plastics piping systems for the supply of gaseous fuels — Unplasticized polyamide (PA-U) piping systems with fusion jointing and mechanical jointing — Part 1: General

ISO 16486-2, Plastics piping systems for the supply of gaseous fuels — Unplasticized polyamide (PA-U) piping systems with fusion jointing and mechanical jointing — Part 2: Pipes

ISO 16486-3, Plastics piping systems for the supply of gaseous fuels — Unplasticized polyamide (PA-U) piping systems with fusion jointing and mechanical jointing — Part 3: Fittings

ISO 16486-5, Plastics piping systems for the supply of gaseous fuels — Unplasticized polyamide (PA-U) piping systems with fusion jointing and mechanical jointing — Part 5: Fitness for purpose of the system

#### 3 Terms and definitions

For the purposes of this document, the terms, definitions, symbols and abbreviated terms given in ISO 16486-1 and ISO 16486-5 and the following apply.

#### 3.1

#### butt fusion machine pressure

pressure indicated on the manometer or on a pressure display on a butt fusion machine, giving an indication of the interface force applied to the pipe or fitting ends

#### 3.2

#### clearance

shortest distance between the outer limits of two objects

#### 3.3

#### drag resistance

frictional resistance due to the weight of the length of pipe fixed in the moveable clamp at the point at which movement of the moveable clamp is initiated (peak drag), or the friction occurring during movement (dynamic drag)

#### 3.4

# iTeh STANDARD PREVIEW

electrofusion control box unit implementing the output fusion parameters of voltage of current and time or energy to execute the fusion cycle as specified by the electrofusion fitting manufacturer

#### ISO 16486-6:2012

3.5 https://standards.iteh.ai/catalog/standards/sist/51242cf2-79ee-45ad-9503-

frictional losses in the butt fusion machine 08705a6dcb/iso-16486-6-2012

force necessary to overcome friction in the whole mechanism of a butt fusion machine

#### 3.6

#### interface force

force between the fusion surfaces of the pipe(s) and/or fitting(s) during the fusion cycle, as specified in the fusion diagram

#### 3.7

#### operator

person authorized to build PA-U systems from pipes and/or fittings, based on a written procedure agreed by the pipeline operator

#### 3.8

#### pipeline operator

private or public organization authorized to design, construct or operate and maintain a gas supply system

#### 3.9

#### soil cover

vertical distance between the top of a buried pipe and the normal surface after finishing work

#### 4 Symbols and abbreviated terms

C design coefficient

- CRS categorized required strength
- *d*e outside diameter of pipe at any point

- *D*<sub>F</sub> derating coefficient
- MOP maximum operating pressure
- MRS minimum required strength
- RCP rapid crack propagation
- SDR standard dimension ratio

#### 5 Design

#### 5.1 General

A written laying procedure, authorized by the pipeline operator, shall be made available prior to the construction of a pipeline. The laying procedure shall include specification of the jointing procedure, the pipe and fitting materials to be used, the trenching and backfilling requirements, the pressure testing and commissioning requirements, and the data to be collected for the traceability system.

The selection of materials, SDR series, dimensions and assembling techniques shall be the responsibility of the pipeline operator.

There are two SDR series in common use for gas supply systems: SDR 17 and SDR 11. Other SDR series can also be used, such as SDR 26 for renovation.

The training and the level of skill of the operator shall be in accordance with the requirements of the jointing procedures.

General guidelines for supervision and quality control are given in Clause 8.

#### 5.2 Materials, components and jointing equipment

https://standards.iteh.ai/catalog/standards/sist/51242cf2-79ee-45ad-9503-The PA-U materials and components used shall conform to ISO 16486-1, ISO 16486-2 and ISO 16486-3, as relevant.

Other components not covered by the above-mentioned parts of ISO 16486 shall conform to the relevant national standards.

If pipes and fittings are to be stored outside, requirements on maximum storage time shall be given in the laying procedure. PA-U materials shall be stabilized to give protection against a UV radiation level of 3,5 GJ/m<sup>2</sup>. It is desirable that national bodies give recommendations for allowed storage times in their countries.

The fusion equipment used for the construction of the pipeline shall comply with the requirements of ISO 12176-1 or ISO 12176-2. If the operation of the fusion equipment requires an operator's badge, the badge shall conform to ISO 12176-3.

#### 5.3 Maximum operating pressure

The maximum operating pressure (MOP) of the system shall be selected by the pipeline operator on the basis of the gas supply system operating requirements and the materials used. The MOP of a PA-U system depends upon the type of resin used (the MRS), the pipe SDR series and the service conditions, and is limited by the design coefficient, *C*, and the RCP criteria.

For greater flexibility in the use of the MRS, the  $CRS_{\theta,t}$  is introduced, where the temperature  $\theta$  and the lifetime *t* may differentiate from the usual values of 20 °C and 50 years. The policy retains the well-established MRS basis for the classification of polyamide materials in accordance with ISO 12162. The categorized required strength,  $CRS_{\theta,t}$ , is defined in ISO 12162.

The design coefficient, *C*, for thermoplastics materials is specified in ISO 12162. This coefficient is used to calculate the MOP of the pipeline. *C* shall be greater than or equal to 2 for PA-U pipeline systems for natural gas.

$$MOP = \frac{20 \times MRS}{C \times (SDR - 1) \times D_{\mathsf{F}}} \tag{1}$$

or

$$MOP = \frac{20 \times CRS_{\theta,t}}{C \times (SDR - 1)}$$
(2)

The derating coefficient,  $D_{F}$ , is a coefficient used in the calculation of the MOP which takes into account the influence of the operating temperature. Derating coefficients for various operating temperatures are given in Annex A.

The ratio of the critical RCP pressure to the MOP shall be  $\geq$  1,5 at the minimum operating temperature. The critical RCP pressure is dependent on temperature, pipe size and type of PA-U material used. It is defined in this subclause in accordance with ISO 16486-1, Table 1, based on the full-scale test method in accordance with ISO 13478 (see Table footnote e).

Where the pipe temperature decreases below 0 °C, the  $p_c/MOP$  ratio shall be recalculated using a  $p_c$  (critical pressure) value determined from the minimum expected operating temperature of the pipe. If necessary, the value of the MOP shall be reduced so as to maintain the  $p_c/MOP$  ratio at a value  $\geq$  1,5.

#### 5.4 Assembly techniques

# Jointing procedures may vary depending Spon the pipe size used PREVIEW

Fusion is the preferred jointing method. Preference shall be given to butt lusion and electrofusion.

Components made from PA-U 11 shall be heat fusion jointed only to components made from PA-U 11.

Components made from PA-UP12 shall be heat fusion jointed only to components made from PA-U 12. 1908705a6dcb/iso-16486-6-2012

Components made from PA-U are not fusion compatible with components made from other polymers.

A written jointing procedure, authorized by the pipeline operator, shall be available prior to the construction of a pipeline. The jointing procedure shall include specification of the jointing method, the fusion parameters, the fusion equipment, the jointing conditions, the level of skill of the operator, and the quality control methods to be used.

#### 5.5 Squeeze-off properties

When squeeze-off techniques are considered, the suitability of the pipe for squeeze-off shall be established in accordance with the manufacturer's recommendations.

#### 6 Installation

#### 6.1 Jointing procedure

The jointing operation shall be performed in accordance with the pipeline operator's written procedure and shall take into account the procedures outlined in ISO 16486-5:2012, Annex A, for butt fusion jointing and ISO 16486-5:2012, Annex B, for electrofusion jointing.

PA-U pipes, fittings and accessories may be jointed by heated-tool fusion jointing or electrofusion jointing. The jointing and quality control methods used for the construction of the gas supply system shall be appropriate to the design of the network and take into account the requirements of ISO 16486-5.

#### 6.2 Training

The operator shall be competent in the appropriate laying and jointing methods. He or she shall possess the necessary skill and knowledge to produce joints of consistently high quality.

Operators shall receive formal training under the supervision of a qualified instructor. The gas company may require a certificate indicating that the operator has reached an adequate standard in accordance with national or local regulations.

#### 6.3 Heated-tool fusion jointing

#### 6.3.1 General

Heated-tool fusion joints shall be made under defined conditions of pressure, time and temperature, using a written procedure (see 6.1). Mating surfaces are heated to their fusion temperature and then brought into contact with one another.

#### 6.3.2 Fusion temperature

The production of a strong fusion bond depends, among other things, upon the fusion temperature of the polyamide material: overheating may degrade the material, and insufficient heating will not soften it adequately.

The temperature range over which any particular polyamide material may be satisfactorily jointed shall be considered. The jointing procedure shall specify the heating cycle and the temperature levels for the polyamide material selected. **Teh STANDARD PREVIEW** 

Cold weather and wind can adversely affect the fusion temperature. Under these circumstances, special precautions, such as shielding, end caps and longer heating times shall be considered.

#### 6.3.3 Fusion equipment

<u>ISO 16486-6:2012</u>

https://standards.iteh.ai/catalog/standards/sist/51242cf2-79ee-45ad-9503-

The butt fusion equipment used shall conform to ISO 12176-7.012

As high-quality fusion joints cannot be made with fusion equipment in poor condition, maintenance of the fusion equipment is very important and shall be carried out on a regular basis. The cleanliness and integrity of the heating surfaces, the ability of the heating tools to produce the correct temperature and the correct alignment and operation of the equipment when used are of paramount importance.

The heating tools are designed to maintain uniform temperatures within the fusion temperature range of the particular polyamide material and shall have calibrated means of measuring and indicating the temperature. A precise temperature measurement device such as a pyrometer or a digital thermometer with a surface temperature sensor may be used to check the surface temperature of the heating tools, although additional care is necessary to avoid inconsistency of readings when such a device is used.

All heating tools used shall be electrically heated.

#### 6.3.4 Butt fusion

#### 6.3.4.1 Principle

The butt fusion technique consists of heating the planed ends of the mating surfaces by holding them against a flat heating plate until molten, removing the heating plate, pushing the two softened ends against one another, holding under pressure for a prescribed time and allowing the joint to cool (see Figure 1).