NOTICE: This standard has either been superseded and replaced by a new version or withdrawn. Contact ASTM International (www.astm.org) for the latest information



Designation: D 2200 – 95 (Reapproved 2001) $^{\epsilon^2}$

Swedish Standards Association Standard SIS 05 59 00 ISO 8501 Steel Structures Painting Council SSPC-Vis 3 Danish Standards Association Danish Standard DS 2019 European Committee of Paint and Printing Ink Manufacturers' Association

Standard Pictorial Surface Preparation Standards for Painting Steel Surfaces¹

This standard is issued under the fixed designation D 2200; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

 ϵ^1 Note—Footnotes were corrected editorially in June 2001.

 ϵ^2 Note—Referenced Documents section was corrected editorially in October 2007.

1. Scope

1.1 The visual surface preparation standards consist of a series of color prints available as separate publications. Three different sets of photographs are described in this standard, designated as Method A (ISO/Swedish Standard²) and Method B and C (SSPC Standards³). The three methods differ in the depiction of the initial surface, in the definition and depiction of the cleaning conditions, and in the number of cleaning methods included. Because of these differences, the specifier should state whether Method A, Method B, or C should be used.

1.2 The colored visual surface preparation standards represent different conditions of hot rolled steel before and after surface preparation. Prior to cleaning, there are four rust grades, A to D, that cover the range from intact mill scale to 100 % rusted and pitted steel. The standards then depict the appearance of the four grades after cleaning by one or more methods (for example, blast cleaning) to various degrees of thoroughness. In addition, Method C includes three painted conditions that contain various degrees of rusting. The Standard⁴ depicts these conditions after various grades of hand and power tool cleaning.

2. Referenced Documents

2.1 Other Standards:

- ISO 8501–1 Preparation of Steel Substrates Before Application of Paints and Related Products—Visual Assessment of Surface Cleanliness^{3,4}
- SSPC VIS 1 Visual Standard For Abrasive Blast Cleaned Steel^{2,3,4}
- **SSPC VIS 3** Guide and Reference Photographs for Steel Surfaces Prepared by Hand and Power Tool Cleaning^{2,3,4}

3. Terminology

3.1 *Definitions:*

3.1.1 The cleanliness definitions for the Method A visual surface preparation standard appear in the text of the pictorial surface preparation standards publication.² The definitions for Methods B and C are found in a separate publication.^{3,4}

4. Significance and Use

4.1 The appearance of the various degrees of blast cleaning are influenced by the initial rust grades of the steel being cleaned. The standards aid visually in judging and evaluating the degree of rusting before cleaning and the degree of cleaning of steel surfaces prior to painting.

4.2 Three methods for visual standards have evolved because of differences in the practice of using visual standards

Copyright © ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States.

¹ This standard is under the jurisdiction of ASTM Committee D01 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.46 on Industrial Protective Coatings.

The pictorial standards described were prepared by the Swedish Corrosion Institute and have been jointly approved by ASTM, The Society For Protective Coatings (SSPC) (Vis 1), and the Swedish Standardizing Commission.

Current edition approved June 10, 2001. Published June 2001. Originally approved in 1966. Last previous edition approved in 1995 as D 2200 – 95.

² The pictorial surface preparation standard Method A is available from The Society for Protective Coatings (SSPC), 40 24th St., 6th Floor, Pittsburgh, PA 15222-4656, http://www.sspc.org and Sveriges Standardiseringskommission, Box 3295, Stockholm 3, Sweden.

³ The Visual Standards Method B and surface cleanliness definitions are available from The Society for Protective Coatings (SSPC), 40 24th St., 6th Floor, Pittsburgh, PA 15222-4656, http://www.sspc.org.

⁴ The Visual Standards Method C and the surface cleanliness definitions are available from The Society for Protective Coatings (SSPC), 40 24th St., 6th Floor, Pittsburgh, PA 15222-4656, http://www.sspc.org.