



Designation: D 4548 – 91 (Reapproved 1996)

AMERICAN SOCIETY FOR TESTING AND MATERIALS
100 Barr Harbor Dr., West Conshohocken, PA 19428
Reprinted from the Annual Book of ASTM Standards. Copyright ASTM

Standard Test Method for Anion-Cation Balance of Mixed Bed Ion-Exchange Resins¹

This standard is issued under the fixed designation D 4548; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method determines the ratio between the equivalents of anion-exchange capacity and the equivalents of cation-exchange capacity present in a physical mixture of salt-splitting anion-exchange material and salt-splitting cation-exchange material.

1.2 The values stated in SI units are to be regarded as the standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:

D 1129 Terminology Relating to Water²

D 1193 Specification for Reagent Water²

D 2187 Test Methods for Physical and Chemical Properties of Particulate Ion-Exchange Resins³

3. Terminology

3.1 *Definitions*—For definitions of terms used in this test method, refer to Terminology D 1129.

3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *anion-exchange material, n*—an ion-exchange material capable of the reversible exchange of negatively charged ions.

3.2.2 *cation-exchange material, n*—an ion-exchange material capable of the reversible exchange of positively charged ions.

3.2.3 *ion-exchange material, n*—an insoluble material that has the ability to exchange reversibly certain ions in its structure or attached to its surface as functional groups with ions in a surrounding medium.

3.2.4 *ion-exchange resin, n*—a synthetic organic ion-exchange material.

3.2.5 *mixed bed, n*—a physical mixture of anion-exchange material and cation-exchange material.

3.2.6 *salt-splitting, adj*—the ability of anion-exchange or cation-exchange materials to exchange hydroxide or hydrogen ions respectively for the ions in neutral salts.

4. Summary of Test Method

4.1 This test method consists of simultaneous conversion of the cation-exchange component to the hydrogen form and the anion-exchange component to the chloride form with hydrochloric acid. After rinsing to remove the excess acid, the hydrogen ion from the cation resin and the chloride ion from the anion resin are simultaneously eluted with neutral sodium nitrate, and the amount eluted is determined by titration of the effluent for both ions.

5. Significance and Use

5.1 This test method is applicable to the analysis of new materials that are sold as mixtures and to samples taken from regenerable units containing mixtures of anion-exchanging and cation-exchanging materials. It is used to determine the ratio of the components without separating them from each other.

5.2 This test method is intended for mixtures of ion-exchange materials that have salt-splitting capacity as measured by Test Method E of Test Methods D 2187 for cation-exchange resins, and Test Method H for anion-exchange resins. In the case of cation-exchange resins, these are styrene-based polymers with sulfonic acid functional groups. The anion-exchanging materials in this class are styrene-based materials with quaternary ammonium functional groups. The test method will determine the amount of anion-exchange material of any functionality present in the mixture. However, when anionic groups that are not salt-splitting are present, the values for cationic groups will be high due to the acidic character of the anion effluent. Cationic groups that do not split salts are not measured.

5.3 Samples are analyzed in this test method as received. It is not necessary that the cation-exchanging resin be in the hydrogen form and the anion-exchanging resin be in the hydroxide form for this test method.

5.4 This test method may be used to determine if new materials are balanced to meet their specification values. In operating regenerable units, it may be used to determine if the components are separating properly or remixing properly. It may also be used to check for improper balance in bedding or for loss of a component during operation.

5.5 This test method begins with the conversion to the hydrogen and chloride forms. However, it may be combined

¹ This test method is under the jurisdiction of ASTM Committee D-19 on Water and is the direct responsibility of Subcommittee D19.08 on Membranes and Ion Exchange Materials.

Current edition approved June 15, 1991. Published February 1992. Originally published as D 4548 – 86. Last previous edition D 4548 – 86.

² *Annual Book of ASTM Standards*, Vol 11.01.

³ *Annual Book of ASTM Standards*, Vol 11.02.