INTERNATIONAL STANDARD



First edition 2014-05-15

Adhesives — Test methods for isotropic electrically conductive adhesives —

Part 2:

Determination of electrical characteristics for use in electronic assemblies (standards.iteh.ai)

Adhésifs — Méthodes d'essai pour adhésifs à conductivité électrique isotrope 16525-2:2014

https://standards.itch.apartie 2: Determination des propriétés électriques pour utilisation 2 dans des assemblages électroniques



Reference number ISO 16525-2:2014(E)

iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>ISO 16525-2:2014</u> https://standards.iteh.ai/catalog/standards/sist/c232be0e-35c3-474d-8964-27aae56fb699/iso-16525-2-2014



COPYRIGHT PROTECTED DOCUMENT

© ISO 2014

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office Case postale 56 • CH-1211 Geneva 20 Tel. + 41 22 749 01 11 Fax + 41 22 749 09 47 E-mail copyright@iso.org Web www.iso.org

Published in Switzerland

Page

Contents

Forew	ordiv
1	Scope1
2	Normative references 1
3	Terms and definitions 1
4	Principle 2
5	Apparatus3
6	Procedure 8 6.1 Atmospheric conditions 8 6.2 Measurement and calculation 8 6.3 Judgement 10
7	Test report 11

iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>ISO 16525-2:2014</u> https://standards.iteh.ai/catalog/standards/sist/c232be0e-35c3-474d-8964-27aae56fb699/iso-16525-2-2014

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2. www.iso.org/directives

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received. www.iso.org/patents

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

The committee responsible for this document is ISO/TC 61, *Plastics*, Subcommittee SC 11, *Products*.

ISO 16525 consists of the following parts, under the general title *Adhesives*—*Test methods for isotropic electrically conductive adhesives*: (standards.iteh.ai)

- Part 1: General test methods
- ISO 16525-2:2014
- Part 2: Determination of electric characteristics for use in electronic assemblies₆₄₋
- Part 3: Determination of heat-transfer properties
- Part 4: Determination of shear strength and electrical resistance using rigid-to-rigid bonded assemblies
- Part 5: Determination of shear fatigue
- Part 6: Determination of pendulum-type shear impact
- Part 7: Environmental test methods
- Part 8: Electrochemical migration test methods
- Part 9: Determination of high-speed signal-transmission characteristics

Adhesives — Test methods for isotropic electrically conductive adhesives —

Part 2: Determination of electrical characteristics for use in electronic assemblies

SAFETY STATEMENT — Persons using this part of ISO 16525 should be familiar with normal laboratory practice. This part of ISO 16525 does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user to establish appropriate safety and health practices and to ensure compliance with any regulatory conditions.

IMPORTANT — Certain procedures specified in this part of ISO 16525 might involve the use or generation of substances, or the generation of waste, that could constitute a local environmental hazard. Reference should be made to appropriate documentation on safe handling and disposal after use.

1 Scope iTeh STANDARD PREVIEW

This part of ISO 16525 specifies test methods for isotropic electrically conductive adhesives used in wiring, die attach, and surface assembly of printed circuit boards of electronic devices. The test methods focus on volume and interfacial contact resistivity.

ISO 16525-2:2014

Normative references 2

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 472, Plastics — Vocabulary

ISO 554, Standard atmospheres for conditioning and/or testing — Specifications

ISO 80000-1, Quantities and units — Part 1: General

IEC 60468, Method of measurement of resistivity of metallic materials

IEC 61249-2-7, Materials for printed boards and other interconnecting structures - Part 2-7: Reinforced base materials clad and unclad - Epoxide woven E-glass laminated sheet of defined flammability (vertical burning test), copper-clad

EN 923, Adhesives – Terms and definitions

ASTM B539-02, Standard Test Methods for Measuring Resistance of Electrical Connections (Static Contacts)

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 472, ASTM B539-02 and EN 923 and the following apply.

3.1

isotropic electrically conductive adhesive

<electronic assembly> resin that contains fillers, which provide electrical conduction, and functions as an adhesive

3.2

volume resistivity

ρ

electrical resistance of the isotropic electrically conductive adhesive for a given cross-sectional area or given length

Note 1 to entry: Electrical volume resistivity is converted to resistance per given cross-sectional area or given length of the isotropic electrically conductive adhesive. This part of ISO 16525 specifies measurement methods for an isotropic electrically conductive adhesive, which is applied to a circuit board that is similar to the one used in practice.

Note 2 to entry: It is expressed as ohm metre ($\Omega \cdot m$).

3.3

interfacial contact resistivity

 $ho_{\rm i}$

electrical resistance that is generated on the contact surface between the isotropic electrically conductive adhesive and the adherend

Note 1 to entry: It is expressed as electrical resistance per given cross-sectional area ($\Omega \cdot m^2$).

Note 2 to entry: Interfacial contact resistance is generated on the contact surface between the isotropic electrically conductive adhesive and the electrode, and it is thought to be associated with the dispersion of the metal component in the vicinity of the electrode interface, oxide film, and the arrangement of conductive particles contained in the isotropic electrically conductive adhesive. In addition, interfacial contact resistivity fluctuates during the endurance test. Apart from the resistance component brought by electrically volume resistivity of the isotropic electrically conductive adhesive, if a resistance component is placed on the contact surface, interfacial resistance is expressed by resistivity per given area and is converted to resistance per given cross-sectional area or length of the isotropic electrically conductive adhesive.

3.4

four-probe method

method for measuring resistance that consists of two terminals for current application and two terminals for voltage measurement

3.5

dry circuit

method for measuring resistance that prevents open-circuit voltage at the time of measurement from exceeding a specific level so that the thin insulating layer that develops at the contact surface cannot be broken

Note 1 to entry: The maximum current limit is 100 mA and voltage is 20 mV in order to prevent breakdown of the microstructure of adhesives.

4 Principle

The test circuit board consists of two or more terminals that are connected using an isotropic electrically conductive adhesive. The measurement of a potential difference, when a current is applied to one of the terminals, can be used for the calculation of electrically volume resistivity and interfacial contact resistivity.

NOTE This test uses the electrical characteristics of isotropic electrically conductive adhesives, which are used for connection of electronic circuits. This part of ISO 16525 describes electrically volume resistivity, which shows the electric characteristic of the isotropic electrically conductive adhesive, and interfacial resistance, which is specific to the isotropic electrically conductive adhesive.

On the contact surface of the isotropic electrically conductive adhesives, a resistance component is present, which can be regarded as interfacial resistance. This might be so high that it cannot be neglected when compared with electrically volume resistivity of the isotropic electrically conductive adhesive. This test provides a measurement, which measures this component only. This test is characterized by calculation of resistivity from a current passing through the test circuit and voltage.

5 Apparatus

5.1 Test apparatus, consisting of a current source and a voltage meter, both as specified in IEC 60468. The potential difference is measured at the voltage terminals by applying a current to the printed circuit board using the current source from the current terminals in a specific direction. Figure 1 and Figure 2 show examples of configuration of the apparatus. A digital ohmmeter, which combines all these devices, may be used as an alternative.

It is preferable to use a dry circuit-type apparatus because it does not affect the irreversibility of conductivity of the interface of the isotropic electrically conductive adhesive. For measurement of interfacial resistance, it is preferable to use a multichannel ohmmeter because it is necessary to switch from one pair of terminals to the other and the lengths of the wires differs.

Resistance is obtained from the voltage drop when a constant current is applied. Therefore, set a current value so that voltage resolution can be sufficiently small compared to the measured voltage. In the unlikely event that the specimen generates heat because an excessively high current occurs, reduce the current value and shorten the period for each measurement session. Usually, a maximum current is recommended to be approximately 10 mAD ARD PREVIEW





Key 1

2

3

Figure 1 — Test apparatus — For measurement of electrically volume resistivity



Figure 2 — Test apparatus — For measurement of interfacial contact resistivity

5.2 Test circuit board, fulfilling the following requirments.

- a) Material of substrate: use a glass fabric-based epoxy resin copper-clad laminate specified as a general-purpose, single-sided substrate, as described in IEC 61249-2-7.
- b) Thickness of substrate: the thickness of substrates is $(1,6 \pm 0,2)$ mm or that specified in IEC 61249-2-7.
- c) Pattern and dimensions of circuit board: a basic pattern for circuit boards to measure electrically volume resistivity and interfacial contact resistivity is shown in Figure 3 (for measurement of electrically volume resistivity) and Figure 4 (for measurement of interfacial contact resistivity), respectively.

The allowed values for dimension a in Figure 3 are from 2 mm to 10 mm and for l are from 20 mm to 100 mm. For workability, the recommended values for dimensions a and l are 10 mm and 50 mm, respectively. Diameter, b, of the wire for measuring a voltage drop should be so thin that it does not affect the measurement and is recommended to be 0,5 mm.

The recommended dimension for a in Figure 4 is 0,8 mm. When dimension a is lower than this value, fluctuation of the measurement becomes large. When it is larger than this value, the measurement sensitivity for interfacial resistance is reduced. The wires connected to the joint, at which measurement is performed, are taken out from both ends so that the current distribution at the location of measurement

will be uniform. Dimension *b* should be as small as possible so that it does not affect measurement of a voltage drop and is recommended to be 0,1 mm.

These dimensions should be observed because they are designed to minimize their impacts on measurement.

d) Plating of the electrode surface of the circuit board: in <u>Figure 3</u>, an antioxidant should be applied to the substrate to prevent oxidation of copper and other metals. In <u>Figure 4</u>, plating of the electrode surface is subject to requirements for uses and/or requirements of the delivering and receiving parties.

iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>ISO 16525-2:2014</u> https://standards.iteh.ai/catalog/standards/sist/c232be0e-35c3-474d-8964-27aae56fb699/iso-16525-2-2014