



**SLOVENSKI STANDARD**  
**SIST ISO 4383:2015**  
**01-marec-2015**

**Nadomešča:**  
**SIST ISO 4383:2002**

---

**Drсни ležaji - Večslojni materiali za tankostene drsne ležaje**

Plain bearings - Multilayer materials for thin-walled plain bearings

**iTeh STANDARD PREVIEW**  
Paliers lisses - Matériaux multicouches pour paliers lisses minces  
**(standards.iteh.ai)**

**Ta slovenski standard je istoveten z: SIST ISO 4383:2012**

<https://standards.iteh.ai/catalog/standards/sist/ab814097-f79a-4134-a6ae-771fde72515/sist-iso-4383-2015>

---

**ICS:**

21.100.10      Drsni ležaji                                      Plain bearings

**SIST ISO 4383:2015**                                      **en**

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[SIST ISO 4383:2015](#)

<https://standards.iteh.ai/catalog/standards/sist/ab814097-f79a-4134-a6ae-771fed72515/sist-iso-4383-2015>

INTERNATIONAL  
STANDARD

ISO  
4383

Fourth edition  
2012-10-15

---

---

**Plain bearings — Multilayer materials  
for thin-walled plain bearings**

*Paliers lisses — Matériaux multicouches pour paliers lisses minces*

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[SIST ISO 4383:2015](https://standards.iteh.ai/catalog/standards/sist/ab814097-f79a-4134-a6ae-771fed72515/sist-iso-4383-2015)

<https://standards.iteh.ai/catalog/standards/sist/ab814097-f79a-4134-a6ae-771fed72515/sist-iso-4383-2015>



Reference number  
ISO 4383:2012(E)

© ISO 2012

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

SIST ISO 4383:2015

<https://standards.iteh.ai/catalog/standards/sist/ab814097-f79a-4134-a6ae-771fed72515/sist-iso-4383-2015>



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2012

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland

<b>Contents</b>		Page
<b>Foreword</b> .....		<b>iv</b>
<b>1 Scope</b> .....		<b>1</b>
<b>2 Normative references</b> .....		<b>1</b>
<b>3 Requirements</b> .....		<b>1</b>
3.1 Chemical composition .....		1
3.2 Steel backings .....		1
3.3 Bearing layers .....		1
3.4 Overlays .....		2
3.5 Guidance on and selection of materials .....		2
<b>4 Designation</b> .....		<b>2</b>
<b>Annex A (informative) Guidance on properties and selection of materials</b> .....		<b>5</b>
<b>Bibliography</b> .....		<b>7</b>

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[SIST ISO 4383:2015](https://standards.iteh.ai/catalog/standards/sist/ab814097-f79a-4134-a6ae-771fede72515/sist-iso-4383-2015)

<https://standards.iteh.ai/catalog/standards/sist/ab814097-f79a-4134-a6ae-771fede72515/sist-iso-4383-2015>

**ISO 4383:2012(E)****Foreword**

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 4383 was prepared by Technical Committee ISO/TC 123, *Plain bearings*, Subcommittee SC 2, *Materials and lubricants, their properties, characteristics, test methods and testing conditions*.

This fourth edition cancels and replaces the third edition (ISO 4383:2000), which has been technically revised.

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[SIST ISO 4383:2015](https://standards.iteh.ai/catalog/standards/sist/ab814097-f79a-4134-a6ae-771fed72515/sist-iso-4383-2015)

<https://standards.iteh.ai/catalog/standards/sist/ab814097-f79a-4134-a6ae-771fed72515/sist-iso-4383-2015>

# Plain bearings — Multilayer materials for thin-walled plain bearings

## 1 Scope

This International Standard specifies requirements for multilayer materials for the manufacture of thin-walled plain bearings (half bearings, bushes, thrust washers). The multilayer material consists of a steel backing, the bearing layer (cast, sintered, roll bonded) and, possibly, an overlay. The chemical composition refers to the original unprocessed material and is intended to be measured on representative samples. Testing results on final bearings can be due to the influence of bearing production. Therefore, these results cannot be compared with data given in this International Standard.

NOTE Environmental concerns will, in the future, restrict the use of some materials such as lead.

## 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 4381, *Plain bearings — Tin casting alloys for multilayer plain bearings*

ISO 4382-1, *Plain bearings — Copper alloys — Part 1: Cast copper alloys for solid and multilayer thick-walled plain bearings*

ISO 6691, *Thermoplastic polymers for plain bearings — Classification and designation*

ISO 6280, *Plain bearings — Requirements on backings for thick-walled multilayer bearings*

## 3 Requirements

### 3.1 Chemical composition

The chemical composition of alloy elements shall be within the limits specified in Tables 1 to 5.

### 3.2 Steel backings

The chemical composition of the steel for backings shall be the subject of agreement between the manufacturer and purchaser. In general, low carbon steel is used.

For bronze/polymer composite materials listed in Table 4, copper-coated steel may be used. Backings shall conform to ISO 6280.

### 3.3 Bearing layers

Bearing metals based on tin shall be in accordance with Table 1.

Bearing metals based on copper shall be in accordance with Table 2.

Bearing metals based on aluminium shall be in accordance with Table 3.

## ISO 4383:2012(E)

Bearing layers based on sintered porous bronze and polymers shall be in accordance with Table 4.

NOTE There is a new class of aluminium-based materials containing both aluminium and silicon or manganese as well as a "soft" material, such as lead or tin. Detailed information is available from individual manufacturers.

### 3.4 Overlays

Overlays in accordance with Table 5 may be applied for bearing metal layers as indicated in Table A.2. The thickness of the overlay and any additional layers between the bearing metal layer and the overlay shall be the subject of agreement between the manufacturer and purchaser.

Despite the electroplated overlays, sputtered and polymer overlays are used for engine bearings. For the chemical composition of sputtered overlays, see Table 6. Polymer overlays consist of a polymer matrix (e.g. PAI) and fillers. The detailed compositions are defined in specific data sheets of the bearing manufacturers.

### 3.5 Guidance on and selection of materials

Guidance of hardness for bearing metal in strip form and use of bearing metals are given in Annex A.

## 4 Designation

EXAMPLE A multilayer material consisting of a steel backing, the bearing metal CuPb24Sn as cast (G) and the overlay PbSn10Cu2 is designated as follows: **Bearing metal** ISO 4383 - G — CuPb24Sn — PbSn10Cu2

iTech STANDARD PREVIEW  
(standards.iteh.ai)

Table 1 — Tin alloys<sup>a</sup>

Chemical element	Chemical composition mass fraction, %
Component	SnSb8Cu4
Sn	Remainder
Sb	7 to 8
Cu	3 to 4
Impurity	
Pb	< 0,35
As	< 0,1
Bi	< 0,08
Zn	< 0,01
Al	< 0,01
Fe	< 0,1
Cd	< 0,05
Total others	0,2

<sup>a</sup> Tin alloys shall conform to ISO 4381.



Table 2 — Copper alloys

Chemical element	Chemical composition mass fraction, %				
	CuPb10Sn10 <sup>a</sup>	CuPb17Sn5	CuPb24Sn4	CuPb24Sn	CuPb30
	G — cast P — sintered	G — cast	G — cast P — sintered	G — cast P — sintered	P — sintered
<b>Components</b>					
Cu	Remainder	Remainder	Remainder	Remainder	Remainder
Pb	9 to 11	14 to 20	19 to 27	19 to 27	26 to 33
Sn	9 to 11	4 to 6	3 to 4,5	0,6 to 2	0,5
<b>Impurity</b>					
Zn	<0,5	<0,5	<0,5	<0,5	<0,5
P	<0,1	<0,1	<0,1	<0,1	<0,1
Fe	<0,7	<0,7	<0,7	<0,7	<0,7
Ni	<0,5	<0,5	<0,5	<0,5	<0,5
Sb	<0,5	<0,5	<0,5	<0,5	<0,5
Total others	0,5	0,5	0,5	0,5	0,5

<sup>a</sup> The chemical composition of this alloy differs from that of solid and multilayer thick-walled plain bearings in accordance with ISO 4382-1.

## iTeH STANDARD PREVIEW

Table 3 — Aluminium alloys

Chemical element	Chemical composition mass fraction, %				
	AlSn20Cu	AlSn6Cu	AlSi11Cu	AlSn12SiCu	AlZn5Si1, 5Cu1Pb1Mg
<b>Component</b>					
Al	Remainder	Remainder	Remainder	Remainder	Remainder
Cu	0,7 to 1,3	0,7 to 1,3	0,7 to 1,3	0,7 to 1,6	0,8 to 1,2
Sn	16,5 to 22,5	5,5 to 7	—	10,0 to 15,0	—
Ni	—	1,3	—	—	—
Si	—	—	10 to 12	1,8 to 3,6	1 to 2
Pb	—	—	—	—	0,7 to 1,3
Zn	—	—	—	—	4,4 to 5,5
Mg	—	—	—	—	0,6
<b>Impurity</b>					
Sn	—	—	<0,2	—	<0,2
Mg	—	—	—	—	—
Ni	<0,1	—	<0,1	—	<0,2
Si	<0,7 <sup>a</sup>	<0,7 <sup>a</sup>	—	—	—
Fe	<0,7 <sup>a</sup>	<0,7 <sup>a</sup>	<0,3	<0,7 <sup>a</sup>	<0,6
Mn	<0,7 <sup>a</sup>	<0,7 <sup>a</sup>	<0,1	—	<0,3
Ti	<0,2	<0,2	<0,1	—	<0,2
Total others	0,5	0,5	0,3	1,0	0,4

<sup>a</sup> Total Si+Fe+Mn content shall not exceed 1,0 %.