

**SLOVENSKI  
STANDARD**

**SIST EN 60249-2-  
5:1997/A4:2002**

prva izdaja  
maj 2002

---

---

Amendment to subclauses 5.8 and 5.9 of EN

**iTeh STANDARD PREVIEW  
(standards.iteh.ai)**

SIST EN 60249-2-5:1997/A4:2002  
<https://standards.iteh.ai/catalog/standards/sist/a499e040-75c3-4123-901e-2e7415af1b2f/sist-en-60249-2-5-1997-a4-2002>

---

---

ICS 13.220.40; 31.180

Referenčna številka  
SIST EN 60249-2-  
5:1997/A4:2002(en)

## iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN 60249-2-5:1997/A4:2002

<https://standards.iteh.ai/catalog/standards/sist/a499e040-75c3-4123-901e-2e7415af1b2fsist-en-60249-2-5-1997-a4-2002>

EUROPEAN STANDARD  
NORME EUROPÉENNE  
EUROPÄISCHE NORM

EN 60249-2-5/A4



October 1995

UDC 621.3.049.75-033.5-41  
ICS 31.180

Descriptors: Printed circuit, composite materials, glass, copper, flammability

English version

**Base materials for printed circuits  
Part 2: Specifications**

**Specification No. 5: Epoxide woven glass fabric copper-clad  
laminated sheet of defined flammability (vertical burning test)  
(IEC 249-2-5:1987/A4:1994)**

Matériaux de base pour circuits  
imprimés

Partie 2: Spécifications

Spécification n° 5: Feuille de tissu  
de verre époxyde recouverte de  
cuivre, d'inflammabilité définie  
(essai de combustion/verticale)  
(CEI 249-2-5:1987/A4:1994)

Basismaterialien für gedruckte  
Schaltungen

Teil 2: Einzelbestimmungen

Einzelbestimmung Nr. 5:

Kupferkaschierte  
Epoxidharz-Glashartgewebetafeln  
definierter Brennbarkeit  
(Prüfung mit vertikaler Probenlage)  
(IEC 249-2-5:1987/A4:1994)

This amendment A4 modifies the European Standard EN 60249-2-5:1994; it was approved by CENELEC  
on 1995-09-20. CENELEC members are bound to comply with the CEN/CENELEC Internal Regulations  
which stipulate the conditions for giving this amendment the status of a national standard without any  
alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on  
application to the Central Secretariat or to any CENELEC member.

This amendment exists in three official versions (English, French, German). A version in any other  
language made by translation under the responsibility of a CENELEC member into its own language and  
notified to the Central Secretariat has the same status as the official versions.

CENELEC members are the national electrotechnical committees of Austria, Belgium, Denmark, Finland,  
France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain,  
Sweden, Switzerland and United Kingdom.

**CENELEC**

European Committee for Electrotechnical Standardization  
Comité Européen de Normalisation Electrotechnique  
Europäisches Komitee für Elektrotechnische Normung

Central Secretariat: rue de Stassart 35, B - 1050 Brussels

### Foreword

The text of amendment 4:1994 to the International Standard IEC 249-2-5:1987, prepared by IEC TC 52, Printed circuits, was submitted to the formal vote and was approved by CENELEC as amendment A4 to EN 60249-2-5:1994 on 1995-09-20 without any modification.

The following dates were fixed:

- latest date by which the amendment has to be implemented at national level by publication of an identical national standard or by endorsement (dop) 1996-09-01
  - latest date by which the national standards conflicting with the amendment have to be withdrawn (dow) 1996-09-01
- 

### Endorsement notice

The text of amendment 4:1994 to the International Standard IEC 249-2-5:1987 was approved by CENELEC as an amendment to the European Standard without any modification.

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

SIST EN 60249-2-5:1997/A4:2002  
<https://standards.iteh.ai/catalog/standards/sist/a499e040-75c3-4123-901e-2e7415af1b2f/sist-en-60249-2-5-1997-a4-2002>

**NORME  
INTERNATIONALE  
INTERNATIONAL  
STANDARD**

**CEI  
IEC**

**249-2-2,  
1985**

**249-2-4, -5, -9, -10  
1987**

**249-2-14  
1988**

**AMENDEMENT 4  
AMENDMENT 4**

**1994-05**

**Amendement 4**

**Matériaux de base pour circuits imprimés**

**Deuxième partie:**

**iTeh STANDARD PREVIEW** Spécifications. Specifications n°s 2, 4, 5, 9, 10 et 14  
**(standards.iteh.ai)**

**Amendment 4**

**SISTEN 60249-2-5:1997/A4:2002**

<https://standards.iteh.ai/catalog/standards/sist/a499e040-75c3-4123-901e-2e1f4518d2ca/60249-2-5:1997/A4:2002>  
**Base materials for printed circuits**

**Part 2:**

**Specifications. Specifications Nos. 2, 4, 5, 9,  
10 and 14**

© CEI 1994 Droits de reproduction réservés — Copyright – all rights reserved

Bureau Central de la Commission Electrotechnique Internationale 3, rue de Varembé Genève, Suisse



Commission Electrotechnique Internationale  
International Electrotechnical Commission  
Международная Электротехническая Комиссия

CODE PRIX  
PRICE CODE

C

Pour prix, voir catalogue en vigueur  
For price, see current catalogue

## FOREWORD

This amendment has been prepared by IEC technical committee 52: Printed circuits.

The text of this amendment is based on the following documents:

DIS	Report on voting
52(CO)396	52(CO)397

Full information on the voting for the approval of this amendment can be found in the report on voting indicated in the above table.

---

This amendment is applicable to the standards listed in the table below (first column). The relevant amendment number to each standard which this amendment modifies is also given in the table (second column).

iTEH STANDARD PREVIEW (standards.iteh.ai)	
IEC standard No.	Amendment No.
249-2-1	3
249-2-2	4
249-2-3	3
249-2-4	4
249-2-5	4
249-2-6	3
249-2-7	3
249-2-9	4
249-2-10	4
249-2-11	3
249-2-12	3
249-2-14	4
249-2-16	2
249-2-17	2
249-2-18	2
249-2-19	2

In publications IEC 249-2-2, IEC 249-2-4, IEC 249-2-5, IEC 249-2-9, IEC 249-2-10 and IEC 249-2-14, replace the existing subclause 5.8 "Size tolerances" and subclause 5.9 "Rectangularity of cut panels" by the following:

### 5.8 Sheet sizes

#### 5.8.1 Typical sheet sizes

Typical sheet sizes are:

- 1 060 mm × 1 150 mm
- 915 mm × 1 220 mm
- 1 000 mm × 1 000 mm
- 1 000 mm × 1 200 mm.

Apart from these typical sheet sizes, fractions of the sizes and other sizes, for example larger, are available on the market.

### 5.8.2 Tolerances for sheet sizes

The size of the sheets delivered by the supplier shall not deviate more than  $^{+20}_0$  mm from the ordered size.

### 5.9 Cut panels

#### 5.9.1 Cut panel sizes

Cut panel sizes shall be, when delivered, in accordance with the purchaser's specification.

#### 5.9.2 Size tolerances for cut panels

For panels cut to size according to the purchaser's specification, the following tolerances for length and width shall apply:

Panel size (mm)	Tolerance $\pm$ (mm)	
	Normal	Close
Up to 300		0,5
Over 300 to 600	2	0,8
Over 600		1,6

iTeh STANDARD PREVIEW  
 (standards.iteh.ai)  
<https://standards.iteh.ai/catalog/standards/sist/a499e040-75c3-4123-901e->  
 NOTE – The specified tolerances include all deviations caused by cutting the panels.

#### 5.9.3 Rectangularity of cut panels

Property	Test method (subclause of IEC 249-1)	Requirements	
		Coarse (mm/m)	Normal (mm/m)
Rectangularity of cut panels	3.15	3	2

## iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN 60249-2-5:1997/A4:2002

<https://standards.iteh.ai/catalog/standards/sist/a499e040-75c3-4123-901e-2e7415af1b2fsist-en-60249-2-5-1997-a4-2002>