



DRAFT INTERNATIONAL STANDARD ISO/DIS12127-1

ISO/TC 94/SC 13

Secretariat: SNV

Voting begins on
2011-05-05

Voting terminates on
2011-10-05

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION • МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ • ORGANISATION INTERNATIONALE DE NORMALISATION

Clothing for protection against heat and flame — Determination of contact heat transmission through protective clothing or constituent materials —

Part 1: Contact heat produced by heating cylinder

Vêtements de protection contre la chaleur et la flamme — Détermination de la transmission thermique par contact à travers les vêtements de protection ou leurs matériaux constitutifs —

Partie 1: Transmission thermique par contact produite par un cylindre de chauffage

[Revision of first edition (ISO 12127-1:2007)]

ICS 13.340.10

ISO/CEN PARALLEL PROCESSING

This draft has been developed within the European Committee for Standardization (CEN), and processed under the **CEN-lead** mode of collaboration as defined in the Vienna Agreement.

This draft is hereby submitted to the ISO member bodies and to the CEN member bodies for a parallel five-month enquiry.

Should this draft be accepted, a final draft, established on the basis of comments received, will be submitted to a parallel two-month approval vote in ISO and formal vote in CEN.

In accordance with the provisions of Council Resolution 15/1993 this document is circulated in the English language only.

Conformément aux dispositions de la Résolution du Conseil 15/1993, ce document est distribué en version anglaise seulement.

To expedite distribution, this document is circulated as received from the committee secretariat. ISO Central Secretariat work of editing and text composition will be undertaken at publication stage.

Pour accélérer la distribution, le présent document est distribué tel qu'il est parvenu du secrétariat du comité. Le travail de rédaction et de composition de texte sera effectué au Secrétariat central de l'ISO au stade de publication.

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

Full standard:
<https://standards.iteh.ai/catalog/standards/sist/2876913-474f-498b-b5e4-43b00127b1bc/iso-12127-1-2015>

Copyright notice

This ISO document is a Draft International Standard and is copyright-protected by ISO. Except as permitted under the applicable laws of the user's country, neither this ISO draft nor any extract from it may be reproduced, stored in a retrieval system or transmitted in any form or by any means, electronic, photocopying, recording or otherwise, without prior written permission being secured.

Requests for permission to reproduce should be addressed to either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Reproduction may be subject to royalty payments or a licensing agreement.

Violators may be prosecuted.

Contents

Page

| | |
|---|----|
| Foreword | iv |
| Introduction..... | v |
| 1 Scope..... | 1 |
| 2 Terms and definitions | 1 |
| 3 Principle..... | 2 |
| 4 Apparatus..... | 2 |
| 4.1 Heating cylinder..... | 2 |
| 4.2 Calorimeter..... | 2 |
| 4.3 Assembly..... | 2 |
| 4.4 Electronic devices | 2 |
| 5 Sampling and conditioning | 3 |
| 5.1 Sampling..... | 3 |
| 5.2 Conditioning | 3 |
| 6 Test method | 3 |
| 6.1 Starting conditions..... | 3 |
| 6.2 Procedure..... | 3 |
| 6.3 Evaluation..... | 3 |
| 7 Test report..... | 3 |
| Annex A (informative) Best practices for cleaning the heating cylinder | 8 |
| Annex ZA (informative) Relationship between this European Standard and the Essential Requirements of EU Directive (89/686/EEC)..... | 9 |

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 12127-1 was prepared by Technical Committee ISO/TC 94, *Personal safety — Protective clothing and equipment*, Subcommittee SC 13, *Protective clothing*.

This second edition cancels and replaces the first edition of ISO 12127-1, of which it constitutes a minor revision.

ISO 12127 consists of the following parts, under the general title *Clothing for protection against heat and flame — Determination of contact heat transmission through protective clothing or constituent materials*:

- *Part 1: Contact heat produced by heating cylinder*
- *Part 2: Contact heat produced by dropping small cylinders*

Introduction

Protective clothing designed to protect against heat and flame can be exposed to direct contact with hot substances or hot surfaces.

The diversity of such contact conditions makes it difficult to evaluate the hazards that can arise from high temperature.

The test method described in this part of ISO 12127 allows this heat transfer to be assessed when a heating cylinder and the clothing material are brought into contact with each other.

This part of ISO 12127 forms part of a series of standards concerned with clothing designed to protect against heat and fire.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

Full standard:
<https://standards.iteh.ai/catalog/standards/sist/2876913-474f-498b-b5e4-43b00127b1bc/iso-12127-1-2015>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

Full standard:
<https://standards.iteh.ai/catalog/standards/sist/2876913-474f-498b-b5e4-43b00127b1bc/iso-12127-1-2015>

Clothing for protection against heat and flame — Determination of contact heat transmission through protective clothing or constituent materials —

Part 1: Contact heat produced by heating cylinder

1 Scope

This part of ISO 12127 specifies a test method for the determination of contact heat transmission. It is applicable to protective clothing (including hand protectors) and its constituent materials intended to protect against high contact temperatures.

Application of this part of ISO 12127 is restricted to contact temperatures between 100 °C and 500 °C.

2 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

2.1

contact force

force acting on the test specimen and the calorimeter when they have been brought into contact with the heating cylinder

2.2

contact temperature

T_c

surface temperature of the contact area of the heating cylinder, this temperature being kept constant

2.3

rate of contact

relative speed with which the heating cylinder and the calorimeter with the test specimen are brought into contact with each other

2.4

start of timing

moment when the upper surface of the calorimeter and the bottom edge of the heating cylinder are within 10 mm of each other

2.5

threshold time

t_t

time between the start of timing and the moment when the temperature of the calorimeter is 10°C above its starting value

3 Principle

The heating cylinder is heated to and maintained at the contact temperature and a test specimen is placed on the calorimeter. The heating cylinder is lowered onto the test specimen supported by the calorimeter or, alternatively, the calorimeter with the specimen is lifted up to the heating cylinder. In either case, the operation is carried out at a constant speed. The threshold time is determined by monitoring the temperature of the calorimeter.

4 Apparatus

4.1 Heating cylinder

The heating cylinder shall be constructed from a suitable metal which can withstand temperatures of over 500 °C (e.g. silver 925). Figure 1, 2 and 3 show an example of the stamp and heating cylinder. The contact surface shall have a diameter of $(25,2 \pm 0,05)$ mm and must be polished. There shall be a central boring which ends 3 mm above the lower surface of the heating cylinder. This boring is intended to hold the temperature sensor, which is necessary for regulation of the temperature of the heating cylinder, and its diameter should be chosen accordingly. The heating cylinder shall be enclosed by heat-resistant insulation, leaving free the bottom contact surface.

4.2 Calorimeter

The calorimeter (as shown in Figure 4) consists of a cylindrical disc of black anodized pure aluminium of $(25 \pm 0,05)$ mm diameter, approximately ± 5 mm thickness and a mass of $(6,63 \pm 0,03)$ g, which is fixed on a mounting made from polyamide 6.6. The upper contact surface of the calorimeter shall be surface ground before anodization and on the lower surface self-adhesive stick-on thermocouple (e.g. PR 6462 BK/02 Thermocoax) shall be fixed.

4.3 Assembly

Figure 5 shows an example of the assembly. The heating cylinder and calorimeter are mounted with parallel faces and with their symmetrical axes in line in a supporting frame. Provision shall be made for moving at a controlled speed of $(5,0 \pm 0,5)$ mm/s either the heating cylinder down towards the calorimeter or the calorimeter up towards the heating cylinder. The additional weight shall be dimensioned in such a way that the contact force is $(49 \pm 0,5)$ N. Between measurement, during cooling periods, e.g. a suitable shielding shall be put between the heating cylinder and the calorimeter in order to prevent the calorimeter from being heated by thermal radiation from the heating cylinder.

4.4 Electronic devices

Suitable electronic devices shall be provided to

- heat the heating cylinder to at least 500 °C and to maintain the temperature;
- control the rate of contact;
- measure and register the calorimeter temperature to an accuracy of $\pm 0,1$ °C;
- measure the threshold time.

5 Sampling and conditioning

5.1 Sampling

At least three circular test specimens of 80 mm diameter shall be taken for each contact temperature from the product or from a piece of the material intended for manufacture of the product.

5.2 Conditioning

Before the test, the test specimens shall be conditioned for at least 24 h in an atmosphere having a temperature of (20 ± 2) °C and relative humidity of (65 ± 5) %.

6 Test method

6.1 Starting conditions

The measurements shall be carried out in an atmosphere having a temperature of (20 ± 5) °C and relative humidity between 15 % and 80 %. The heating cylinder shall be brought to ± 2 % of the selected contact temperature (in degrees Celsius). The temperature of the calorimeter shall be at room temperature ± 2 °C before the start of each test. The test shall be started not later than 3 min after the test specimen has been taken out of the conditioning atmosphere (see 5.2).

6.2 Procedure

Place the test specimen on the calorimeter so that its outer face is upwards. Remove the shielding between the heating cylinder and the calorimeter and bring the heating cylinder into contact with the calorimeter with a rate of contact of $(5,0 \pm 0,2)$ mm/s. Measure and record the temperature of the calorimeter during the test. Carry out at least three measurements at each contact temperature.

6.3 Evaluation

Determine the threshold time, t_t , to the nearest 0,1 s.

7 Test report

The test report shall contain the following elements:

- a) reference to ISO 12127-1;
- b) name of the supplier of the product or material;
- c) name, as given by the supplier, and description of the product or material;
- d) contact temperature(s), T_c ;
- e) threshold time, t_t (individual values or, if five or more measurements per contact temperature have been made, the mean value and standard deviation);
- f) description of observed changes in the test specimens;
- g) date of test;
- h) any deviation from the test method specified in this part of ISO 12127.