



Designation: A487/A487M – 93 (Reapproved 2007)

Standard Specification for Steel Castings Suitable for Pressure Service¹

This standard is issued under the fixed designation A487/A487M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope

1.1 This specification² covers low-alloy steels and martensitic stainless steels in the normalized and tempered, or quenched and tempered, condition suitable for pressure-containing parts. The weldability of the classes in this specification varies from readily weldable to weldable only with adequate precautions, and the weldability of each class should be considered prior to assembly by fusion welding.

1.2 Selection will depend on design, mechanical, and service conditions. Users should note that hardenability of some of the grades mentioned may restrict the maximum size at which the required mechanical properties are obtained.

1.3 The values stated in either inch-pound units or SI units are to be regarded separately as standard. Within the text, the SI units are shown in brackets. The values stated in each system are not exact equivalents; therefore, each system must be used independently of the other. Combining values from the two systems may result in nonconformance with the specification. Inch-pound units are applicable for material ordered to Specification A487 and SI units for material ordered to Specification A487M.

2. Referenced Documents

2.1 *ASTM Standards*:³

A370 Test Methods and Definitions for Mechanical Testing of Steel Products

A488/A488M Practice for Steel Castings, Welding, Qualifications of Procedures and Personnel

A703/A703M Specification for Steel Castings, General Requirements, for Pressure-Containing Parts

E165 Practice for Liquid Penetrant Examination for General Industry

E709 Guide for Magnetic Particle Testing

2.2 *American Society of Mechanical Engineers:*
ASME Boiler and Pressure Vessel Code, Section IX⁴

2.3 *Manufacturers Standardization Society of the Valve and Fittings Industry Standards*:⁵

SP-55 Quality Standard for Steel Castings-Visual Method

3. General Conditions for Delivery

3.1 Material furnished to this specification shall conform to the requirements of Specification **A703/A703M** including any supplementary requirements that are indicated in the purchase order. Failure to comply with the general requirements of Specification **A703/A703M** constitutes nonconformance with this specification. In case of conflict between the requirements of this specification and Specification **A703/A703M**, this specification shall prevail.

4. Ordering Information

4.1 The inquiry and order should include or indicate the following:

4.1.1 A description of the casting by pattern number or drawing (dimensional tolerances shall be included on the casting drawing),

4.1.2 ASTM designation and year of issue,

4.1.3 Grade and class of steel,

4.1.4 Options in the specification, and

4.1.5 The supplementary requirements desired including the standard of acceptance.

5. Heat Treatment

5.1 All castings shall receive a heat treatment indicated in **Table 1**. Preliminary heat treatment prior to final heat treatment as well as multiple tempering is permitted.

5.2 Heat treatment shall be performed after the castings have been allowed to cool below the transformation range.

5.3 The furnace temperature for heat treating shall be effectively controlled by use of recording-type pyrometers.

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.18 on Castings.

Current edition approved Nov. 1, 2007. Published November 2007. Originally approved in 1963. Last previous edition approved in 2003 as A487/A487M–93 (2003). DOI: 10.1520/A0487_A0487M-93R07.

² For ASME Boiler and Pressure Vessel Code applications see related Specifications SA-487 in Section II of that code.

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

⁴ Available from American Society of Mechanical Engineers (ASME), ASME International Headquarters, Three Park Ave., New York, NY 10016-5990, <http://www.asme.org>.

⁵ Available from Manufacturers Standardization Society of the Valve and Fittings Industry (MSS), 127 Park St., NE, Vienna, VA 22180-4602, <http://www.mss-hq.com>.

TABLE 1 Heat Treat Requirement

Grade	Class	Austenitizing Temperature, min, °F [°C]	Media ^A	Quenching Cool Below °F [°C]	Tempering Temperature, °F [°C] ^B
1	A	1600 [870]	A	450 [230]	1100 [595]
1	B	1600 [870]	L	500 [260]	1100 [595]
1	C	1600 [870]	A or L	500 [260]	1150 [620]
2	A	1600 [870]	A	450 [230]	1100 [595]
2	B	1600 [870]	L	500 [260]	1100 [595]
2	C	1600 [870]	A or L	500 [260]	1150 [620]
4	A	1600 [870]	A or L	500 [260]	1100 [595]
4	B	1600 [870]	L	500 [260]	1100 [595]
4	C	1600 [870]	A or L	500 [260]	1150 [620]
4	D	1600 [870]	L	500 [260]	1150 [620]
4	E	1600 [870]	L	500 [260]	1100 [595]
6	A	1550 [845]	A	500 [260]	1100 [595]
6	B	1550 [845]	L	500 [260]	1100 [595]
7	A	1650 [900]	L	600 [315]	1100 [595]
8	A	1750 [955]	A	500 [260]	1250 [675]
8	B	1750 [955]	L	500 [260]	1250 [675]
8	C	1750 [955]	L	500 [260]	1250 [675]
9	A	1600 [870]	A or L	500 [260]	1100 [595]
9	B	1600 [870]	L	500 [260]	1100 [595]
9	C	1600 [870]	A or L	500 [260]	1150 [620]
9	D	1600 [870]	L	500 [260]	1150 [620]
9	E	1600 [870]	L	500 [260]	1100 [595]
10	A	1550 [845]	A	500 [260]	1100 [595]
10	B	1550 [845]	L	500 [260]	1100 [595]
11	A	1650 [900]	A	600 [315]	1100 [595]
11	B	1650 [900]	L	600 [315]	1100 [595]
12	A	1750 [955]	A	600 [315]	1100 [595]
12	B	1750 [955]	L	400 [205]	1100 [595]
13	A	1550 [845]	A	500 [260]	1100 [595]
13	B	1550 [845]	L	500 [260]	1100 [595]
14	A	1550 [845]	L	500 [260]	1100 [595]
16 (J31200)	A	1600 [870] ^C	A	600 [315]	1100 [595]
CA15	A	1750 [955]	A or L	400 [205]	900 [480]
CA15	B	1750 [955]	A or L	400 [205]	1100 [595]
CA15	C	1750 [955]	A or L	400 [205]	1150 [620] ^{DE}
CA15	D	1750 [955]	A or L	400 [205]	1150 [620] ^{DE}
CA15M	A	1750 [955]	A or L	400 [205]	1100 [595]
CA6NM	A	1850 [1010]	A or L	200 [95]	1050–1150 [565–620]
CA6NM	B	1850 [1010]	A or L	200 [95]	1225–1275 [665–690] ^{E,F}
					1050–1150 [565–620] ^G

^A A = air, L = Liquid.

^B Minimum temperature unless range is specified.

^C Double austenitize.

^D Double temper with the final temper at a lower temperature than the intermediate temper.

^E Air cool to below 200°F [95°C] after first temper.

^F Intermediate.

^G Final.

6. Chemical Composition

6.1 The steel shall conform to the requirements as to chemical composition prescribed in **Table 2**. Product analysis tolerance shall conform to the product analysis tolerance shown in Specification **A703/A703M**. Product analysis tolerances for stainless grades are not presently applicable pending development of these limits.

7. Tensile Requirements

7.1 Tensile properties of steel used for the castings shall conform to the requirements prescribed in **Table 3**.

8. Quality

8.1 The surface of the casting shall be free of adhering sand, scale, cracks, and hot tears as determined by visual examination. Other surface discontinuities shall meet the visual accep-

tance standards specified in the order. Visual Method **SP-55** or other visual standards may be used to define acceptable surface discontinuities and finish. Unacceptable visual surface discontinuities shall be removed and their removal verified by visual examination of the resultant cavities. When methods involving high temperatures are used in the removal and repair of discontinuities, the casting shall be preheated to at least the minimum temperature in **Table 4**.

8.2 The castings shall not be peened, plugged, or impregnated to stop leaks.

9. Repair By Welding

9.1 For castings, other than those intended for use under ASME Boiler and Pressure Vessel Code, repairs shall be made using procedures and welders qualified under Practice **A488/A488M**.

TABLE 2 Chemical Requirements (Maximum Percent Unless Range is Given)

Grade	1.	2.	4.	6.	7.	8.	9.	10.	11.	12.
Class Type	ABC Vanadium	ABC Manganese-Molybdenum	ABCDE Nickel-Chromium-Molybdenum	AB Manganese-Nickel-Chromium-Molybdenum	A Nickel-Chromium-Molybdenum-Vanadium ^A	ABC Chromium-Molybdenum	ABCDE Chromium-Molybdenum	AB Nickel-Chromium-Molybdenum	AB Nickel-Chromium-Molybdenum	AB Nickel-Chromium-Molybdenum
Carbon	0.30	0.30	0.30	0.05–0.38	0.05–0.20	0.05–0.20	0.05–0.33	0.30	0.05–0.20	0.05–0.20
Manganese	1.00	1.00–1.40	1.00	1.30–1.70	0.60–1.00	0.50–0.90	0.60–1.00	0.60 to 1.00	0.50–0.80	0.40–0.70
Phosphorus	0.04	0.04	0.04	0.04	0.04	0.04	0.04	0.04	0.04	0.04
Sulfur	0.045	0.045	0.045	0.045	0.045	0.045	0.045	0.045	0.045	0.045
Silicon	0.80	0.80	0.80	0.80	0.80	0.80	0.80	0.80	0.60	0.60
Nickel	0.40–0.80	0.40–0.80	0.70–1.00	1.40–2.00	0.70–1.10	0.60–1.00
Chromium	0.40–0.80	0.40–0.80	0.40–0.80	2.00–2.75	0.75–1.10	0.55–0.90	0.50–0.80	0.50–0.90
Molybdenum	...	0.10–0.30	0.15–0.30	0.30–0.40	0.40–0.60	0.90–1.10	0.15–0.30	0.20–0.40	0.45–0.65	0.90–1.20
Vanadium	0.04–0.12	0.03–0.10
Boron	0.002–0.006
Copper	0.15–0.50
Residual Elements:										
Copper	0.50	0.50	0.50	0.50	0.50	0.50	0.50	0.50	0.50	0.50
Nickel	0.50	0.50	0.50
Chromium	0.35	0.35
Mo + W	0.25
Tungsten	...	0.10	0.10	0.10	0.10	0.10	0.10	0.10	0.10	0.10
Vanadium	...	0.03	0.03	0.03	...	0.03	0.03	0.03	0.03	0.03
Total content of residual elements	1.00	1.00	0.60	0.60	0.60	0.60	1.00	0.60	0.50	0.50

Grade	13.	14.	16	CA15	CA15M	CA6NM
Class Type	AB Nickel-Molybdenum	A Nickel-Molybdenum	A Low Carbon Manganese-Nickel (J31200)	ABCD Martensitic Chromium	A Martensitic Chromium	AB Martensitic Chromium Nickel
Carbon	0.30	0.55	0.12 ^B	0.15	0.15	0.06
Manganese	0.80–1.10	0.80–1.10	2.10 ^B	1.00	1.00	1.00
Phosphorus	0.04	0.04	0.02	0.040	0.040	0.04
Sulfur	0.045	0.045	0.02	0.040	0.040	0.03
Silicon	0.60	0.60	0.50	1.50	0.65	1.00
Nickel	1.40–1.75	1.40–1.75	1.00–1.40	1.00	1.0	3.5–4.5
Chromium	11.5–14.0	11.5–14.0	11.5–14.0
Molybdenum	0.20–0.30	0.20–0.30	...	0.50	0.15–1.0	0.4–1.0
Boron
Copper
Residual Elements						
Copper	0.50	0.50	0.20	0.50	0.50	0.50
Nickel
Chromium	0.40	0.40	0.20
Molybdenum	0.10
Tungsten	0.10	0.10	0.10	0.10	0.10	0.10
Vanadium	0.03	0.03	0.02	0.05	0.05	0.05
Total content of residual elements	0.75	0.75	0.50	0.50	0.50	0.50

^A Proprietary steel composition.

^B For each reduction of 0.01 % below the specified maximum carbon content, an increase of 0.04 % manganese above the specified maximum will be permitted up to a maximum of 2.30 %.

9.2 On castings intended for use under the ASME Boiler and Pressure Vessel Code, repairs shall be made by procedures and welders qualified under Section IX of that code.

9.3 After repair welding, all castings shall be postweld heat treated in accordance with Table 4 or reheat treated in accordance with Table 1.

9.4 Weld repairs shall be inspected using the same quality standards as are used to inspect the castings. Re-examination

of the weld repair by radiography when Supplementary Requirement S5 has been specified will not be necessary when an applicable surface inspection method was used to locate the discontinuity except for the following:

9.4.1 Weld repairs on castings which have leaked on hydrostatic test.