



Designation: C171 – 07

Standard Specification for Sheet Materials for Curing Concrete¹

This standard is issued under the fixed designation C171; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope*

1.1 This specification covers materials in sheet form used for covering the surfaces of hydraulic cement concrete to inhibit moisture loss during the curing period and, in the case of the white reflective type materials, to also reduce temperature rise in concrete exposed to radiation from the sun. The following types are included:

1.1.1 Curing Paper:

1.1.1.1 Regular.

1.1.1.2 White.

1.1.2 Polyethylene Film:

1.1.2.1 Clear.

1.1.2.2 White Opaque.

1.1.3 White-Burlap-Polyethylene Sheet.

1.2 The values stated in SI units are to be regarded as the standard. Inch-pound units are provided in parentheses for information only.

NOTE 1—This specification does not cover materials such as burlap, cotton mats, or rugs used with additional applications of water to maintain a water-saturated environment on such surfaces. Procedures employing these materials are discussed in ACI 308R. Sheet materials having additional characteristics such as insulating properties and the ability to carry additional water to the curing region are commercially available but are not currently addressed in this specification.

1.3 The text of this standard references notes and footnotes which provide explanatory material. These notes and footnotes shall not be considered as requirements of the standard.

2. Referenced Documents

2.1 ASTM Standards:²

C156 Test Method for Water Loss [from a Mortar Specimen] Through Liquid Membrane-Forming Curing Compounds for Concrete

¹ This specification is under the jurisdiction of ASTM Committee C09 on Concrete and Concrete Aggregates and is the direct responsibility of Subcommittee C09.22 on Materials Applied to New Concrete Surfaces.

Current edition approved Nov. 1, 2007. Published December 2007. Originally approved in 1942. Last previous edition approved in 2003 as C171–03. DOI: 10.1520/C0171-07.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

D829 Test Methods for Wet Tensile Breaking Strength of Paper and Paper Products (Withdrawn 2009)³

D4397 Specification for Polyethylene Sheeting for Construction, Industrial, and Agricultural Applications

E96/E96M Test Methods for Water Vapor Transmission of Materials

E1347 Test Method for Color and Color-Difference Measurement by Tristimulus Colorimetry

2.2 ACI Standard:

ACI 308R Standard Practice for Curing Concrete⁴

3. Terminology

3.1 Definitions:

3.1.1 *curing paper, n*—a composite consisting of two layers of kraft paper bonded together with a bituminous material and reinforced with fiber, used for covering the surface of fresh concrete to inhibit moisture loss during the curing period.

4. Ordering Information

4.1 The purchaser shall specify the type of curing material to be furnished under this specification.

4.2 Lengths and widths of the rolls or mats of the sheet materials furnished shall be as agreed upon between the purchaser and seller.

5. Performance Requirements

5.1 The sheet materials furnished under this specification shall be tough, strong, resilient, and capable of withstanding normal job use without puncturing or tearing.

5.2 The sheet material shall exhibit a water vapor transmission rate (WVTR) of no more than 10 g/m² in 24 h when tested according to Test Methods E96/E96M using the Water Method in the environment (test cabinet) specified in Test Method C156.

5.3 The daylight reflectance of the white side of white curing paper shall be at least 50 % when measured by Test Method E1347. The daylight reflectance of white polyethylene

³ The last approved version of this historical standard is referenced on www.astm.org.

⁴ Available from American Concrete Institute (ACI), P.O. Box 9094, Farmington Hills, MI 48333-9094, http://www.aci-int.org.

*A Summary of Changes section appears at the end of this standard