DRAFT INTERNATIONAL STANDARD ISO/DIS 16742



ISO/TC 102/SC 1

Secretariat: JISC

Voting begins on 2013-04-05

Voting terminates on 2013-07-05

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION • MEXICYHAPODHAR OPFAHUSALUN FIO CTAHDAPTUSALUN • ORGANISATION INTERNATIONALE DE NORMALISATION

Iron ores — Sampling of slurries

Minerais de fer — Échantillonnage des schlamms

ICS 73.060.10

n, this document is 'ecretariat work of jon, le pr 'avail -'st' To expedite distribution, this document is circulated as received from the committee secretariat. ISO Central Secretariat work of editing and text composition will be undertaken at publication stage.

Pour accélérer la distribution, le présent document est distribué tel qu'il est parvenu du secrétariat du comité. Le travail de rédaction et de composition de texte sera effectué au Secrétariat central de l'ISO au stade de publication.

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.





COPYRIGHT PROTECTED DOCUMENT

© ISO 2013

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office Case postale 56 • CH-1211 Geneva 20 Tel. + 41 22 749 01 11 Fax + 41 22 749 09 47 E-mail copyright@iso.org Web www.iso.org

Published in Switzerland

Contents

Forewo	ord	. v
1	Scope	.1
2	Normative references	.1
3	Definitions	.2
4	General considerations for sampling slurries	.2
4.1	Basic requirements	.2
4.2	Sampling errors	.3
4.3	Establishing a sampling scheme	.4
5	Fundamentals of sampling and sample preparation	.6
5.1	Minimization of bias	.6
5.2	Volume of increment for falling stream samplers to avoid bias	.7
5.2.1	Linear cross-stream cutter	.7
5.2.2	Vezin cutter	.8
5.3	Volume of increment for manual sampling to avoid bias	.8
5.4	Overall precision	.9
5.5	Quality variation	0
5.6	Sampling precision and number of primary increments	11
5.7	Precision of sample preparation and overall precision	11
6	Minimum mass of solids in gross and partial samples	12
6.1	General	12
6.2	Minimum mass of solids in gross samples	2
6.3	Minimum mass of solids in partial samples	13
-	Time have a sum line have been	
1		13
7.1	General	13
1.2		13
7.3	Cutters	13
7.4	Constitution of groot or partial complex	14
7.5	Division of pross of partial samples	14
7.0	Division of areas complex	14
79	Number of cuts for division	14
1.0		14
8	Stratified random sampling within fixed time intervals	14
9	Mechanical sampling from moving streams	15
9.1	General	15
9.2	Design of the sampling system	15
9.2.1	Safety of operators	15
9.2.2	Location of sample cutters	15
9.2.3	Provision for duplicate sampling	15
9.2.4	System for checking the precision and bias	15
9.2.5	Minimizing bias	6
9.3	Slurry sample cutters	6
9.3.1	General	6
9.3.2	Falling-stream cutters	17
9.3.3	Cutter velocities	17
9.4	Mass of solids in increments	17
9.5	Number of primary increments	17
9.6	Routine checking	17

10	Manual sampling from moving streams	18
10.1	General	18
10.2	Choosing the sampling location	18
10.3	Sampling implements	18
10.4	Volume of increments	18
10.5	Number of primary increments	18
10.6	Sampling procedures	19
11	Sampling of stationary slurries	19
12	Sample preparation procedures	19
12.1	General	19
12.2	Grinding mills	20
12.3	Sample division	20
12.4	Chemical analysis samples	20
12.5	Physical test samples	20
13	Packing and marking of samples	20
Annex	A (informative) Examples of correct slurry sampling devices	21
Annex	B (informative) Examples of incorrect slurry sampling devices	23
Annex	C (normative) Manual sampling implements	26

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75% of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

This Working Draft was prepared by Technical Committee ISO/TC 102/SC 1, Iron ores and direct reduced iron - Sampling.

Hensilsandanapageenalingenalis

Iron ores – Sampling of slurries

WARNING – This International Standard may involve hazardous materials, operations and equipment, and does not purport to address all the safety issues associated with its use. It is the responsibility of the user of this International Standard to establish appropriate health and safety practices and determine the applicability of regulatory limitations prior to use.

1 Scope

This International Standard sets out the basic methods for sampling fine iron ore of nominal top size <1 mm that is mixed with water to form a slurry. At very high ratios of fine solids to water when the material assumes a soft plastic form (about 80% solids depending on the particle size distribution of the solids), the mixture is correctly termed a paste. Sampling of pastes is not covered in this International Standard.

The procedures described in this International Standard apply to sampling of iron ore that is transported in moving streams as a slurry. These streams may fall treely or be confined in pipes, launders, chutes, spirals or similar channels. Sampling of slurries in pressurised pipes is not covered in this International Standard. The slurry stream can only be sampled satisfactorily at a transfer point prior to the pressurised pipe at the end of the pipe when the slurry is no longer under pressure. In addition, sampling of slurries in stationary situations, such as a settled or even a well-stirred slurry in a tank, holding vessel or dam, is not recommended and is not covered in this International Standard.

This International Standard describes procedures that are designed to provide samples representative of the slurry solids and particle size distribution of the slurry under examination. After filtration of the slurry sample, damp samples of the contained solids in the slurry are available for drying (if required) and measurement of one or more characteristics in an unbiased manner and with a known degree of precision. The characteristics are measured by chemical analysis, physical testing or both.

The sampling methods described are applicable to slurries that require inspection to verify compliance with product specifications, determination of the value of a characteristic as a basis for settlement between trading partners or estimation of a set of average characteristics and variances that describe a system or procedure.

Provided flow rates are not too high, the reference method against which other sampling procedures are compared is one where the entire stream is diverted into a vessel for a specified time or volume interval, ensuring that all parts of the stream are diverted into the vessel for the same period of time. This method corresponds to the stopped-belt method described in ISO 3082. Reference increments shall be taken as close as possible to increments taken using the sampling procedure under evaluation.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the cited edition applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IS0 565, Test sieves – Metal wire cloth, perforated metal plate and electroformed sheet – Nominal top sizes of openings.

IS0 3082, Iron ores – Sampling and sample preparation procedures.

IS0 3084, Iron ores – Experimental methods for evaluation of quality variation.

ISO 3085, Iron ores – Experimental methods for checking the precision of sampling, sample preparation and measurement.

IS0 3086, Iron ores – Experimental methods for checking the bias of sampling.

IS0 3087, Iron ores - Determination of the moisture content of a lot.

IS0 4701, Iron ores – Determination of size distribution by sieving.

IS0 11323, Iron ore and direct reduced iron - Vocabulary.

3 Definitions

For the purpose of this International Standard, the definitions given in ISO 11323 apply.

4 General considerations for sampling slurries

4.1 Basic requirements

In this International Standard, a slurry is defined as iron ore of nominal top size <1 mm that is mixed with water, which is frequently used as a convenient form to transport iron ore by means of pumps and pipelines and under gravity in launders or chutes or through long distances in slurry pipelines. Tailings from wet plants are also discharged as a slurry through pipelines to tailings dams. In many of these operations, collection of increments at selected sample points is required for evaluation of the iron ore in the slurry.

A gross or partial sample is constituted from a set of unbiased primary increments from a lot. The sample containers and their contained combined increments are weighed immediately after collection to avoid water loss by evaporation or spillage. Weighing is necessary to determine the percentage of solids by mass in the gross sample. The gross or partial sample may then be filtered, dried and weighed. Alternatively, the gross or partial sample may be sealed in plastic bags after filtering for transport and drying at a later stage.

Test samples are prepared from gross or partial samples after filtering and drying after breaking up any lumps that have formed during drying using a lump breaker or forcing the sample through a sieve of appropriate aperture. Test portions may then be taken from the test sample and analysed using an appropriate analytical method or test procedure under prescribed conditions.

The objective of the measurement chain is to determine the characteristic of interest in an unbiased manner with an acceptable and affordable degree of precision. The general sampling theory, which is based on the additive property of variances, can be used to determine how the variances of sampling, sample preparation and chemical analysis or physical testing propagate and hence determine the total variance for the measurement chain. This sampling theory can also be used to optimise mechanical sampling systems and manual sampling methods.

If a sampling scheme is to provide representative samples, all parts of the slurry in the lot must have an equal opportunity of being selected and appearing in the gross sample for testing. Any deviation from this basic requirement can result in an unacceptable loss of trueness. A sampling scheme having incorrect selection techniques, i.e. with non-uniform selection probabilities, cannot be relied upon to provide representative samples.

Sampling of slurries should preferably be carried out by systematic sampling on a time basis (see Clause 7). If the slurry flow rate and the solids concentration vary with time, the slurry volume and the dry solids mass for each increment will vary accordingly. It needs to be shown that no systematic error (bias) is introduced by periodic variation in quality or quantity where the proposed sampling interval is approximately equal to a

multiple of the period of variation in quantity or quality. Otherwise, stratified random sampling should be used (see Clause 8).

Best practice for sampling slurries is to mechanically cut freely falling streams (see Clause 9), with a complete cross section of the stream being taken during the traverse of the cutter. Access to freely falling streams can sometimes be engineered at the end of pipes or by incorporating steps or weirs in launders and chutes. If samples are not collected in this manner, non-uniform concentration of solids in the slurry due to segregation and stratification of the solids may lead to bias in the sample that is collected. Slurry flow in pipes can be homogenous with very fine particles dispersed uniformly in turbulent suspension along the length and across the diameter of the pipe. However, more commonly, the slurry in a pipe will have significant particle concentration gradients across the pipe and there may be concentration fluctuations along the length of the pipe. These common conditions are called heterogeneous flow. Examples of such flow are full pipe flow of a heterogeneous suspension or partial pipe flow of a fine suspension above a slower moving or even stationary bed of coarser particles in the slurry.

For heterogeneous flow, bias is likely to occur where a tapping is made into the slurry pipe to locate either a flush fitting sample take-off pipe or a sample tube projecting into the slurry stream for extraction of samples. The bias is caused by non-uniform concentration profiles in the pipe and the different trajectories followed by particles of different masses due to their inertia, resulting in larger or denser particles being preferentially rejected from or included in the sample.

In slurry channels such as launders, heterogenous flow is almost always present, and this non-uniformity in particle concentration is usually preserved in the discharge over a weir or step. However, sampling at a weir or step allows complete access to the full width and breadth of the stream, thereby enabling all parts of the slurry stream to be collected with equal probability. N:0

Sampling of slurries in stationary situations, such as a settled or even a well-stirred slurry in a tank, holding vessel or dam is not recommended, because it is virtually impossible to ensure that all parts of the slurry in the lot have an equal opportunity of being selected and appearing in the gross sample for testing. Instead, sampling should be carried out from moving streams as the tank, vessel or dam is filled or emptied. Sitehaile

4.2 Sampling errors procedure has its own uncertainty appearing as variations in the final results. When the average of these variations is close to zero, they are called random errors. More serious variations contributing to the uncertainty of results are systematic errors, which have averages biased away from zero. There are also human errors that introduce variations due to departures from prescribed procedures for which statistical analysis procedures are not applicable.

Sampling from moving slurry streams usually involves methods that fall into three broad operational categories as follows:

- Taking the whole stream part of the time with a cross-stream cutter as shown in Figure 1(a) (after Pitard, a) 1993), usually when the slurry falls from a pipe or over a weir or step. Cuts 1 and 2 show correct sampling with the cutter diverting all parts of the stream for the same length of time. Cuts 3, 4 and 5 show incorrect sampling where the cutter diverts different parts of the stream for different lengths of time.
- b) Taking part of the stream all of the time as shown in Figure 1(b) (after Pitard, 1993) with an in-stream point sampler or probe within a pipe or channel, which is always incorrect.
- Taking part of the stream part of the time as shown in Figure 1(c) (after Pitard, 1993), also with an in-C) stream point sampler or probe within a pipe or channel, which is always incorrect.



Figure 1 — Plan view of slurry volumes diverted by sample cutters

4.3 Establishing a sampling scheme

Most sampling operations are routine and are carried out to determine the average quality characteristics of a lot as well as variations in quality characteristics between lots for monitoring and controlling quality. In establishing a sampling scheme for routine sampling so that the required precision for a lot can be obtained, it is necessary to carry out the following sequence of steps. This sequence includes experimental procedures that are non-routine and carried out infrequently, e.g. determining quality variation in step (d), particularly when a significant change has occurred to the slurry source or to the sampling equipment. The procedure is as follows:

- a) Define the purpose for which the samples are being taken. Sampling for commercial transactions is usually the main purpose of sampling standards. However, the procedures described in this standard are equally applicable to monitoring plant performance, process control and metallurgical accounting.
- b) Define the lot by specifying the duration of slurry flow, e.g. one day of operation.
- c) Identify the quality characteristics to be measured and specify the overall precision (combined precision of sampling, sample preparation and measurement) required for each quality characteristic. If the required

precision results in impractical numbers of increments and/or partial samples, it may be necessary to adopt a poorer precision.

- d) Determine the quality variation of the contained solids in the slurry and the precision of preparation and measurement for the quality characteristics under consideration (see 5.5).
- e) Determine the number of increments required to attain the desired precision (see 5.6).
- f) Ascertain the apparent density of the solids in the slurry and the percentage solids by mass in the slurry for determining the mass of the solids in each slurry increment (see 5.2).
- g) Check that the procedures and equipment for taking slurry increments minimise bias (see 5.1).
- h) Determine the sampling interval in minutes for time-basis systematic sampling (see Clause 7) or stratified random sampling within fixed time intervals (see Clause 8).
- i) Take slurry increments at the intervals determined in step (h) during the whole period of handling the lot.

During sampling operations, partial samples may be combined to constitute a single gross sample for analysis (see Figure 2). Alternatively, increments may be used to constitute partial samples for analysis, which will also improve the overall precision of the measured quality characteristics of the lot. Other reasons for separate preparation and analysis of partial samples are:

- a) For convenience of materials handling;
- b) To provide progressive information on the quality of the lot; or
- c) To provide reference or reserve samples after division

Each increment may also be analysed separately to determine the increment variance of quality characteristics of the lot. In addition, assuming there is no correlation between adjacent increments, it is recommended that the precision achieved in practice should be checked on an ongoing basis by duplicate sampling where alternate increments are diverted to partial or gross samples A and B from which two test samples are prepared and analysed. A substantial number of sample pairs is required (preferably at least 20) to obtain a reliable estimate of precision (see ISO 3085).

In most situations the solids in the slurry increment will not need to be crushed or pulverised to allow further division, since most slurries contain only fine particles. However, if the particles are coarse and particle size reduction is required to allow further division, it is necessary to re-determine the minimum sample mass for the lot using the new nominal top size of the crushed solids (see 6.2).

The initial design of a sampling scheme for a new plant or a slurry with unfamiliar characteristics should, wherever possible, be based on experience with similar handling plants and material types. Alternatively, a substantial number of increments, e.g. 100, can be taken and used to determine the quality variation of the contained solids, but the precision of sampling cannot be determined *a priori*.

Sampling of slurries in stationary situations, such as a settled or even a well-stirred slurry in a tank, holding vessel or dam, is not recommended and is not covered in this International Standard.