

Third edition  
2014-12-15

Corrected version  
2014-12-15

---

---

**Jewellery — Determination of gold in  
gold jewellery alloys — Cupellation  
method (fire assay)**

*Joallerie — Dosage de l'or dans les alliages d'or pour la bijouterie-  
joallerie — Méthode de coupellation (essai au feu)*

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[ISO 11426:2014](https://standards.iteh.ai/catalog/standards/sist/c694ef18-af1a-40ed-a744-a82e43fec21d/iso-11426-2014)

[https://standards.iteh.ai/catalog/standards/sist/c694ef18-af1a-40ed-a744-  
a82e43fec21d/iso-11426-2014](https://standards.iteh.ai/catalog/standards/sist/c694ef18-af1a-40ed-a744-a82e43fec21d/iso-11426-2014)



Reference number  
ISO 11426:2014(E)

© ISO 2014

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

ISO 11426:2014

<https://standards.iteh.ai/catalog/standards/sist/c694ef18-af8a-40ed-a744-a82e43fec21d/iso-11426-2014>



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2014

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

|  | Page      |
|--|-----------|
| <b>Foreword</b> .....  | <b>iv</b> |
| <b>Introduction</b> .....  | <b>v</b>  |
| <b>1 Scope</b> .....   | <b>1</b>  |
| <b>2 Normative references</b> .....  | <b>1</b>  |
| <b>3 Principle</b> .....   | <b>1</b>  |
| <b>4 Reagents</b> .....  | <b>1</b>  |
| <b>5 Apparatus</b> .....   | <b>2</b>  |
| <b>6 Sampling</b> .....  | <b>3</b>  |
| <b>7 Procedure</b> .....   | <b>3</b>  |
| 7.1 General.....   | 3         |
| 7.2 Yellow and red gold alloys, free of nickel, and palladium white gold alloys..... | 3         |
| 7.2.1 Assay sample.....  | 3         |
| 7.2.2 Proof assay samples.....   | 3         |
| 7.2.3 Cupellation and treatment of precious metal buttons.....                       | 3         |
| 7.2.4 Parting of the silver/gold samples.....  | 3         |
| 7.3 White gold alloys containing nickel.....   | 4         |
| 7.3.1 General.....   | 4         |
| 7.3.2 Cupellation with additional lead.....  | 4         |
| 7.3.3 Scorification.....   | 4         |
| 7.4 White gold alloys containing palladium.....                                      | 5         |
| 7.5 Gold alloys incorporating more than 40 % silver.....                             | 5         |
| 7.6 Alloys containing 999 ‰ gold.....  | 5         |
| <b>8 Calculation and expression of results</b> .....                                 | <b>5</b>  |
| 8.1 Proof assay sample factor.....   | 5         |
| 8.2 Calculation of gold content.....   | 6         |
| 8.3 Repeatability.....   | 6         |
| <b>9 Test report</b> .....   | <b>6</b>  |
| <b>Bibliography</b> .....  | <b>7</b>  |

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT), see the following URL: [Foreword — Supplementary information](#).

The committee responsible for this document is ISO/TC 174, *Jewellery*.

This third edition cancels and replaces the second edition (ISO 11426:1997), which has been technically revised with the following changes:

- change in the scope that this method is the referee method;
- change of requirement for sampling in [Clause 6](#);
- addition of a warning in [Clause 7](#) that suitable health and safety procedures should be followed;
- addition of red gold alloys in [7.2](#);
- addition of requirements in [7.3.1](#) for white gold alloys containing nickel and palladium;
- standard editorially revised.

This corrected version of ISO 11426:2014 incorporates the following correction:

- In 4.5, first dash: change of the value “999,99” into “999,9”.

## Introduction

The following definitions apply in understanding how to implement an ISO International Standard and other normative ISO deliverables (TS, PAS, IWA).

- “shall” indicates a requirement
- “should” indicates a recommendation
- “may” is used to indicate that something is permitted
- “can” is used to indicate that something is possible, for example, that an organization or individual is able to do something

ISO/IEC Directives, Part 2 (sixth edition, 2011), 3.3.1 defines a requirement as an “expression in the content of a document conveying criteria to be fulfilled if compliance with the document is to be claimed and from which no deviation is permitted.”

ISO/IEC Directives, Part 2 (sixth edition, 2011), 3.3.2 defines a recommendation as an “expression in the content of a document conveying that among several possibilities one is recommended as particularly suitable, without mentioning or excluding others, or that a certain course of action is preferred but not necessarily required, or that (in the negative form) a certain possibility or course of action is deprecated but not prohibited.”

## iTeh STANDARD PREVIEW (standards.iteh.ai)

[ISO 11426:2014](https://standards.iteh.ai/catalog/standards/sist/c694ef18-af8a-40ed-a744-a82e43fec21d/iso-11426-2014)

<https://standards.iteh.ai/catalog/standards/sist/c694ef18-af8a-40ed-a744-a82e43fec21d/iso-11426-2014>

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[ISO 11426:2014](#)

<https://standards.iteh.ai/catalog/standards/sist/c694ef18-affa-40ed-a744-a82e43fec21d/iso-11426-2014>

# Jewellery — Determination of gold in gold jewellery alloys — Cupellation method (fire assay)

## 1 Scope

This International Standard specifies a cupellation method (fire assay) for the determination of gold in gold jewellery alloys. The gold content of the alloys should preferably lie between 333 and 999 parts per thousand (‰).

The procedure is applicable specifically to gold alloys incorporating silver, copper, and zinc. Some modifications are indicated where nickel and/or palladium are present in the so-called white gold alloys, as well as for alloys containing 990 or more parts per thousand (‰) of gold.

This International Standard is intended to be used as the recommended method for the determination of fineness in alloys covered by ISO 9202.

## 2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 11596, *Jewellery — Sampling of precious metal alloys for and in jewellery and associated products*

## 3 Principle

<https://standards.iteh.ai/catalog/standards/sist/c694ef18-af4a-40ed-a744-a82e43fec21d/iso-11426-2014>

The gold alloys are inquarted with silver, compounded with lead, and cupelled in a cupellation furnace until a precious metal button is obtained. After flattening and rolling, the silver is extracted (parted) in nitric acid and the gold weighed. Possible systematic errors in the procedure are eliminated by assaying standard proof samples in parallel.

**NOTE** Inquartation is the addition of silver to gold alloys in a specific ratio in order to enable the parting of gold from silver by means of nitric acid.

## 4 Reagents

During the analysis, unless otherwise stated, use only reagents of recognized analytical grade and only distilled water or water of equivalent purity.

**4.1 Nitric acid (HNO<sub>3</sub>)**, 33 % (mass fraction), with sufficiently low content of halides (check with silver nitrate test).

**4.2 Nitric acid (HNO<sub>3</sub>)**, 49 % (mass fraction), with sufficiently low content of halides (check with silver nitrate test).

**4.3 Lead**, assay grade, free of precious metals and bismuth, as foil, beads, or tablets.

**4.4 Pure silver**, for inquartation, minimum purity 999 parts per thousand (‰) by mass, free of gold and platinum group metals.

**4.5 Pure gold**, for proof samples

## ISO 11426:2014(E)

- for determination of gold between 333 and 990 parts per thousand (‰) by mass, minimum purity 999,9 parts per thousand (‰) by mass, and
- for determination of gold more than 990 parts per thousand (‰) by mass, minimum purity 999,99 parts per thousand (‰) by mass.

**4.6 Pure palladium**, for proof samples, minimum purity 999,5 parts per thousand (‰) by mass, free of gold.

**4.7 Nickel**, for proof samples, in a form of an appropriate pre-alloy (free of precious metals).

**4.8 Copper (foil or wire)**, for proof samples, minimum purity 999 parts per thousand (‰) by mass, free of gold and platinum group metals.

**4.9 Sodiumtetraborate (Na<sub>2</sub>B<sub>4</sub>O<sub>7</sub>)**, anhydrous.

## 5 Apparatus

**5.1 Ordinary laboratory apparatus.**

**5.2 Cupellation furnace**, in which an oxidizing atmosphere can be maintained.

**CAUTION** — A standard muffle furnace is not satisfactory for this purpose.

**5.3 Magnesia cupels**, in form of single or block cupels, capable of absorbing the resulting lead and base metal oxides.

**5.4 Parting flasks or nitric acid resistant basket, with thimbles.**

**5.5 Annealing crucibles**, made of refractory materials.

**5.6 Cupellation tongs.**

**5.7 Assay pliers.**

**5.8 Polished anvil**, which may be replaced by a press, polished and reserved for this purpose.

**5.9 Polished hammer**, of minimum mass 400 g, which may be replaced by a press, polished, and reserved for this purpose.

**5.10 Scorification dishes**, usually of 50 mm in diameter.

**5.11 Jewellers' rolls.**

**5.12 Scorification tongs.**

**5.13 Assay cleaning brush.**

**5.14 Analytical balance**, with a reading accuracy of 0,01 mg.



## 6 Sampling

The sampling procedure for jewellery gold alloys shall be performed in accordance with ISO 11596.

## 7 Procedure

**WARNING — Suitable health and safety procedures should be followed.**

### 7.1 General

When the composition of the samples is unknown, a preliminary analysis by suitable means should be used to determine the approximate composition of the material, e.g. XRF analysis.

### 7.2 Yellow and red gold alloys, free of nickel, and palladium white gold alloys

#### 7.2.1 Assay sample

Transfer at least two samples of the alloy, preferably between 125 mg and 250 mg, weighed to the nearest 0,01 mg, into assay-grade lead foil (4.3). The mass of the foil (or foil and beads) should be at least 4 g for considered gold alloy samples up to 200 mg, and 6 g for samples from 201 mg to 300 mg. Add pure silver (4.4) equivalent to 2,3 to 3 times the mass of fine gold present. Roll and compress the lead foil into a tight ball.

#### 7.2.2 Proof assay samples

Weigh, as in 7.2.1, at least two proof assay samples of pure gold (4.5) and pure silver (4.4) in masses which correspond to the expected gold and silver contents (including the inquartation addition) of the assay sample. The total content of base metals in the assay samples is taken into consideration by the addition of a corresponding quantity of copper.

Treat the proof assay samples and the assay samples in 7.2.3 and 7.2.4 in the same manner.

#### 7.2.3 Cupellation and treatment of precious metal buttons

Place the assay and the proof assay samples (7.2.2), tightly wrapped in lead foil, on magnesia cupels (5.3), which have been preheated to at least 1 000 °C in the cupellation furnace (5.2).

Place the cupels with the proof assay samples as close as possible to the corresponding assay samples in the cupellation furnace maintained at 1 050 °C to 1 150 °C. Continue heating (about 25 min) under oxidizing conditions until the cupellation process is completed. Remove the cupels from the furnace. Allow the precious metal buttons to cool down before lifting them from the cupels with the assay pliers (5.7). Squeeze the buttons and brush their undersides carefully with a brush (5.13) to remove any adhering cupel material. Flatten the beads on the polished anvil (5.8) with a polished hammer (5.9) and anneal by heating just to red heat.

Roll them into 0,12 mm to 0,15 mm thick strips and anneal again. Roll the strips into cornets without contamination or loss of gold.

The cupel should be examined carefully to ensure that the precious metal bead contains all gold of the sample. If small droplet residues are present, a full assay has to be repeated.

#### 7.2.4 Parting of the silver/gold samples

**CAUTION — For the parting operations with nitric acid, a fume hood should be kept clean and used exclusively for this determination.**