



Designation: D 4643 – 00

Standard Test Method for Determination of Water (Moisture) Content of Soil by the Microwave Oven Heating¹

This standard is issued under the fixed designation D 4643; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope *

1.1 This test method outlines procedures for determining the water (moisture) content of soils by incrementally drying soil in a microwave oven.

1.2 This test method can be used as a substitute for Test Method D 2216 when more rapid results are desired to expedite other phases of testing and slightly less accurate results are acceptable.

1.3 When questions of accuracy between this test method and Test Method D 2216 arise, Test Method D 2216 shall be the referee method.

1.4 This test method is applicable for most soil types. For some soils, such as those containing significant amounts of halloysite, mica, montmorillonite, gypsum or other hydrated materials, highly organic soils, or soils in which the pore water contains dissolved solids (such as salt in the case of marine deposits), this test method may not yield reliable water content values.

1.5 The values stated in SI units are to be regarded as the standard.

1.6 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use. See Section 7.*

2. Referenced Documents

2.1 ASTM Standards:

D 653 Terminology Relating to Soil, Rock, and Contained Fluids²

D 2216 Test Method for Laboratory Determination of Water (Moisture) Content of Soil and Rock²

D 3740 Practice for Minimum Requirements for Agencies Engaged in the Testing and/or Inspection of Soil and Rock

as Used in Engineering Design and Construction²
D 4753 Specification for Evaluating, Selecting, and Specifying Balances and Scales for Use in Testing Soil, Rock, and Related Construction Materials²

3. Terminology

3.1 Definitions:

3.1.1 All definitions are in accordance with Terminology D 653.

3.2 Definitions of Terms Specific to This Standard:

3.2.1 *microwave heating*—a process by which heat is induced within a material due to the interaction between dipolar molecules of the material and an alternating, high frequency electric field. Microwaves are electromagnetic waves with 1 mm to 1 m wavelengths.

3.2.2 *water (moisture) content*—the ratio, expressed as a percentage, of the mass of “pore” or “free” water in a given mass of soil to the mass of the solid particles.

4. Summary of Test Method

4.1 A moist soil specimen is placed in a suitable container and its mass is determined. It is then placed in a microwave oven, subjected to an interval of drying, and removed from the oven and its new mass is determined. This procedure is repeated until the mass becomes nearly constant.

4.2 The difference between the mass of the moist specimen and the dried specimen is used as the mass of water originally contained in the specimen. The water content is determined by dividing the mass of water by the dry mass of soil, multiplied by 100. For a given soil and sample size, the time to achieve a constant dry mass can be noted and used as a minimum drying time for subsequent tests using the same size specimen of the same soil.

5. Significance and Use

5.1 The water content of a soil is used throughout geotechnical engineering practice both in the laboratory and in the field. The use of Test Method D 2216 for water content determination can be time consuming and there are occasions

¹ This test method is under the jurisdiction of ASTM Committee D-18 on Soil and Rock and is the direct responsibility of Subcommittee D18.08 on Special and Construction Control Tests.

Current edition approved Feb. 10, 2000. Published April 2000. Originally published as D4643 – 87. Last previous edition D4643 – 93.

² *Annual Book of ASTM Standards*, Vol 04.08.

*A Summary of Changes section appears at the end of this standard.

when a more expedient method is desirable. The use of a microwave oven is one such method.

5.2 The principal objection to the use of the microwave oven for water-content determination has been the possibility of overheating the soil, thereby yielding a water content higher than would be determined by Test Method D 2216. While not eliminating this possibility, the incremental drying procedure described in this test method will minimize its effects. Some microwave ovens have settings at less than full power, which can also be used to reduce overheating.

5.3 The behavior of a soil, when subjected to microwave energy, is dependent on its mineralogical compositions, and as a result no one procedure is applicable for all types of soil. Therefore, the procedure recommended in this test method is meant to serve as a guide when using the microwave oven.

5.4 This test method is best suited for minus No. 4 sized material. Larger size particles can be tested; however, care must be taken because of the increased chance of particle shattering.

5.5 The use of this method may not be appropriate when highly accurate results are required, or the test using the data is extremely sensitive to moisture variations.

5.6 Due to the localized high temperatures that the specimen is exposed to in microwave heating, the physical characteristics of the soil may be altered. Degregation of individual particles may occur, along with vaporization or chemical transition. It is therefore recommended that samples used in this test method not be used for other tests subsequent to drying.

NOTE 1—The quality of the results produced by this test method is dependent on the competence of the personnel performing it and the suitability of the equipment and facilities used. Agencies that meet the criteria of Practice D 3740 are generally considered capable of competent and objective testing. Users of this test method are cautioned that compliance with Practice D 3740 does not in itself ensure reliable results. Reliable results depend on many factors; Practice D 3740 provides a means of evaluating some of those factors.

6. Apparatus

6.1 *Microwave Oven*—A microwave oven, preferably with a vented chamber, is suitable. The required size and power rating of the oven is dependent on its intended use. Ovens with variable power controls and input power ratings of about 700 W have been found to be adequate for this use. Variable power controls are important and reduce the potential for overheating of the test specimen.

NOTE 2—Microwave ovens equipped with built-in scales and computer controls have been developed for use in drying soils. Their use is compatible with this test method.

6.2 *Balances*, having a capacity of 2000 g or greater and meeting the requirements of Specification D 4753 for a balance of 0.1 g readability.

6.3 *Specimen Containers*—Suitable containers made of a nonmetallic nonabsorbent material, resistant to thermal shock, and not subject to changes in mass or shape when subjected to repeated heating, cooling, or cleaning. Porcelain evaporating dishes and standard borosilicate glass dishes perform satisfactorily. Other containers, such as paper cups or plates, also have been used satisfactorily; however, they may require pre-drying prior to use.

6.4 *Container Handling Apparatus*—A glove or holder, suitable for removing hot containers from the oven.

6.5 *Desiccator*—A desiccator cabinet or jar of suitable size containing silica gel, anhydrous calcium phosphate, or equivalent. It is preferable to use a desiccant that changes color to indicate that it needs reconstitution.

6.6 *Heat Sink*—A material or liquid placed in the microwave to absorb energy after the moisture has been driven from the test specimen. The heat sink reduces the possibility of overheating the specimen and damage to the oven. Glass beakers filled with water and materials that have a boiling point above water, such as nonflammable oils, have been used successfully. Moistened bricks have also been used.

6.7 *Stirring Tools*—Spatulas, putty knives, and glass rods for cutting and stirring the test specimen before and during the test. Short lengths of glass rods have been found useful for stirring and may be left in the specimen container during testing, reducing the possibility of specimen loss due to adhesion to the stirring tool.

7. Hazards

7.1 Handle hot containers with a container holder. Some soil types can retain considerable heat, and serious burns could result from improper handling.

7.2 Suitable eye protection is recommended due to the possibility of particle shattering during the heating, mixing, or mass determinations.

7.3 Safety precautions supplied by the manufacturer of the microwave should be observed. Particular attention should be paid to keeping the door sealing gasket and door interlocks clean and in good working condition.

NOTE 3—The use of a microwave oven for the drying of soils may be considered abusive by the manufacturers and constitute voiding of warranties. Microwave drying of soils containing metallic materials may cause arcing in the oven. Highly organic soils and soils containing oils and coal may ignite and burn during microwave drying. Continued operation of the oven after the soil has reached constant weight may also cause damage or premature failure of the microwave oven.

NOTE 4—When first introduced, microwave ovens were reported to affect heart pacemakers, primarily because of the operating frequencies of the two devices. Since that time, pacemakers have been redesigned, and the microwave oven is not regarded as the health hazard it once was. However, it may be advisable to post warnings that a microwave is in use.

7.4 Highly organic soils and soils containing oil or other contaminants may ignite into flames during microwave drying. Means for smothering flames to prevent operator injury or oven damage should be available during testing. Fumes given off from contaminated soils or wastes may be toxic, and the oven should be vented accordingly.

7.5 Due to the possibility of steam explosions, or thermal stress shattering porous or brittle aggregates, a covering over the sample container may be appropriate to prevent operator injury or oven damage. A cover of heavy paper toweling has been found satisfactory for this purpose. This also prevents scattering of the test sample in the oven during the drying cycle.

7.6 Do not use metallic containers in a microwave oven because arcing and oven damage may result.