

Designation: F1580 - 07

# Standard Specification for Titanium and Titanium-6 Aluminum-4 Vanadium Alloy Powders for Coatings of Surgical Implants<sup>1</sup>

This standard is issued under the fixed designation F1580; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon  $(\varepsilon)$  indicates an editorial change since the last revision or reapproval.

## 1. Scope\*

- 1.1 This specification covers the requirements for unalloyed titanium and Ti-6Al-4V alloy powders for use in fabricating coatings on titanium alloy implants.
- 1.2 Powders covered under this specification may be used to form coatings by sintering or thermal spraying techniques.
- 1.3 This specification covers powder requirements only. It does not address properties of the coatings formed from them.
- 1.4 Finely divided titanium powder may be considered pyrophoric and should be handled in accordance with the appropriate guidelines.

# 2. Referenced Documents

2.1 ASTM Standards:<sup>2</sup>

B214 Test Method for Sieve Analysis of Metal Powders

B215 Practices for Sampling Metal Powders

**B299** Specification for Titanium Sponge

E11 Specification for Woven Wire Test Sieve Cloth and Test Sieves

E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications

E2371 Test Method for Analysis of Titanium and Titanium Alloys by Atomic Emission Plasma Spectrometry

F67 Specification for Unalloyed Titanium, for Surgical Implant Applications (UNS R50250, UNS R50400, UNS R50550, UNS R50700)

F981 Practice for Assessment of Compatibility of Biomaterials for Surgical Implants with Respect to Effect of Materials on Muscle and Bone

F1472 Specification for Wrought Titanium-6Aluminum-4Vanadium Alloy for Surgical Implant Applications (UNS R56400)

2.2 ISO Standards:<sup>3</sup>

ISO 9001 Quality Management System Requirements 2.3 American Society for Quality (ASQ) Standards:<sup>4</sup>

ASQ C1 General Requirements for a Quality Program 2.4 *Aerospace Material Specifications:*<sup>5</sup>

AMS 2249 Chemical Check Analysis Limits, Titanium and Titanium Alloys

AMS 4998 Powder, 6Al-4V

## 3. Significance and Use

3.1 Coatings formed from metallic powders have become widely used as a means of improving tissue attachment to implants. Such coatings have also been demonstrated to improve bonding of acrylic cement to prostheses. This specification addresses the special requirements of the metal powders used to form these coatings.

## 4. Methods of Manufacture

4.1 Powders may be manufactured by the plasma rotating electrode process, inert gas atomization, hydride-dehydride, or other method capable of producing powder meeting the requirements of this specification.

#### 5. Chemical Requirements

- 5.1 The chemical analysis of the powder shall conform to the requirements specified in Table 1.
- 5.1.1 Requirements for the major and minor elemental constituents for unalloyed titanium and Ti-6Al-4V alloy powders are listed in Table 1. Also listed are all important residual elements. Analysis for elements not listed in Table 1 is not required to verify compliance with this specification.
- 5.2 The product analysis tolerance shall conform to the requirements set forth in Table 2.
  - 5.3 For referee purposes, Test Method E2371 shall be used.
- 5.4 Intentional elemental additions other than those specified in Table 1 are not permitted.

<sup>&</sup>lt;sup>1</sup> This specification is under the jurisdiction of ASTM Committee F04 on Medical and Surgical Materials and Devices and is under the direct responsibility of Subcommittee F04.12 on Metallurgical Materials.

Current edition approved Dec. 1, 2007. Published December 2007. Originally approved in 1995. Last previous edition approved in 2001 as F1580 - 01. DOI: 10.1520/F1580-07.

<sup>&</sup>lt;sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>&</sup>lt;sup>3</sup> Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, http://www.ansi.org.

<sup>&</sup>lt;sup>4</sup> Available from American Society for Quality (ASQ), 600 N. Plankinton Ave., Milwaukee, WI 53203, http://www.asq.org.

<sup>&</sup>lt;sup>5</sup> Available from Society of Automotive Engineers (SAE), 400 Commonwealth Dr., Warrendale, PA 15096-0001, http://www.sae.org.

**TABLE 1 Chemical Requirements** 

Element	Unalloyed Ti Powder <sup>A</sup> % (mass/mass)		Ti Sponge Powder <sup>B</sup> % (mass/mass)		Ti-6Al-4V Powder <sup>C</sup> % (mass/mass)		
	Min	Max	Min	Max	Min	Max	
Al				0.05	5.50	6.75	
V					3.50	4.50	
0		0.40		$0.40^{D}$		0.20	
Fe		0.50		0.15		0.30	
С		0.08		0.03		0.08	
Н		0.05		0.03		0.015	
N		0.05		0.02		0.05	
Cu						0.10	
Sn						0.10	
Si				0.04			
CI				0.20 <sup>E</sup>			
Na				F			
Υ						$0.005^{C}$	
Ti	balance <sup>G</sup>		bala	balance <sup>G</sup>		balance <sup>G</sup>	

<sup>&</sup>lt;sup>A</sup> Chemistry per Specification F67 except hydrogen.

TABLE 2 Product Analysis Tolerances<sup>A</sup>

Element	Element Variation Under Min or Over Max		
	IVIUX		
Aluminum	0.04		
Vanadium	0.015		
Oxygen	$0.03^{B}$		
Oxygen	$0.02^{c}$		
Hydrogen	0.002		
Iron	0.10		
Carbon	0.02		
Nitrogen	0.02 ASTM F1		
Copper	0.05		
tintps://standards.ite	eh.ai/catalog/stand0.15 s/sist/406ed4		
Silicon	0.02		
Yttrium	0.0005 <sup>C</sup>		

A Refer to AMS 2249.

5.5 For powder that includes particle size fractions finer than 200 mesh (74  $\mu$ m), the oxygen content limits shall be agreed upon between buyer and seller.

#### 6. Particle Size

6.1 Powder shall be sieved to the customer's requirements with stainless steel screens conforming to Specification E11.

Analysis of sieved powder for conformance to the customer's particle size range requirements shall be in accordance with Test Method B214.

## 7. Cleanliness

- 7.1 Powder shall be handled at all times so as to ensure freedom from contamination with nonmetallic materials or other metal alloy powders or both.
- 7.2 Powder cleanliness shall be determined by examining a representative sample, per Practices B215 or as agreed upon between buyer and seller, comprising at least 1 in.<sup>2</sup> (6.45 cm<sup>2</sup>) of a closely packed mono-layer of powder per lot at 20× magnification. No foreign material shall be visible under these conditions.

## 8. Significance of Numerical Limits

8.1 The following applies to all specified numerical limits in this specification. To determine conformance to these limits, an observed or calculated value shall be rounded to the nearest unit in the last right hand digit used in expressing the specification limit, in accordance with the rounding method of Practice E29.

#### 9. Certification

- 9.1 Powder shipped under this specification shall be accompanied by certification that includes:
  - 9.1.1 ASTM designation and date of issue.
  - 9.1.2 Quantity (weight).
  - 9.1.3 Method of manufacture.
- 9.1.4 Chemical analysis per 5.1.
- 9.1.5 Sieve analysis per 6.1.
- 9.1.6 Powder cleanliness per 7.2.
- 580-9.1.7 Other requirements.

# 10. Quality Program Requirements

- 10.1 The supplier shall maintain a quality program, such as that defined in the ASQ C1 or ISO 9001, for example.
- 10.2 The purchaser shall be ensured of the supplier's quality program for conformance to the intent of ASQ C1 or other recognized programs.

# 11. Keywords

11.1 coatings; metallic; metals (for surgical implants titanium alloys); orthopaedic medical devices (titanium/titanium alloys); powder; porous coatings; titanium/titanium alloys (for surgical implants)

<sup>&</sup>lt;sup>B</sup> Chemistry per Specification B299, general purpose grade.

<sup>&</sup>lt;sup>C</sup> Chemistry per Specification F1472.

<sup>&</sup>lt;sup>D</sup> Oxygen per Specification B299 is 0.15 %. This level is reasonable for sponge product but not for powder because of the increased surface area of small particle powder product.

<sup>&</sup>lt;sup>E</sup>Lower maximum chlorine content may be agreed upon between buyer purchaser and seller supplier.

<sup>&</sup>lt;sup>F</sup> Sodium or magnesium, 0.50 maximum.

<sup>&</sup>lt;sup>G</sup> The percentage of titanium is determined by difference and need not be measured.

<sup>&</sup>lt;sup>B</sup> For unalloyed Ti powder.

<sup>&</sup>lt;sup>C</sup> For Ti-6Al-4V alloy powder.