



Designation: C1283 – 07a

Standard Practice for Installing Clay Flue Lining¹

This standard is issued under the fixed designation C1283; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This practice covers the minimum requirements for installing clay flue lining for residential concrete or masonry chimneys.

1.2 The values stated in inch-pound units are to be regarded as the standard. The values stated in parentheses are for informational purposes only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

- C24 Test Method for Pyrometric Cone Equivalent (PCE) of Fireclay and High Alumina Refractory Materials
- C27 Classification of Fireclay and High-Alumina Refractory Brick
- C55 Specification for Concrete Building Brick
- C90 Specification for Loadbearing Concrete Masonry Units
- C99 Test Method for Modulus of Rupture of Dimension Stone
- C129 Specification for Nonloadbearing Concrete Masonry Units
- C170 Test Method for Compressive Strength of Dimension Stone
- C199 Test Method for Pier Test for Refractory Mortars
- C216 Specification for Facing Brick (Solid Masonry Units Made from Clay or Shale)
- C270 Specification for Mortar for Unit Masonry
- C315 Specification for Clay Flue Liners and Chimney Pots

¹ This practice is under the jurisdiction of ASTM Committee C04 on Vitrified Clay Pipe and is the direct responsibility of Subcommittee C04.20 on Methods of Test and Specifications.

Current edition approved Dec. 1, 2007. Published December 2007. Originally approved in 1994. Last previous edition approved in 2007 as C1283 – 07. DOI: 10.1520/C1283-07A.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

- C652 Specification for Hollow Brick (Hollow Masonry Units Made From Clay or Shale)
- C896 Terminology Relating to Clay Products
- C1184 Specification for Structural Silicone Sealants

3. Terminology

3.1 *General*—Terminology C896 should be used for clarification of definitions in this practice.

3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *chimney connector*—tubular unit or pipe used to convey products of combustion from a heating or cooking appliance to the chimney.

3.2.2 *flue*—passageway within a chimney through which products of combustion are conveyed.

3.2.3 *flue liner*—manufactured tubular nonloadbearing fired clay unit, normally used for conveying hot gases in chimneys.

3.2.4 *masonry chimney*—vertical structure constructed of brick, concrete, concrete masonry units, or stone, which contains one or more flues, and conveys products of combustion from a heat source or cooking appliance.

3.2.5 *smoke chamber*—section of a fireplace above the throat and below the flue, which is an area of transition from the shape of the throat to the shape of the flue.

3.2.6 *thimble*—manufactured tubular nonloadbearing fired clay unit normally used to connect the chimney connector from an appliance through the wall of the chimney to the flue.

4. Footings and Foundations

4.1 Footings for masonry chimneys shall be constructed of concrete or solid masonry at least 12 in. (305 mm) thick, and it shall extend at least 6 in. (150 mm) beyond the face of the foundation or support wall on all sides. Footings shall be founded below frost depth on natural undisturbed earth or engineered fill. In areas not subjected to freezing, footings shall be founded at least 12 in. (305 mm) below finished grade.

4.2 The foundation shall be placed, with respect to adjacent structures existing or anticipated, to minimize the possibility of damage by construction operations or by transmission of additional loads to the supporting soils.

4.3 Concrete footings and foundations shall conform to local building codes.