## INTERNATIONAL STANDARD

Third edition 2014-05-01

Corrected version 2014-06-01

# Welding — Arc stud welding of metallic materials

Soudage — Soudage à l'arc des goujons sur les matériaux métalliques

## iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 14555:2014 https://standards.iteh.ai/catalog/standards/sist/c3d3084c-e0c8-41a1-a9bd-6992283ea2a7/iso-14555-2014



Reference number ISO 14555:2014(E)

## iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 14555:2014 https://standards.iteh.ai/catalog/standards/sist/c3d3084c-e0c8-41a1-a9bd-6992283ea2a7/iso-14555-2014



### **COPYRIGHT PROTECTED DOCUMENT**

### © ISO 2014

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office Case postale 56 • CH-1211 Geneva 20 Tel. + 41 22 749 01 11 Fax + 41 22 749 09 47 E-mail copyright@iso.org Web www.iso.org

Published in Switzerland

### Contents

Forev	word	v
Introduction		vi
1	Scono	1
1		I
2	Normative references	1
3	Terms and definitions	2
4	Symbols and abbreviated terms	4
4.1	Symbols	4
4.2	Abbreviated terms	4
5	Technical review	5
6	Welding personnel	5
6.1	Stud-welding operators	5
6.2	Welding coordination	6
7	Equipment	6
7.1	Production equipment	6
7.2	Description of the equipment	6
7.3	Maintenance	7
8	Production planning	7
9	Welding procedure specification (WPS) 4555:2014	7
91	General https://standards.iteh.ai/catalog/standards/sist/c3d3084c-e0c8-41a1-a9bd-	7
9.2	Information related to the manufacture 7/180-14555-2014	
9.3	Information related to the parent material	8
9.4	Welding process	8
9.5	Joint	8
9.6	Auxiliaries	9
9.7	Power source	9
9.8	Movable fixtures	9
9.9	Welding variables	
9.10	Thermal conditions	
9.11	Post-weid heat-treatment	
9.12	Non-thermal treatment after welding	
10	Welding procedure qualification	
10.1	Principles	
10.2	Welding procedure tests	
10.3	Pre-production tests	
10.4	Wolding procedure qualification record (WDOD)	13 15
10.5	weiung procedure quanneation record (wr QK)	
11	Examination and testing	
11.1	General	
11.Z	Visual examination	
11.3	Bena testing	
11.4 11 『	I EIISIIE LESUIIg	
11.3 11.6	I UI YUE LESL	
11.0	Radiographic examination	
11.8	Ring test	
	o	

12	Acceptance criteria	24
12.1	General	24
12.2	Acceptance criteria for visual examination	24
12.3	Acceptance criteria for bend testing	25
12.4	Acceptance criteria for tensile testing	25
12.5	Acceptance criteria for torque testing	25
12.6	Acceptance criteria for macro examination	25
12.7	Acceptance criteria for radiographic examination	25
12.8	Acceptance criteria for ring tests	25
12.9	Acceptance criteria for additional tests	26
13	Workmanship	26
14	Process control	26
14.1	General	26
14.2	Production test	27
14.3	Simplified production test	27
14.4	Re-testing for production test or simplified production test	28
14.5	Production surveillance	28
14.6	Production surveillance record	28
14.7	Non-conformance and corrective actions	29
14.8	Calibration of the measuring and testing equipment	29
Annex A (informative) Processing of stud welding		
Annex B (normative) Quality requirements for stud welding		
Annex	C (informative) Manufacturer's welding procedure specification (WPS)	51
Annex	D (informative) Welding procedure qualification record form (WPQR) (for drawn-arc stud welding with ceramic ferrule or shielding gas and short-cycle drawn-arc stud welding)	53
Annex	E (informative) Welding procedure qualification record form (WPQR) (for capacitor discharge stud welding with tip ignition and capacitor discharge drawn-arc stud welding)	58
Annex	F (informative) Test results — Production test (for drawn-arc stud welding with ceramic ferrule or shielding gas and short-cycle drawn-arc stud welding)	62
Annex	G (informative) Test results — Production test (for capacitor discharge stud welding with tip ignition and capacitor discharge drawn-arc stud welding)	65
Annex	H (informative) Example of production surveillance record	68
Bibliog	raphy	69

### Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see <a href="https://www.iso.org/directives">www.iso.org/directives</a>).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see <a href="http://www.iso.org/patents">www.iso.org/patents</a>).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement. **Teh STANDARD PREVIEW** 

For an explanation on the meaning of **ISO specific terms and expressions** related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: <u>Foreword - Supplementary information</u> 2014

https://standards.iteh.ai/catalog/standards/sist/c3d3084c-e0c8-41a1-a9bd-The committee responsible for this document is ISO/TC 44, Welding and allied processes, Subcommittee SC 10, Unification of requirements in the field of metal welding.

This third edition cancels and replaces the second edition (ISO 14555:2006), which has been technically revised.

This corrected version of ISO 14555:2014 incorporates the following corrections:

— 9.5.6 was renumbered 9.6; consequently, subclauses 9.7 to 9.12 were also renumbered;

in 11.1, "The methods described in 11.2 to 11.7 may be used ..." was replaced with "The methods described in 11.2 to 11.8 may be used ... ";

— in Table A.6, No. 5, the incorrect figure was replaced with the correct one;

— in Annex C, "ℤ yes ℤ no" was replaced with "□ yes □ no".

### Introduction

The purpose of arc stud welding is to weld predominantly pin-shaped metal parts to metal workpieces. In this International Standard it is referred to simply as stud welding. Amongst other things, stud welding is used in bridge building (especially in composite structures), steel structures, shipbuilding, facade-wall fabrication, vehicle manufacture, equipment design, steam-boiler construction, and the manufacture of household appliances.

The quality of a stud weld depends not only on strict compliance with the welding procedure specification but also on the correct function of the actuating mechanism (e.g. welding guns), and on the condition of the components, of the accessories and of the power supply.

This International Standard does not invalidate former specifications, providing the technical requirements are equivalent and satisfied.

## iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 14555:2014 https://standards.iteh.ai/catalog/standards/sist/c3d3084c-e0c8-41a1-a9bd-6992283ea2a7/iso-14555-2014

## Welding — Arc stud welding of metallic materials

### 1 Scope

This International Standard covers arc stud welding of metallic materials subject to static and fatigue loading. It specifies requirements that are particular to stud welding, in relation to welding knowledge, quality requirements, welding procedure specification, welding procedure qualification, qualification testing of operators and testing of production welds.

This International Standard is appropriate where it is necessary to demonstrate the capability of a manufacturer to produce welded construction of a specified quality.

NOTE General quality requirements for fusion welding of metallic materials are given in ISO 3834-1, ISO 3834-2, ISO 3834-3, ISO 3834-4 and ISO 3834-5.

This International Standard has been prepared in a comprehensive manner, with a view to it being used as a reference in contracts. The requirements contained within it can be adopted in full, or partially, if certain requirements are not relevant to a particular construction (see Annex B).

## (standards.iteh.ai)

### 2 Normative references

### <u>ISO 14555:2014</u>

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 857-1, Welding and allied processes — Vocabulary — Part 1: Metal welding processes

ISO 3834-1, Quality requirements for fusion welding of metallic materials — Part 1: Criteria for the selection of the appropriate level of quality requirements

ISO 3834-2, Quality requirements for fusion welding of metallic materials — Part 2: Comprehensive quality requirements

ISO 3834-3, Quality requirements for fusion welding of metallic materials — Part 3: Standard quality requirements

ISO 3834-4, Quality requirements for fusion welding of metallic materials — Part 4: Elementary quality requirements

ISO 4063, Welding and allied processes — Nomenclature of processes and reference numbers

ISO 6947, Welding and allied processes — Welding positions

ISO 9606-1, Approval testing of welders — Fusion welding — Part 1: Steels

ISO 9606-2, Qualification test of welders — Fusion welding — Part 2: Aluminium and aluminium alloys

ISO 13918:2008, Welding — Studs and ceramic ferrules for arc stud welding

ISO 14175, Welding consumables — Shielding gases for arc welding and cutting

### ISO 14555:2014(E)

ISO 14731, Welding coordination — Tasks and responsibilities

ISO 14732:1998, Welding personnel — Approval testing of welding operators for fusion welding and of resistance weld setters for fully mechanized and automatic welding of metallic materials

ISO 15607:2003, Specification and qualification of welding procedures for metallic materials — General rules

ISO/TR 15608, Welding — Guidelines for a metallic materials grouping system

ISO 15611, Specification and qualification of welding procedures for metallic materials — Qualification based on previous welding experience

ISO 15613, Specification and qualification of welding procedures for metallic materials — Qualification based on pre-production welding test

ISO 15614-1:2004, Specification and qualification of welding procedures for metallic materials — Welding procedure test — Part 1: Arc and gas welding of steels and arc welding of nickel and nickel alloys

ISO 15614-2, Specification and qualification of welding procedures for metallic materials — Welding procedure test — Part 2: Arc welding of aluminium and its alloys

ISO 17636-1, Non-destructive testing of welds — Radiographic testing — X- and gamma-ray techniques with film

ISO 17636-2, Non-destructive testing of welds — Radiographic testing — X- and gamma-ray techniques with digital detectors **iTeh STANDARD PREVIEW** 

ISO 17662, Welding — Calibration, verification and validation of equipment used for welding, including ancillary activities

ISO 14555:2014

## 3 Terms and definitions://standards.iteh.ai/catalog/standards/sist/c3d3084c-e0c8-41a1-a9bd-

6992283ea2a7/iso-14555-2014

For the purposes of this document, the terms and definitions given in ISO 857-1, ISO 3834-1, ISO 4063, ISO 14731, ISO 14732 and ISO 15607 and the following apply.

### 3.1

stud

fastener to be attached by stud welding

### 3.2

auxiliaries

ceramic ferrules and shielding gases

### 3.3

### stud-welding operator

operating personnel for stud-welding equipment

Note to entry In special cases (e.g. mass production at the manufacturer's factory) the welding can be carried out by suitable auxiliary personnel, appropriately trained and supervised.

### 3.4 stud diameter d

stud nominal diameter

Note 1 to entry See ISO 13918.

### 3.5

### welding diameter

 $d_{\mathbf{W}}$ 

diameter at the weld base

### 3.6

### weld zone

welded area underneath the welding diameter

### 3.7

### current intensity

root-mean-square (RMS) value of the welding current in the steady state during the burning time of the arc

Note to entry Current intensity is not applicable to capacitor discharge.

### 3.8

### welding time

time difference between the ignition and the final extinction of the main arc

### 3.9

### lift

L.

distance between the stud tip and the work piece surface with the stud-lifting mechanism in position and activated

Note 1 to entry For tip ignition, this definition applies to the ignition gap.

See Figure th STANDARD PREVIEW Note 2 to entry

## (standards.iteh.ai)

### 3.10 plunge

axial movement of the stud towards the surface of the work piece

https://standards.iteh.ai/catalog/standards/sist/c3d3084c-e0c8-41a1-a9bd-3.11 6992283ea2a7/iso-14555-2014

#### protrusion Р

(unregulated lifting mechanism) distance between the tip of the stud and the face of the support device in their initial positions, where the support device faces the work piece

Note 1 to entry A spring-loaded lifting mechanism is an unregulated lifting mechanism.

Note 2 to entry See Figure A.1.

### 3.12

### arc blow

magnetic deflection of the arc from the axial direction of the stud

### 3.13

### flux

aluminium additive on the weld end of the stud, which improves the ignition and de-oxidizes the weld pool

### 3.14

### dual-material stud

two-material stud composed of a material at the weld tip, similar to that of the parent material, and a dissimilar material outside the weld tip, which are joined by a friction weld, thus avoiding a mixed structure in the weld zone when stud welding

### 3.15

### structure subjected to fatigue loading

structure subject to a set of typical load events described by the positions or movements of loads, their variation in intensity and their frequency and sequence of occurrence

### 3.16

### through-deck stud-welding

application where shear connectors are welded to a steel structure through thin steel sheet with a thickness of less than 3 mm

#### Symbols and abbreviated terms 4

### 4.1 Symbols

For the purposes of this document, the following symbols apply.

- С capacitance (expressed in mF)
- d stud diameter (expressed in mm)
- welding diameter (expressed in mm)  $d_{\rm W}$
- h length of the threaded part of the nut
- Ι current intensity (expressed in A)
- lift L
- protrusion Р
- thickness of plate t
- welding time (expressed in ms or s) TANDARD PREVIEW  $t_{\rm W}$
- (standards.iteh.ai) Т torque (expressed in Nm)
- U charging voltage (expressed in V)

ISO 14555:2014

- charging energy (expressed in Ws) eh.ai/catalog/standards/sist/c3d3084c-e0c8-41a1-a9bd-Ε
- 6992283ea2a7/iso-14555-2014 bending angle (expressed in °) α

#### Abbreviated terms 4.2

For the purposes of this document, the following abbreviated terms apply.

- CF ceramic ferrule
- HAZ heat-affected zone
- NP no protection
- PA flat welding position
- РС horizontal welding position
- PE overhead welding position
- preliminary welding procedure specification pWPS
- SG shielding gas
- WPS welding procedure specification
- WPQR welding procedure qualification record

### 5 Technical review

When a technical review is required by an application standard, by specification or by use of ISO 3834-2, ISO 3834-3 or ISO 3834-4, the manufacturer shall check, as appropriate, the following aspects:

- a) the accessibility and welding position of the stud weld;
- b) the nature of the surface and the collar shape of the welded joint;
- c) materials and combinations of materials (see Tables A.3 and A.4); including decking material where the through-deck technique is being proposed;
- d) the ratio of stud diameter to parent metal thickness (avoidance of damage on the reverse side of the parent metal);
- e) dimensions and details of the weld preparation and of the finished weld, including the nature of the stud and parent -metal surfaces, positional and angular accuracy and the length tolerance of the welded stud;
- f) the use of special techniques to avoid damage to the reverse side of the parent metal;
- g) techniques to assure the angular position of the welded stud.

NOTE Consideration is paid to the multi-axial stress state arising from localized heating/cooling. This stress concentration reduces the fatigue strength of a component with welded studs.

## iTeh STANDARD PREVIEW <sup>mel</sup> (standards.iteh.ai)

### 6 Welding personnel

### 6.1 Stud-welding operators

### ISO 14555:2014

https://standards.iteh.ai/catalog/standards/sist/c3d3084c-e0c8-41a1-a9bd-The qualification can be done by a welding procedure test-(see 10.2) or a pre-production test (see 10.3) and shall include testing in accordance with the acceptance criteria specified in 12, if relevant.

Stud-welding operators shall have appropriate knowledge to operate the equipment, to adjust it properly, to carry out the welding correctly and, while doing so, to pay attention to good contact and suitable connection between the work piece cables and uniform distribution of ferromagnetic materials (see Table A.8).

The welding personnel shall be qualified in accordance with ISO 14732.

The qualified operator shall be deemed to be qualified for any stud welding equipment with the same mode of selecting the parameters which was used in the qualification test. Change in the welding process variant (numbers 783, 784, 785, 786 of ISO 4063) requires a new qualification.

A test of job knowledge is required for all qualification methods. This test shall cover, as a minimum:

- a) setting up the welding equipment in accordance with the welding procedure specification;
- b) basic knowledge of the way in which suitable connection of work piece cables, the polarity of the stud, and arc blowing can influence the weld result (see Table A.8);
- c) basic assessment of the welded joint for imperfections (see Tables A.5, A.6 and A.7);
- d) safe execution of the welding operations, i.e. good contact of the stud in the stud holder, no movement during the welding process, operation checking and correct positioning of the welding gun).

### 6.2 Welding coordination

Welding coordination shall be performed in accordance with ISO 14731. Refer to Annex B for quality level according ISO 3834 for the welding coordinator.

Welding coordination personnel for stud welding shall have knowledge of and experience in the relevant studwelding process, and shall be able to select and set the correct parameters, e.g. lift, protrusion (plunge), current intensity, and welding time.

A welding coordinator is not required for stud welding to structures subjected to unspecified static loading (see Annex B).

### 7 Equipment

### 7.1 **Production equipment**

Suitable stud-welding equipment shall be used, with power supplies of sufficient capacity to weld the stud properly to the parent material when the equipment is correctly set up. The following equipment shall be available, as required:

- a) power sources, control unit and movable fixtures;
- b) cables with sufficient cross-section, solid connection terminals and sufficient earth connection;
- I I Eh STANDARD PREVIEW
- c) handling equipment for the technical aspects of welding fabrication (jigs, fixtures); (standards.iteh.ai)
- d) weld data monitoring equipment;

e) cleaning facilities for contact points and welding points and sist/c3d3084c-e0c8-41a1-a9bd-

f) measuring and testing equipment;

g) equipment for pre- and post-treatment;

h) equipment and welding plant for retouching.

### 7.2 Description of the equipment

A list of the stud-welding equipment shall be maintained, which shall serve as evidence of the performance and stud-welding application field. It shall include:

6992283ea2a7/iso-14555-2014

- a) details of the smallest and largest weldable stud diameter;
- b) the maximum number of studs to be welded per unit of time;
- c) the regulating range of the power supply;
- d) the mode of operation and performance of mechanized or automatic stud-welding equipment;
- e) details of the available test equipment.

### 7.3 Maintenance

The correct functioning of the equipment shall be ensured. During production, a function check of the actuation mechanisms shall be performed at fixed intervals. Cables, terminals, stud and ceramic ferrule holders shall be regularly checked and replaced at the appropriate time. For mass production and comprehensive quality requirements in accordance with ISO 3834-2, a maintenance plan for additional essential systems shall be drawn up. Examples of such systems are:

- a) stud sorting and feeding systems;
- b) stud and ceramic ferrule holders;
- c) mechanical guides and fixtures;
- d) measuring equipment;
- e) cables, hoses, connecting elements;
- f) a monitoring system.

### 8 Production planning

For stud welding, the production planning shall also contain the following elements:

- TTEN STANDARD PREVI
- a) a definition of the required stud-welding procedures and equipment; (standards.iteh.ai)
- b) details of which jigs and fixtures are used;
- c) the surface preparation method, ai/catalog/standards/sist/c3d3084c-e0c8-41a1-a9bd-6992283ea2a7/iso-14555-2014

### 9 Welding procedure specification (WPS)

### 9.1 General

The welding procedure specification (WPS) shall give details of how a welding operation shall be performed and shall contain all relevant information about the welding work.

Information listed in 9.2 to 9.13 is adequate for most welding operations. For some applications, it may be necessary to supplement or reduce the list. The relevant information shall be specified in the WPS.

Ranges and tolerances shall be specified when appropriate. An example of the WPS format is given in Annex C.

### 9.2 Information related to the manufacturer

### 9.2.1 Identification of the manufacturer

— unambiguous identification.

### 9.2.2 Identification of the WPS

— alphanumeric designation (reference code).

### ISO 14555:2014(E)

### 9.2.3 Reference to the welding procedure qualification record (WPQR) or other relevant documents

— alphanumeric designation (reference code).

### 9.3 Information related to the parent material

### 9.3.1 Parent material type

- identification of material, preferably by reference to an appropriate standard;
- parent material(s) delivery condition;
- identification of coating or any other surface condition.

NOTE A WPS can cover a material group in accordance with ISO/TR 15608. See also ISO/TR 20172, ISO/TR 20173 and ISO/TR 20174.

### 9.3.2 Dimensions

- the thickness or range of thicknesses of the parent material;
- other relevant dimensions (e.g. thickness and configuration of the steel sheet for through-deck applications).

### 9.4 Welding process iTeh STANDARD PREVIEW

designation in accordance with ISO 4063standards.iteh.ai)

### 9.5 Joint

<u>ISO 14555:2014</u> https://standards.iteh.ai/catalog/standards/sist/c3d3084c-e0c8-41a1-a9bd-6992283ea2a7/iso-14555-2014

- 9.5.1 Joint design
- --- sketch of the joint design showing the relative positions of studs and tolerances;
- the sequence of the welding of studs shall be indicated on the sketch if essential for application.

### 9.5.2 Welding position

— welding positions shall be specified in accordance with ISO 6947.

### 9.5.3 Preparation of parent material surface

- method of surface preparation, if necessary (e.g. cleaning, degreasing, pickling);
- maximum time permitted between preparation and welding (if required).

### 9.5.4 Jigs and fixtures

- the methods to be used (if required);
- fixture details, templates, etc.

### 9.5.5 Support

- the method of support;
- specification of supporting material;
- dimensions of support (when welding thin plates).

### 9.6 Studs

### 9.6.1 Designation

— designation according to standard, supplier or trade name; non-standard studs shall be specified.

### 9.6.2 Handling

— if the studs are to be treated (e.g. by cleaning) before use, this shall be specified.

### 9.7 Auxiliaries

### 9.7.1 Ceramic ferrules (if any)

- designation according to standard, supplier or trade name; non-standard ceramic ferrules shall be specified;
- ceramic ferrules shall be stored in a clean and dry environment.

### 9.7.2 Protective gas (if any)

 <u>ISO 14555:2014</u>
designation in accordance with ISO 14175/standards/sist/c3d3084c-e0c8-41a1-a9bd-6992283ea2a7/iso-14555-2014

### 9.8 Power source

— manufacturer, type.

### 9.9 Movable fixtures

### 9.9.1 Welding gun/lift mechanism

- manufacturer, type;
- damper.

### 9.9.2 Shielding gas system (if used)

- gas flow rate;
- (schematic) description showing nozzle dimensions and position of nozzle(s) in relation to stud and work piece.

### 9.9.3 Stud feeding system (if any)

— description of stud feeding system including sketch.