



Designation: A307 – 07b

Standard Specification for Carbon Steel Bolts and Studs, 60 000 PSI Tensile Strength¹

This standard is issued under the fixed designation A307; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope*

1.1 This specification² covers the chemical and mechanical requirements of three grades of carbon steel bolts and studs in sizes 1/4 in. through 4 in. The fasteners are designated by “Grade” denoting tensile strength and intended use, as follows:

Grade	Description
Grade A	Bolts and studs having a minimum tensile strength of 60 ksi and intended for general applications,
Grade B	Bolts and studs having a tensile strength of 60 to 100 ksi and intended for flanged joints in piping systems with cast iron flanges, and
Grade C	Replaced by Specification F1554 Gr.36

1.1.1 The term *studs* includes stud stock, sometimes referred to as *threaded rod*.

1.2 This specification does not cover requirements for machine screws, thread cutting/forming screws, mechanical expansion anchors or similar externally threaded fasteners.

1.3 Suitable nuts are covered in Specification **A563**. Unless otherwise specified, the grade and style of nut for each grade of fastener, of all surface finishes, shall be as follows:

Fastener Grade and Size	Nut Grade and Style ⁴
A 1/4 to 1 1/2 in.	A, hex
A over 1 1/2 to 4 in.	A, heavy hex
B, 1/4 to 4 in.	A, heavy hex

⁴ Nuts of other grades and styles having specified proof load stresses (Specification **A563**, Table 3) greater than the specified grade and style of nut are also suitable.

1.4 The values stated in inch-pound units are to be regarded as the standard.

1.5 Supplementary Requirement S1 of an optional nature is provided, which describes additional restrictions to be applied when bolts are to be welded. It shall apply only when specified in the inquiry, order, and contract.

¹ This specification is under the jurisdiction of ASTM Committee **F16** on Fasteners and is the direct responsibility of Subcommittee **F16.02** on Steel Bolts, Nuts, Rivets and Washers.

Current edition approved Dec. 1, 2007. Published January 2008. Originally approved in 1947. Last previous edition approved in 2007 as A307 – 07a. DOI: 10.1520/A0307-07B.

² For *ASME Boiler and Pressure Vessel Code* applications see related Specification SA-307 in Section II of that Code.

1.6 Terms used in this specification are defined in Terminology **F1789** unless otherwise defined herein.

2. Referenced Documents

2.1 ASTM Standards:³

- A563** Specification for Carbon and Alloy Steel Nuts
- A706/A706M** Specification for Low-Alloy Steel Deformed and Plain Bars for Concrete Reinforcement
- A751** Test Methods, Practices, and Terminology for Chemical Analysis of Steel Products
- B695** Specification for Coatings of Zinc Mechanically Deposited on Iron and Steel
- D3951** Practice for Commercial Packaging
- F606** Test Methods for Determining the Mechanical Properties of Externally and Internally Threaded Fasteners, Washers, Direct Tension Indicators, and Rivets
- F1470** Practice for Fastener Sampling for Specified Mechanical Properties and Performance Inspection
- F1554** Specification for Anchor Bolts, Steel, 36, 55, and 105-ksi Yield Strength
- F1789** Terminology for F16 Mechanical Fasteners
- F2329** Specification for Zinc Coating, Hot-Dip, Requirements for Application to Carbon and Alloy Steel Bolts, Screws, Washers, Nuts, and Special Threaded Fasteners

2.2 ASME Standards:

- B 1.1** Unified Screw Threads⁴
- B 18.2.1** Square and Hex Bolts and Screws⁴
- B 18.24** Part Identifying Number (PIN) Code System⁵

3. Ordering Information

3.1 Orders for externally threaded fasteners (including nuts and accessories) under this specification shall include the following:

- 3.1.1 ASTM designation and year of issue,
- 3.1.2 Name of product, bolts or studs; and bolt head style, that is, hex or heavy hex,

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard’s Document Summary page on the ASTM website.

⁴ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036.

⁵ Available from American Society of Mechanical Engineers (ASME), ASME International Headquarters, Three Park Ave., New York, NY 10016-5990.

*A Summary of Changes section appears at the end of this standard.

3.1.3 Grade, that is, A, or B. If no grade is specified, Grade A is furnished.

3.1.4 Quantities (number of pieces by size including nuts),

3.1.5 Fastener size and length,

3.1.6 Washers—Quantity and size (separate from bolts),

3.1.7 Zinc Coating—Specify the zinc-coating process required, for example, hot-dip, mechanically deposited, or no preference (see 4.5).

3.1.8 Other Finishes—Specify other protective finish, if required.

3.1.9 Specify if inspection at point of manufacture is required,

3.1.10 Specify if certified test report is required (see 8.2), and

3.1.11 Specify additional testing (8.3) or special requirements.

3.1.12 For establishment of a part identifying system, see ASME B 18.24.

4. Materials and Manufacture

4.1 Steel for bolts and studs shall be made by the open-hearth, basic-oxygen, or electric-furnace process.

4.2 Bolts shall be produced by hot or cold forging of the heads or machining from bar stock.

4.3 Heat Treatment:

4.3.1 Cold headed fasteners with head configurations other than hex shall be stress relief annealed.

4.3.2 Stress relieving of hex head fasteners shall be at the manufacturer's option.

4.4 Bolt and stud threads shall be rolled or cut.

4.5 Zinc Coatings, Hot-Dip and Mechanically Deposited:

4.5.1 When zinc-coated fasteners are required, the purchaser shall specify the zinc-coating process, for example hot dip, mechanically deposited, or no preference.

4.5.2 When hot-dip is specified, the fasteners shall be zinc-coated by the hot-dip process in accordance with the requirements of Specification F2329.

4.5.3 When mechanically deposited is specified, the fasteners shall be zinc-coated by the mechanical-deposition process in accordance with the requirements of Class 55 of Specification B695.

4.5.4 When no preference is specified, the supplier may furnish either a hot-dip zinc coating in accordance with Specification F2329, or a mechanically deposited zinc coating in accordance with Specification B695, Class 55. Threaded components (bolts and nuts) shall be coated by the same zinc-coating process and the supplier's option is limited to one process per item with no mixed processes in a lot.

5. Chemical Composition

5.1 Grade A and B bolts and studs shall have a heat analysis conforming to the requirements specified in Table 1 based on the steel producer's heat analysis.

5.2 The purchaser shall have the option of conducting product analyses on finished bolts in each lot, which shall conform to the product analysis specified in Table 1.

5.3 In case of conflict or for referee purposes, the product analysis shall take precedence.

TABLE 1 Chemical Requirements for Grades A and B Bolts and Studs

	Heat Analysis		Product Analysis	
	min	max	min	max
Carbon, max	0.29		0.33	
Manganese, max	1.20		1.25	
Phosphorus, max	0.04		0.041	
Sulfur, max				
Grade A	0.15		A	
Grade B	0.05		0.051	

^A Resulfurized steel is not subject to rejection based on product analysis for sulfur.

5.4 Bolts and studs are customarily furnished from stock, in which case individual heats of steel cannot be identified.

5.5 Application of heats of steel to which bismuth, selenium, tellurium, or lead has been intentionally added shall not be permitted for Grade B bolts and studs.

5.6 Chemical analyses shall be performed in accordance with Test Methods, Practices, and Terminology A751.

6. Mechanical Properties

6.1 Grades A and B bolts and studs shall conform to the hardness specified in Table 2.

6.2 Grade A and B bolts and studs 1½ in. in diameter or less, other than those excepted in 6.4, shall be tested full size and shall conform to the requirements for tensile strength specified in Table 3.

6.3 Grade A and B bolts and studs larger than 1½ in. in diameter, other than those excepted in 6.4, shall preferably be tested full size and when equipment of sufficient capacity is available and shall conform to the requirements for tensile strength specified in Table 3. When equipment of sufficient capacity for full-size bolt testing is not available, or when the length of the bolt makes full-size testing impractical, machined specimens shall be tested and shall conform to the requirements specified in Table 4.

6.4 Grades A and B bolts and studs less than three diameters in length or bolts with drilled or undersize heads are not subject to tensile tests.

6.5 In the event that bolts are tested by both full size and by machine test specimen methods, the full-size test shall govern if a controversy between the two methods exists.

6.6 For bolts and studs on which both hardness and tension tests are performed, acceptance based on tensile requirements shall take precedence in the event that there is controversy over low readings of hardness tests.

TABLE 2 Hardness Requirements for Bolts and Studs

Grade	Length, in.	Hardness ^A			
		Brinell		Rockwell B	
		min	max	min	max
A	Less than 3 × dia ^B	121	241	69	100
	3 × dia and longer	...	241	...	100
B	Less than 3 × dia ^B	121	212	69	95
	3 × dia and longer	...	212	...	95

^A As measured anywhere on the surface or through the cross section.

^B Also bolts with drilled or undersize heads. These sizes and bolts with modified heads shall meet the minimum and maximum hardness as hardness is the only requirement.