



# Standard Test Method for Vibratory Packing Density of Large Formed Catalyst and Catalyst Carrier Particles<sup>1</sup>

This standard is issued under the fixed designation D 4699; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This test method covers the determination of the vibratory packing density of formed catalyst and catalyst carrier particles that will not break up significantly under test conditions. For the purpose of this test, catalyst particles are defined as extrudates, spheres or formed pellets greater than 4.8 mm ( $3/16$  in.).

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

## 2. Referenced Documents

### 2.1 ASTM Standards:

- E 177 Practice for Use of the Terms Precision and Bias in ASTM Test Methods<sup>2</sup>
- E 456 Terminology Relating to Quality and Statistics<sup>2</sup>
- E 691 Practice for Conducting an Interlaboratory Study to Determine the Precision of a Test Method<sup>2</sup>

## 3. Summary of Test Method

3.1 A known sample of environmentally equilibrated formed catalyst or catalyst carrier particles is vibrated in a graduated cylinder. The vibratory packing density is determined for a specified drying condition.

## 4. Significance and Use

4.1 This test method is used for measuring the vibratory packing density of formed particles used in fixed bed reactors, driers, etc.

## 5. Apparatus

- 5.1 *Graduated Cylinder*,<sup>3,4</sup> capacity 2000-mL.

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee D-32 on Catalysts and is the direct responsibility of Subcommittee D 32.02 on Physical-Mechanical Properties.

Current edition approved Oct. 10, 1999. Published December 1999. Originally published as D 4699 – 87. Last previous edition D 4699 – 94.

<sup>2</sup> *Annual Book of ASTM Standards*, Vol 14.02.

<sup>3</sup> If you are aware of alternative suppliers, please provide this information to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend.

<sup>4</sup> Nalgene 3663-2000 has been found satisfactory; also an equivalent may be used.

- 5.2 *Vibratory Plate*.<sup>3,5</sup>

5.3 *Desiccator*, with a desiccant grade molecular sieve such as 4A.

- 5.4 *Balance* having a sensitivity of 1.0 g.

- 5.5 *Balance* having a sensitivity of 0.1 g.

- 5.6 *Drying Oven*.

## 6. Procedure

6.1 Equilibrate test sample to laboratory environment for 4 h.

6.2 Pour between 1000 to 2000 mL of the test specimen carefully into a tared beaker and weigh to the nearest 1 g. Record as  $W$ .

6.3 Separately weigh to the nearest tenth of a gram about 100 g of additional test sample,  $W_p$ , that will be used for moisture loss. Heat this sample at 673 K (400°C)  $\pm$  15 K for not less than 3 h. Normally, this treatment can take place in air; however, in the case of materials that might react with air at elevated temperature (such as prerduced catalysts) the heat treatment should take place in an inert atmosphere. After heating, cool the test sample in a desiccator or other suitable container to eliminate the possibility of moisture adsorption prior to weighing. Weigh the sample to the nearest tenth of a gram,  $W_H$ .

NOTE 1—The conditions may not be appropriate for all materials.

NOTE 2—Since many catalyst formulations are strong adsorbents, the use of a 4A indicating (cobalt-treated) molecular sieve as a desiccating medium is recommended. The desiccant should be regenerated at 493 K (220°C) to 533 K (260°C), as required.

NOTE 3—Multiple samples can be pretreated but must be desiccated prior to analysis.

6.4 Clamp the cylinder to the vibratory plate (see example Fig. 1).

6.5 Start vibrator at a setting at the midpoint of the rheostat range and pour the 1000 to 2000-mL test specimen carefully into the graduated cylinder using a funnel. The entire transfer time should be between 90 and 120 s. Those vibrating plate machines that operate at a frequency other than 60 Hz will require appropriate adjustment of the vibrating time.

- 6.6 Continue vibrating for 5 min.

- 6.7 When vibration is completed, read the packed volume,

<sup>5</sup> Syntron Vibrating Machine, manufactured by FMC, Model V-2-B with Power Pulse Controller has been found satisfactory. An equivalent may be used.