



Designation: F2150 – 07

Standard Guide for Characterization and Testing of Biomaterial Scaffolds Used in Tissue-Engineered Medical Products¹

This standard is issued under the fixed designation F2150; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This guide is a resource of currently available test methods for the characterization of the compositional and structural aspects of biomaterial scaffolds used to develop and manufacture tissue-engineered medical products (TEMPs).

1.2 The test methods contained herein guide characterization of the bulk physical, chemical, mechanical, and surface properties of a scaffold construct. Such properties may be important for the success of a TEMP, especially if they affect cell retention, activity and organization, the delivery of bioactive agents, or the biocompatibility and bioactivity within the final product.

1.3 This guide may be used in the selection of appropriate test methods for the generation of an original equipment manufacturer (OEM) specification. This guide also may be used to characterize the scaffold component of a finished medical product.

1.4 This guide is intended to be utilized in conjunction with appropriate characterization(s) and evaluation(s) of any raw or starting material(s) utilized in the fabrication of the scaffold, such as described in Guide F2027.

1.5 This guide addresses natural, synthetic, or combination scaffold materials with or without bioactive agents or biological activity. This guide does not address the characterization or release profiles of any biomolecules, cells, drugs, or bioactive agents that are used in combination with the scaffold. A determination of the suitability of a particular starting material and/or finished scaffold structure to a specific cell type and/or tissue engineering application is essential, but will require additional *in vitro* and/or *in vivo* evaluations considered to be outside the scope of this guide.

1.6 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate*

appropriate safety and health practices and determine the applicability of regulatory requirements prior to use.

2. Referenced Documents

2.1 ASTM Standards:²

- D412 Test Methods for Vulcanized Rubber and Thermoplastic Elastomers—Tension
- D570 Test Method for Water Absorption of Plastics
- D638 Test Method for Tensile Properties of Plastics
- D648 Test Method for Deflection Temperature of Plastics Under Flexural Load in the Edgewise Position
- D671 Test Method for Flexural Fatigue of Plastics by Constant-Amplitude-of-Force (Withdrawn 2002)³
- D695 Test Method for Compressive Properties of Rigid Plastics
- D747 Test Method for Apparent Bending Modulus of Plastics by Means of a Cantilever Beam
- D790 Test Methods for Flexural Properties of Unreinforced and Reinforced Plastics and Electrical Insulating Materials
- D792 Test Methods for Density and Specific Gravity (Relative Density) of Plastics by Displacement
- D882 Test Method for Tensile Properties of Thin Plastic Sheeting
- D1042 Test Method for Linear Dimensional Changes of Plastics Under Accelerated Service Conditions
- D1238 Test Method for Melt Flow Rates of Thermoplastics by Extrusion Plastometer
- D1388 Test Method for Stiffness of Fabrics
- D1621 Test Method for Compressive Properties of Rigid Cellular Plastics
- D1623 Test Method for Tensile and Tensile Adhesion Properties of Rigid Cellular Plastics
- D1708 Test Method for Tensile Properties of Plastics by Use of Microtensile Specimens
- D2857 Practice for Dilute Solution Viscosity of Polymers

¹ This guide is under the jurisdiction of ASTM Committee F04 on Medical and Surgical Materials and Devices and is the direct responsibility of Subcommittee F04.42 on Biomaterials and Biomolecules for TEMPs.

Current edition approved Dec. 1, 2007. Published January 2008. Originally approved in 2002. Last previous edition approved in 2002 as F2150 – 02^{e1}. DOI: 10.1520/F2150-07.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ The last approved version of this historical standard is referenced on www.astm.org.

- D2873** Test Method for Interior Porosity of Poly(Vinyl Chloride) (PVC) Resins by Mercury Intrusion Porosimetry (Withdrawn 2003)³
- D2990** Test Methods for Tensile, Compressive, and Flexural Creep and Creep-Rupture of Plastics
- D3016** Practice for Use of Liquid Exclusion Chromatography Terms and Relationships
- D3039/D3039M** Test Method for Tensile Properties of Polymer Matrix Composite Materials
- D3417** Test Method for Enthalpies of Fusion and Crystallization of Polymers by Differential Scanning Calorimetry (DSC) (Withdrawn 2004)³
- D3418** Test Method for Transition Temperatures and Enthalpies of Fusion and Crystallization of Polymers by Differential Scanning Calorimetry
- D4001** Test Method for Determination of Weight-Average Molecular Weight of Polymers By Light Scattering
- D4404** Test Method for Determination of Pore Volume and Pore Volume Distribution of Soil and Rock by Mercury Intrusion Porosimetry
- D4603** Test Method for Determining Inherent Viscosity of Poly(Ethylene Terephthalate) (PET) by Glass Capillary Viscometer
- D5226** Practice for Dissolving Polymer Materials
- D5296** Test Method for Molecular Weight Averages and Molecular Weight Distribution of Polystyrene by High Performance Size-Exclusion Chromatography
- D5732** Test Method for Stiffness of Nonwoven Fabrics Using the Cantilever Test (Withdrawn 2008)³
- D6125** Test Method for Bending Resistance of Paper and Paperboard (Gurley Type Tester) (Withdrawn 2010)³
- D6420** Test Method for Determination of Gaseous Organic Compounds by Direct Interface Gas Chromatography-Mass Spectrometry
- D6474** Test Method for Determining Molecular Weight Distribution and Molecular Weight Averages of Polyolefins by High Temperature Gel Permeation Chromatography
- D6539** Test Method for Measurement of Pneumatic Permeability of Partially Saturated Porous Materials by Flowing Air
- D6579** Practice for Molecular Weight Averages and Molecular Weight Distribution of Hydrocarbon, Rosin and Terpene Resins by Size-Exclusion Chromatography
- E128** Test Method for Maximum Pore Diameter and Permeability of Rigid Porous Filters for Laboratory Use
- E177** Practice for Use of the Terms Precision and Bias in ASTM Test Methods
- E456** Terminology Relating to Quality and Statistics
- E473** Terminology Relating to Thermal Analysis and Rheology
- E691** Practice for Conducting an Interlaboratory Study to Determine the Precision of a Test Method
- E793** Test Method for Enthalpies of Fusion and Crystallization by Differential Scanning Calorimetry
- E794** Test Method for Melting And Crystallization Temperatures By Thermal Analysis
- E967** Test Method for Temperature Calibration of Differential Scanning Calorimeters and Differential Thermal Analyzers
- E968** Practice for Heat Flow Calibration of Differential Scanning Calorimeters
- E996** Practice for Reporting Data in Auger Electron Spectroscopy and X-ray Photoelectron Spectroscopy
- E1078** Guide for Specimen Preparation and Mounting in Surface Analysis
- E1142** Terminology Relating to Thermophysical Properties
- E1294** Test Method for Pore Size Characteristics of Membrane Filters Using Automated Liquid Porosimeter (Withdrawn 2008)³
- E1298** Guide for Determination of Purity, Impurities, and Contaminants in Biological Drug Products
- E1356** Test Method for Assignment of the Glass Transition Temperatures by Differential Scanning Calorimetry
- E1642** Practice for General Techniques of Gas Chromatography Infrared (GC/IR) Analysis
- E1829** Guide for Handling Specimens Prior to Surface Analysis
- E1994** Practice for Use of Process Oriented AOQL and LTPD Sampling Plans
- F151** Test Method for Residual Solvents in Flexible Barrier Materials (Withdrawn 2004)³
- F316** Test Methods for Pore Size Characteristics of Membrane Filters by Bubble Point and Mean Flow Pore Test
- F748** Practice for Selecting Generic Biological Test Methods for Materials and Devices
- F1249** Test Method for Water Vapor Transmission Rate Through Plastic Film and Sheeting Using a Modulated Infrared Sensor
- F1251** Terminology Relating to Polymeric Biomaterials in Medical and Surgical Devices (Withdrawn 2012)³
- F1634** Practice for *In-Vitro* Environmental Conditioning of Polymer Matrix Composite Materials and Implant Devices
- F1635** Test Method for *in vitro* Degradation Testing of Hydrolytically Degradable Polymer Resins and Fabricated Forms for Surgical Implants
- F1884** Test Methods for Determining Residual Solvents in Packaging Materials
- F1980** Guide for Accelerated Aging of Sterile Barrier Systems for Medical Devices
- F1983** Practice for Assessment of Compatibility of Absorbable/Resorbable Biomaterials for Implant Applications
- F2025** Practice for Gravimetric Measurement of Polymeric Components for Wear Assessment
- F2027** Guide for Characterization and Testing of Raw or Starting Biomaterials for Tissue-Engineered Medical Products
- F2312** Terminology Relating to Tissue Engineered Medical Products
- F2450** Guide for Assessing Microstructure of Polymeric Scaffolds for Use in Tissue-Engineered Medical Products
- G120** Practice for Determination of Soluble Residual Contamination by Soxhlet Extraction

2.2 AAMI Standards:⁴

AAMI STBK9-1 Sterilization—Part 1: Sterilization in Health Care Facilities

AAMI STBK9-2 Sterilization—Part 2: Sterilization Equipment

AAMI STBK9-3 Sterilization—Part 3: Industrial Process Control

2.3 ANSI Standards:⁵

ANSI/ISO/ASQ Q9000-2000: Quality Management Systems—Fundamentals and Vocabulary

ANSI/ISO/ASQ Q9001-2000: Quality Management Systems: Requirements

2.4 British Standards Institute:⁵

EN 1244-1 British Standard—Animal Tissues and Their Derivatives Utilized in the Manufacture of Medical Devices—Part 1: Analysis and Management of Risk

EN 12442-2 British Standard—Animal Tissues and Their Derivatives Utilized in the Manufacture of Medical Devices—Part 2: Controls on Sourcing, Collection, and Handling

EN 12442-3 British Standard—Animal Tissues and Their Derivatives Utilized in the Manufacture of Medical Devices—Part 3: Validation of the Elimination and/or Inactivation of Viruses and Transmissible Agents

2.5 ISO Standards:⁵

ISO 31-8 Physical Chemistry and Molecular Physics—Part 8: Quantities and Units

ISO 1133 Determination of the Melt-Mass Flow Rate (MFR) and the Melt Volume-Flow Rate (MVR) of Thermoplastics

ISO 10993-9 Biological Evaluation of Medical Devices—Part 9: Degradation of Materials Related to Biological Testing

ISO 10993-13 Biological Evaluation of Medical Devices—Part 13: Identification and Quantification of Degradation Products from Polymers

ISO 10993-14 Biological Evaluation of Medical Devices—Part 14: Identification and Quantification of Degradation Products from Ceramics

ISO 10993-15 Biological Evaluation of Medical Devices—Part 15: Identification and Quantification of Degradation Products from Coated and Uncoated Metals and Alloys

ISO 11357-1 Plastics—Differential Scanning Calorimetry (DSC)—Part 1: General Principles

ISO 11357-2 Plastics—Differential Scanning Calorimetry (DSC)—Part 2: Determination of Glass Transition Temperature

2.6 U.S. Code of Federal Regulations:⁶

21 CFR Part 58 Title 21—Food And Drug Administration, Part 58—Good Laboratory Practice For Nonclinical Laboratory Studies

21 CFR Part 820 Title 21—Food and Drugs Services, Part 820—Quality System Regulation

2.7 U.S. Pharmacopeia (USP) Standards:⁷

Source: General Tests and Assays—USP30/NF25, May 1, 2007

2.8 NIST Document:⁸

NIST SP811 Special Publication SP811: Guide for the Use of the International System of Units (SI)

2.9 Other Documents/Web Sites:

U.S. Food & Drug Administration (FDA) Center for Devices & Radiologic Health (CDRH), Consensus Standards Database⁹

FDA-CDRH Guidance Documents Database¹⁰

FDA-CDRH Premarket Approval (PMA) Database¹¹

FDA-CDRH 510(k) (Premarket Notification) Database¹²

3. Terminology

3.1 Unless provided otherwise in 3.2, terminology shall be in conformance with Terminologies **F1251** and **F2312**.

3.2 Definitions:

3.2.1 *bioactive agents, n*—any molecular component in, on, or within the interstices of a device that elicits a desired tissue or cell response. Growth factors, antibiotics, and antimicrobials are typical examples of bioactive agents. Device structural components or degradation byproducts that evoke limited localized bioactivity are not included.

3.2.2 *pores, n*—an inherent or induced network of channels and open spaces within an otherwise solid structure.

3.2.3 *porometry, n*—the determination of the distribution of pore diameters relative to direction of fluid flow by the displacement of a wetting liquid as a function of pressure.

3.2.4 *porosimetry, n*—the determination of pore volume and pore size distribution through the use of a nonwetting liquid (typically mercury) intrusion into a porous material as a function of pressure.

3.2.5 *porosity, n*—property of a solid which contains an inherent or induced network of channels and open spaces. Porosity can be measured by the ratio of pore (void) volume to the apparent (total) volume of a porous material and is commonly expressed as a percentage.

4. Summary of Guide

4.1 The physicochemical and three-dimensional characteristics of the scaffold material are expected to influence the

⁷ Available from U.S. Pharmacopeia, 12601 Twinbrook Pkwy., Rockville, MD 20852, or through <http://www.usp.org/products/USPNF/>. The standards will be listed by appropriate USP citation number. Succeeding USP editions alternately may be referenced.

⁸ Available from National Institute of Standards and Technology (NIST), 100 Bureau Dr., Stop 1070, Gaithersburg, MD 20899-1070, <http://www.nist.gov>.

⁹ Available from <http://www.accessdata.fda.gov/scripts/cdrh/cfdocs/cfStandards/search.cfm>.

¹⁰ Available from <http://www.accessdata.fda.gov/scripts/cdrh/cfdocs/cfpgp/search.cfm>.

¹¹ Available from <http://www.accessdata.fda.gov/scripts/cdrh/cfdocs/cfPMA/pma.cfm>.

¹² Available from <http://www.accessdata.fda.gov/scripts/cdrh/cfdocs/cfPMN/pmn.cfm>.

⁴ Available from the Association for the Advancement of Medical Instrumentation, 1110 N. Glebe Rd., Suite 220, Arlington, VA 22201-4795.

⁵ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.

⁶ Available from U.S. Government Printing Office Superintendent of Documents, 732 N. Capitol St., NW, Mail Stop: SDE, Washington, DC 20401, <http://www.access.gpo.gov>.

properties of TEMPs. It is the intent of this guide to provide a compendium of materials characterization techniques for properties that may be related directly to the functionality of scaffolds for TEMPs.

4.2 Other characterizations for scaffolds utilized in TEMPs may include compositional identity, physical and chemical properties or characteristics, viable sterilization techniques, degradability/resorbability, and mechanical properties.

4.3 Application of the test methods contained within this guide does not guarantee clinical success of a finished product but will help to ensure consistency in the properties and characterization of a given scaffold material.

4.4 This guide does not suggest that all of the listed tests be conducted. The decision regarding applicability or suitability of any particular test method remains the responsibility of the supplier, user, or regulator of the scaffold material based on applicable regulations, characterizations, and preclinical/clinical testing.

5. Significance and Use

5.1 Scaffolds potentially may be metallic, ceramic, polymeric, natural, or composite materials. Scaffolds are usually porous to some degree, but may be solid. Scaffolds can range from mechanically rigid to gelatinous and can be either absorbable/degradable or nonresorbable/nondegradable. The scaffold may or may not have a surface treatment. Because of this large breadth of possible starting materials and scaffold constructions, this guide cannot be considered as exhaustive in its listing of potentially applicable tests. A voluntary guidance for the development of tissue-engineered products can be found in Omstead, et al (1).¹³ Guide F2027 contains a listing of potentially applicable test methods specific to various starting materials.

5.2 Each TEMP scaffold product is unique and may require testing not within the scope of this guide or other guidance documents. Users of this guide are encouraged to examine the references listed herein and pertinent FDA or other regulatory guidelines or practices, and conduct a literature search to identify other procedures particularly pertinent for evaluation of their specific scaffold material (2,3,4). It is the ultimate responsibility of the TEMP scaffold designer to determine the appropriate testing, whether or not it is described in this guide.

5.3 A listing of potentially applicable tests for characterizing and analyzing the materials utilized to fabricate the scaffold may be found in Guide F2027. However, conformance of a raw material to this and/or any other compendial standard(s) does not, in itself, ensure that the selected material is suitable or that the provided quality is adequate to meet the needs of a particular application. Thus, other characterization procedures may also be relevant and not covered by this guide.

5.4 The following provides a listing of links to U.S. Food & Drug Administration (FDA)—Center for Devices & Radiologic Health (CDRH) web sites that may potentially contain

¹³ The boldface numbers in parentheses refer to the list of references at the end of this standard.

additional guidance relevant to biomaterial scaffolds covered within this document.

5.4.1 *Recognized FDA-CDRH Consensus Standards Database:*

5.4.1.1 <http://www.accessdata.fda.gov/scripts/cdrh/cfdocs/cfStandards/search.cfm>

5.4.1.2 This database provides a resource for locating FDA recognized consensus standards for medical products.

5.4.2 *FDA-CDRH Good Guidance Practice (GGP) Database:*

5.4.2.1 <http://www.accessdata.fda.gov/scripts/cdrh/cfdocs/cfggp/search.cfm>

5.4.2.2 This database provides a resource for locating non-binding FDA guidance documents intended for CDRH staff, regulated industry and the public that relate to the processing, content, and evaluation of regulatory submissions, the design, production, manufacturing, and testing of regulated products, and FDA inspection and enforcement procedures.

5.4.2.3 A document within this database possessing content that warrants particular consideration for its potential applicability for tissue engineering scaffolds is *Guidance for the Preparation of a Premarket Notification Application for a Surgical Mesh; Final*.

5.4.3 *FDA-CDRH Premarket Approval (PMA) Database:*

5.4.3.1 <http://www.accessdata.fda.gov/scripts/cdrh/cfdocs/cfPMA/pma.cfm>

5.4.4 *FDA-CDRH 510(k) (Premarket Notification) Database:*

5.4.4.1 <http://www.accessdata.fda.gov/scripts/cdrh/cfdocs/cfPMN/pmnm.cfm>

6. Chemical Properties and Tests

NOTE 1—Chemical properties are the chemical composition characteristics of a compound. Chemical tests provide information about the identity or nature of the chemical components of a scaffold. Chemical tests include those that provide information about the nature or size of constituent molecules, the product's purity, and/or the chemical nature of the scaffold surface.

6.1 *Identification of Impurities:*

6.1.1 Chemical impurities are expected and unexpected materials that are not part of the intended design of the scaffold. Acceptable levels are a function of the nature of the impurity and the scaffold's intended *in vitro* or *in vivo* application, and may be evaluated by appropriate qualification studies. A more precise definition of both contaminants and impurities and guidance regarding their significance may be found in Guide E1298.

6.1.2 Expected impurities of potential biological significance should be monitored through appropriate analytic means. Impurities can occur in both synthetic and natural based materials (for example, proteins, such as collagen and elastin; polysaccharides, such as cellulose, alginate, hyaluronan, and chitin based derivatives) and may include, but are not limited to processing aids or solvents, unreacted cross-linking agents, residual monomers, endotoxins, sterilization residuals, and residual solutions that, by their chemical nature or relative concentrations, carry potential for influencing cell or tissue response.

6.1.3 Impurities may be identified or quantitatively determined by infrared (IR) spectroscopy, nuclear magnetic resonance (NMR), combined gas chromatography/mass spectrometry (GC/MS), or other analytic methods as appropriate. Polyacrylamide gel electrophoresis is a possible method for assessing the presence of impurities in biologically derived scaffold materials (for example, collagen, hyaluronic acid). Impurities separated within such gels can be detected with Coomassie Blue (as a general protein stain) or silver (as a general protein and carbohydrate stain), and characterized further by immunoblot analysis and/or protein sequencing to identify specific impurities that may possess critical biological activities (for example, elastin immunogenicity, cytokines and growth factors). Once characterized, such impurities can be assessed by other robust and sensitive methods well suited to a manufacturing environment (for example, ELISA for specific substances identified by immunoblot analysis or protein sequencing.)

6.1.4 Generally, impurities are isolated more readily when the scaffold in its entirety can be solvated along with possible contaminants. If the scaffold cannot be dissolved, exhaustive extraction with one or more solvents appropriate to the suspected impurity is necessary.

6.1.4.1 *Solvation/Dissolution*—In the absence of known or established dissolution solvents for a particular material, Practice **D5226** may provide added guidance in identifying suitable potential solvents for dissolving a scaffold material. Samples should not be dissolved in analytic solvents that can be considered as potential contaminants or create analytic interferences.

6.1.4.2 Extraction of residuals may be undertaken by methods such as Practice **G120**. The extract may then be concentrated and analyzed by appropriate chromatographic analysis.

6.1.5 The amount of any expected impurity should be quantified and the analytic detection limit reported. Both solvated and extracted samples should provide results that specify the amount of expected impurity per mass of test sample in either percentage, ppm ($\mu\text{g/g}$; mg/kg), ppb (ng/g ; $\mu\text{g/kg}$), or other appropriate units.

6.1.6 The following analytic methods may be applicable in the determination and quantification of potential impurities:

6.1.6.1 Gas chromatography (GC) may be used for the routine detection of volatile relatively low molecular mass (formerly known as molecular weight) impurities or contaminants. Some methods that may prove suitable include Test Methods **F151** and **F1884**.

6.1.6.2 Gas chromatography can be coupled with both quantitative and qualitative analytic methods such as IR or MS to provide compositional identification while quantitatively detecting low molecular mass volatile impurities or contaminants. Some particular methods that may prove useful include Test Method **D6420** and Practice **E1642**.

6.2 Molar Mass Determination:

NOTE 2—The term molecular weight (abbreviated MW) is obsolete and should be replaced by the SI (Système Internationale) equivalent of either relative molecular mass (M_r), which reflects the dimensionless ratio of the mass of a single molecule to an atomic mass unit (see ISO 31-8), or molar mass (M), which refers to the mass of a mole of a substance and is

typically expressed as grams/mole. For polymers and other macromolecules, use of the symbols M_w , M_n , and M_z continue, referring to mass-average molar mass, number-average molar mass, and z-average molar mass, respectively. For more information regarding proper utilization of SI units, see NIST SP811.

6.2.1 For polymeric materials (synthetic or natural), the molar mass and molar mass distribution may be determined through size exclusion chromatography (SEC) or gel permeation chromatography (GPC). Other procedures such as inherent or intrinsic viscosity (both abbreviated with the acronym “IV”), light scattering, or membrane osmometry may be used. For protein impurities, SDS-Polyacrylamide Gel Electrophoresis (SDS-PAGE) has proven robust and generally applicable. In specific instances, mass spectrometry can provide highly accurate mass determinations as well.

6.2.2 In any of the preceding tests, the solvent solubility characteristics of the scaffold will be highly significant in allowing determination of suitable molar mass test methods. In the absence of known or established dissolution solvents for a particular scaffold construct, Practice **D5226** provides added guidance in identifying suitable potential solvents for dissolving a particular material.

6.2.3 The following test methods may be applicable in the determining the molar mass of the fabricated scaffold.

NOTE 3—The following GPC/SEC and IV methods are considered to be suitable for use on linear polymer systems only. Branched polymer systems should use light-scattering techniques.

6.2.3.1 *Gel Permeation Chromatography (GPC), Also Known as Size Exclusion Chromatography (SEC)*—See Test Methods **D5296** and **D6474** and Practices **D3016** and **D6579**.

NOTE 4—The SEC solvent system and calibration standard polymer type should be specified with any obtained result.

6.2.3.2 *Inherent Viscosity*—See Practice **D2857** and Test Method **D4603**.

NOTE 5—The test temperature, solvent system, and sample concentration should be included with any reported result.

6.2.3.3 *Light Scattering*—See Test Method **D4001**.

NOTE 6—This test method is suitable for both linear and branched polymer systems.

TABLE 1 USP Chemical Tests

USP Test No.	Test Description
<197>	Spectrophotometric identification
<231>	Heavy metals
<381>	Elastomeric closures for injections—physicochemical test procedures
<731>	Loss in drying (water content)
<736>	Mass spectroscopy-purity or elemental analysis
<761>	Nuclear magnetic resonance-purity or component analysis (for example, copolymers)
<851>	Spectrophotometry and light scattering (molar mass information)
<891>	Thermal analysis (purity)
<911>	Viscosity (molar mass)
<921>	Water determination

6.2.3.4 *Melt Flow*—If a scaffold or starting material is found to be insoluble after utilizing the guidance contained within Practice D5226, melt rheology (melt flow rate) may replace the measurements of solution properties to obtain an indication of the material’s molar mass and molar mass distributions. Potentially useful methods include Test Method D1238 and ISO 1133–1991.

6.3 *USP Chemical Tests*—See Table 1.

7. Physical Properties and Tests

NOTE 7—Physical properties are those of a compound that can change without involving a change in chemical composition (5). Physical testing determines the physical properties of materials based on observation and measurement. Such tests include those that provide information about the porosity, density, crystallinity, or physical surface properties of a scaffold material.

7.1 *Porosity Characterization*—The porous macrostructure and microstructure of a scaffold exerts a strong influence on both the elicited cell response and the tissue engineered result. Guide F2450 provides an overview of available pore characterization methods and their respective range of applicability with respect to pore sizes and material characteristics. While Guide F2450 may indicate more suitable method(s) for a specific scaffold’s structure, the following test methodologies are recommended for consideration in the evaluation and characterization of the porosity of scaffolds possessing the 50 to 500 µm pore sizes most typical for the encouragement of cell growth within TEMPs (see X1.2 of this guide for further discussion on the nature, significance, and potential applicability of these test methods):

7.1.1 *Porosimetry (Liquid Intrusion)*—Methodologies suitable for the mercury intrusion measurement of porosity include Test Methods D2873 and D4404.

NOTE 8—An alternative porosimetry suitable non-wetting liquid may be utilized instead of mercury, provided that the resulting maximum pore size limitation is acceptable based on scaffold design and both recognized and accounted for within the results interpretation.

7.1.2 The sample data recommended to be obtained and reported are as follows:

- Median pore diameter and standard deviation (based on volume)—in µm
- Pore diameter range or distribution—in µm
- Total intrusion (void) volume—in cm³/g
- Bulk density—in g/cm³
- Total percentage porosity

$$\frac{\text{Total intrusion (void) volume, cm}^3/\text{g}}{1/\text{bulk density, g/cm}^3} \times 100 = \text{total \% porosity}$$

7.1.3 *Porometry*—Methodology suitable for the capillary flow measurement of pore size and its distribution include Test Methods E128, E1294, and F316.

7.1.4 The sample data recommended to be obtained and reported are maximum or bubble point pore diameter (in micrometres); mean flow pore diameter (in micrometres); and pore size range or distribution, or both, (in micrometres).

7.1.5 *Pneumatic Permeability*—The methodology suitable for measurement of the pneumatic permeability of a scaffold structure includes Test Method D6539.

7.1.5.1 The sample data recommended to be obtained and reported is as follows:

Average coefficient of pneumatic permeability—report in Darcy (0.99 µm²) or millidarcy (0.000 99 µm²)

NOTE 9—In each of the aforementioned porosity, porometry, and permeability tests, bulkier samples may require modification into a thinner profile to allow proper specimen placement into the apparatus (for example, microtome or other sectioning techniques). In such situations, the specimen thickness should be adjusted to be as thick as practical and the test thickness as tested reported with the result. If the sample is anisotropic in nature, separate porometry or permeability sampling profiles for each orientation is recommended.

NOTE 10—If evidence of collapse or distortion of the scaffold’s porous structure is observed as a result of the application of analytic test pressures (that is, induced reversible or non-reversible distortions not reasonably expected under *in vivo* or *in vitro* service conditions), either method modifications (for example, use of an alternative fluid or reduced test pressure range) or alternative pore characterization methodologies should be employed. If significant distortion or other analytic interferences are suspected, utilization of one or more alternative characterization methods may be needed to either corroborate or discard the obtained results.

NOTE 11—If scaffold construction can be reasonably expected to possess either bimodal (for example, both macroporosity and microporosity) or multi-modal distribution of pore sizes, such characteristics should be both quantified and reported and, dependent on actual pore size, may require utilization of multiple pore characterization methodologies.

7.2 Glass transition temperatures, melting temperatures, and crystallinity may have an effect on the mechanical properties of polymer-based scaffolds. Measurement of these properties may be appropriate to ensure consistency in mechanical properties and to identify lot-to-lot variations of scaffold materials.

7.2.1 Methodologies that may be suitable for differential scanning calorimetry (DSC) measurement of glass transition and melting temperatures, or crystallinity of scaffolds include Test Methods D3417, D3418, E793, E794, E1356; Terminologies E473 and E1142; and Practices E967 and E968. Other potentially relevant standards include ISO 11357–1 and ISO 11357–2.

NOTE 12—Crystallinity also may be determined by X-ray diffraction.

7.3 *USP Physical Tests*—See Table 2.

7.4 *Other Physical Tests:*

7.4.1 Water absorption characteristics may be ascertained using Test Method D570.

7.4.2 Density may be assessed using Test Methods D792 if not evaluated within a porosimetry method as described in 7.1.1.

TABLE 2 USP Physical Tests

USP Test No.	Test Description
<616>	Bulk density and tapped density
<661>	Containers—biological tests (PET, PE and Ophthalmic polymers)
<699>	Density of solids
<701>	Disintegration
<741>	Melting range or temperature
<776>	Optical microscopy
<786>	Particle size distribution by analytical sieving
<846>	Specific surface area
<941>	X-ray diffraction—crystallinity
<1045>	Biotechnology derived articles (may be useful for natural materials)
<1181>	Scanning electron microscopy (characterization of surfaces)