



SLOVENSKI STANDARD

SIST EN 13445-3:2014

01-december-2014

Nadomešča:

SIST EN 13445-3:2009

SIST EN 13445-3:2009/A1:2012

SIST EN 13445-3:2009/A2:2014

Neogrevane tlačne posode - 3. del: Konstruiranje

Unfired pressure vessels - Part 3: Design

Unbefeuerte Druckbehälter - Teil 3: Konstruktion

Réceptifs sous pression non soumis à la flamme - Partie 3 : conception

<https://standards.iteh.ai/catalog/standards/sist/c30aeabc-3285-44d3-99a7-80dbea9f1105/sist-en-13445-3-2014>

Ta slovenski standard je istoveten z: **EN 13445-3:2014**

ICS:

23.020.30	Tlačne posode, plinske jeklenke	Pressure vessels, gas cylinders
-----------	---------------------------------	---------------------------------

SIST EN 13445-3:2014

en,fr,de

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 13445-3:2014

<https://standards.iteh.ai/catalog/standards/sist/c30aeabc-3285-44d3-99a7-80dbea9f1105/sist-en-13445-3-2014>

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN 13445-3

September 2014

ICS 23.020.30

Supersedes EN 13445-3:2009

English Version

Unfired pressure vessels - Part 3: Design

Réipients sous pression - Partie 3: Conception

Unbefeuerte Druckbehälter - Teil 3: Konstruktion

This European Standard was approved by CEN on 19 August 2014.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

(standards.iteh.ai)

SIST EN 13445-3:2014

<https://standards.iteh.ai/catalog/standards/sist/c30aeabc-3285-44d3-99a7-80dbea9f1105/sist-en-13445-3-2014>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

Foreword	6
1 Scope	8
2 Normative references	8
3 Terms and definitions	9
4 Symbols and abbreviations	11
5 Basic design criteria	13
5.1 General	13
5.2 Corrosion, erosion and protection.....	13
5.3 Load cases.....	15
5.4 Design methods	19
5.5 Thickness calculations (DBF).....	20
5.6 Joint coefficient.....	21
5.7 Design requirements of welded joints	22
6 Maximum allowed values of the nominal design stress for pressure parts	25
6.1 General	25
6.2 Steels (except castings), other than austenitic steels covered by 6.4 and 6.5, with a minimum rupture elongation, as given in the relevant technical specification for the material, below 30 %	26
6.3 Alternative route for steels (except castings), other than austenitic steels covered by 6.4 and 6.5, with a minimum rupture elongation, as given in the relevant technical specification for the material, below 30 %	26
6.4 Austenitic steels (except castings) with a minimum elongation after rupture, as given in the relevant technical specification for the material, from 30 % to 35 %	27
6.5 Austenitic steels (except castings) with a minimum rupture elongation, as given in the relevant technical specification for the material, from 35 %	27
6.6 Cast steels	28
7 Shells under internal pressure	29
7.1 Purpose.....	29
7.2 Specific definitions	29
7.3 Specific symbols and abbreviations.....	29
7.4 Cylindrical and spherical shells	29
7.5 Dished ends.....	30
7.6 Cones and conical ends	35
7.7 Nozzles which encroach into the knuckle region	43
8 Shells under external pressure	48
8.1 Purpose.....	48
8.2 Specific definitions	48
8.3 Specific symbols and definitions	48
8.4 General	51
8.5 Cylindrical shells.....	52
8.6 Conical shell	73
8.7 Spherical shells.....	81
8.8 Vessel ends	82
9 Openings in shells	83
9.1 Purpose.....	83
9.2 Specific definitions	83
9.3 Specific symbols and abbreviations.....	84
9.4 General.....	87
9.5 Isolated openings.....	99
9.6 Multiple openings.....	115
9.7 Openings close to a shell discontinuity	125

10	Flat ends	133
10.1	Purpose.....	133
10.2	Specific definitions	133
10.3	Specific symbols and abbreviations.....	133
10.4	Unpierced circular flat ends welded to cylindrical shells.....	135
10.5	Unpierced bolted circular flat ends.....	142
10.6	Pierced circular flat ends	146
10.7	Flat ends of non-circular or annular shape.....	150
11	Flanges.....	154
11.1	Purpose.....	154
11.2	Specific definitions	154
11.3	Specific symbols and abbreviations.....	154
11.4	General.....	157
11.5	Narrow face gasketed flanges	161
11.6	Full face flanges with soft ring type gaskets	176
11.7	Seal welded flanges	179
11.8	Reverse narrow face flanges	179
11.9	Reverse full face flanges.....	182
11.10	Full face flanges with metal to metal contact	186
12	Bolted domed ends.....	189
12.1	Purpose.....	189
12.2	Specific definitions	189
12.3	Specific symbols and abbreviations.....	189
12.4	General.....	189
12.5	Bolted domed ends with narrow face gaskets.....	189
12.6	Bolted domed ends with full face joints	191
13	Heat Exchanger Tubesheets.....	193
13.1	Purpose.....	193
13.2	Specific definitions	193
13.3	Specific symbols and abbreviations.....	193
13.4	U-tube tubesheet heat exchangers.....	196
13.5	Fixed tubesheet heat exchangers.....	210
13.6	Floating tubesheet heat exchangers.....	238
13.7	Tubesheet characteristics.....	255
13.8	Maximum permissible tube to tubesheet joint stress	262
13.9	Maximum permissible longitudinal compressive stress for tubes.....	263
13.10	Design of tubesheet flange extension with a narrow face gasket.....	266
13.11	Design of tubesheet flange extension with a full face gasket.....	269
13.12	Special tube-to-tubesheet welded joints	272
14	Expansion bellows.....	275
14.1	Purpose.....	275
14.2	Specific definitions	275
14.3	Specific symbols and abbreviations.....	277
14.4	Conditions of applicability	279
14.5	U-shaped unreinforced bellows	281
14.6	U-shaped reinforced bellows	295
14.7	Toroidal bellows.....	303
14.8	Fabrication.....	310
14.9	Inspection and testing.....	312
14.10	Bellows subjected to axial, lateral or angular displacements.....	314
15	Pressure vessels of rectangular section.....	319
15.1	Purpose.....	319
15.2	Specific definitions	319
15.3	Specific symbols and abbreviations.....	319
15.4	General.....	320

iTech STANDARD PREVIEW

(standards.itech.ai)

ST EN 13445-3:2014
<http://www.italianstandards.org/standards/sist/c30aebc-3285-44d3-99a7-2685e6600000/standards/sist/en-13445-3-2014>

15.5	Unreinforced vessels.....	320
15.6	Reinforced vessels	326
15.7	Openings.....	333
16	Additional non-pressure loads	335
16.1	Purpose.....	335
16.2	Specific definitions	335
16.3	Specific symbols and abbreviations.....	336
16.4	Local loads on nozzles in spherical shells	337
16.5	Local loads on nozzles in cylindrical shells	347
16.6	Line loads	355
16.7	Lifting lugs.....	361
16.8	Horizontal vessels on saddle supports	365
16.9	Horizontal vessels on ring supports.....	379
16.10	Vertical vessels on bracket supports	384
16.11	Vertical vessels with supporting legs.....	389
16.12	Vertical vessels with skirts	391
16.13	Vertical vessels with ring supports.....	422
16.14	Global loads.....	433
17	Simplified assessment of fatigue life.....	438
17.1	Purpose.....	438
17.2	Specific definitions	438
17.3	Specific symbols and abbreviations.....	440
17.4	Conditions of applicability	441
17.5	General.....	442
17.6	Determination of allowable number of pressure cycles	447
17.7	Assessment rule	472
17.8	Design and manufacture	472
17.9	Testing	473
18	Detailed assessment of fatigue life.....	474
18.1	Purpose.....	474
18.2	Specific definitions	474
18.3	Specific symbols and abbreviations.....	477
18.4	Limitations	479
18.5	General.....	481
18.6	Welded material.....	483
18.7	Unwelded components and bolts.....	488
18.8	Elastic-plastic conditions.....	491
18.9	Fatigue action	493
18.10	Fatigue strength of welded components.....	496
18.11	Fatigue strength of unwelded components	517
18.12	Fatigue strength of steel bolts.....	522
19	Creep design	525
19.1	Purpose.....	525
19.2	Specific definitions	525
19.3	Specific symbols and abbreviations.....	525
19.4	Design in the creep range	526
19.5	Nominal Design stress in the creep range	526
19.6	Weld joint factor in the creep range.....	531
19.7	Pressure loading of predominantly non-cyclic nature in the creep range	531
19.8	Design procedures for DBF	531
20	Design rules for reinforced flat walls.....	535
20.1	General.....	535
20.2	Stayed flat walls	535
20.3	Specific definitions for stayed flat walls.....	535
20.4	Required thickness of stayed flat walls.....	535
20.5	Required dimensions and layout of staybolts and stays	535
20.6	Requirements for threaded staybolts	536
20.7	Requirements for welded-in staybolts and welded stays.....	536
20.8	Tables for stayed flat walls	537
20.9	Figures for Stayed Flat Walls.....	538

21	Circular flat ends with radial reinforcement ribs	541
21.1	Purpose.....	541
21.2	Specific definitions	541
21.3	Specific symbols and abbreviations.....	543
21.4	Ends without additional peripheral bending moment.....	544
21.5	Ends with additional peripheral bending moment	546
21.6	Openings.....	548
21.7	Welds.....	548
21.8	Central Ring.....	548
22	Static analysis of tall vertical vessels on skirts.....	550
22.1	Purpose.....	550
22.2	Definitions.....	550
22.3	Specific symbols and abbreviations.....	551
22.4	Loads.....	552
22.5	Load combinations	555
22.6	Stress analysis of pressure vessel shells and skirts.....	558
22.7	Design of joint between skirt and pressure vessel (at dished end or cylindrical shell).....	558
22.8	Design of anchor bolts and base ring assembly.....	558
22.9	Foundation loads	559
Annex A (normative) Design requirements for pressure bearing welds.....		560
Annex B (normative) Design by Analysis – Direct Route		584
Annex C (normative) Design by analysis - Method based on stress categories.....		614
Annex D (informative) Verification of the shape of vessels subject to external pressure.....		633
Annex E (normative) Procedure for calculating the departure from the true circle of cylinders and cones.....		640
Annex F (normative) Allowable external pressure for vessels outside circularity tolerance		643
Annex G (normative) Alternative design rules for flanges and gasketed flange connections		645
Annex GA (informative) Alternative design rules for flanges and gasketed flange connections		692
Annex H (informative) Gasket factors m and y		755
Annex I (informative) Additional information on heat exchanger tubesheet design.....		758
Annex J (normative) Alternative method for the design of heat exchanger tubesheets.....		762
Annex K (informative) Additional information on expansion bellows design.....		807
Annex L (informative) Basis for design rules related to additional non-pressure loads		813
Annex M (informative) In service monitoring of vessels operating in fatigue or creep		815
Annex N (informative) Bibliography to Clause 18		818
Annex O (informative) Physical properties of steels		819
Annex P (normative) Classification of weld details to be assessed using principal stresses		827
Annex Q (normative) Simplified procedure for the fatigue assessment of unwelded zones		840
Annex R (informative) Coefficients for creep-rupture model equations for extrapolation of creep-rupture strength		841
Annex S (informative) Extrapolation of the nominal design stress based on time- independent behaviour in the creep range		845
Annex T (normative) Design by experimental methods.....		851
Annex Y (informative) History of EN 13445-3.....		864
Annex ZA (informative) Relationship between this European Standard and the Essential Requirements of the EU Pressure Equipment Directive 97/23/EC.....		865

EN 13445-3:2014 (E)
Issue 1 (2014-09)

Foreword

This document (EN 13445-3:2014) has been prepared by Technical Committee CEN/TC 54 “Unfired pressure vessels”, the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by December 2014, and conflicting national standards shall be withdrawn at the latest by December 2014.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association, and supports essential requirements of EU Directive(s).

For relationship with EU Directive(s), see informative annex ZA, which is an integral part of this document.

This European Standard consists of the following Parts:

- Part 1: *General.*
- Part 2: *Materials.*
- Part 3: *Design.*
- Part 4: *Fabrication.*
- Part 5: *Inspection and testing.*
- Part 6: *Requirements for the design and fabrication of pressure vessels and pressure parts constructed from spheroidal graphite cast iron.*
- CR 13445-7, *Unfired pressure vessels — Part 7: Guidance on the use of conformity assessment procedures.*
- Part 8: *Additional requirements for pressure vessels of aluminium and aluminium alloys.*
- CEN/TR 13445-9, *Unfired pressure vessels — Part 9: Conformance of EN 13445 series to ISO 16528*

Although these Parts may be obtained separately, it should be recognised that the Parts are inter-dependant. As such the manufacture of unfired pressure vessels requires the application of all the relevant Parts in order for the requirements of the Standard to be satisfactorily fulfilled.

Corrections to the standard interpretations where several options seem possible are conducted through the Migration Help Desk (MHD). Information related to the Help Desk can be found at <http://www.unm.fr/en13445@unm.fr>. A form for submitting questions can be downloaded from the link to the MHD website. After subject experts have agreed an answer, the answer will be communicated to the questioner. Corrected pages will be given specific issue number and issued by CEN according to CEN Rules. Interpretation sheets will be posted on the website of the MHD.

This document supersedes EN 13445-3:2009. This new edition incorporates the Amendments which have been approved previously by CEN members, and the corrected pages up to Issue 5 without any further technical change. Annex Y provides details of significant technical changes between this European Standard and the previous edition.

Amendments to this new edition may be issued from time to time and then used immediately as alternatives to rules contained herein. It is intended to deliver a new Issue of EN 13445:2014 each year, starting with the present document as Issue 1, consolidating these Amendments and including other identified corrections.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

iTeh STANDARD PREVIEW

(standards.iteh.ai)

[SIST EN 13445-3:2014](https://standards.iteh.ai/catalog/standards/sist/c30aeabc-3285-44d3-99a7-80dbea9f1105/sist-en-13445-3-2014)

<https://standards.iteh.ai/catalog/standards/sist/c30aeabc-3285-44d3-99a7-80dbea9f1105/sist-en-13445-3-2014>

EN 13445-3:2014 (E)
Issue 1 (2014-09)

1 Scope

This Part of this European Standard specifies requirements for the design of unfired pressure vessels covered by EN 13445-1:2014 and constructed of steels in accordance with EN 13445-2:2014.

EN 13445-5:2014, Annex C specifies requirements for the design of access and inspection openings, closing mechanisms and special locking elements.

NOTE This Part applies to design of vessels before putting into service. It may be used for in service calculation or analysis subject to appropriate adjustment.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 286-2:1992, *Simple unfired pressure vessels designed to contain air or nitrogen — Part 2: Pressure vessels for air braking and auxiliary systems for motor vehicles and their trailers*

EN 764-1:2004, *Pressure equipment — Terminology — Part 1: Pressure, temperature, volume, nominal size*

EN 764-2:2012, *Pressure equipment — Part 2: Quantities, symbols and units*

EN 764-3:2002, *Pressure equipment — Part 3: Definition of parties involved*

EN 837-1:1996, *Pressure gauges — Part 1: Bourdon tube pressure gauges — Dimensions, metrology, requirements and testing*

EN 837-3:1996, *Pressure gauges — Part 3: Diaphragm and capsule pressure gauges — Dimensions, metrology, requirements and testing*

EN 1092-1:2007, *Flanges and their joints — Circular flanges for pipes, valves, fittings and accessories, PN-designated — Part 1: Steel flanges*

EN 1591-1:2011, *Flanges and their joints — Design rules for gasketed circular flange connections — Calculation method*

EN 1708-1:2010, *Welding — Basic weld joint details in steel — Part 1: Pressurized components*

EN 1990, *Eurocode — Basis of structural design*

EN 1992-1-1:2005, *Eurocode 2 — Design of concrete structures — Part 1-1: General rules and rules for buildings*

EN 1991-1-4:2005, *Eurocode 1: Actions on structures — Part 1-4: General actions — Wind actions*

EN 1991-1-6, *Eurocode 1 — Actions on structures — Part 1-6: General actions — Actions during execution*

EN 1998-1:2004, *Design of structures for earthquake resistance — Part 1: General rules, seismic actions and rules for buildings*

EN 10222-1:1998, EN 10222-1:1998/A1:2002, *Steel forgings for pressure purposes — Part 1: General requirements for open die forgings*

EN 13445-1:2014, *Unfired pressure vessels — Part 1: General*

EN 13445-2:2014, *Unfired pressure vessels — Part 2: Materials*

EN 13445-4:2014, *Unfired pressure vessels — Part 4: Fabrication*

EN 13445-5:2014, *Unfired pressure vessels — Part 5: Inspection and testing*

EN 13445-8:2014, *Unfired pressure vessels — Part 8: Additional requirements for pressure vessels of aluminium and aluminium alloys*

EN ISO 4014:2011, *Hexagon head bolts — Product grades A and B (ISO 4014:2011)*

EN ISO 4016:2011, *Hexagon head bolts — Product grade C (ISO 4016:2011)*

EN ISO 15613:2004, *Specification and qualification of welding procedures for metallic materials — Qualification based on pre-production welding test*

ISO 261:1998, *ISO general purpose metric threads — General plan*

3 Terms and definitions

For the purposes of this Part of this European Standard, the terms and definitions given in EN 13445-1:2014, EN 13445-2:2014 and the following apply:

NOTE EN 13445-1:2014 and EN 13445-2:2014 have adopted terminology, symbols and definitions of EN 764-1:2004, EN 764-2:2012 and EN 764-3:2002.

iTech STANDARD PREVIEW
(standards.iteh.ai)

3.1

action

imposed thermo-mechanical influence which causes stress and/or strain in a structure, e.g. an imposed pressure, force, temperature

SIST EN 13445-3:2014
<https://standards.iteh.ai/catalog/standards/sist/c50acabc-3283-44d5-97a7-80dbea9f1105/sist-en-13445-3-2014>

3.2

analysis thickness

effective thickness available to resist the loading depending on the load case, see 5.3.2

3.3

assumed thickness

thickness assumed by the designer between the minimum required shell thickness e and the shell analysis thickness e_a

3.4

calculation pressure

differential pressure used for the purpose of the design calculations for a component [EN 764-1:2004]

3.5

calculation temperature

temperature used for the purpose of the design calculations for a component [EN 764-1:2004]

3.6

chamber

fluid space within a unit of pressure equipment [EN 764-1:2004]

3.7

component

part of pressure equipment which can be considered as an individual item for the calculation [EN 764-1:2004]

EN 13445-3:2014 (E)
Issue 1 (2014-09)

3.8

creep range

temperature range in which material characteristics used in design are time dependent

NOTE See also 5.1.

3.9

cryogenic applications

applications involving liquefied gases at low temperature

3.10

design pressure

pressure at the top of each chamber of the pressure equipment chosen for the derivation of the calculation

pressure of each component

[EN 764-1:2004]

NOTE Any other location may be specified.

3.11

design temperature

temperature chosen for the derivation of the calculation temperature of each component

[EN 764-1:2004]

3.12

differential pressure

pressure which algebraic value is equal to the pressure difference on either side of a separation wall

[EN 764-1:2004]

3.13

governing weld joint

main full penetration butt joint the design of which, as a result of membrane stresses, governs the thickness of the component

3.14

load case

combination of coincident actions

3.15

main joint

weld joint assembling main pressure bearing parts

3.16

maximum permissible pressure

maximum pressure obtained from the design by formulae or relevant procedures of EN 13445-3:2014 for a given component in a given load case, or for the whole pressure vessel the minimum of these maximum permissible pressures of all components

NOTE 1 The differences of the nominal design stress f , the analysis thickness e_a and the joint coefficient z for the calculation of the maximum permissible pressure in different load cases are specified in 5.3.2.

NOTE 2 If no explicit formula is given for the maximum permissible pressure P_{max} then P_{max} may be calculated as pressure which gives the required thickness equal to the analysis thickness.

NOTE 3 The maximum permissible pressure P_{max} used for the simplified assessment of fatigue life in Clause 17 and for the calculation of the equivalent full pressure in 5.4.2 is calculated for normal operating load cases.

3.17

minimum possible fabrication thickness

minimum possible thickness after fabrication

3.18**nominal design stress**

stress value to be used in the formulae for the calculation of pressure components

3.19**nominal thickness**

thickness as specified on the drawings

3.20**test pressure**

pressure to which the equipment is subjected for test purposes

[EN 764-1:2004]

3.21**test temperature**

temperature at which the pressure test of the pressure equipment is carried out

[EN 764-1:2004]

3.22**volume**

internal volume of a chamber, including the volume of nozzles to the first connection (flange, coupling, weld) and excluding the volume of internal permanent parts (e.g. baffles, agitators)

[EN 764-1:2004]

3.23**weld throat thickness of a fillet weld**

height of the inscribed isosceles triangle measured from the theoretical root point

iTeh STANDARD PREVIEW
(standards.iteh.ai)

4 Symbols and abbreviations

SIST EN 13445-3:2014

[https://standards.iteh.ai/catalog/standards/sist/c30aeabc-3285-44d3-99a7-](https://standards.iteh.ai/catalog/standards/sist/c30aeabc-3285-44d3-99a7-80dbea9f1105/sist-en-13445-3-2014)

[80dbea9f1105/sist-en-13445-3-2014](https://standards.iteh.ai/catalog/standards/sist/c30aeabc-3285-44d3-99a7-80dbea9f1105/sist-en-13445-3-2014)

For the purposes of this Part of this European Standard, the general symbols and abbreviations shall be in accordance with EN 13445-1:2014, EN 13445-2:2014 and Table 4-1:

Table 4-1 — Symbols, quantities and units ^c

Symbol	Quantity	Unit
a	weld throat thickness	mm
e	required thickness	mm
e_n	nominal thickness	mm
e_{\min}	minimum possible fabrication thickness	mm
e_a	analysis thickness	mm
c	corrosion allowance	mm
f	nominal design stress	MPa
f_d	maximum value of the nominal design stress for normal operating load cases	MPa
f_{exp}	maximum value of the nominal design stress for exceptional load cases	MPa
f_{test}	maximum value of the nominal design stress for testing load cases	MPa
n_{eq}	number of equivalent full pressure cycles (see 5.4.2)	-
P	calculation pressure	MPa ^a
P_d	design pressure	MPa ^a
P_{max}	maximum permissible pressure	MPa ^a
PS, P_s	maximum allowable pressure	MPa ^a
P_{test}	test pressure	MPa ^a
R_{eH}	upper yield strength	MPa
R_m	tensile strength	MPa
$R_{m/T}$	tensile strength at temperature T	MPa
$R_{p0,2}$	0,2 % proof strength	MPa
$R_{p0,2/T}$	0,2 % proof strength at temperature T	MPa
$R_{p1,0}$	1,0 % proof strength	MPa
$R_{p1,0/T}$	1,0 % proof strength at temperature T	MPa
T	calculation temperature	°C
T_d	design temperature	°C
T_{test}	test temperature	°C
$TS_{\text{max}}, TS_{\text{min}}$	maximum/minimum allowable temperatures	°C
V	volume	mm ³ ^b
Z	joint coefficient	—
ν	Poisson's ratio	—

^a MPa for calculation purpose only, otherwise the unit may be bar (1 MPa = 10 bar).

^b mm³ for calculation purpose only, otherwise the unit should be litre.

^c Formulae used in this standard are dimensional.

5 Basic design criteria

5.1 General

EN 13445-3:2014 is applicable only when:

- a) materials and welds are not subject to localized corrosion in the presence of products which the vessel is to contain or which can be present in the vessel under reasonably foreseeable conditions.
- b) either all calculation temperatures are below the creep range **or** a calculation temperature is in the creep range and time dependent material characteristics are available in the materials standard.

NOTE See definition 3.8 of creep range.

For the purpose of design, the creep range is the temperature range in which time independent material characteristics are no more governing in the determination of the nominal design stress.

The material strength characteristics used shall be related to the specified lifetimes in the various creep load cases

5.2 Corrosion, erosion and protection

5.2.1 General

Whenever the word "corrosion" is used in this standard it shall be taken to mean corrosion, oxidation, scaling, abrasion, erosion and all other forms of wastage.

NOTE 1 Stress corrosion cracking may occur under certain conditions of temperature and environment. A corrosion allowance is not an appropriate way of dealing with stress corrosion. Under such conditions, consideration shall be given to the materials used and the residual stresses in the fabricated vessel.

NOTE 2 It is impossible to lay down definite precautionary guidelines to safeguard against the effects of corrosion owing to the complex nature of corrosion itself, which may occur in many forms, including but not limited to the following:

- chemical attack where the metal is dissolved by the reagents. It may be general over the whole surface or localized (causing pitting) or a combination of the two;
- rusting caused by the combined action of moisture and air;
- erosion corrosion where a reagent otherwise innocuous flows over the surface at velocity greater than some critical value;
- high temperature oxidation (scaling).

Consideration should be given to the effect which corrosion (both internal and external) may have upon the useful life of the vessel. When in doubt, corrosion tests should be undertaken. These should be carried out on the actual metal (including welds or combination of metals) under exposure to the actual chemicals used in service. Corrosion tests should be continued for a sufficiently long period to determine the trend of any change in the rate of corrosion with respect to time.

NOTE 3 It is very dangerous to assume that the major constituent of a mixture of chemicals is the active agent, as in many cases small traces of a substance can exert an accelerating or inhibiting effect out of all proportion to the amount present. Fluid temperatures and velocities from corrosion test data should be equivalent to those met in operation.