

Designation: A575 - 96(Reapproved 2007)

Standard Specification for Steel Bars, Carbon, Merchant Quality, M-Grades¹

This standard is issued under the fixed designation A575; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope

- 1.1 This specification covers hot-wrought merchant quality carbon steel bars produced to a chemical composition. Merchant quality bars are used for structural and similar miscellaneous bar applications involving moderate cold bending, moderate hot forming, punching, and welding as used in the production of noncritical parts. Moderate cold bending involves a generous bend radius with the axis of the bend transverse to the direction of rolling.
- 1.2 Special quality hot-wrought carbon steel bars are covered in Specification A576.
- 1.3 Some end uses may require one or more of the available designations shown under Supplementary Requirements.
- 1.4 The values stated in inch-pound units are to be regarded as the standard.

2. Referenced Documents

2.1 ASTM Standards:²

A29/A29M Specification for Steel Bars, Carbon and Alloy,
Hot-Wrought, General Requirements for
ASTM A575

A576 Specification for Steel Bars, Carbon, Hot-Wrought, Special Quality

3. Ordering Information

- 3.1 Orders under this specification should include the following as required to describe adequately the desired material:
 - 3.1.1 ASTM specification number and date of issue,
- 3.1.2 Grade designation or chemical composition (Section 7 and appropriate chemical analysis tables),
 - 3.1.3 Supplementary Requirements or additions, if required,
 - 3.1.4 Dimensions and quantity, and
 - 3.1.5 End use and processing.
- ¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.15 on Bars.
- Current edition approved Sept. 1, 2007. Published January 2008. Originally approved in 1967. Last previous edition approved in 2002 as A575-96 (2002). DOI: 10.1520/A0575-96R07.
- ² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

4. Materials and Manufacture

4.1 The steel shall be made by the open-hearth, basic-oxygen, or electric-furnace process.

5. Conditions

- 5.1 Merchant quality bars are available in rounds, squares, round cornered squares, hexagons, and bar size shapes under 3 in. (76.2 mm), and in flats less than 40.8 lb/ft (60.7 kg/m). Hot-wrought merchant quality carbon steel bars are produced in cut lengths and coils; the producer should be consulted regarding sections and sizes available in coils.
- 5.2 Merchant quality is available within a composition of 0.50 % maximum carbon, 0.60 % maximum manganese, nonresulfurized, non-leaded. The phosphorus content is 0.04 %, max, and the sulfur content is 0.05 %, max. Merchant quality grades of steel are shown in Table 1 and chemical ranges and limits in Table 2; the grade numbers are designated with the prefix "M." Merchant quality bars are not produced to any specified silicon content, grain size, or other requirement that would influence the type of steel.
- 5.3 Merchant quality bars shall be free of visible pipe; however, they may contain pronounced chemical segregation. Internal porosity, surface seams, and other surface irregularities may be present in this quality.

6. Chemical Composition

6.1 The steel shall conform on heat analysis to the requirements of chemical composition in Table 1, or chemical compositions can be specified that conform to the ranges and limits in Table 2. The heat analysis shall be reported to the purchaser for the elements specified.

7. General Requirements

7.1 Material furnished under this specification shall conform to the requirements of the current edition of Specification A29/A29M.

iTeh Standards (https://standards.iteh.ai) Document Preview

ASTM A575-96(2007)

https://standards.iteh.ai/catalog/standards/sist/1fb07c75-95d2-41b6-acd3-d290b1456c78/astm-a575-962007