



**Designation: A 192/A 192M-02 Designation: A192/A192M – 02 (Reapproved 2007)**

## Standard Specification for Seamless Carbon Steel Boiler Tubes for High-Pressure Service<sup>1</sup>

This standard is issued under the fixed designation A192/A192M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the Department of Defense.*

### 1. Scope <sup>\*</sup>

1.1 This specification<sup>2</sup> covers minimum-wall-thickness, seamless carbon steel boiler and superheater tubes for high-pressure service.

1.2 The tubing sizes and thicknesses usually furnished to this specification are ½ in. to 7 in. [12.7 to 177.8 mm] outside diameter and 0.085 to 1.000 in. [2.2 to 25.4 mm], inclusive, in minimum wall thickness. Tubing having other dimensions may be furnished, provided such tubes comply with all other requirements of this specification.

1.3 Mechanical property requirements do not apply to tubing smaller than ⅛ in. [3.2 mm] inside diameter or 0.015 in. [0.4 mm] thickness.

1.4 The values stated in either inch-pound units or SI units are to be regarded separately as standard. Within the text, the SI units are shown in brackets. The values stated in each system are not exact equivalents; therefore, each system must be used independently of the other. Combining values from the two systems may result in nonconformance with the specification. The inch-pound units shall apply unless the “M” designation of this specification is specified in the order.

### 2. Referenced Documents

2.1 *ASTM Standards*:<sup>3</sup>

A450/A450M [Specification for General Requirements for Carbon, Ferritic Alloy, Carbon and Austenitic Low Alloy Steel Tubes](https://standards.it-ebooks.info)

### 3. Ordering Information

3.1 Orders for material under this specification should include the following, as required, to describe the desired material adequately:

3.1.1 Quantity (feet, metres, or number of lengths),

3.1.2 Name of material (seamless tubes),

3.1.3 Manufacture (hot-finished or cold-finished),

3.1.4 Size (outside diameter and minimum wall thickness),

3.1.5 Length (specific or random),

3.1.6 Optional requirements (Section 8),

3.1.7 Test report required (see section on Certification of Specification A 450/A 450M A450/A450M),

3.1.8 Specification designation, and

3.1.9 Special requirements.

### 4. General Requirements

4.1 Material furnished under this specification shall conform to the applicable requirements of the current edition of Specification A 450/A 450M A450/A450M, unless otherwise provided herein.

### 5. Manufacture

5.1 Tubes shall be made by the seamless process and shall be either hot-finished or cold-finished, as specified.

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.09 on Carbon Steel Tubular Products.

Current edition approved Sept. 10, 2002. Published November 2002. Originally published as A 192-36T. Last previous edition A 192/A 192M – 91 (2001).

Current edition approved Nov. 1, 2007. Published January 2008. Originally approved in 1936. Last previous edition approved in 2002 as A192/A192M– 02. DOI: 10.1520/A0192\_A0192M-02R07.

<sup>2</sup> For ASME Boiler and Pressure Vessel Code applications see related Specification SA-192 in Section II of that Code.

<sup>3</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

## 6. Heat Treatment

6.1 Hot-finished tubes need not be heat treated. Cold-finished tubes shall be heat treated after the final cold-finishing at a temperature of 1200°F [650°C] or higher.

## 7. Chemical Composition

7.1 The steel shall conform to the following requirements as to chemical composition:

Carbon, %	0.06–0.18
Manganese, %	0.27–0.63
Phosphorus, max, %	0.035
Sulfur, max, %	0.035
Silicon, max, %	0.25

7.2 Supplying an alloy grade of steel that specifically requires the addition of any element other than those listed in 7.1 is not permitted.

## 8. Product Analysis

8.1 When requested on the purchase order, a product analysis shall be made by the supplier from one tube per 100 pieces for sizes over 3 in. [76.2 mm] and one tube per 250 pieces for sizes 3 in. [76.2 mm] and under; or when tubes are identified by heat, one tube per heat shall be analyzed. The chemical composition thus determined shall conform to the requirements specified.

8.2 If the original test for product analysis fails, retests of two additional billets or tubes shall be made. Both retests, for the elements in question, shall meet the requirements of the specification; otherwise all remaining material in the heat or lot (see Note 1) shall be rejected or, at the option of the producer, each billet or tube may be individually tested for acceptance. Billets or tubes which do not meet the requirements of the specification shall be rejected.

NOTE 1—A lot consists of 250 tubes for sizes 3 in. [76.2 mm] and under and of 100 tubes for sizes over 3 in. [76.2 mm], prior to cutting to length.

## 9. Hardness Requirements

9.1 The tubes shall have a hardness number not exceeding the following:

Brinell Hardness Number (Tubes 0.200 in. [5.1 mm] and over in wall thickness)	Rockwell Hardness Number (Tubes less than 0.200 in. [5.1 mm] in wall thickness)
137 HB	77 HRB

## 10. Mechanical Tests Required

10.1 *Flattening Test*—One flattening test shall be made on specimens from each end of two tubes selected from each lot (see Note 1) or fraction thereof.

10.2 *Flaring Test*—One flaring test shall be made on specimens from each end of two tubes selected from each lot (see Note 1) or fraction thereof. These tubes shall be selected apart from those used for the flattening test.

10.3 *Hardness Test*—Brinell or Rockwell hardness tests shall be made on specimens from two tubes from each lot. The term *lot* applies to all tubes prior to cutting, of the same nominal diameter and wall thickness which are produced from the same heat of steel. When final heat treatment is in a batch-type furnace, a lot shall include only those tubes of the same size and the same heat which are heat treated in the same furnace charge. When the final heat treatment is in a continuous furnace, a lot shall include all tubes of the same size and heat, heat treated in the same furnace at the same temperature, time at heat, and furnace speed.

10.4 *Hydrostatic Test*—Each tube shall be subjected to the hydrostatic pressure test, or instead of this test, a nondestructive test may be used when specified by the purchaser.

## 11. Forming Operations

11.1 Tubes when inserted in the boiler shall stand expanding and beading without showing cracks or flaws. Superheater tubes when properly manipulated shall stand all forging, welding, and bending operations necessary for application without developing defects.

## 12. Product Marking

12.1 In addition to the marking prescribed in Specification A 450/A450M/A 450M/A 450M<sub>2</sub>, the marking shall indicate whether the tube is hot finished or cold finished.

## 13. Keywords

13.1 boiler tubes; seamless steel tube; steel tube-carbon

## EXPLANATORY NOTES

NOTE 1—For purposes of design, the following tensile properties may be assumed: