This document is not an ASTM standard and is intended only to provide the user of an ASTM standard an indication of what changes have been made to the previous version. Because it may not be technically possible to adequately depict all changes accurately, ASTM recommends that users consult prior editions as appropriate. In all cases only the current version of the standard as published by ASTM is to be considered the official document.

# INTERNATIONAL

#### Designation:A413/A413M-01 Designation: A 413/A 413M - 07

## Standard Specification for Carbon Steel Chain<sup>1</sup>

This standard is issued under the fixed designation A 413/A 413M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

#### 1. Scope\*

1.1 This specification covers carbon steel chain for such applications as railroad cars, construction, industrial uses, load binding, and general purposes other than overhead lifting.

Note 1-This specification does not cover carbon steel chain for sprocket applications.

1.2 Three classes of carbon steel chain are covered:

1.2.1 Grade 30—Proof coil chain.

1.2.2 Grade 43—High test chain.

1.2.3 Grade 70—Transport chain.

1.3The values stated in either acceptable metric units or in other units shall be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system must be used independently of the other, without combining values in any way.

1.3 The Grade designation is 1/10 of the minimum breaking strength in newtons divided by two times the nominal cross-sectional area of the chain in square millimetres.

<u>1.4 The values stated in either acceptable metric units or in other units shall be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system must be used independently of the other, without combining values in any way.</u>

#### 2. Referenced Documents

2.1 ASTM Standards: <sup>2</sup>

A 29/A 29M Specification for Steel Bars, Carbon and Alloy, Hot-Wrought and Cold-Finished, General Requirements for Specification for Steel Bars, Carbon and Alloy, Hot-Wrought, General Requirements for

A 751 Test Methods, Practices, and Terminology for Chemical Analysis of Steel Products

E30Test Methods for Chemical Analysis of Steel, Cast Iron, Open-Hearth Iron and Wrought Iron

E44Definitions of Terms Relating to Heat Treatment of Metals E350Test Methods for Chemical Analysis of Carbon Steel, Low-Alloy Steel, Silicon Electrical Steel, Ingot Iron and Wrought Iron

E415Test Method for Optical Emission Vacuum Spectrometric Analysis of Carbon and Low-Alloy Steel A 941 Terminology

Relating to Steel, Stainless Steel, Related Alloys, and Ferroalloys

#### 3. Terminology

#### 3.1 Definitions of Terms Specific to This Standard:

<u>3.1.1.1 Discussion</u>—This test is a manufacturer's attribute acceptance test and shall not be used as criteria for service.

3.1.2 *lot*<u>lot</u>, <u>n</u>—for the purpose of acceptance testing, a lot shall consist of 3000 ft [1000 m], or fraction thereof, of the same

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For Annual Book of ASTM Standards, Vol 01.05. volume information, refer to the standard's Document Summary page on the ASTM website.

#### \*A Summary of Changes section appears at the end of this standard.

Copyright © ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States.

<sup>&</sup>lt;sup>1</sup> This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel, Steel and Related Alloys and is the direct responsibility of Subcommittee A01.27 on Steel Chain.

Current edition approved Sept. 10, 2001. Nov. 1, 2007. Published November 2001. 2007. Originally published as A413-57T. approved in 1957. Last previous edition approved in 2001 as A 413/A 413M - 001.

### **出於 A 413/A 413M – 07**

grade and size chain. If a continuous length of chain exceeds 3000 ft [1000 m], it shall also be considered a lot.

3.1.3 proof test, n—a quality—quality control tensile test applied to chain for the purpose of verifying weld and material quality.

3.1.3.1 Discussion—It is the minimum force in pounds or newtons which the chain has withstood at the time it left the producer, under a test in which a constantly increasing force has been applied in direct tension to a straight length of chain. Proof test loads are a manufacturing integrity test and shall not be used as criteria for service or design purposes.

3.1.4 working load limit (WLL)—the maximum, n—maximum combined static and dynamic load in pounds or kilograms that shall be applied in direct tension to an undamaged straight length of chain.

#### 4. Ordering Information

4.1 It shall be the responsibility of the purchaser to specify all requirements that are necessary for material ordered under this specification. Such requirements may include, but are not limited to, the following:

4.1.1 Product to conform to Specification A 413 or A 413M and date of issue,

4.1.2 Grade of chain,

4.1.3 Nominal size of chain (in. or mm),

4.1.4 Quantity of chain (ft or m),

4.1.5 Length of each piece, if required,

4.1.6 Finish, if required,

4.1.7 Certification of test(s), if required, and

4.1.8 Acceptance of inspection by purchaser, if required.

#### 5. Material Requirements

5.1 *Heat Analysis*—The selection of the steel is left to the judgment of the individual chain manufacturer provided the steel meets the following criteria:

| Carbon, max, %     |  | 0.370 |
|--------------------|--|-------|
| Phosphorus, max, % |  | 0.048 |
| Sulfur, max, %     |  | 0.058 |

5.2 Product Analysis—The steel used may be analyzed by the purchaser and shall conform to the requirements of 5.1 subject to the product analysis tolerances specified in Specification A 29/A 29M<del>/A29M.</del> Test samples may be taken from rods, bars, or finished chain. Samples for analysis shall be so taken as to represent the full cross section of the specimen.

5.3Test Methods E30, E350, or E4155.3 Test Methods, Practices, and Terminology A 751shall be used for referee purposes.

#### 6. Manufacture

6.1 Welding Process—Carbon steel chain may be made by the forge welding, electric welding, or gas welding process.

6.2 Heat Treatment—Grades 30 and 43 do not require heat treatment, but may be heat treated at the manufacturer's discretion. Grade 70, after welding, shall be heat treated. Heat treatment shall include quenching and tempering as described in Definitions E44Terminology A 941.

#### 7. Dimensional Requirements

7.1 The chain shall conform to the dimensional requirements specified in Tables 1-3 for the appropriate grade and size chain. 7.2 Diameter—The diameter of the material from which the chain is manufactured shall not be smaller than the material diameter listed in Tables 1-3 within the following tolerance: -7 %. Oversized material may be used for all applications.

#### 8. Workmanship, Finish, and Appearance

8.1 The chain at the time of shipment shall be free of discontinuities that would prevent the chain from enduring the working load limit forces.

|                       | TABLE 1 Grade 30 From Con Chain |                      |      |                            |      |                                 |       |  |       |                       |      |                      |      |
|-----------------------|---------------------------------|----------------------|------|----------------------------|------|---------------------------------|-------|--|-------|-----------------------|------|----------------------|------|
| Nominal Chain<br>Size |                                 | Material<br>Diameter |      | Working Load<br>Limit, max |      | Proof Test, <sup>A</sup><br>min |       | Minimum Breaking<br>Force <sup>A</sup> |       | Inside Length,<br>max |      | Inside Width,<br>min |      |
| in.                   | mm                              | in.                  | mm   | lb                         | kg   | lb                              | kN    | lb                                     | kN    | in.                   | mm   | in.                  | mm   |
| 1/8                   | 4.0                             | 0.156                | 4.0  | 400                        | 180  | 800                             | 3.6   | 1600                                   | 7.2   | 0.94                  | 23.9 | 0.25                 | 6.4  |
| 3⁄16                  | 5.5                             | 0.217                | 5.5  | 800                        | 365  | 1600                            | 7.2   | 3200                                   | 14.4  | 0.98                  | 24.8 | 0.30                 | 7.7  |
| 1/4                   | 7.0                             | 0.276                | 7.0  | 1300                       | 580  | 2600                            | 11.6  | 5200                                   | 23.2  | 1.24                  | 31.5 | 0.38                 | 9.8  |
| 5⁄16                  | 8.0                             | 0.331                | 8.4  | 1900                       | 860  | 3800                            | 16.9  | 7600                                   | 33.8  | 1.29                  | 32.8 | 0.44                 | 11.2 |
| 3⁄8                   | 10.0                            | 0.394                | 10.0 | 2650                       | 1200 | 5300                            | 23.6  | 10 600                                 | 47.2  | 1.38                  | 35.0 | 0.55                 | 14.0 |
| 7/16                  | 11.9                            | 0.488                | 11.9 | 3700                       | 1680 | 7400                            | 32.9  | 14 800                                 | 65.8  | 1.64                  | 41.6 | 0.65                 | 16.6 |
| 1/2                   | 13.0                            | 0.512                | 13.0 | 4500                       | 2030 | 9000                            | 40.0  | 18 000                                 | 80.0  | 1.79                  | 45.5 | 0.72                 | 18.2 |
| 5/8                   | 16.0                            | 0.630                | 16.0 | 6900                       | 3130 | 13 800                          | 61.3  | 27 600                                 | 122.6 | 2.20                  | 56.0 | 0.79                 | 20.0 |
| 3/4                   | 20.0                            | 0.787                | 20.0 | 10 600                     | 4800 | 21 200                          | 94.3  | 42 400                                 | 188.6 | 2.76                  | 70.0 | 0.98                 | 25.0 |
| 7/8                   | 22.0                            | 0.866                | 22.0 | 12 800                     | 5810 | 25 600                          | 114.1 | 51 200                                 | 228.2 | 3.03                  | 77.0 | 1.08                 | 27.5 |
| 1                     | 26.0                            | 1.02                 | 26.0 | 17 900                     | 8140 | 35 800                          | 159.1 | 71 600                                 | 318.2 | 3.58                  | 90.9 | 1.25                 | 31.7 |

TABLE 1 Grade 30 Proof Coil Chain

<sup>A</sup> The proof test and minimum breaking force loads *shall not* be used as criteria for service or design purposes (see Section 4).