

SLOVENSKI STANDARD
oSIST prEN ISO 11124-3:2017
01-december-2017

**Priprava jeklenih podlag pred nanašanjem barv in sorodnih premazov -
Specifikacije za kovinske granulate za peskanje - 3. del: Kroglice (shot) in sekanci
(grit) iz visokoogljčnega litega jekla (ISO/DIS 11124-3:2017)**

Preparation of steel substrates before application of paints and related products -
Specifications for metallic blast-cleaning abrasives - Part 3: High-carbon cast-steel shot
and grit (ISO/DIS 11124-3:2017)

Vorbereitung von Stahloberflächen vor dem Auftragen von Beschichtungsstoffen -
Anforderungen an metallische Strahlmittel - Teil 3: Stahlguss mit hohem
Kohlenstoffgehalt, kugelig und kantig (Shot und Grit) (ISO/DIS 11124-3:2017)

<https://standards.iteh.ai/catalog/standards/sist/fb5e3bc2-a012-4e4f-bdf2-11fd4bb1892a/sist-en-iso-11124-3-2018>

Préparation des subjectiles d'acier avant application de peintures et de produits
assimilés - Spécifications pour abrasifs métalliques destinés à la préparation par
projection - Partie 3: Grenailles ronde et angulaire en acier coulé à haut carbone
(ISO/DIS 11124-3:2017)

Ta slovenski standard je istoveten z: prEN ISO 11124-3

ICS:

25.220.10	Priprava površine	Surface preparation
87.020	Postopki za nanašanje barvnih premazov	Paint coating processes

oSIST prEN ISO 11124-3:2017

en,fr,de

DRAFT INTERNATIONAL STANDARD

ISO/DIS 11124-3

ISO/TC 35/SC 12

Secretariat: BSI

Voting begins on:
2017-10-04Voting terminates on:
2017-12-27

Preparation of steel substrates before application of paints and related products — Specifications for metallic blast-cleaning abrasives —

Part 3: High-carbon cast-steel shot and grit

Préparation des subjectiles d'acier avant application de peintures et de produits assimilés — Spécifications pour abrasifs métalliques destinés à la préparation par projection —

Partie 3: Grenaille ronde et angulaire en acier coulé à haut carbone

ICS: 25.220.10

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 11124-3:2018](https://standards.iteh.ai/catalog/standards/sist/fb5e3bc2-a012-4e4f-bdf2-11fd4bb1892a/sist-en-iso-11124-3-2018)

<https://standards.iteh.ai/catalog/standards/sist/fb5e3bc2-a012-4e4f-bdf2-11fd4bb1892a/sist-en-iso-11124-3-2018>

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

This document is circulated as received from the committee secretariat.

ISO/CEN PARALLEL PROCESSING



Reference number
ISO/DIS 11124-3:2017(E)

© ISO 2017

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN ISO 11124-3:2018

<https://standards.iteh.ai/catalog/standards/sist/fb5e3bc2-a012-4e4f-bdf2-11fd4bb1892a/sist-en-iso-11124-3-2018>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2017, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

	Page
Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	2
4 Designation of abrasives	3
5 Sampling	3
6 Requirements for high-carbon cast-steel shot and grit abrasives	3
7 Package identification and lot traceability	3
8 Information to be provided by the manufacturer or supplier	4
Annex A (informative) Approximately equivalent codings for shot and grit abrasives	7
Bibliography	9

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN ISO 11124-3:2018

<https://standards.iteh.ai/catalog/standards/sist/fb5e3bc2-a012-4e4f-bdf2-11fd4bb1892a/sist-en-iso-11124-3-2018>

ISO/DIS 11124-3:2017(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

The committee responsible for this document is ISO/35, *Paints and varnishes, subcommittee SC12, Preparation of steel substrates before application of paints and related products*.

This second edition cancels and replaces the first edition (1993), [clause 7](#), [Tables 1, 2, 3](#) and [A.1](#) and [annexe A](#) of which have been technically revised.

ISO 11124 consists of the following parts, under the general title *Preparation of steel substrates before application of paints and related products — Specifications for metallic blast-cleaning abrasives*:

- *Part 1: General introduction and classification*
- *Part 2: Chilled-iron grit*
- *Part 3: High-carbon cast-steel shot and grit*
- *Part 4: Low-carbon cast-steel shot*
- *Part 5: Cut steel wire*

At the time of publication of this part of ISO 11124, ISO 11124-5 was in course of preparation [Annex A](#) of this part of ISO 11124 is for information only.

Preparation of steel substrates before application of paints and related products — Specifications for metallic blast-cleaning abrasives —

Part 3: High-carbon cast-steel shot and grit

WARNING — Equipment, materials and abrasives used for surface preparation can be hazardous. Many national regulations exist for those materials and abrasives that are considered to be hazardous during or after use (waste management), such as free silica or carcinogenic or toxic substances. It is important to ensure that adequate instructions are given and that all required precautions are exercised.

1 Scope

This part of ISO 11124 specifies requirements for 14 grades of high-carbon cast-steel shot and 11 grades of high-carbon cast-steel grit, as supplied for blast-cleaning processes. Values are specified for hardness, density, defect/structural requirements and chemical composition.

The requirements specified in this part of ISO 11124 apply to abrasives supplied in the “new” condition only. They do not apply to abrasives either during or after use.

Test methods for metallic blast-cleaning abrasives are given in the various parts of ISO 11125.

High-carbon cast-steel shot and grit are used in both static and site blasting equipment. They are most often selected where a facility exists for the recovery and re-use of the abrasive.

NOTE 1 Information on commonly referenced national standards for metallic abrasives and their approximate relationship with ISO 11124 is given in [Annex A](#).

NOTE 2 Although this part of ISO 11124 has been developed specifically to meet requirements for preparation of steelwork, the properties specified will generally be appropriate for use when preparing other material surfaces, or components, using blast-cleaning techniques. These techniques are described in ISO 8504-2:1992, *Preparation of steel substrates before application of paints and related products — Surface preparation methods — Part 2: Abrasive blast-cleaning*.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 439, *Steel and iron — Determination of total silicon content — Gravimetric method*

ISO 629, *Steel and cast iron — Determination of manganese content — Spectrophotometric method*

ISO 4935, *Steel and iron — Determination of sulfur content — Infrared absorption method after combustion in an induction furnace*

ISO 9556, *Steel and iron — Determination of total carbon content — Infrared absorption method after combustion in an induction furnace*

ISO 10714, *Steel and iron — Determination of phosphorus content — Phosphovanadomolybdate spectrophotometric method*

ISO/DIS 11124-3:2017(E)

ISO 11125-1, *Preparation of steel substrates before application of paints and related products — Test methods for metallic blast-cleaning abrasives — Part 1: Sampling*

ISO 11125-2, *Preparation of steel substrates before application of paints and related products — Test methods for metallic blast-cleaning abrasives — Part 2: Determination of particle size distribution*

ISO 11125-3, *Preparation of steel substrates before application of paints and related products — Test methods for metallic blast-cleaning abrasives — Part 3: Determination of hardness*

ISO 11125-4, *Preparation of steel substrates before application of paints and related products — Test methods for metallic blast-cleaning abrasives — Part 4: Determination of apparent density*

ISO 11125-5, *Preparation of steel substrates before application of paints and related products — Test methods for metallic blast-cleaning abrasives — Part 5: Determination of percentage defective particles and of microstructure*

ISO 11125-6, *Preparation of steel substrates before application of paints and related products — Test methods for metallic blast-cleaning abrasives — Part 6: Determination of foreign matter*

ISO 11125-7, *Preparation of steel substrates before application of paints and related products — Test methods for metallic blast-cleaning abrasives — Part 7: Determination of moisture*

3 Terms and definitions

For the purposes of this part of ISO 11124, the following terms and definitions apply.

3.1 high-carbon cast-steel shot
metallic blast-cleaning abrasive produced by a casting process in which molten high-carbon steel is formed into shot (3.3) by means of an atomization process

3.2 high-carbon cast-steel grit
metallic blast-cleaning abrasive obtained by crushing various high-carbon cast-steel shot sizes into sharp-edged angular particles

3.3 shot
particles that are predominantly round, that have a length of less than twice the maximum particle width and that do not have edges, broken faces or other sharp surface defects

3.4 grit
particles that are predominantly angular, that have fractured faces and sharp edges and that are less than half round in shape

3.5 defect
fault or weakness in an abrasive which, if present at or above a given level, can be detrimental to the performance characteristics of the abrasive (see Table 3)

3.5.1 void
smooth-surfaced internal cavity considered undesirable when greater than 10 % of the cross-sectional area of a particle

3.5.2 shrinkage defect
internal cavity with a rough dendritic surface or a zone of microporosity, considered undesirable when greater than 40 % of the cross-sectional area of a particle

3.5.3**crack**

linear discontinuity that has a length-to-width ratio of 3:1 or greater, that extends over more than 20 % of the diameter or shortest dimension of a particle and that is radial in direction

3.6**foreign matter**

material or particles mixed with the abrasive which are not attached to the abrasive particles and which are nonmagnetic

4 Designation of abrasives

High-carbon cast-steel shot and grit shall be identified by “Abrasive ISO 11124” and the abbreviation “M/HCS” indicating metallic, high-carbon cast-steel abrasive. The symbol “S” or “G” shall follow to indicate the required particle shape of the shot or grit as purchased. The designation shall be completed by a 3-digit number denoting the grade, or nominal particle size, required. If alternative hardnesses of abrasive are available, the particular Vickers hardness (HV) range required shall be specified (see Example 2).

EXAMPLE 1

— Abrasive ISO 11124 M/HCS/S140

denotes an abrasive of the metallic, high-carbon cast-steel type, conforming to the requirements of this part of ISO 11124, of particle shape shot and grade 140 (i.e. nominal particle size 1,40 mm).

EXAMPLE 2

— Abrasive ISO 11124 M/HCS/G140/570-710HV

denotes an abrasive of the metallic, high-carbon cast-steel type, conforming to the requirements of this part of ISO 11124, of particle shape grit and grade 140 (i.e. nominal particle size 1,40 mm), and with a hardness range of 570 HV to 710 HV.

This full product designation shall be quoted on all orders.

NOTE 1 Grade requirements and codes are specified in [Tables 1](#) and [2](#). The grade code is based on a 3-digit number indicating the nominal size of the particle size range, for each grade, expressed in millimeter × 100.

NOTE 2 [Annex A](#) provides guidance on approximately equivalent grades and codings in other commonly referenced national standards for cast-metal abrasives.

5 Sampling

Sampling procedures shall be as specified in ISO 11125-1.

6 Requirements for high-carbon cast-steel shot and grit abrasives

The requirements for high-carbon cast-steel shot and grit abrasives shall be as specified in [Table 3](#).

7 Package identification and lot traceability

All supplies shall be clearly marked and identified using the designation system specified in [Clause 4](#). The unit of sale, i.e. commercial packaging unit, shall be clearly labelled with the full product coding, including hardness range, if applicable.

Sub-units, i.e. bags, shall be marked with the particle shape and grade codes.

ISO/DIS 11124-3:2017(E)

Inclusion of additional marking to allow product traceability to a particular production period or lot is recommended. Traceability references should be included at least at the pallet, drum or box level of package marking.

8 Information to be provided by the manufacturer or supplier

The manufacturer or supplier shall provide, if requested, a test report detailing results for any relevant property as determined by the appropriate method specified in [Table 3](#).

Cast-steel shot and grit abrasives shall be supplied and used in a dry condition.

Table 1 — Screening specifications by grade - High-carbon cast-steel shot — Cumulative % retained

code	sieve mesh aperture, mm																		
	4,75	4	3,35	2,8	2,36	2	1,7	1,4	1,18	1	0,85	0,71	0,60	0,50	0,425	0,355	0,300	0,180	0,125
S280	0	<30		>90	>97														
S236		0	<30		>90	>97													
S200			0	<30		>90	>97												
S170				0	<30		>90	>97											
S140					0	<30		>90	>97										
S118						0	<30		>90	>97									
S100							0	<30		>90	>97								
S085								0	<30		>90	>97							
S071									0	<30		>90	>97						
S060										0	<30		>90	>97					
S050											0	<30		>90	>97				
S035												0	<30		>90	>97			
S030													0	<30			>90	>97	
S018														0	<30			>90	>97

Table 2 — Screening specifications by grade — High-carbon cast-steel grit — Cumulative % retained

code	sieve mesh aperture, mm																
	2,8	2,36	2	1,7	1,4	1,18	1,00	0,85	0,71	0,60	0,50	0,425	0,355	0,300	0,180	0,125	0,075
G170	0	<30		>85	>95												
G140		0	<30		>85	>95											
G118			0	<30		>85	>95										
G100				0	<30		>85	>95									
G071					0	<30		>85	>95								
G060						0	<30		>85	>95							
G050							0	<30		>85	>95						
G035								0	<30				>85	>95			
G030									0	<30				>85	>95		
G012											0	<30				>85	>95
G007													0	<30			>85