

SLOVENSKI STANDARD
oSIST prEN ISO 11125-3:2017
01-december-2017

Priprava jeklenih podlag pred nanašanjem barv in sorodnih premazov - Preskusne metode za kovinske granulate za peskanje - 3. del: Ugotavljanje trdote (ISO/DIS 11125-3:2017)

Preparation of steel substrates before application of paints and related products - Test methods for metallic blast-cleaning abrasives - Part 3: Determination of hardness (ISO/DIS 11125-3:2017)

Vorbereitung von Stahloberflächen vor dem Auftragen von Beschichtungsstoffen - Prüfverfahren für metallische Strahlmittel - Teil 3: Bestimmung der Härte (ISO/DIS 11125-3:2017)

<https://standards.iteh.ai/catalog/standards/sist/e6415a46-253e-48f5-affd-a7f92383bfe5/sist-en-iso-11125-3-2018>

Préparation des subjectiles d'acier avant application de peintures et de produits assimilés - Méthodes d'essai pour abrasifs métalliques destinés à la préparation par projection - Partie 3: Détermination de la dureté (ISO/DIS 11125-3:2017)

Ta slovenski standard je istoveten z: prEN ISO 11125-3

ICS:

25.220.10	Priprava površine	Surface preparation
87.020	Postopki za nanašanje barvnih premazov	Paint coating processes

oSIST prEN ISO 11125-3:2017

en,fr,de

DRAFT INTERNATIONAL STANDARD

ISO/DIS 11125-3

ISO/TC 35/SC 12

Secretariat: BSI

Voting begins on:
2017-10-04Voting terminates on:
2017-12-27

Preparation of steel substrates before application of paints and related products — Test methods for metallic blast-cleaning abrasives —

Part 3: Determination of hardness

Préparation des subjectiles d'acier avant application de peintures et de produits assimilés — Méthodes d'essai pour abrasifs métalliques destinés à la préparation par projection —

Partie 3: Détermination de la dureté

ICS: 25.220.10

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 11125-3:2018](https://standards.iteh.ai/catalog/standards/sist/e6415a46-253e-48f5-affd-a7f92383bfe5/sist-en-iso-11125-3-2018)

<https://standards.iteh.ai/catalog/standards/sist/e6415a46-253e-48f5-affd-a7f92383bfe5/sist-en-iso-11125-3-2018>

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

This document is circulated as received from the committee secretariat.

ISO/CEN PARALLEL PROCESSING



Reference number
ISO/DIS 11125-3:2017(E)

© ISO 2017

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN ISO 11125-3:2018

<https://standards.iteh.ai/catalog/standards/sist/e6415a46-253e-48f5-affd-a7f92383bfe5/sist-en-iso-11125-3-2018>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2017, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

	Page
Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Apparatus	1
5 Sampling	2
6 Preparation of the sample	2
7 Procedure	2
8 Expression of results	3
9 Alternative hardness scales	3
10 Test report	3
Annex A (informative) International Standards for metallic blast-cleaning abrasives	4

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN ISO 11125-3:2018

<https://standards.iteh.ai/catalog/standards/sist/e6415a46-253e-48f5-affd-a7f92383bfe5/sist-en-iso-11125-3-2018>

ISO/DIS 11125-3:2017(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

The committee responsible for this document is ISO/ TC 35, Paints and varnishes, Subcommittee SC 12, *Preparation of steel substrates before application of paints and related products*.

This second edition cancels and replaces the first edition (1993), [Annex A](#) of which has been technically revised. <https://standards.iteh.ai/catalog/standards/sist/e6415a46-253e-48f5-affd-a7f92383bfe5/sist-en-iso-11125-3-2018>

ISO 11125 consists of the following parts, under the general title *Preparation of steel substrates before application of paints and related products — Test methods for metallic blast-cleaning abrasives*:

- *Part 1: Sampling*
- *Part 2: Determination of particle size distribution*
- *Part 3: Determination of hardness*
- *Part 4: Determination of apparent density*
- *Part 5: Determination of percentage defective particles and of microstructure*
- *Part 6: Determination of foreign matter*
- *Part 7: Determination of moisture*
- *Part 9: Wear testing, efficiency testing*

At the time of publication of this part of ISO 11125, ISO 11125-9 was in course of preparation.

[Annex A](#) of this part of ISO 11125 is for information only.

Preparation of steel substrates before application of paints and related products — Test methods for metallic blast-cleaning abrasives —

Part 3: Determination of hardness

1 Scope

This part of ISO 11125 specifies a test method for the determination of the Vickers hardness of metallic blast-cleaning abrasives.

This method is not recommended for the testing of particle sizes below 0,3 mm.

NOTE Accurate testing of particles below 0,3 mm (grades S040/G050) is extremely difficult.

This is one of a number of parts of ISO 11125 dealing with the sampling and testing of metallic abrasives for blast-cleaning.

The types of metallic abrasive and requirements on each are contained in the various parts of ISO 11124.

The ISO 11124 and ISO 11125 series have been drafted as a coherent set of International Standards on metallic blast-cleaning abrasives. Information on all parts of both series is given in [Annex A](#).

2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this part of ISO 11125. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this part of ISO 11125 are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 6507-2, *Metallic materials — Hardness test — Vickers test — Part 2: HV 0,2 to less than HV 5*

ISO 11125-1, *Preparation of steel substrates before application of paints and related products — Test methods for metallic blast-cleaning abrasives — Part 1: Sampling*

3 Terms and definitions

No terms and definitions are listed in this document.

4 Apparatus

4.1 Hardness tester, for application of a test force up to 10 N, and an **optical device** for magnification of the hardness-test indentations to at least $\times 200$.

4.2 Hardness comparison plates, of hardness range similar to the product under test.

4.3 Metallurgical sample mounting material, which will harden at temperatures below 140 °C.

ISO/DIS 11125-3:2017(E)

NOTE 1 The elongation limit value of the mounting material should preferably be at least twice the value of the compressive stress which is exerted on the test specimen due to the applied test force.

EXAMPLE

A particle of nominal diameter 0,4 mm has an area of about 0,126 mm². At an applied test force of 9,807 N, a compressive stress of about 80 N/mm² results. The elongation limit of the mounting medium should therefore be above 160 N/mm².

NOTE 2 Use of a metallurgical sample mounting material which hardens at temperatures above 140 °C may lead to a tempering action on the material under test and affect the hardness values obtained.

4.4 Metallurgical sample moulds, at least 25 mm in diameter.

5 Sampling

Take a representative sample of the product to be tested, as described in ISO 11125-1.

6 Preparation of the sample

The abrasive particles shall be placed in a single layer in the base of a metallurgical sample mould (4.4) and embedded in the metallurgical sample mounting material (4.3) so that a test sample is obtained which can be abraded and polished. Wet abrading of the sample shall take place until one-half of the nominal particle diameter is exposed. The bearing area and the test surface of the mount shall be parallel.

NOTE 1 Sufficient particles should preferably be taken for each test sample to ensure, as far as possible, that at least half the base area of the test specimen is covered after abrading and polishing.

NOTE 2 This mounted sample prepared for hardness testing may also be used for the determination of defective particles and microstructure as described in ISO 11125-5 (see Annex A).

7 Procedure

Carry out the determination in duplicate.

7.1 Carry out all hardness measurements at ambient temperature in accordance with ISO 6507-2.

7.2 Prior to measuring the hardness of the sample, check the calibration using a hardness comparison plate (4.2) of range similar to the product to be tested.

7.3 Measure the hardness of the samples using a test force of 9,807 N, i.e. HV 1, when testing particles with a diameter greater than 0,5 mm. Measure the hardness of the samples using a test force of 4,904 N, i.e. HV 0,5, when testing particles with a diameter of 0,3 mm to 0,5 mm. Use a test duration of between 10 s and 15 s.

7.4 Do not carry out measurements on particles which are located less than 3 mm from the edge of the test sample. Make the hardness indentations halfway between the edge and the centre of each particle.

Metallic abrasives sometimes contain internal shrinkage defects and voids which remain undetected beneath the surface in a mounted and polished sample. These hidden cavities cause a non-uniform hardness indentation and give an erroneous hardness reading. These indentations shall be ignored.

NOTE Definitions of defects are given in the part of ISO 11124 appropriate to the material under test.

7.5 Make ten acceptable indentations in different particles for each test sample, disregarding any indentations that have a difference between the two diagonals of greater than 5 %. Record the ten hardness values obtained.

8 Expression of results

From the ten hardness values obtained, calculate the percentage conformance with the requirements specified in the appropriate part of ISO 11124 (see [Annex A](#)).

NOTE The arithmetic mean may also be calculated, although this is not necessary when using this method to assess compliance with the appropriate parts of ISO 11124.

9 Alternative hardness scales

There is no general procedure for accurately converting Vickers hardness into other scales of hardness or into tensile strength. Such conversions should therefore be avoided, unless a reliable basis for conversion can be obtained by comparison tests.

A strict comparison of hardness values is only possible at identical test forces.

10 Test report

The test report shall contain at least the following information:

- a) all details necessary to identify the product tested, in accordance with the appropriate part of ISO 11124 (see [Annex A](#)), if applicable;
- b) a reference to this part of ISO 11125 (ISO 11125-3);c) the result of the test;
- d) any deviation from the test method specified;
- e) the date of the test;
- f) the name of the person who carried out the test.

Annex A (informative)

International Standards for metallic blast-cleaning abrasives

Requirements and test methods for metallic blast-cleaning abrasives are contained in ISO 11124 and ISO 11125, respectively.

ISO 11124 will consist of the following parts, under the general title:

Preparation of steel substrates before application of paints and related products — Specification for metallic blast-cleaning abrasives

- *Part 1: General introduction and classification*
- *Part 2: Chilled-iron grit*
- *Part 3: High-carbon cast-steel shot and grit*
- *Part 4: Low-carbon cast-steel shot*
- *Part 5: Cut steel wire*

At the time of publication of this part of ISO 11125, ISO 11124-5 was in course of preparation.

ISO 11125 will consist of the following parts, under the general title:

Preparation of steel substrates before application of paints and related products — Test methods for metallic blast-cleaning abrasives

- *Part 1: Sampling*
- *Part 2: Determination of particle size distribution*
- *Part 3: Determination of hardness*
- *Part 4: Determination of apparent density*
- *Part 5: Determination of percentage defective particles and of microstructure*
- *Part 6: Determination of foreign matter*
- *Part 7: Determination of moisture*
- *Part 9: Wear testing, efficiency testing*

At the time of publication of this part of ISO 11125, ISO 11125-9 was in course of preparation.