

SLOVENSKI STANDARD
oSIST prEN ISO 11125-7:2017
01-december-2017

Priprava jeklenih podlag pred nanašanjem barv in sorodnih premazov - Preskusne metode za kovinske granulate za peskanje - 7. del: Ugotavljanje vlage (ISO/DIS 11125-7:2017)

Preparation of steel substrates before application of paints and related products - Test methods for metallic blast-cleaning abrasives - Part 7: Determination of moisture (ISO/DIS 11125-7:2017)

Vorbereitung von Stahloberflächen vor dem Auftragen von Beschichtungsstoffen - Prüfverfahren für metallische Strahlmittel - Teil 7: Bestimmung der Feuchte (ISO/DIS 11125-7:2017)

Préparation des subjectiles d'acier avant application de peintures et de produits assimilés - Méthodes d'essai pour abrasifs métalliques destinés à la préparation par projection - Partie 7: Détermination de l'humidité (ISO/DIS 11125-7:2017)

Ta slovenski standard je istoveten z: prEN ISO 11125-7

ICS:

25.220.10	Priprava površine	Surface preparation
87.020	Postopki za nanašanje barvnih premazov	Paint coating processes

oSIST prEN ISO 11125-7:2017

en,fr,de

DRAFT INTERNATIONAL STANDARD

ISO/DIS 11125-7

ISO/TC 35/SC 12

Secretariat: BSI

Voting begins on:
2017-10-04Voting terminates on:
2017-12-27

Preparation of steel substrates before application of paints and related products — Test methods for metallic blast-cleaning abrasives —

Part 7: Determination of moisture

Préparation des subjectiles d'acier avant application de peintures et de produits assimilés — Méthodes d'essai pour abrasifs métalliques destinés à la préparation par projection —

Partie 7: Détermination de l'humidité

ICS: 25.220.10

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 11125-7:2018

<https://standards.iteh.ai/catalog/standards/sist/3c233d6b-1d99-4ed1-ae00-405691939146/sist-en-iso-11125-7-2018>

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

This document is circulated as received from the committee secretariat.

ISO/CEN PARALLEL PROCESSING



Reference number
ISO/DIS 11125-7:2017(E)

© ISO 2017

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN ISO 11125-7:2018

<https://standards.iteh.ai/catalog/standards/sist/3c233d6b-1d99-4ed1-ae00-405691939146/sist-en-iso-11125-7-2018>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2017, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

	Page
Foreword.....	iv
1 Scope.....	1
2 Normative references.....	1
3 Terms and definitions.....	1
4 Apparatus.....	1
5 Sampling.....	2
6 Procedure.....	2
7 Expression of results.....	2
8 Test report.....	2
Annex A (informative) International Standards for metallic blast-cleaning abrasives.....	3

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN ISO 11125-7:2018

<https://standards.iteh.ai/catalog/standards/sist/3c233d6b-1d99-4ed1-ae00-405691939146/sist-en-iso-11125-7-2018>

ISO/DIS 11125-7:2017(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

The committee responsible for this document is ISO/TC 35, *Paints and varnishes*, Subcommittee SC 12, *Preparation of steel substrates before application of paints and related products*.

This second edition cancels and replaces the first edition (1993), [annex A](#) of which has been technically revised.

ISO 11125-7 consists of the following parts, under the general title *Preparation of steel substrates before application of paints and related products — Test methods for metallic blast-cleaning abrasives*:

- *Part 1: Sampling*
- *Part 2: Determination of particle size distribution*
- *Part 3: Determination of hardness*
- *Part 4: Determination of apparent density*
- *Part 5: Determination of percentage defective particles and of microstructure*
- *Part 6: Determination of foreign matter*
- *Part 7: Determination of moisture*
- *Part 9: Wear testing, efficiency testing*

At the time of publication of this part of ISO 11125, ISO 11125-9 was in course of preparation.

Annex A of this part of ISO 11125 is for information only.

Preparation of steel substrates before application of paints and related products — Test methods for metallic blast-cleaning abrasives —

Part 7: Determination of moisture

1 Scope

This part of ISO 11125 specifies a test method for the determination of the level of free moisture present in metallic blast-cleaning abrasives. It is determined by measuring the mass lost on heating.

This is one of a number of parts of ISO 11125 dealing with the sampling and testing of metallic abrasives for blast-cleaning.

The types of metallic abrasive and requirements for each are contained in the various parts of ISO 11124.

The ISO 11124 and ISO 11125 series have been drafted as a coherent set of International Standards on metallic blast-cleaning abrasives. Information on all parts of both series is given in [Annex A](#)

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 11125-1, *Preparation of steel substrates before application of paints and related products — Test methods for metallic blast-cleaning abrasives — Part 1: Sampling*

3 Terms and definitions

No terms and definitions are listed in this document.

4 Apparatus

Ordinary laboratory apparatus and glassware, together with the following:

- 4.1 **Balance**, capable of weighing to an accuracy of 0,01 g.
- 4.2 **Oven**, capable of being maintained at a temperature of (110 ± 5) °C.
- 4.3 **Container** or **tray**, capable of withstanding the heat applied and of sufficient volume to allow the test portion to be spread in a thin layer.
- 4.4 **Desiccator**, containing a desiccant such as dried silica gel impregnated with cobalt chloride.