



Designation: E601-07<sup>€1</sup> Designation: E 601 – 07a

## Standard Test Method for Measuring Electromotive Force (emf) Stability of Base-Metal Thermoelement Materials with Time in Air<sup>1</sup>

This standard is issued under the fixed designation E 601; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

<sup>€1</sup>Note—Editorial changes were made throughout in July 2007.

### 1. Scope

1.1 This test method measures emf stability of base-metal thermoelement materials in air referenced to platinum at specified constant elevated temperatures using dual, simultaneous, emf indicators, or using a single emf indicator, with the test and reference emf measured alternately. This test is conducted over a period of weeks.

1.2 A calibrated platinum-rhodium/platinum thermocouple is used as a reference standard to establish the test temperature.

1.3 The useful life of a thermocouple depends on the stability of the emf generated at given temperatures for a required time interval. This method provides a quantitative measure of the stability of individual thermoelements. By combining the results of the positive (P) and negative (N) thermoelements, the stability of a thermocouple comprised of both P and N thermoelements may be obtained. The emf of an individual thermoelement is measured against platinum, which may be the platinum leg of the platinum-rhodium/platinum reference thermocouple, or an additional platinum reference.

NOTE 1—Some thermoelements may show insignificant emf drift while undergoing relatively rapid oxidation. In these cases, failure of the thermoelement may be indicated only by a large rise in the electrical resistance of the thermocouple between joined thermoelements, as measured between the reference junctions.

NOTE 2—See ASTM MNL 12 for recommended upper temperature limits in air.<sup>2</sup>

NOTE 3—This test method is only applicable for initially new thermoelements. Base-metal thermoelements exposed to temperatures above 200 °C become thermoelectrically inhomogeneous, and stability testing of inhomogeneous thermoelements will give ambiguous results.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

### 2. Referenced Documents

#### 2.1 ASTM Standards:<sup>3</sup>

E 220 Practice for Comprehensive Building Asbestos Surveys—Test Method for Calibration of Thermocouples By Comparison Techniques

E 230 Practice for Comprehensive Building Asbestos Surveys—Specification and Temperature-Electromotive Force (EMF) Tables for Standardized Thermocouples

E 344 Practice for Comprehensive Building Asbestos Surveys—Terminology Relating to Thermometry and Hydrometry

E 563 Practice for Comprehensive Building Asbestos Surveys—Practice for Preparation and Use of an Ice-Point Bath as a Reference Temperature

E 1159 Practice for Comprehensive Building Asbestos Surveys—Specification for Thermocouple Materials, Platinum-Rhodium Alloys, and Platinum

### 3. Terminology

3.1 *Definitions*—The definitions given in Terminology E 344 shall apply to this test method.

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee E20 on Temperature Measurement and is the direct responsibility of Subcommittee E20.04 on Thermocouples.

Current edition approved May 1, 2007. Published June 2007. Originally approved in 1977. Last previous edition approved in 1997 as E601-81(1997) which was withdrawn in January 2006 and reinstated in May 2007.

Current edition approved Nov. 1, 2007. Published January 2008. Originally approved in 1977. Last previous edition approved in 2007 as E 601 – 07.

<sup>2</sup> *Manual on the Use of Thermocouples in Temperature Measurement: Fourth Edition*, Available from ASTM Headquarters, 100 Barr Harbor Drive, West Conshohocken, PA 19428, www.astm.org.

<sup>3</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

### 3.2 Definitions of Terms Specific to This Standard:

3.2.1 *emf indicator, n*—an instrument that measures the emf and displays the value, for example, a digital voltmeter (DVM).

3.2.2 *emf stability, n*—change in emf (or in equivalent temperature) with time, with the thermocouple junctions held at fixed temperatures and with the thermal profile along the thermoelements held constant.

3.2.3 *immersion depth*—half-maximum heated length, *n*—the distance between the tip of the temperature sensor and the position along the length of the sensor leads or sheath where the temperature equals the average of the calibration-point and ambient temperatures.

3.2.4 *gradient zone, n*—the section of a thermocouple that is exposed during a measurement to temperatures in the range from  $t_{\text{amb}} + 0.1(t_m - t_{\text{amb}})$  to  $t_{\text{amb}} + 0.9(\text{amb} + 0.9(t_m - t_{\text{amb}}))$ , where  $t_{\text{amb}}$  is ambient temperature and  $t_m$  is the temperature of the measuring junction.

3.2.5 *reference thermocouple, n*—calibrated Type S or Type R thermocouple.

3.2.6 *test thermocouple, n*—thermocouple composed of the thermoelement being tested and the platinum reference thermoelement.

3.2.7 *normalize, v*—to mathematically adjust experimental emf data acquired at a set of temperatures to values corresponding to a common reference temperature.

## 4. Summary of Test Method

4.1 In this test method, the emf of a test thermocouple, comprised of a base-metal thermoelement relative to a platinum reference thermoelement, is determined as a function of time for a specified test temperature and thermal profile. If care is taken to maintain the chemical purity and annealed metallurgical state of the platinum thermoelement, the platinum will be thermoelectrically stable. In that case, variation in this emf value is attributed to instability of the base-metal thermoelement. The emf of the reference thermocouple ( $E_{\text{ref}}$ ) is used to measure the test temperature, and the emf ( $E_{\text{test}}$ ) of the test thermocouple is measured either simultaneously or alternately with  $E_{\text{ref}}$ . The test method consists of the measurement of  $E_{\text{test}}$  at specified time intervals and at a specified constant value of  $E_{\text{ref}}$  which corresponds to a specified, constant temperature, until the required time of the test is exceeded or until an open circuit in the base-metal thermoelement results.

4.2 This test method is based on Method A of Test Method E 220, where the reference thermocouple of Test Method E 220 becomes the reference thermocouple used to measure the test temperature and one specified constant temperature replaces the series of measured temperatures of Test Method E 220.

## 5. Significance and Use

5.1 This test method is important because the accuracy of a temperature measurement by a thermocouple is directly related to the emf stability of the thermoelements.

5.2 This test method is used to verify that the tested thermoelements meet the intended requirements.

5.3 This test method is useful in comparing the emf stability of two base metal thermoelements under the same conditions. The test and reference emf may be measured either simultaneously or alternately.

5.4 The relative stabilities of base metal thermoelements determined by this test method are valid only under the specified test conditions. Results would be affected by changes in the following conditions: (1) temperature profile or gradient along the length of the thermoelements; (2) abundance, velocity and composition of the air surrounding the test pieces; (3) thermoelectric inhomogeneity of the test thermoelements; (4) stability of the platinum thermoelement.

5.5 The test method does not address the determination of base metal thermoelement stabilities over a series of temperature changes.

5.6 The reliability of this test method depends on the emf stability of the reference platinum thermoelement. For testing the relative emf stability of base-metal thermoelements, a reference element of platinum that has sufficient thermoelectric stability to determine any significant change in emf of base-metal thermoelements shall be used. To ascertain that the experimental method protects the platinum sufficiently from degradation, the method shall be validated by performing the procedure described in Appendix X1 prior to the actual test.

5.7 The test result does not apply to applications in which the temperature distribution, for a given measuring junction temperature, changes with time.

## 6. Apparatus

6.1 *Thermocouple Used to Measure the Test Temperature*—A reference Type S or Type R thermocouple with 0.50 mm diameter (24 AWG) thermoelements or larger shall be used to measure the test temperature. The reference thermocouple shall consist of either standard tolerance or special tolerance wire as per Table 1 in Specification E 230. The choice of tolerance will not affect the determination of thermoelement drift. This thermocouple shall be of sufficient length to minimize the effect of heat conduction along the lengths of the wires upon the measuring junction temperature. (Note: platinum is a better heat conductor than most base metal thermocouple wires.) Length shall be sufficient to enable the reference thermocouple's measuring junction to be located within the test furnace's zone of nearly uniform temperature (refer to 6.5.2).

6.2 *Platinum Reference Thermoelement*—The emf of the test thermoelements shall be measured relative to a 0.50 mm diameter (24 AWG) platinum wire. This wire may be the platinum wire of the Type S or R reference thermocouple or a second 0.50 mm

diameter (24 AWG) platinum wire. The length of this wire shall exceed that of the test specimen to minimize the transfer of heat from the measuring junction to the reference junction during testing (see 6.3). For more information concerning a platinum reference thermoelement, Specification E 1159 may be consulted.

6.3 *Test Specimens*— The test specimens shall be lengths of wires, rods, ribbons, or strips of the coils or spools of the base-metal thermoelements to be evaluated. Their lengths shall be adequate to minimize the transfer of heat from the measuring junctions to the reference junctions during the period of test. The lengths shall be at least 0.8 m (30 in.) depending on the length of the testing medium and the transverse sizes of the thermoelements. The specimens shall be free of kinks or other defects due to mechanical deformation, and shall be continuous without splices between the measuring and reference junctions.

6.4 *Reference Junction Temperature* —The reference junction ends of the test specimens, of the platinum reference element, if used, and of the reference thermocouple must be maintained at a known constant temperature during a measurement cycle. The uncertainty attributable to the reference junction temperature shall be less than  $\pm 0.1$  °C. Ice point reference junction baths provide a relatively simple and reliable means for maintaining the reference junction at 0 °C (32 °F) when proper precautions are exercised in their use. Practice E 563 provides an acceptable method for utilizing the ice point as a reference junction bath. Section 7.3 of Test Method E 220 may be consulted for alternative methods of providing a reference junction temperature.

6.5 *Tube Furnace*— The test shall be conducted in an electrically heated tube furnace such as described in Section 7.2.3 of E 220. The furnace employed shall have the following capabilities: The furnace tube shall be long enough to permit a depth of immersion of the thermocouple measuring junctions that is sufficient to assure that the temperature of the measuring junctions is not affected by heat conduction along the thermoelements.

6.5.1 Means shall be provided to control the temperature of the furnace to within  $\pm 10$  °C ( $\pm 18$  °F) of a nominal temperature during the performance of the test.

6.5.2 The test shall be conducted in a uniformly heated furnace providing a nearly isothermal work zone sufficiently large to maintain all junctions at the same temperature.

6.5.3 To determine the uncertainty resulting from temperature non-uniformities in the work zone, measure the temperature profile along the thermocouple axis in the vicinity of the work zone, using a platinum-rhodium alloy thermocouple or a platinum resistance thermometer prior to commencement of the test. If the furnace temperature is not sufficiently stable to obtain a temperature profile with a single thermometer, it may be useful to place one thermometer at a fixed immersion depth, half-maximum heated length, and to move a second thermometer along the furnace-tube axis. Adjust the readings of the moveable thermometer by adding the correction  $-(t_{\text{fixed}}(\text{time}) - t_{\text{fixed}}(\text{initial}))$ , where  $t_{\text{fixed}}$  is the temperature indication of the thermometer at fixed immersion depth.

6.5.3.1 ~~The characteristic length for a wire to achieve thermal equilibrium with its surroundings is given by the approximate correlation:~~ is the temperature indication of the thermometer at fixed half-maximum heated length.

6.5.3.1 A thermoelement extending from ambient temperature into an isothermal zone of a furnace will come to equilibrium with the temperature of the isothermal zone through radiative, convective, and conductive heat transfer between the thermoelement and the surrounding furnace environment. The distance of immersion into the isothermal zone needed to achieve thermal equilibrium depends significantly on both the thermoelement diameter and its thermal conductivity. The characteristic length for a wire to achieve thermal equilibrium with its surroundings is given by the approximate correlation:

$$L_{eq} = (2.5 \text{ cm}) \left( \frac{d}{1 \text{ mm}} \right)^{1/2} \left( \frac{k}{100 \text{ W/(m} \cdot \text{K)}} \right)^{1/2} \quad (1)$$

where  $k$  is the thermal conductivity of the thermoelement, and  $d$  is the diameter of the thermoelement. Calculate the distance  $L_{eq}$  for each tested thermoelement in units of W/(m · K), and  $d$  is the diameter of the thermoelement in millimeters. The equivalent equation in English units, with  $d$  in units of inches and  $k$  in units of BTU/(hr · ft · °F) is:

$$L_{eq} = (1 \text{ in}) \left( \frac{d}{0.04 \text{ in}} \right)^{1/2} \left( \frac{k}{58 \text{ BTU/(hr} \cdot \text{ft} \cdot \text{°F)}} \right)^{1/2} \quad (2)$$

Calculate the distance  $L_{eq}$  for each tested thermoelement and the platinum reference thermoelement. The approximate thermal conductivities listed in Table 1 may be used for this purpose. Measure the diameter  $d_{mj}$  of the measuring junction assembly (see 7.1). Identify the maximum  $L_{max}$  of the set of all calculated  $L_{eq}$  values and  $d_{mj}$  values and  $d_{mj}$ .

NOTE 4—Eq 1 was derived for a temperature of 200 °C, which is near the lower limit of observable thermoelement drift. For higher temperatures, the

**TABLE 1 Approximate Thermal Conductivities of Thermoelement Materials at 200 °C**

Thermoelement Type	$k$ (W/(m · K))
Pt	72
EP, KP	21
EN, JN, TN	31
JP	62
KN	32
NP	19
NN	31
TP	380

value of  $L_{eq}$  from Eq 1 will give an upper limit on the actual equilibration length.

6.5.3.2 The standard uncertainty due to thermal non-uniformity is the maximum temperature variation in the profile from Section 6.5.3 between the measuring junction location and a distance  $L_{max}$  away from the measuring junction.

6.5.3.3 Alternative methods may be used to determine the standard uncertainty due to thermal non-uniformity, such as comparison of results in the test furnace with results obtained either in fixed-point cells or in a stirred liquid bath of high temperature uniformity; or numerical heat-transfer calculations.

6.6 *Electromotive Force Indicator*—The emf measuring instrumentation shall have a measurement uncertainty of not more than 1  $\mu$ V at 1 000  $\mu$ V and 12  $\mu$ V at 50 000  $\mu$ V for this test. The emf indicators may be potentiometers or digital voltmeters. Sections 6.2 and 7.4 of Test Method E 220 may be consulted for further discussions of thermal emf indicators and methods of emf measurement.

6.7 *Connecting Wires*—Connecting wires from the reference junctions to the emf indicator or indicators shall be electrically insulated copper. If the test is sensitive to electrostatic interference, the wires shall be electrically shielded. If electromagnetic interference is present, the conductors shall be twisted to minimize this effect.

6.8 *Selector Switches*—When more than one thermoelement is to be tested, a selector switch is introduced into the copper part of the circuit between the reference junctions and the thermal-emf indicators. These switches shall comply with 7.5.1 of Test Method E 220.

6.9 *Thermocouple Insulation*—For the segment of the thermoelements exposed to temperatures above ambient, ceramic tubing may be used to support and electrically insulate the test thermoelement, the thermocouple used to measure the test temperature, and the platinum reference thermoelement, if used.

6.9.1 For the test thermoelements, the ceramic tubing shall be aluminum oxide ( $Al_2O_3$ ) with total impurities of less than 0.5 % (mass), and the maximum limit for specific impurities shall be: 0.04 % (mass) for  $Fe_2O_3$ .

6.9.2 For the thermocouple used to measure the test temperature and for the platinum reference thermoelement, the ceramic tubing shall be aluminum oxide ( $Al_2O_3$ ) with total impurities of less than 0.5 % (mass), and the maximum limit for specific impurities shall be: 0.04 % (mass) for  $Fe_2O_3$ , and 0.08 % (mass) for Si.

6.9.3 To avoid unnecessary mass and to minimize axial heat conduction in the region of the measuring junction, the ceramic tubing should be relatively thin-walled and should have bore diameters large enough to allow threading of the thermoelements without bending or straining them and to avoid binding. If possible the test thermocouple(s) and the reference thermocouple should be welded individually and then the measuring junctions welded all together to create a loose fitting bundle with a common measuring junction.

6.9.4 To minimize contamination, single lengths of ceramic insulation and not short pieces shall be used. Additionally, if using ceramics that were previously used, insert only thermocouples of the same type as previously used. Insert the positive and negative thermoelement into the bore previously used for that thermoelement to prevent cross contamination from previous testing.

## 7. Procedure

7.1 *Preparation of Thermocouples for Test*—The thermoelement junction shall be prepared by welding, using a procedure proven by experience, or by testing, to produce junctions that are mechanically secure and electrically conductive at the test temperature for the life of the test.<sup>4</sup> The measuring junctions of all of the thermocouples may be welded together into a common bead to provide good thermal contact between the junctions of the different thermocouples. Weld a reference thermocouple to the test specimen to form a mechanically sound junction assembly. If a platinum wire other than the reference thermocouple platinum leg is to be used as the platinum reference then it shall be welded to the junction assembly. If it is not convenient to weld the junctions together, the junction of each thermocouple must be welded separately and the junctions brought into good electrical and thermal contact by wrapping them with a thermally-conductive wire or platinum foil.

7.1.1 Electrically insulate the test specimens from each other, except at the junction, and insulate the reference thermocouple and the additional platinum leg from the test specimens with ceramic insulators (sufficiently loose to thread the thermoelements through the bore without bending or straining them). Slip the insulating tubes down on the thermoelements as close to the measuring junctions as possible without stressing the wires. Thermoelements may be ~~mounted in~~ inserted into the insulating tubes before or after fabrication of the measuring junction. The number of test specimens joined to the platinum reference may be as many as the volume of the testing medium permits, provided that thermal conduction along the thermoelements does not impair isothermal conditions.

7.1.2 To prepare the reference junction, make the electrical connection between the individual legs of the test thermocouple and their respective copper leads using a screw or spring connector, or by soldering, welding, or crimping, or any other suitable means. These connections are then placed into individual clean glass, plastic, or metal tubes. If metal tubes are used, the thermoelements must be electrically insulated from the tubes, and the tubes shall be fabricated from stainless steel or another alloy that will not have excessive thermal conductance with the ambient environment. As stated in Test Method E 220; care must be taken to keep thermal conduction losses within the limits of experimental error typically by immersing the thermocouple into the bath until no further change in indicated emf is noted. Completely clean finished junctions of any harmful contaminants, especially if any soldering or brazing fluxes have been used.

<sup>4</sup> For more information on welding of measuring junctions, see *Manual on the Use of Thermocouples in Temperature Measurement: Fourth Edition*.