

SLOVENSKI STANDARD

kSIST FprEN 754-2:2016

01-junij-2016

**Aluminij in aluminijeve zlitine - Hladno vlečene palice/drogovi in cevi - 2. del:
Mehanske lastnosti**

Aluminium and aluminium alloys - Cold drawn rod/bar and tube - Part 2: Mechanical properties

Aluminium und Aluminiumlegierungen - Gezogene Stangen und Rohre - Teil 2:
Mechanische Eigenschaften

Aluminium et alliages d'aluminium - Barres et tubes étirés - Partie 2: Caractéristiques mécaniques

Ta slovenski standard je istoveten z: FprEN 754-2

ICS:

77.150.10 Alumijski izdelki Aluminium products

kSIST FprEN 754-2:2016 en,fr,de

**EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM**

**FINAL DRAFT
FprEN 754-2**

April 2016

ICS 77.150.10

Will supersede EN 754-2:2013

English Version

**Aluminium and aluminium alloys - Cold drawn rod/bar
and tube - Part 2: Mechanical properties**

Aluminium et alliages d'aluminium - Barres et tubes
étirés - Partie 2: Caractéristiques mécaniques

Aluminium und Aluminiumlegierungen - Gezogene
Stangen und Rohre - Teil 2: Mechanische Eigenschaften

This draft European Standard is submitted to CEN members for unique acceptance procedure. It has been drawn up by the Technical Committee CEN/TC 132.

If this draft becomes a European Standard, CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

This draft European Standard was established by CEN in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

Recipients of this draft are invited to submit, with their comments, notification of any relevant patent rights of which they are aware and to provide supporting documentation.

Warning : This document is not a European Standard. It is distributed for review and comments. It is subject to change without notice and shall not be referred to as a European Standard.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

	Page
European foreword.....	3
1 Scope.....	4
2 Normative references.....	4
3 Mechanical property limits	4
3.1 General.....	4
3.2 Elongation.....	4
3.3 Reference list of the tables of mechanical properties of the relevant aluminium and aluminium alloys.....	5
3.4 Detailed tables of mechanical properties.....	6
Annex A (informative) List of tempers used in Tables 1 to 37	35
Bibliography.....	37

European foreword

This document (FprEN 754-2:2016) has been prepared by Technical Committee CEN/TC 132 "Aluminium and aluminium alloys", the secretariat of which is held by AFNOR.

This document is currently submitted to the Unique Acceptance Procedure.

This document will supersede EN 754-2:2013.

CEN/TC 132 affirms its policy that if a patentee refuses to grant licenses on standardized products under reasonable and not discriminatory conditions, this product will be removed from the corresponding document.

EN 754 comprises the following parts under the general title "*Aluminium and aluminium alloys — Cold drawn rod/bar and tube*":

- *Part 1: Technical conditions for inspection and delivery*
- *Part 2: Mechanical properties*
- *Part 3: Round bars, tolerances on dimensions and form*
- *Part 4: Square bars, tolerances on dimensions and form*
- *Part 5: Rectangular bars, tolerances on dimensions and form*
- *Part 6: Hexagonal bars, tolerances on dimensions and form*
- *Part 7: Seamless tubes, tolerances on dimensions and form*
- *Part 8: Porthole tubes, tolerances on dimensions and form*

1 Scope

This European Standard specifies the mechanical property limits resulting from tensile testing applicable to aluminium and aluminium alloy cold drawn rod/bar and tube.

Technical conditions for inspection and delivery, including product and testing requirements, are specified in EN 754-1. Temper designations are defined in EN 515. The chemical composition limits for these materials are given in EN 573-3.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 754-1:2008, *Aluminium and aluminium alloys — Cold drawn rod/bar and tube — Part 1: Technical conditions for inspection and delivery*

EN ISO 6892-1, *Metallic materials — Tensile testing — Part 1: Method of test at room temperature (ISO 6892-1)*

3 Mechanical property limits

3.1 General

The mechanical properties shall be in conformity with those specified in Table 1 to Table 37 or those agreed upon between supplier and purchaser and stated in the order document.

For all alloys the condition F (as fabricated) can be used, but without guaranteed mechanical properties.

Table 1 to Table 37 contain limits of mechanical property values obtained by tensile testing according to EN ISO 6892-1 after sampling and test piece preparation according to EN 754-1.

NOTE The mechanical properties refer to test pieces taken in the longitudinal direction. Mechanical properties of test pieces taken in other directions can differ from those for the longitudinal direction quoted in this standard.

Brinell hardness values given in Table 1 to Table 37 expressed as HBW values are for information only.

3.2 Elongation

If not otherwise agreed, the A value shall be used.

The A value for elongation is the % elongation measured over a gauge length of $5,65\sqrt{S_0}$ (where S_0 is the initial cross-sectional area of the test-piece), and expressed in percent.

For certain products the supplier may choose (if not otherwise specified in the order documents) to use the elongation based on A_{50mm} . Consequently, values for the A_{50mm} are included in the following tables.

The A_{50mm} value is the elongation measured over a gauge length of 50 mm and expressed in percent.

Test pieces and their location in the specimen are given in EN 754-1.

3.3 Reference list of the tables of mechanical properties of the relevant aluminium and aluminium alloys

	Page	
Table 1 : Aluminium EN AW-1050A	[AI 99,5]	6
Table 2 : Aluminium EN AW-1200	[AI 99,0]	7
Table 3 : Alloy EN AW-2007	[AI Cu4PbMgMn]	8
Table 4 : Alloy EN AW-2011	[AI Cu6BiPb]	9
Table 5 : Alloy EN AW-2011A	[AI Cu6BiPb(A)]	10
Table 6 : Alloy EN AW-2014	[AI Cu4SiMg]	11
Table 7 : Alloy EN AW-2014A	[AI Cu4SiMg(A)]	12
Table 8 : Alloy EN AW-2017A	[AI Cu4MgSi(A)]	13
Table 9 : Alloy EN AW-2024	[AI Cu4Mg1]	14
Table 10 : Alloy EN AW-2030	[AI Cu4PbMg]	15
Table 11 : Alloy EN AW-3003	[AI Mn1Cu]	16
Table 12 : Alloy EN AW-3103	[AI Mn1]	17
Table 13 : Alloy EN AW-5005	[AI Mg1(B)]	18
Table 14 : Alloy EN AW-5005A	[AI Mg1(C)]	19
Table 15 : Alloy EN AW-5019	[AI Mg5]	20
Table 16 : Alloy EN AW-5049	[AI Mg2Mn0,8]	21
Table 17 : Alloy EN AW-5251	[AI Mg2Mn0,3]	22
Table 18 : Alloy EN AW-5052	[AI Mg2,5]	23
Table 19 : Alloy EN AW-5154A	[AI Mg3,5(A)]	24
Table 20 : Alloy EN AW-5754	[AI Mg3]	25
Table 21 : Alloy EN AW-5083	[AI Mg4,5Mn0,7]	26
Table 22 : Alloy EN AW-5086	[AI Mg4]	27
Table 23 : Alloy EN AW-6012	[AI MgSiPb]	28
Table 24 : Alloy EN AW-6026	[AI MgSiBi]	29
Table 25 : Alloy EN AW-6060	[AI MgSi]	30
Table 26 : Alloy EN AW-6061	[AI Mg1SiCu]	31
Table 27 : Alloy EN AW-6262	[AI Mg1SiPb]	32
Table 28 : Alloy EN AW-6262A	[AI Mg1SiSn]	33
Table 29 : Alloy EN AW-6063	[AI Mg0,7Si]	34
Table 30 : Alloy EN AW-6063A	[AI Mg0,7Si(A)]	35
Table 31 : Alloy EN AW-6064A	[AI Mg1SiBi]	36
Table 32 : Alloy EN AW-6065	[AI Mg1Bi1Si]	37
Table 33 : Alloy EN AW-6082	[AI Si1MgMn]	38
Table 34 : Alloy EN AW-7020	[AI Zn4,5Mg1]	39
Table 35 : Alloy EN AW-7022	[AI Zn5Mg3Cu]	40
Table 36 : Alloy EN AW-7049A	[AI Zn8MgCu]	41
Table 37 : Alloy EN AW-7075	[AI Zn5,5MgCu]	42

3.4 Detailed tables of mechanical properties

Table 1 — Aluminium EN AW-1050A [Al 99,5]

Drawn rod/bar									
Temper	Dimensions		R_m		$R_{p0,2}$		A %	$A_{50\text{ mm}}$ % min.	<i>HBW</i> Typical value
	mm	MPa	min.	max.	min.	max.			
O, H111	≤ 80	≤ 60	60	95	-	-	25	22	20
H14	≤ 40	≤ 10	100	135	70	-	6	5	30
H16	≤ 15	≤ 5	120	160	105	-	4	3	35
H18	≤ 10	≤ 3	145	-	125	-	3	3	43
Drawn tube									
Temper	Wall thickness <i>t</i> mm	R_m		$R_{p0,2}$		A %	$A_{50\text{ mm}}$ % min.	<i>HBW</i> Typical value	
		MPa	min.	max.	min.	max.			
O, H111	≤ 20	60	95	-	-	25	22	20	
H14	≤ 10	100	135	70	-	6	5	30	
H16	≤ 5	120	160	105	-	4	3	35	
H18	≤ 3	145	-	125	-	3	3	43	

a D = Diameter for round bar.

b S = Width across flats for square and hexagonal bar, thickness for rectangular bar.