



SLOVENSKI STANDARD
oSIST prEN 13227:2014
01-december-2014

Lesene talne obloge - Masivni tanki parket

Wood flooring - Solid lamparquet products

Holzfußböden - Massivholz-Lamparkettprodukte

Plancher en bois - Produits de lamparquet massif

Ta slovenski standard je istoveten z: prEN 13227

<https://standards.iteh.ai/catalog/standards/sist/983ccb75-dd30-4817-8a0d-71c6642c9307/sist-en-13227-2014>

ICS:

79.080

Polizdelki iz lesa

Semi-manufactures of timber

oSIST prEN 13227:2014

en,fr,de

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

DRAFT
prEN 13227

October 2014

ICS 79.080

Will supersede EN 13227:2002

English Version

Wood flooring - Solid lamparquet products

Plancher en bois - Produits de lamparquet massif

Holzfußböden - Massivholz-Lamparkettprodukte

This draft European Standard is submitted to CEN members for enquiry. It has been drawn up by the Technical Committee CEN/TC 175.

If this draft becomes a European Standard, CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

This draft European Standard was established by CEN in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

Recipients of this draft are invited to submit, with their comments, notification of any relevant patent rights of which they are aware and to provide supporting documentation.

Warning : This document is not a European Standard. It is distributed for review and comments. It is subject to change without notice and shall not be referred to as a European Standard.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

	page
Foreword.....	3
Introduction	4
1 Scope	5
2 Normative references	5
3 Terms and definitions	5
4 Symbols and abbreviations	6
5 Specific product requirements.....	6
5.1 Wood species.....	6
5.2 Finishing.....	6
5.3 Appearance	6
5.3.1 General rules	6
5.3.2 Rules for the most commonly used species	7
5.3.3 Free class	13
5.3.4 Natural colours.....	14
5.4 Moisture content.....	14
5.5 Geometrical characteristics.....	14
5.5.1 General.....	14
5.5.2 Profile.....	14
5.5.3 Nominal dimensions.....	15
5.5.4 Limit deviations.....	16
5.5.5 Machining	17
5.6 Technical specifications and properties	17
5.6.1 Hardness.....	17
5.6.2 Specific site requirements	17
5.6.3 Appearance	17
5.6.4 Renovation and repair.....	17
6 Labelling	18
Annex A (informative) Botanical and trade names of the most commonly used species for wood flooring (hardwood and softwood species)	19
Annex B (normative) Principles for the classification of the free class	25
Annex C (informative) Moisture content	27
Bibliography.....	28

Foreword

This document (prEN 13227:2014) has been prepared by Technical Committee CEN/TC 175 “Round and sawn timber”, the secretariat of which is held by AFNOR.

This document is currently submitted to the CEN Enquiry.

This document will supersede EN 13227:2002.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 13227:2018

<https://standards.iteh.ai/catalog/standards/sist/983ccb75-dd30-4817-8a0d-71c6642c9307/sist-en-13227-2018>

Introduction

This European Standard is one of a series of standards about wood flooring and wood panelling and cladding.

This European Standard specifies the characteristics of solid lamparquet products including solid large lamparquet products. It is based upon current dimensional standards used in the industry and other characteristics together with functions which have been verified by test.

A large amount of knowledge exists about solid parquet elements and values for product characteristics are attested by long use and experience. It is therefore not necessary to have test results. For new products technical data will have to be verified by testing.

The appearance of the parquet is mainly influenced by species, classification and the pattern.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 13227:2018

<https://standards.iteh.ai/catalog/standards/sist/983ccb75-dd30-4817-8a0d-71c6642c9307/sist-en-13227-2018>

1 Scope

This European Standard specifies the characteristics of solid lamparquet products for internal use as flooring. It applies to elements. This European Standard does not apply to panels made from elements, for which the EN 13810-1 applies.

This European Standard covers products without surface treatment.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 844-1:1995, *Round and sawn timber – Terminology – Part 1: General terms common to round timber and sawn timber*

EN 844-3:1995, *Round and sawn timber – Terminology – Part 3: General terms relating to sawn timber*

EN 844-4:1997, *Round and sawn timber – Terminology – Part 4: Terms relating to structure content*

EN 844-6:1997, *Round and sawn timber – Terminology - Part 6: Terms relating to dimensions of sawn timber*

EN 844-7:1997, *Round and sawn timber – Terminology - Part 7: Terms relating to anatomical structure of timber*

EN 844-9:1997, *Round and sawn timber – Terminology - Part 9: Terms relating to features of sawn timber*

EN 844-10:1998, *Round and sawn timber – Terminology - Part 10: Terms relating to stain and fungal attack*

EN 844-11:1998, *Round and sawn timber – Terminology - Part 11: Terms relating to degrade by insects*

EN 844-12:2000, *Round and sawn timber – Terminology - Part 12: Additional terms and general index*

EN 1310:1997, *Round and sawn timber - Method of measurement of features*

EN 1311, *Round and sawn timber - Method of measurement of biological degrade*

EN 1534, *Wood and parquet flooring – Determination of resistance to indentation (Brinell) - Test method*

EN 13183-1, *Moisture content of a piece of sawn timber - Part 1: Determination by oven dry method*

EN 13183-2, *Moisture content of a piece of sawn timber - Part 2: Estimation by electrical resistance method*

EN 13647, *Wood and parquet flooring and wood panelling and cladding – Measurement of geometrical characteristics*

EN 13756:2002, *Wood flooring – Terminology*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in EN 844-1:1995, EN 844-3:1995, EN 844-4:1997, EN 844-6:1997, EN 844-7:1997, EN 844-9:1997, EN 844-10:1998, EN 844-11:1998, EN 844-12:2000 and EN 13756:2002 and the following apply.

prEN 13227:2014 (E)**3.1****lamparquet element**

parquet element of small dimensions having flat edges

[SOURCE: EN 13756:2002]

3.2**large lamparquet element**

element defined by the relevant dimensional limits in Table 7

3.3**parquet tapis**

large lamparquet to be laid by gluing and nailing

3.4**maxi lamparquet element**

element defined by the relevant dimensional limits in Table 7

4 Symbols and abbreviations

L Length of the face of the element

b Width of the face of the element

t Thickness between the face and the back of the element

a Slope of the lip.

5 Specific product requirements

[SIST EN 13227:2018](https://standards.iteh.ai/catalog/standards/sist/983ccb75-dd30-4817-8a0d-71c6642c9307/sist-en-13227-2018)

<https://standards.iteh.ai/catalog/standards/sist/983ccb75-dd30-4817-8a0d-71c6642c9307/sist-en-13227-2018>

5.1 Wood species

A list of the most commonly used species for parquet elements as described in this European Standard is given in Annex A.

5.2 Finishing

The product can be delivered with a factory applied surface coating which allows the product to be taken into use immediately after installation. The surface treatment used and any artificial change of the natural wood colour shall be stated in the product description.

5.3 Appearance**5.3.1 General rules**

Tables 1 to 6 define the classification relating to appearance rules for the face and for the non-visible parts (back and edges) of an element, of the most commonly used species for solid wood flooring as defined in this European Standard.

Features shall be measured according to EN 1310 (knots assessed according to the general method of 4.1 in EN 1310:1997). Biodeterioration is measured according to EN 1311.

A classification with three appearance classes is specified, designated ○, △ and □.

A classification named "Free class" is based on the principles laid out in Annex B.

The face shall include all the visible surface of the element. It shall therefore extend to the chamfering ¹⁾, if any.

The face shall be free from shake and the wood shall be sound.

Any continuous glue joint which allows renovation without significantly changing the appearance or the functional characteristics is acceptable.

5.3.2 Rules for the most commonly used species

5.3.2.1 *Quercus* spp. (oak)

Rules for oak are given in Table 1.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 13227:2018

<https://standards.iteh.ai/catalog/standards/sist/983ccb75-dd30-4817-8a0d-71c6642c9307/sist-en-13227-2018>

1) The chamfering is visible when elements are assembled.

Table 1 — Classification for *Quercus* spp. (oak)

Face of the element			
Features	Class		
	○	△	□
Sound sapwood	Not permitted	Permitted ^a	Slight traces permitted
Knots Sound and intergrown b < 70 mm b ≥ 70 mm Unsound knots	Permitted if: diameter ≤ 2 mm diameter ≤ 3 mm Not permitted	Permitted if: diameter ≤ 5 mm diameter ≤ 10 mm diameter ≤ 3 mm	Permitted if: diameter ≤ 15 mm diameter ≤ 30 mm diameter ≤ 10 mm
Checks	Not permitted	Permitted	All features permitted without limit to size or quantity if these do not impair the strength or the wearing quality of the wood flooring.
Bark pockets	Not permitted	Not permitted	
Lightning shake	Not permitted	Not permitted	
Slope of grain	Permitted, no limit	Permitted, no limit	
Colour variation	Slight variation permitted	Permitted ^b	
Medullary ray	Permitted	Permitted	Not permitted, except blue stain and black holes
Biodeterioration	Not permitted	Not permitted	
Non-visible parts			
All features permitted without limit to size or quantity if these do not impair the strength or the wearing quality of the wood flooring. Sound sapwood is permitted up to 50 % of the thickness.			
^a For large and maxi lamparquet elements, sound sapwood not exceeding 15 % of the face is permitted.			
^b Brown oak.			

5.3.2.2 *Fraxinus excelsior* (European ash) and *Acer* spp. (maple)

Rules for European ash and maple are given in Table 2.

Table 2 — Classification for *Fraxinus excelsior* (European ash) and *Acer* spp. (maple)

Face of the element			
Features	Class		
	○	△	□
Sound sapwood	Not applicable	Not applicable	Not applicable
Knots	Permitted if:	Permitted if:	Permitted if:
Sound and intergrown			
b < 70 mm	diameter ≤ 2 mm	diameter ≤ 5 mm	diameter ≤ 15 mm
b ≥ 70 mm	diameter ≤ 3 mm	diameter ≤ 10 mm	diameter ≤ 30 mm
Unsound knots	Not permitted	diameter ≤ 3 mm	diameter ≤ 10 mm
Checks	Not permitted	Not permitted	Not permitted
Bark pockets	Not permitted	Not permitted	Not permitted
Lightning shake	Not permitted	Not permitted	Not permitted
Slope of grain	Permitted, no limit	Permitted, no limit	Permitted, no limit
Colour variation	Slight variation permitted. Slight traces of natural discoloration (mineral lines) permitted.	Permitted	Permitted
Stick marks	Not permitted	Permitted	Permitted
Biodeterioration	Not permitted	Not permitted	Not permitted, except blue stain and black holes
Non-visible parts			
All features permitted without limit to size or quantity if these do not impair the strength or the wearing quality of the wood flooring.			

prEN 13227:2014 (E)

5.3.2.3 *Fagus sylvatica* (European beech)

Rules for European beech are given in Table 3.

Table 3 — Classification for *Fagus sylvatica* (European beech)

Face of the element			
Features	Class		
	○	Δ	□
Sound sapwood	Not applicable	Not applicable	Not applicable
Knots Sound and intergrown b < 70 mm b ≥ 70 mm Unsound knots	Permitted if: diameter ≤ 2 mm diameter ≤ 3 mm Not permitted	Permitted if: diameter ≤ 5 mm diameter ≤ 10 mm diameter ≤ 3 mm	Permitted if: diameter ≤ 15 mm diameter ≤ 30 mm diameter ≤ 10 mm
Checks	Not permitted	Not permitted	Not permitted
Bark pockets	Not permitted	Not permitted	Not permitted
Lightning shake	Not permitted	Not permitted	Not permitted
Slope of grain	Permitted, no limit	Permitted, no limit	Permitted, no limit
Biodeterioration	Not permitted	Not permitted	Not permitted, except blue stain and black holes
Colour variation	Slight variation permitted ^a . Slight traces of natural discoloration permitted.	Permitted	Permitted
Red heart	Not permitted	Permitted	Permitted
Stick marks	Not permitted	Permitted	Permitted
Medullary ray	Permitted	Permitted	Permitted
Non-visible parts			
All features permitted without limit to size or quantity if these do not impair the strength or the wearing quality of the wood flooring.			
^a Permitted for steamed beech.			