



SLOVENSKI STANDARD

SIST EN 14307:2016

01-februar-2016

Nadomešča:

SIST EN 14307:2010+A1:2013

Toplotnoizolacijski proizvodi za opremo stavb in industrijske inštalacije - Proizvodi iz ekstrudiranega polistirena (XPS) - Specifikacija

Thermal insulation products for building equipment and industrial installations - Factory made extruded polystyrene foam (XPS) products - Specification

Wärmedämmstoffe für die technische Gebäudeausrüstung und für betriebstechnische Anlagen in der Industrie - Werkmäßig hergestellte Produkte aus extrudiertem Polystyrolschaum (XPS) - Spezifikation

Produits isolants thermiques pour l'équipement du bâtiment et les installations industrielles - Produits manufacturés en mousse de polystyrène extrudé (XPS) - Spécification

Ta slovenski standard je istoveten z: EN 14307:2015

ICS:

91.100.60	Materiali za toplotno in zvočno izolacijo	Thermal and sound insulating materials
-----------	---	--

SIST EN 14307:2016

en,fr,de

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 14307:2016

<https://standards.iteh.ai/catalog/standards/sist/219ff163-4729-4d27-b33f-1aab8b581936/sist-en-14307-2016>

EUROPEAN STANDARD

EN 14307

NORME EUROPÉENNE

EUROPÄISCHE NORM

December 2015

ICS 91.100.60

Supersedes EN 14307:2009+A1:2013

English Version

Thermal insulation products for building equipment and industrial installations - Factory made extruded polystyrene foam (XPS) products - Specification

Produits isolants thermiques pour l'équipement du bâtiment et les installations industrielles - Produits manufacturés en mousse de polystyrène extrudé (XPS) - Spécification

Wärmedämmstoffe für die technische Gebäudeausrüstung und für betriebstechnische Anlagen in der Industrie - Werkmäßig hergestellte Produkte aus extrudiertem Polystyrolschaum (XPS) - Spezifikation

This European Standard was approved by CEN on 24 October 2015.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

(standards.iteh.ai)

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

<https://standards.iteh.ai/catalog/standards/sist/219ff163-4729-4d27-b33f>

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents	Page
European foreword.....	4
1 Scope.....	6
2 Normative references.....	6
3 Terms, definitions, symbols, units and abbreviated terms	8
3.1 Terms and definitions	8
3.1.1 Terms and definitions as given in EN ISO 9229:2007	8
3.1.2 Additional terms and definitions	8
3.2 Symbols, units and abbreviated terms.....	9
3.2.1 Symbols and units used in this standard.....	9
3.2.2 Abbreviations used in this standard.....	10
4 Requirements.....	10
4.1 General.....	10
4.2 For all applications.....	11
4.2.1 Thermal conductivity	11
4.2.2 Dimensions and tolerances	11
4.2.3 Dimensional stability.....	12
4.2.4 Reaction to fire of the product as placed on the market.....	13
4.2.5 Durability characteristics.....	13
4.3 For specific applications.....	13
4.3.1 General.....	13
4.3.2 Maximum service temperature.....	13
4.3.3 Minimum service temperature.....	14
4.3.4 Compressive stress or compressive strength.....	14
4.3.5 Water vapour diffusion transmission properties	14
4.3.6 Short-term water absorption by partial immersion	15
4.3.7 Trace quantities of water soluble ions and the pH-value	15
4.3.8 Release of dangerous substances.....	15
4.3.9 Continuous glowing combustion	15
5 Test methods	15
5.1 Sampling.....	15
5.2 Conditioning.....	15
5.3 Testing.....	15
5.3.1 General.....	15
5.3.2 Thermal conductivity	16
5.3.3 Reaction to fire.....	16
6 Designation code.....	18
7 Assessment and Verification of the Constancy of Performance (AVCP).....	18
7.1 General.....	18
7.2 Product Type Determination (PTD).....	18
7.3 Factory Production Control (FPC).....	19
8 Marking and labelling.....	19
Annex A (normative) Factory production control.....	20
Annex B (normative) Determination of the aged values of thermal conductivity.....	22

B.1	Scope	22
B.2	Procedure for XPS foam without diffusion tight laminates.....	22
B.3	Procedure for XPS foam for use with diffusion tight facings on both sides.....	23
B.4	Blowing agent.....	23
Annex C (informative) Additional properties.....		24
C.1	General	24
C.2	Behaviour under cyclic loading.....	24
C.3	Compressive modulus of elasticity.....	24
C.4	Bending strength	24
C.5	Shear strength.....	24
C.6	Deformation under specified compressive load and temperature conditions.....	25
C.7	Compressive creep.....	25
C.8	Tensile strength perpendicular to facings	26
C.9	Long term water absorption by diffusion.....	26
C.10	Long term water absorption by immersion.....	26
C.11	Freeze–thaw resistance.....	27
C.12	Apparent density	27
C.13	Coefficient of thermal expansion.....	27
C.14	Closed cell content.....	27
Annex ZA (informative) Clauses of this European Standard addressing the provisions of the EU Construction Products Regulation.....		29
ZA.1	Scope and relevant characteristics	29
ZA.2	Procedures for AVCP of factory made extruded polystyrene foam products.....	31
ZA.3	CE Marking and labelling	38
Bibliography		40

EN 14307:2015 (E)**European foreword**

This document (EN 14307:2015) has been prepared by Technical Committee CEN/TC 88 “Thermal insulating materials and products”, the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by June 2016, and conflicting national standards shall be withdrawn at the latest by September 2017.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 14307:2009+A1:2013.

This document is identifying those clauses of the standard which are needed for the compliance of the European Standard with the Construction Products Regulation (CPR).

The main technical changes that have been made in this new edition of EN 14307 are the following:

- a) an addition to the foreword;
- b) an addition in 3.2.2;
- c) a new 4.3.8;
- d) modification of 5.3.2;
- e) modification of Clause 7;
- f) modification of Clause 8;
- g) modification of Annex A;
- h) a new Annex ZA.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN 14307:2016](https://standards.iteh.ai/catalog/standards/sist/219ff163-4729-4d27-b33f-1aab8b581936/sist-en-14307-2016)

<https://standards.iteh.ai/catalog/standards/sist/219ff163-4729-4d27-b33f-1aab8b581936/sist-en-14307-2016>

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association, and supports essential requirements of Regulation (EU) No. 305/2011.

For relationship with Regulation (EU) No. 305/2011, see informative Annex ZA, which is an integral part of this document.

Locally responsible authorities and contracting entities, who are bound by EU Directives to specify their requirements using European harmonized product standards, are allowed to demand additional properties outside the provisions of this standard if this is technically necessary because of prevailing operational conditions of the building equipment or the industrial installation projected or because of safety regulations.

This European Standard contains six annexes:

- Annex A (normative), Factory production control;
- Annex B (normative), Determination of the aged values of thermal conductivity;
- Annex C (informative), Additional properties;

- Annex ZA (informative), Clauses of this European Standard addressing the provisions of the EU Construction Products Regulation.

This standard includes a bibliography.

This European Standard is one of a series of standards for insulation products used in building equipment and industrial installations, but this standard may be used in other areas, where appropriate.

In pursuance of Resolution BT 20/1993 revised, CEN/TC 88 have proposed defining the standards listed below as a European package of standards, setting 21 months after availability as the date of withdrawal (dow) of national standards which conflict with the European standards of this package.

The package of standards comprises the following group of interrelated standards for the specifications of factory made thermal insulation products, all of which come within the scope of CEN/TC 88:

EN 14303, *Thermal insulation products for building equipment and industrial installations — Factory made mineral wool (MW) products — Specification*

EN 14304, *Thermal insulation products for building equipment and industrial installations — Factory made flexible elastomeric foam (FEF) products — Specification*

EN 14305, *Thermal insulation products for building equipment and industrial installations — Factory made cellular glass (CG) products — Specification*

EN 14306, *Thermal insulation products for building equipment and industrial installations — Factory made calcium silicate (CS) products — Specification*

EN 14307, *Thermal insulation products for building equipment and industrial installations — Factory made extruded polystyrene foam (XPS) products — Specification*

EN 14308, *Thermal insulation products for building equipment and industrial installations — Factory made rigid polyurethane foam (PUR) and polyisocyanurate foam (PIR) products — Specification*

EN 14309, *Thermal insulation products for building equipment and industrial installations — Factory made expanded polystyrene (EPS) products — Specification*

EN 14313, *Thermal insulation products for building equipment and industrial installations — Factory made polyethylene foam (PEF) products — Specification*

EN 14314, *Thermal insulation products for building equipment and industrial installations — Factory made phenolic foam (PF) products — Specification*

EN 15501, *Thermal insulation products for building equipment and industrial installations — Factory made expanded perlite (EP) and exfoliated vermiculite (EV) products — Specification*

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

EN 14307:2015 (E)

1 Scope

This European Standard specifies the requirements for factory made extruded polystyrene foam products which are used for the thermal insulation of building equipment and industrial installations with an operating temperature in the range of approximately - 180 °C to + 75 °C.

Below an operating temperature of - 50 °C, special tests regarding the suitability of the material in the intended application are advised (e.g. liquefaction of oxygen). Manufacturer's advice should be heeded in all cases.

The products are manufactured in the form of faced or unfaced boards, pipe sections, segments and prefabricated ware.

This European Standard describes product characteristics and includes procedures for testing, evaluation of conformity, marking and labelling.

Products covered by this standard are also used in prefabricated thermal insulating systems and composite panels; the performance of systems incorporating these products is not covered.

This European Standard does not specify the required level of a given property that should be achieved by a product to demonstrate fitness for purpose in a particular application. The levels required for a given application can be found in regulations and invitations to tender.

Products with a declared thermal conductivity greater than 0,060 W/(m·K) at a mean temperature of 10 °C are not covered by this standard.

This European Standard does not cover products intended to be used for the insulation of the building structure nor for acoustical insulation.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 822, *Thermal insulating products for building applications - Determination of length and width*

EN 823, *Thermal insulating products for building applications - Determination of thickness*

EN 824, *Thermal insulating products for building applications - Determination of squareness*

EN 825, *Thermal insulating products for building applications - Determination of flatness*

EN 826, *Thermal insulating products for building applications - Determination of compression behaviour*

EN 1604, *Thermal insulating products for building applications - Determination of dimensional stability under specified temperature and humidity conditions*

EN 1605, *Thermal insulating products for building applications - Determination of deformation under specified compressive load and temperature conditions*

EN 1609, *Thermal insulating products for building applications - Determination of short term water absorption by partial immersion*

EN 12086, *Thermal insulating products for building applications - Determination of water vapour transmission properties*

EN 12667, *Thermal performance of building materials and products - Determination of thermal resistance by means of guarded hot plate and heat flow meter methods - Products of high and medium thermal resistance*

EN 12939, *Thermal performance of building materials and products - Determination of thermal resistance by means of guarded hot plate and heat flow meter methods - Thick products of high and medium thermal resistance*

EN 13164, *Thermal insulation products for buildings - Factory made extruded polystyrene foam (XPS) products - Specification*

EN 13172:2012, *Thermal insulation products - Evaluation of conformity*

EN 13467, *Thermal insulating products for building equipment and industrial installations - Determination of dimensions, squareness and linearity of preformed pipe insulation*

EN 13468, *Thermal insulating products for building equipment and industrial installations - Determination of trace quantities of water soluble chloride, fluoride, silicate, sodium ions and pH*

EN 13501-1:2007+A1:2009, *Fire classification of construction products and building elements - Part 1: Classification using data from reaction to fire tests*

EN 13823, *Reaction to fire tests for building products — Building products excluding flooring exposed to the thermal attack by a single burning item*

EN 14706, *Thermal insulating products for building equipment and industrial installations - Determination of maximum service temperature*

EN 15715:2009, *Thermal insulation products - Instructions for mounting and fixing for reaction to fire testing - Factory made products*

EN ISO 8497, *Thermal insulation - Determination of steady-state thermal transmission properties of thermal insulation for circular pipes (ISO 8497)*

EN ISO 9229:2007, *Thermal insulation - Vocabulary (ISO 9229:2007)*

EN ISO 10456, *Building materials and products - Hygrothermal properties - Tabulated design values and procedures for determining declared and design thermal values (ISO 10456)*

EN ISO 11925-2, *Reaction to fire tests - Ignitability of products subjected to direct impingement of flame - Part 2: Single-flame source test (ISO 11925-2)*

EN ISO 13787:2003, *Thermal insulation products for building equipment and industrial installations - Determination of declared thermal conductivity (ISO 13787:2003)*

3 Terms, definitions, symbols, units and abbreviated terms

3.1 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1.1 Terms and definitions as given in EN ISO 9229:2007

3.1.1.1

extruded polystyrene foam

rigid cellular plastic insulation material expanded and extruded with or without a skin from polystyrene or one of its co-polymers and that has a closed-cell structure

3.1.1.2

block

(insulation) product generally of rectangular cross-section and with a thickness not significantly smaller than the width

3.1.1.3

board

(insulation) rigid or semi-rigid product of rectangular shape and cross-section in which the thickness is uniform and substantially smaller than the other dimensions

Note 1 to entry: Boards may be supplied in tapered form.

3.1.1.4

lag

segment

rigid or semi-rigid insulation product for application to large diameter cylindrical or spherical equipment

3.1.1.5

pipe section

section

(insulation) product in the shape of a cylindrical annulus that may be split to facilitate application

3.1.1.6

production batch

definite quantity of some commodity manufactured or produced under conditions that are presumed uniform

3.1.2 Additional terms and definitions

3.1.2.1

class

combination of two levels of the same property between which the performance shall fall

3.1.2.2

level

given value which is the upper or lower limit of a requirement

Note 1 to entry: The level is given by the declared value of the characteristic concerned.

3.1.2.3**prefabricated ware**

pieces cut, abraded or otherwise formed from a board, a block or a billet of product, e.g. elbows, T-pieces, etc

3.1.2.4**production line**

assemblage of equipment that produces products in a continuous process

3.1.2.5**production unit**

assemblage of equipment that produces products in a discontinuous process

3.2 Symbols, units and abbreviated terms**3.2.1 Symbols and units used in this standard**

b	is the width	mm
D_i	is the inside diameter of pipe shell	mm
d	is the thickness	mm
d_D	is the declared thickness of the product	mm
$\Delta\varepsilon_b$	is the relative change in width	mm
$\Delta\varepsilon_d$	is the relative change in thickness	mm
$\Delta\varepsilon_l$	is the relative change in length	mm
L	is the deviation from linearity for pipe shell	mm/m
l	is the length	mm
λ	is the thermal conductivity	W/(m·K)
λ_D	is the declared thermal conductivity	W/(m·K)
μ	is the water vapour diffusion resistance factor	—
S_b	is the deviation from squareness of the edge (width or length)	mm/m
S_d	is the deviation from squareness of the edge (thickness)	mm/m
S_{max}	is the deviation from flatness	mm
σ_{10}	is the compressive stress at 10 % deformation	kPa
σ_m	is the compressive strength	kPa
v	is the deviation from the squareness for pipe section	mm/m
W_p	is the short-term water absorption by partial immersion	kg/m ²
Z	is the water vapour resistance	m ² · h · Pa/mg
CL	is the symbol of the declared level for soluble chloride ions	
CS(10\Y)	is the symbol of the declared level for compressive stress or strength	
DS(TH)	is the symbol of the declared value for the dimensional stability under specified temperature and humidity conditions	

EN 14307:2015 (E)

F	is the symbol of the declared level of soluble fluoride ions
MU	is the symbol of the declared level for water vapour diffusion resistance factor
NA	is the symbol of the declared level of soluble sodium ions
pH	is the symbol of the declared level of the pH value
SI	is the symbol of the declared level of soluble silicate ions
ST(+)	is the symbol of the declared level for maximum service temperature
ST(-)	is the symbol of the declared level for minimum service temperature
T	is the symbol of the declared class for thickness tolerances
WS	is the symbol of the declared level for short-term water absorption by partial immersion
Z	is the symbol of the declared value for water vapour resistance

3.2.2 Abbreviations used in this standard

AVCP	is A ssessment and V erification of C onstancy of P erformance (previously named attestation of conformity)
DoP	is D eclaration of P erformance
FPC	is F actory P roduction C ontrol
PTD	is P roduct T ype D etermination (previously named ITT for Initial Type Test)
RtF	is R eaction to F ire
SBI	is S ingle B urning I tem
ThIBEII	is T hermal I nsulation for B uilding E quipment and I ndustrial I nstallations
VCP	is V erification of C onstancy of P erformance (previously named evaluation of conformity)
XPS	is e Xtruded P oly S tirene foam

4 Requirements**4.1 General**

Product properties shall be assessed in accordance with Clause 5. To comply with this standard, products shall meet the requirements of 4.2, and the requirements of 4.3 as appropriate.

NOTE Information on additional properties is given in Annex C.

One test result for a product property is the average of the measured values on the number of test specimens given in Table 5.

Apparent density is a useful parameter, among others, for the identification but it should not be used as a basis for the quality assessment of XPS products.

Apparent density of XPS boards and billets, if voluntary declared by the manufacturer will be determined in accordance with EN 1602, *Thermal insulating products for building applications — Determination of the apparent density*.

Apparent density of pipe sections, if voluntary declared by the manufacturer will be determined in accordance with EN 13470, *Thermal insulating products for building equipment and industrial installations — Determination of the apparent density of preformed pipe insulation*.

Products manufactured from XPS can have the same thermal and mechanical properties at different densities. For this reason, product density is not quoted as requirement in this standard.

4.2 For all applications

4.2.1 Thermal conductivity

For flat specimens, the thermal conductivity shall be based upon measurements carried out in accordance with EN 12667 or EN 12939 for thick products. For cylindrical specimens EN ISO 8497 shall be used as specified in 5.3.2.

In both cases, the thermal conductivity values shall be determined by the manufacturer and verified in accordance with EN ISO 13787:2003, 5.3.1, and Annex B of this standard. They shall be declared by the manufacturer at reference mean temperatures covering the product service temperature range. The following conditions apply:

- the measured values shall be expressed with three significant figures;
- the declared conductivity curve shall be given as a limit curve, defined in EN ISO 13787;
- the value of the declared thermal conductivity, λ_D , shall be rounded upwards to the nearest 0,001 W/(m·K);
- the lowest reference mean test temperature required is - 170 °C, where relevant.

The declared equation/limit curve is the “declared reference” with three significant figures, that is to 0,000 1 W/(m·K) for λ values below 0,1 W/(m·K) and in 0,001 W/(m·K) for λ values above 0,1 W/(m·K). This shall be used as a reference for the verification of the declaration.

When thermal conductivity is declared as a table derived from the equation, rounding upwards to the next 0,001 W/(m·K) has to be done for the full range of the thermal conductivity.

NOTE Determinations of the declared thermal conductivity of pipe sections, following EN ISO 8497, having joints in metering area, include the effects of these joints as defined in EN ISO 23993.

4.2.2 Dimensions and tolerances

4.2.2.1 Linear dimensions of boards

The length, l , and width, b , shall be determined in accordance with EN 822, the squareness, S_b , in accordance with EN 824, and flatness, S_{max} , in accordance with EN 825. No test result shall deviate from the declared values by more than the tolerances given in Table 1.

Table 1 — Tolerances of length, width, squareness and flatness of boards

Length or width mm	Tolerances		
	Length or width mm	Squareness on length and width S_b mm/m	Flatness S_{max} mm
Less than 1 000	±8	5	7,0
1 000 to 2 000	±10	5	14,0
> 2 000 to 4 000	±10	5	28,0
> 4 000	±10	5	35,0