



SLOVENSKI STANDARD

SIST EN 14309:2016

01-februar-2016

Nadomešča:

SIST EN 14309:2010+A1:2013

Toplotnoizolacijski proizvodi za opremo stavb in industrijske inštalacije - Proizvodi iz ekspandiranega polistirena (EPS) - Specifikacija

Thermal insulation products for building equipment and industrial installations - Factory made products of expanded polystyrene (EPS) - Specification

Wärmedämmstoffe für die technische Gebäudeausrüstung und für betriebstechnische Anlagen in der Industrie - Werkmäßig hergestellte Produkte aus expandiertem Polystyrol (EPS) - Spezifikation

Produits isolants thermiques pour l'équipement du bâtiment et les installations industrielles - Produits manufacturés en polystyrène expansé (PSE) - Spécification

Ta slovenski standard je istoveten z: EN 14309:2015

ICS:

91.100.60	Materiali za toplotno in zvočno izolacijo	Thermal and sound insulating materials
-----------	---	--

SIST EN 14309:2016

en,fr,de

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 14309:2016

<https://standards.iteh.ai/catalog/standards/sist/301ff52c-ecc1-4829-89a9-6555ffa62337/sist-en-14309-2016>

EUROPEAN STANDARD

EN 14309

NORME EUROPÉENNE

EUROPÄISCHE NORM

December 2015

ICS 91.100.60

Supersedes EN 14309:2009+A1:2013

English Version

Thermal insulation products for building equipment and industrial installations - Factory made products of expanded polystyrene (EPS) - Specification

Produits isolants thermiques pour l'équipement du bâtiment et les installations industrielles - Produits manufacturés en polystyrène expansé (PSE) - Spécification

Wärmedämmstoffe für die technische Gebäudeausrüstung und für betriebstechnische Anlagen in der Industrie - Werkmäßig hergestellte Produkte aus expandiertem Polystyrol (EPS) - Spezifikation

This European Standard was approved by CEN on 24 October 2015.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

(standards.iteh.ai)

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

<https://standards.iteh.ai/catalog/standards/sist/301ff52c-ecc1-4829-89a9-b07e70707070>

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents	Page
European foreword.....	4
1 Scope	6
2 Normative references	6
3 Terms, definitions, symbols, units and abbreviated terms	8
3.1 Terms and definitions	8
3.1.1 Terms and definitions as given in EN ISO 9229:2007	8
3.1.2 Additional terms and definitions	9
3.2 Symbols, units and abbreviated terms	10
3.2.1 Symbols and units used in this standard	10
3.2.2 Abbreviated terms used in this standard	12
4 Requirements	12
4.1 General	12
4.2 For all applications	12
4.2.1 Thermal conductivity	12
4.2.2 Dimensions and tolerances	13
4.2.3 Dimensional stability	13
4.2.4 Reaction to fire of the product as placed on the market	14
4.2.5 Durability characteristics	14
4.3 For specific applications	15
4.3.1 General	15
4.3.2 Maximum service temperature	15
4.3.3 Minimum service temperature	15
4.3.4 Dimensional stability under specified temperature and humidity conditions	15
4.3.5 Compressive stress at 10 % deformation	15
4.3.6 Tensile strength perpendicular to faces	16
4.3.7 Bending strength	16
4.3.8 Compressive creep	17
4.3.9 Water absorption	18
4.3.10 Water vapour transmission	18
4.3.11 Apparent density	19
4.3.12 Dynamic stiffness	19
4.3.13 Compressibility	19
4.3.14 Trace quantities of water soluble ions and pH	20
4.3.15 Release of dangerous substances	20
4.3.16 Continuous glowing combustion	21
5 Test methods	21
5.1 Sampling	21
5.2 Conditioning	21
5.3 Testing	21
5.3.1 General	21
5.3.2 Thermal conductivity	23
5.3.3 Reaction to fire	24
6 Designation code	24
7 Assessment and Verification of the Constancy of Performance (AVCP)	25

7.1	General	25
7.2	Product Type Determination (PTD)	25
7.3	Factory Production Control (FPC)	25
8	Marking and labelling	26
Annex A (normative) Factory production control		27
A.1	Indirect testing	30
Annex B (normative) Product classification		34
Annex C (normative) Determination of minimum service temperature.....		35
C.1	Definitions.....	35
C.2	Principle.....	35
C.3	Apparatus	35
C.4	Test specimens	35
C.5	Procedure.....	36
C.6	Calculation and expression of results	36
C.7	Accuracy of measurements	37
C.8	Test report	37
Annex D (informative) Additional properties		39
D.1	General	39
D.2	Long-term compressive behaviour	39
D.3	Shear behaviour	39
D.4	Water vapour diffusion resistance factor	40
D.5	Coefficient of thermal expansion.....	40
D.6	Behaviour under cyclic loading.....	40
D.7	Test methods.....	41
D.8	Additional information.....	41
Annex ZA (informative) Clauses of this European Standard addressing the provisions of the EU Construction Products Regulation.....		42
ZA.1	Scope and relevant characteristics	42
ZA.2	Procedures for AVCP of factory made products of expanded polystyrene (EPS).....	44
ZA.3	CE Marking and labelling	51
Bibliography		53

EN 14309:2015 (E)**European foreword**

This document (EN 14309:2015) has been prepared by Technical Committee CEN/TC 88 “Thermal insulating materials and products”, the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by June 2016, and conflicting national standards shall be withdrawn at the latest by September 2017.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 14309:2009+A1:2013.

This document is identifying those clauses of the standard which are needed for the compliance of the European Standard with the Construction Products Regulation (CPR).

The main technical changes that have been made in this new edition of EN 14309 are the following:

- a) an addition to the foreword;
- b) an addition in 3.2.2;
- c) a new 4.3.15;
- d) modification of 5.3.2;
- e) modification of Clause 7;
- f) modification of Clause 8;
- g) modification of Annex A;
- h) a new Annex ZA.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN 14309:2016](https://standards.iteh.ai/catalog/standards/sist/301ff52c-ecc1-4829-89a9-6555ffa62337/sist-en-14309-2016)

<https://standards.iteh.ai/catalog/standards/sist/301ff52c-ecc1-4829-89a9-6555ffa62337/sist-en-14309-2016>

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association, and supports essential requirements of Regulation (EU) No. 305/2011.

For relationship with Regulation (EU) No. 305/2011, see informative Annex ZA, which is an integral part of this document.

Locally responsible authorities and contracting entities, who are bound by EU Directives to specify their requirements using European harmonized product standards, are allowed to demand additional properties outside the provisions of this standard if this is technically necessary because of prevailing operational conditions of the building equipment or the industrial installation projected or because of safety regulations.

This European Standard contains five annexes:

- Annex A (normative), Factory production control;
- Annex B (normative), Product classification;
- Annex C (normative), Determination of minimum service temperature;
- Annex D (informative), Additional properties;

- Annex ZA (informative), Clauses of this European Standard addressing the provisions of the EU Construction Products Regulation.

This document includes a bibliography.

This European Standard is one of a series of standards for insulation products used in building equipment and industrial installations, but this standard can be used in other areas, where appropriate.

In pursuance of Resolution BT 20/1993 revised, CEN/TC 88 have proposed defining the standards listed below as a European package of standards, setting 21 months after availability as the date of withdrawal (dow) of national standards which conflict with the European Standards of this package.

The package of standards comprises the following group of interrelated standards for the specifications of factory made thermal insulation products, all of which come within the scope of CEN/TC 88:

EN 14303, *Thermal insulation products for building equipment and industrial installations — Factory made mineral wool (MW) products — Specification*

EN 14304, *Thermal insulation products for building equipment and industrial installations — Factory made flexible elastomeric foam (FEF) products — Specification*

EN 14305, *Thermal insulation products for building equipment and industrial installations — Factory made cellular glass (CG) products — Specification*

EN 14306, *Thermal insulation products for building equipment and industrial installations — Factory made calcium silicate (CS) products — Specification*

EN 14307, *Thermal insulation products for building equipment and industrial installations — Factory made extruded polystyrene foam (XPS) products — Specification*

EN 14308, *Thermal insulation products for building equipment and industrial installations — Factory made rigid polyurethane foam (PUR) and polyisocyanurate foam (PIR) products — Specification*

EN 14309, *Thermal insulation products for building equipment and industrial installations — Factory made products of expanded polystyrene (EPS) — Specification*

EN 14313, *Thermal insulation products for building equipment and industrial installations — Factory made polyethylene foam (PEF) products — Specification*

EN 14314, *Thermal insulation products for building equipment and industrial installations — Factory made phenolic foam (PF) products — Specification*

EN 15501, *Thermal insulation products for building equipment and industrial installations — Factory made expanded perlite (EP) and exfoliated vermiculite (EV) products — Specification*

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

EN 14309:2015 (E)

1 Scope

This European Standard specifies the requirements for factory made products of expanded polystyrene which are used for the thermal insulation of building equipment and industrial installations with an operating temperature range of approximately - 180 °C to + 80 °C. Modified expanded polystyrene polymers with a higher temperature resistance are also covered by this standard.

Below an operating temperature of - 50 °C, special tests regarding the suitability of the product in the intended application are advised (e.g. liquefaction of oxygen). Manufacturers' advice should be heeded in all cases.

The products are manufactured in the form of faced or unfaced boards, rolls, lags, pipe sections or other prefabricated ware.

This standard describes product characteristics and includes procedures for testing, evaluation of conformity, marking and labelling.

Products covered by this standard are also used in prefabricated thermal insulation systems and composite panels; the performance of systems incorporating these products is not covered.

This standard does not specify the required level or class of a given property that should be achieved by a product to demonstrate fitness for purpose in a particular application. The classes and levels required for a given application can be found in regulations and invitations to tender.

Products with a declared thermal conductivity greater than 0,060 W/(m·K) at 10 °C are not covered by this standard.

This standard does not cover products for *in situ* insulation (for loose fill or poured insulation) or products for the insulation of the building structure.

2 Normative references

SIST EN 14309:2016

<https://standards.iteh.ai/catalog/standards/sist/301ff52c-ecc1-4829-89a9-163877777777/EN-14309-2015>

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 822, *Thermal insulating products for building applications - Determination of length and width*

EN 823, *Thermal insulating products for building applications - Determination of thickness*

EN 824, *Thermal insulating products for building applications - Determination of squareness*

EN 825, *Thermal insulating products for building applications - Determination of flatness*

EN 826, *Thermal insulating products for building applications - Determination of compression behaviour*

EN 1602, *Thermal insulating products for building applications - Determination of the apparent density*

EN 1603, *Thermal insulating products for building applications - Determination of dimensional stability under constant normal laboratory conditions (23 °C/ 50 % relative humidity)*

EN 1604, *Thermal insulating products for building applications - Determination of dimensional stability under specified temperature and humidity conditions*

EN 1606, *Thermal insulating products for building applications - Determination of compressive creep*

EN 1607, *Thermal insulating products for building applications - Determination of tensile strength perpendicular to faces*

EN 12085, *Thermal insulating products for building applications - Determination of linear dimensions of test specimens*

EN 12086, *Thermal insulating products for building applications - Determination of water vapour transmission properties*

EN 12087, *Thermal insulating products for building applications - Determination of long term water absorption by immersion*

EN 12088, *Thermal insulating products for building applications - Determination of long term water absorption by diffusion*

EN 12089, *Thermal insulating products for building applications - Determination of bending behaviour*

EN 12091, *Thermal insulating products for building applications - Determination of freeze-thaw resistance*

EN 12431, *Thermal insulating products for building applications - Determination of thickness for floating floor insulating products*

EN 12667, *Thermal performance of building materials and products - Determination of thermal resistance by means of guarded hot plate and heat flow meter methods - Products of high and medium thermal resistance*

EN 12939, *Thermal performance of building materials and products - Determination of thermal resistance by means of guarded hot plate and heat flow meter methods - Thick products of high and medium thermal resistance*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

EN 13163, *Thermal insulation products for buildings - Factory made expanded polystyrene (EPS) products - Specification*

SIST EN 14309:2016

6555fa62337/sist-en-14309-2016

EN 13172:2012, *Thermal insulation products - Evaluation of conformity*

EN 13467, *Thermal insulating products for building equipment and industrial installations - Determination of dimensions, squareness and linearity of preformed pipe insulation*

EN 13468, *Thermal insulating products for building equipment and industrial installations - Determination of trace quantities of water soluble chloride, fluoride, silicate, sodium ions and pH*

EN 13469, *Thermal insulating products for building equipment and industrial installations - Determination of water vapour transmission properties of preformed pipe insulation*

EN 13470, *Thermal insulating products for building equipment and industrial installations - Determination of the apparent density of preformed pipe insulation*

EN 13501-1:2007+A1:2009, *Fire classification of construction products and building elements - Part 1: Classification using data from reaction to fire tests*

EN 13823, *Reaction to fire tests for building products — Building products excluding floorings exposed to the thermal attack by a single burning item*

EN 14706, *Thermal insulating products for building equipment and industrial installations - Determination of maximum service temperature*

EN 14309:2015 (E)

EN 14707, *Thermal insulating products for building equipment and industrial installations - Determination of maximum service temperature for preformed pipe insulation*

EN 14933, *Thermal insulation and light weight fill products for civil engineering applications - Factory made products of expanded polystyrene (EPS) - Specification*

EN 15715:2009, *Thermal insulation products - Instructions for mounting and fixing for reaction to fire testing - Factory made products*

EN 29052-1, *Acoustics - Determination of dynamic stiffness - Part 1: Materials used under floating floors in dwellings*

EN ISO 1182, *Reaction to fire tests for products - Non-combustibility test (ISO 1182:2010)*

EN ISO 1716, *Reaction to fire tests for products - Determination of the gross heat of combustion (calorific value) (ISO 1716:2010)*

EN ISO 8497, *Thermal insulation - Determination of steady-state thermal transmission properties of thermal insulation for circular pipes (ISO 8497:1994)*

EN ISO 9229:2007, *Thermal insulation - Vocabulary (ISO 9229:2007)*

EN ISO 11925-2, *Reaction to fire tests - Ignitability of products subjected to direct impingement of flame - Part 2: Single-flame source test (ISO 11925-2:2010)*

EN ISO 13787, *Thermal insulation products for building equipment and industrial installations - Determination of declared thermal conductivity (ISO 13787:2003)*

3 Terms, definitions, symbols, units and abbreviated terms

3.1 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1.1 Terms and definitions as given in EN ISO 9229:2007

3.1.1.1

pipe section

(insulation) product in the shape of a cylindrical annulus which may be split to facilitate application

3.1.1.2

board

slab

(insulation) rigid or semi-rigid product of rectangular shape and cross-section in which the thickness is uniform and substantially smaller than the other dimensions

Note 1 to entry: Boards are usually thinner than slabs. They may also be delivered in tapered form.

3.1.1.3

roll

(insulation) product supplied in the form of a wound cylinder

3.1.1.4**lag
segment**

rigid or semi-rigid insulation product for application on large diameter cylindrical or spherical equipment

3.1.2 Additional terms and definitions**3.1.2.1****expanded polystyrene (EPS)**

rigid cellular plastics insulation material, manufactured by moulding beads of expandable polystyrene or one of its copolymers and which has a closed cellular structure filled with air

3.1.2.2**expanded polystyrene block**

rigid insulation product or material generally of rectangular cross section and with a thickness not significantly smaller than the width. Blocks are supplied trimmed or untrimmed

3.1.2.3**expanded polystyrene board**

rigid insulation product (cut, moulded or continuously foamed) of rectangular shape and cross section in which the thickness is significantly smaller than the other dimensions

Note 1 to entry: Boards can be of uniform thickness or tapered. The board edges can be of various sorts (e.g. square, half lapped, tongue and groove).

3.1.2.4**level**

given value, which is the upper or lower limit of a requirement

Note 1 to entry: The level is given by the declared value of the characteristic concerned.

3.1.2.5**class**

combination of two levels of the same property between which the performance shall fall

3.1.2.6**production line**

assemblage of equipment that produces products using a continuous process

3.1.2.7**production unit**

assemblage of equipment that produces products using a discontinuous process

Note 1 to entry: For PTD and FPC, units using the same process in one factory are considered together (as one production line).

3.1.2.8**prefabricated ware**

pieces cut, abraded or otherwise formed from a board or block of product e.g. elbows, T-pieces etc

EN 14309:2015 (E)

3.1.2.9

product

material, element or component about which information is required. Refers to a construction product, as defined in the Construction Products Regulation, from an individual producer

3.2 Symbols, units and abbreviated terms

3.2.1 Symbols and units used in this standard

α	is the confidence level	—
b	is the width	mm
d	is the thickness	mm
D_i	is the inside diameter	mm
D	is the water vapour permeability	mg/(m·h·Pa)
d_D	is the declared thickness of a product	mm
$\Delta\varepsilon_b$	is the relative change in width	%
$\Delta\varepsilon_l$	is the relative change in length	%
$\Delta\varepsilon_d$	is the relative change in thickness	%
E_{dyn}	is the dynamic elasticity modulus	MN/m ²
k	is a factor related to the number of test results available	—
l	is the length	mm
L	is the deviation from linearity	mm
$\lambda_{90, 90}$	is the thermal conductivity of 90 % fractile and 90 % confidence level	W/(m·K)
λ_D	is the declared thermal conductivity	W/(m·K)
λ_i	is one test result of thermal conductivity	W/(m·K)
λ_{mean}	is the mean value of the measured thermal conductivity	W/(m·K)
μ	is the water vapour diffusion resistance factor	—
p	is the fractile value (quantile)	—
ρ_a	is the apparent density	kg/m ³
s'	is the dynamic stiffness	MN/m ³
σ_{10}	is the compressive stress at 10 % deformation	kPa
σ_b	is the bending strength	kPa
σ_{mt}	is the tensile strength perpendicular to faces	kPa
S_b	is the deviation from squareness	mm/m
s_λ	is the estimate of the standard deviation of the thermal conductivity	W/(m·K)
S_{max}	is the deviation from flatness	mm
s_R	is the estimate of the standard deviation of the thermal resistance	(m ² ·K)/W
τ	is the shear strength	kPa

v	is the deviation of squareness	mm
W_{dV}	is the water absorption by diffusion	vol.-%
W_{It}	is the long-term water absorption by total immersion	vol.-%
W_{Ip}	is the long-term water absorption by partial immersion	kg/m ²
X_0	is the initial deformation (after 60 s from the beginning of the loading)	mm
X_{ct}	is the absolute compressive creep	mm or %
X_t	is the deformation at time t	mm
Z	is the water vapour resistance	(m ² ·h·Pa)/mg
BS	is the symbol of the declared level for bending strength	
CC($i_1/i_2/y$) σ_c	is the symbol of the declared level for compressive creep	
CL	is the symbol of the declared level for water soluble chloride ions	
CS(10)	is the symbol of the declared level for compressive stress at 10 % deformation	
DS(N)	is the symbol of the declared class for dimensional stability under normal laboratory conditions	
DS(T\L)	is the symbol of the declared level for dimensional stability under load and temperature	
F	is the symbol of the declared level of water soluble fluoride ions	
L	is the symbol of the declared class for length tolerances	
MU	is the symbol for the declared water vapour diffusion factor	
NA	is the symbol of the declared level of water soluble sodium ions	
P	is the symbol of the declared class for flatness tolerance	
pH	is the symbol of the declared level for the pH-value	
S	is the symbol of the declared class for squareness tolerance	
SI	is the symbol of the declared level of water soluble silicate ions	
ST(+)	is the symbol of the declared level of maximum service temperature	
ST(-)	is the symbol of the declared level of minimum service temperature	
T	is the symbol of the declared class for thickness tolerance	
TR	is the symbol of the declared level for tensile strength perpendicular to faces	
W	is the symbol of the declared class for width tolerance	
WD(V)	is the symbol of the declared level for water absorption by diffusion	
WL(T)	is the symbol of the declared level for water absorption by total immersion	
WS	is the symbol of the declared level for short-term water absorption	
Z	is the symbol of the declared water vapour resistance value	

EN 14309:2015 (E)

3.2.2 Abbreviated terms used in this standard

AVCP	is Assessment and Verification of Constancy of Performance (previously named attestation of conformity)
DoP	is Declaration of Performance
EPS	is Expanded PolyStyrene
FPC	is Factory Production Control
PTD	is Product Type Determination (previously named ITT for Initial Type Test)
RtF	is Reaction to Fire
THIBEII	is Thermal Insulation for Building Equipment and Industrial Installations
VCP	is Verification of Constancy of Performance (previously named evaluation of conformity)

4 Requirements

4.1 General

Product properties shall be assessed in accordance with Clause 5. To comply with this standard, products shall meet the requirements of 4.2, and the requirements of 4.3 as appropriate.

NOTE Information on additional properties is given in Annex D.

One test result on a product property is the average of the measured values on the number of test specimens given in Table 12.

4.2 For all applications

4.2.1 Thermal conductivity

SIST EN 14309:2016
<https://standards.iteh.ai/catalog/standards/sist/301ff52c-ecc1-4829-89a9-6555ffa62337/sist-en-14309-2016>

For flat specimens, thermal conductivity shall be based upon measurements carried out in accordance with EN 12667 or EN 12939 for thick products. For cylindrical specimens EN ISO 8497 shall be used as specified in 5.3.2.

In both cases, the thermal conductivity values shall be determined by the manufacturer and verified in accordance with EN ISO 13787. They shall be declared by the manufacturer according to the measuring standards mentioned above covering the product service temperature range. The following conditions apply:

- the measured values shall be expressed to three significant figures;
- the declared thermal conductivity curve shall be given as a limit curve, defined in EN ISO 13787;
- the value of the declared thermal conductivity, λ_D , shall be rounded upwards to the nearest 0,001 W/(m·K).

The declared equation/ limit curve is the “declared reference” with three significant figures, that is to 0,000 1 W/(m·K) for λ values below 0,1 W/(m·K) and in 0,001 W/(m·K) for λ values above 0,1 W/(m·K). This shall be used as a reference for the verification of the declaration.

When thermal conductivity is declared as a table derived from the equation, rounding upwards to the next 0,001 W/(m·K) has to be done for the full range of the thermal conductivity.

NOTE Determinations of the declared thermal conductivity of pipe sections, following EN ISO 8497, having joints in the metering area, include the effects of these joints as defined in EN ISO 23993.

4.2.2 Dimensions and tolerances

4.2.2.1 Linear dimensions

The length, l , width, b , and thickness, d , of flat products shall be determined in accordance with EN 822 and EN 823.

The length, l , thickness, d , and inside diameter, D_i , of pipe sections, segments and prefabricated ware shall be determined in accordance with EN 13467.

No test result shall deviate from the declared values by more than the tolerances given in Table 1 for the labelled class.

Table 1 — Dimensional tolerances

Form of delivery	Length	Width	Thickness	Inside diameter	Squareness
Board	$\pm 0,6\%$ or $\pm 3\text{ mm}^a$	$\pm 0,6\%$ or $\pm 3\text{ mm}^a$	$\pm 2\text{ mm}$		$\pm 5\text{ mm/m}$
Pipe section or segment, prefabricated ware	$\pm 0,6\%$ or $\pm 3\text{ mm}^a$		$\pm 2\text{ mm}$	$+ 2\%$ or $+3\text{ mm}$	$\pm 3\text{ mm/m}$

^a Whichever gives the greatest numerical tolerance.

4.2.2.2 Squareness

Deviation of squareness, S_p , of boards shall be determined in accordance with EN 824. Deviation of squareness of pipe sections shall be determined in accordance with EN 13467. No test result shall exceed the corresponding tolerance given in Table 1.

4.2.2.3 Flatness

Flatness shall be determined in accordance with EN 825 for boards. The deviation from flatness, S_{\max} , shall not exceed 3 mm.

4.2.2.4 Pipe section linearity

Linearity shall be determined in accordance with EN 13467 for pipe sections and segments. The deviation from linearity, L , shall not exceed 3 mm.

4.2.3 Dimensional stability

4.2.3.1 Dimensional stability under normal laboratory conditions

Dimensional stability under normal laboratory conditions (23 °C, 50 % relative humidity) shall be determined in accordance with EN 1603. The relative changes in length, $\Delta\epsilon_l$, and width, $\Delta\epsilon_b$, shall not exceed the values given in Table 2 for the declared class.

Table 2 — Classes of dimensional stability under normal laboratory conditions

Classes	Requirement %
DS(N) 5	$\pm 0,5$
DS(N) 2	$\pm 0,2$