



SLOVENSKI STANDARD

SIST EN 14314:2016

01-februar-2016

Nadomešča:

SIST EN 14314:2010+A1:2013

Toplotnoizolacijski proizvodi za opremo stavb in industrijske inštalacije - Proizvodi iz fenolne pene (PF) - Specifikacija

Thermal insulation products for building equipment and industrial installations - Factory made phenolic foam (PF) products - Specification

Wärmedämmstoffe für die technische Gebäudeausrüstung und für betriebstechnische Anlagen in der Industrie - Werkmäßig hergestellte Produkte aus Phenolharzschaum (PF) - Spezifikation

Produits isolants thermiques pour l'équipement du bâtiment et les installations industrielles - Produits manufacturés en mousse phénolique (PF) - Spécification

Ta slovenski standard je istoveten z: EN 14314:2015

ICS:

91.100.60	Materiali za toplotno in zvočno izolacijo	Thermal and sound insulating materials
-----------	---	--

SIST EN 14314:2016

en,fr,de

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN 14314:2016](#)

<https://standards.iteh.ai/catalog/standards/sist/3d81586d-b3c4-44ad-8ef0-fc0cab089e7d/sist-en-14314-2016>

EUROPEAN STANDARD

EN 14314

NORME EUROPÉENNE

EUROPÄISCHE NORM

December 2015

ICS 91.100.60

Supersedes EN 14314:2009+A1:2013

English Version

Thermal insulation products for building equipment and industrial installations - Factory made phenolic foam (PF) products - Specification

Produits isolants thermiques pour l'équipement du bâtiment et les installations industrielles - Produits manufacturés en mousse phénolique (PF) - Spécification

Wärmedämmstoffe für die technische Gebäudeausrüstung und für betriebstechnische Anlagen in der Industrie - Werkmäßig hergestellte Produkte aus Phenolharzschaum (PF) - Spezifikation

This European Standard was approved by CEN on 24 October 2015.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents	Page
European foreword.....	4
1 Scope	6
2 Normative references	6
3 Terms, definitions, symbols, units and abbreviated terms	8
3.1 Terms and definitions	8
3.1.1 Terms and definitions as given in EN ISO 9229	8
3.1.2 Additional terms and definitions	8
3.2 Symbols, units and abbreviated terms	9
3.2.1 Symbols and units used in this standard	9
3.2.2 Abbreviated terms used in this standard	10
4 Requirements	11
4.1 General	11
4.2 For all applications	11
4.2.1 Thermal conductivity	11
4.2.2 Dimensions and tolerances	11
4.2.3 Dimensional stability	13
4.2.4 Reaction to fire of the product as placed on the market	13
4.2.5 Durability characteristics	13
4.3 For specific applications	14
4.3.1 General	14
4.3.2 Maximum service temperature	14
4.3.3 Minimum service temperature	14
4.3.4 Dimensional stability under specified conditions	14
4.3.5 Compression resistance properties	15
4.3.6 Water vapour diffusion resistance	16
4.3.7 Water absorption	16
4.3.8 Closed cell content	17
4.3.9 Trace quantities of water soluble chloride and the pH-value	17
4.3.10 Release of dangerous substances	17
4.3.11 Continuous glowing combustion	17
5 Test methods	18
5.1 Sampling	18
5.2 Conditioning	18
5.3 Testing	18
5.3.1 General	18
5.3.2 Thermal conductivity	20
5.3.3 Reaction to Fire	21
6 Designation code	21
7 Assessment and Verification of the Constancy of Performance (AVCP)	21
7.1 General	21
7.2 Product Type Determination (PTD)	22
7.3 Factory Production Control (FPC)	22
8 Marking and labelling	22

Annex A (normative) Factory production control	23
Annex B (normative) Determination of the aged value of thermal conductivity	25
B.1 General	25
B.2 Preparation of test sample	25
B.3 Determination of the initial value of thermal conductivity	26
B.4 Determination of the aged value of thermal conductivity	26
B.5 Blowing agent	27
B.6 Declaration of thermal resistance and thermal conductivity	27
Annex C (normative) Determination of minimum service temperature	28
C.1 Definitions	28
C.2 Principle	28
C.3 Apparatus	28
C.4 Test specimens	29
C.5 Procedure	29
C.6 Calculation and expression of results	30
C.7 Accuracy of measurements	30
C.8 Test report	30
C.9 Modifications of and additions to the general test method for phenolic foams	31
Annex D (informative) Additional properties	34
D.1 General	34
D.2 Apparent density	34
D.3 Coefficient of thermal expansion	34
D.4 Water vapour transmission of preformed pipe insulation	34
D.5 Tensile strength perpendicular to faces	34
D.6 Shear strength	34
D.7 Bending strength	35
D.8 Cell gas composition	35
D.9 Cryogenic application	35
Annex ZA (informative) Clauses of this European Standard addressing the provisions of the EU Construction Products Regulation	36
ZA.1 Scope and relevant characteristics	36
ZA.2 Procedures for AVCP of factory made phenolic foam	38
ZA.3 CE Marking and labelling	45
Bibliography	47

EN 14314:2015 (E)**European foreword**

This document (EN 14314:2015) has been prepared by Technical Committee CEN/TC 88 “Thermal insulating materials and products”, the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by June 2016, and conflicting national standards shall be withdrawn at the latest by September 2017.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 14314:2009+A1:2013.

This document is identifying those clauses of the standard which are needed for the compliance of the European Standard with the Construction Products Regulation (CPR).

The main technical changes that have been made in this new edition of EN 14314 are the following:

- a) an addition to the foreword;
- b) modifications in 3.2.2;
- c) a new 4.3.10;
- d) modification of 5.3.2;
- e) replacement of Clause 7;
- f) modification of Clause 8;
- g) modification of Annex A;
- h) a new Annex ZA.

iTeh STANDARD PREVIEW
(standards.iteh.ai)
<https://standards.iteh.ai/catalog/standards/sist/3d81586d-b3c4-44ad-8ef0-fc0cab089e7d/sist-en-14314-2016>

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association, and supports essential requirements of Regulation (EU) No. 305/2011.

For relationship with Regulation (EU) No. 305/2011, see informative Annex ZA, which is an integral part of this document.

Locally responsible authorities and contracting entities, who are bound by EU Directives to specify their requirements using European harmonized product standards, are allowed to demand additional properties outside the provisions of this standard if this is technically necessary because of prevailing operational conditions of the building equipment or the industrial installation projected or because of safety regulations.

This European Standard contains five annexes:

- Annex A (normative), Factory production control;
- Annex B (normative), Determination of the aged value of thermal conductivity;
- Annex C (normative), Determination of minimum service temperature;
- Annex D (informative), Additional properties;

- Annex ZA (informative), Clauses of this European Standard addressing the provisions of the EU Construction Products Regulation.

This document includes a bibliography.

This European Standard is one of a series of standards for insulation products used in building equipment and industrial installations but this standard can be used in other areas, where appropriate.

In pursuance of Resolution BT 20/1993 revised, CEN/TC 88 have proposed defining the standards listed below as a European package of standards, setting 21 months after availability as the date of withdrawal (dow) of national standards which conflict with the European Standards of this package.

The package of standards comprises the following group of interrelated standards for the specifications of factory made thermal insulation products, all of which come within the scope of CEN/TC 88:

EN 14303, *Thermal insulation products for building equipment and industrial installations — Factory made mineral wool (MW) products — Specification*

EN 14304, *Thermal insulation products for building equipment and industrial installations — Factory made flexible elastomeric foam (FEF) products — Specification*

EN 14305, *Thermal insulation products for building equipment and industrial installations — Factory made cellular glass (CG) products — Specification*

EN 14306, *Thermal insulation products for building equipment and industrial installations — Factory made calcium silicate (CS) products — Specification*

EN 14307, *Thermal insulation products for building equipment and industrial installations — Factory made extruded polystyrene foam (XPS) products — Specification*

EN 14308, *Thermal insulation products for building equipment and industrial installations — Factory made rigid polyurethane foam (PUR) and polyisocyanurate foam (PIR) products — Specification*

EN 14309, *Thermal insulation products for building equipment and industrial installations — Factory made products of expanded polystyrene (EPS) — Specification*

EN 14313, *Thermal insulation products for building equipment and industrial installations — Factory made polyethylene foam (PEF) products — Specification*

EN 14314, *Thermal insulation products for building equipment and industrial installations — Factory made phenolic foam (PF) products — Specification*

EN 15501, *Thermal insulation products for building equipment and industrial installations — Factory made expanded perlite (EP) and exfoliated vermiculite (EV) products — Specification*

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

EN 14314:2015 (E)

1 Scope

This European Standard specifies the requirements for factory made phenolic foam products which are used for the thermal insulation of building equipment and industrial installations with an operating temperature in the range of approximately - 200 °C to + 120 °C.

Below an operating temperature of - 50 °C, special tests regarding the suitability of the products in the intended application are advised (e.g. liquefaction of oxygen). Manufacturer's advice should be heeded in all cases.

The products are manufactured in the form of blocks, faced or unfaced, boards, pipe sections, segments and prefabricated ware.

This European Standard describes product characteristics and includes procedures for testing, evaluation of conformity, marking and labelling.

Products covered by this standard are also used in prefabricated thermal insulating systems and composite panels; the performance of systems incorporating these products is not covered.

This European Standard does not specify the required level of a given property that should be achieved by a product to demonstrate fitness for purpose in a particular application. The levels required for a given application can be found in regulations and invitations to tender.

Products with a declared thermal conductivity greater than 0,050 W/(m·K) at 10 °C are not covered by this standard.

This European Standard does not cover products for *in situ*-insulation (blowing or pouring) or products for the insulation of the building structure.

This European Standard does not cover the following acoustical aspects: direct airborne sound insulation and impact noise transmission index.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 822, *Thermal insulating products for building applications - Determination of length and width*

EN 823, *Thermal insulating products for building applications - Determination of thickness*

EN 824, *Thermal insulating products for building applications - Determination of squareness*

EN 825, *Thermal insulating products for building applications - Determination of flatness*

EN 826, *Thermal insulating products for building applications - Determination of compression behaviour*

EN 1604, *Thermal insulating products for building applications - Determination of dimensional stability under specified temperature and humidity conditions*

EN 1606, *Thermal insulating products for building applications - Determination of compressive creep*

EN 1608, *Thermal insulating products for building applications - Determination of tensile strength parallel to faces*

EN 1609, *Thermal insulating products for building applications - Determination of short term water absorption by partial immersion*

EN 12085, *Thermal insulating products for building applications - Determination of linear dimensions of test specimens*

EN 12086, *Thermal insulating products for building applications - Determination of water vapour transmission properties*

EN 12429, *Thermal insulating products for building applications - Conditioning to moisture equilibrium under specified temperature and humidity conditions*

EN 12667:2001, *Thermal performance of building materials and products - Determination of thermal resistance by means of guarded hot plate and heat flow meter methods - Products of high and medium thermal resistance*

EN 12939, *Thermal performance of building materials and products - Determination of thermal resistance by means of guarded hot plate and heat flow meter methods - Thick products of high and medium thermal resistance*

EN 13166, *Thermal insulation products for buildings - Factory made phenolic foam (PF) products - Specification*

EN 13172:2012, *Thermal insulation products - Evaluation of conformity*

EN 13467, *Thermal insulating products for building equipment and industrial installations - Determination of dimensions, squareness and linearity of preformed pipe insulation*

EN 13468, *Thermal insulating products for building equipment and industrial installations - Determination of trace quantities of water soluble chloride, fluoride, silicate, sodium ions and pH*

EN 13501-1:2007+A1:2009, *Fire classification of construction products and building elements - Part 1: Classification using data from reaction to fire tests*

EN 13823, *Reaction to fire tests for building products — Building products excluding flooring exposed to the thermal attack by a single burning item*

EN 14706, *Thermal insulating products for building equipment and industrial installations - Determination of maximum service temperature*

EN 14707, *Thermal insulating products for building equipment and industrial installations - Determination of maximum service temperature for preformed pipe insulation*

EN 15715:2009, *Thermal insulation products - Instructions for mounting and fixing for reaction to fire testing - Factory made products*

EN ISO 4590, *Rigid cellular plastics - Determination of the volume percentage of open cells and of closed cells (ISO 4590)*

EN ISO 8497, *Thermal insulation - Determination of steady-state thermal transmission properties of thermal insulation for circular pipes (ISO 8497)*

EN ISO 9229, *Thermal insulation - Vocabulary (ISO 9229)*

EN ISO 10456, *Building materials and products - Hygrothermal properties - Tabulated design values and procedures for determining declared and design thermal values (ISO 10456)*

EN 14314:2015 (E)

EN ISO 11925-2, *Reaction to fire tests - Ignitability of products subjected to direct impingement of flame - Part 2: Single-flame source test (ISO 11925-2)*

EN ISO 13787, *Thermal insulation products for building equipment and industrial installations - Determination of declared thermal conductivity (ISO 13787)*

3 Terms, definitions, symbols, units and abbreviated terms**3.1 Terms and definitions**

For the purposes of this document, the following terms and definitions.

3.1.1 Terms and definitions as given in EN ISO 9229**3.1.1.1****phenolic foam**

rigid cellular insulation foam, the polymer structure of which is made primarily from the polycondensation of phenol, its homologues and/or derivatives, with aldehydes or ketones

3.1.1.2**block****billet**

(insulation) product generally of rectangular cross-section and with a thickness not significantly smaller than the width

iTeh STANDARD PREVIEW
(standards.iteh.ai)

Note 1 to entry: In English, some industries define a large block as a billet.

3.1.1.3**board****slab**

(insulation) rigid or semi-rigid product of rectangular shape and cross section in which the thickness is uniform and substantially smaller than the other dimensions

SIST EN 14314:2016
<https://standards.iteh.ai/catalog/standards/sist/3d81586d-b3c4-44ad-8ef0-f60cab089e7d/sist-en-14314-2016>

Note 1 to entry: Boards are usually thinner than slabs. They can also be supplied in tapered form.

3.1.1.4**pipe section****section**

(insulation) product in the shape of a cylindrical annulus which may be split to facilitate application

3.1.1.5**lag****segment**

rigid or semi-rigid insulation product for application to large diameter cylindrical or spherical equipment

3.1.2 Additional terms and definitions**3.1.2.1****level**

given value which is the upper or lower limit of a requirement

Note 1 to entry: The level is given by the declared value of the characteristic concerned.

3.1.2.2**class**

combination of two levels of the same property between which the performance shall fall

3.1.2.3**prefabricated ware**

pieces cut, abraded or otherwise formed from a board or block of product, e.g. elbows, T-pieces, etc

3.1.2.4**production line**

assemblage of equipment that produces products using a continuous process

3.1.2.5**production unit**

assemblage of equipment that produces products using a discontinuous process

3.1.2.6**end-use application**

real application of a product in relation to all aspects that influence the behaviour of that product under different fire situations

Note 1 to entry: The term covers aspects of the product such as its quantity, its orientation, its position in relation to other adjacent products and its method of fixing.

3.1.2.7**end-use application parameter** (standards.iteh.ai)

aspect of the mounting and fixing arrangement of a product reflecting/simulating its end use application (for example: type of substrate, lining, fixing method, position and type of joints) which may or may not affect the fire performance

3.2 Symbols, units and abbreviated terms**3.2.1 Symbols and units used in this standard**

b	is the width	mm
D_i	is the inside diameter of pipe sections	mm
d	is the thickness	mm
d_D	is the declared thickness of the product	mm
$\Delta\varepsilon_b$	is the relative change in width	%
$\Delta\varepsilon_d$	is the relative change in thickness	%
$\Delta\varepsilon_l$	is the relative change in length	%
X_{ct}	is the compressive creep	%
ε_t	is the total thickness reduction	%
L	is the deviation from linearity	mm
l	is the length	mm
λ	is the thermal conductivity	W/(m·K)
λ_D	is the declared thermal conductivity	W/(m·K)

EN 14314:2015 (E)

μ	is the water vapour diffusion resistance factor	—
S_b	is the deviation from squareness for boards on length and width	mm/m
S_d	is the deviation from squareness for boards on thickness	mm
S_{max}	is the deviation from flatness	mm
σ_{10}	is the compressive stress at 10 % deformation	kPa
σ_c	is the compressive stress	kPa
σ_m	is the compressive strength	kPa
v	is the deviation from squareness for pipe sections	mm
ψ_0	is the closed cell content (corrected)	%
Z	is the water vapour resistance	$m^2 \cdot h \text{ Pa/mg}$
$CC(i_1/i_2/y) \sigma_c$	is the symbol of the declared level of compressive creep	
CL	is the symbol of the declared level for soluble chloride ions	
CS(10\Y)	is the symbol of the declared level for compressive stress or compressive strength	
CV	is the symbol of the declared value for closed cell content	
DS(T+)	is the symbol of the declared value for dimensional stability at specified temperature	
DS(T-)	is the symbol of the declared value for dimensional stability at - 20 °C	
MU	is the symbol of the declared value for water vapour diffusion resistance factor	
ST(+)	is the symbol of the declared level for maximum service temperature	
ST(-)	is the symbol of the declared level for minimum service temperature	
WVT	is the symbol for the declared level for water vapour transmission rate	
WVP	is the symbol for the declared value of water vapour permanence	
WVPE	is the symbol for the declared value of water vapour permeability	
Z	is the symbol of the declared value for water vapour resistance	

3.2.2 Abbreviated terms used in this standard

AVCP	is A ssessment and V erification of C onstancy of P erformance (previously named attestation of conformity)
DoP	is D eclaration of P erformance
FPC	is F actory P roduction C ontrol
PF	is P henolic F oam
PTD	is P roduct T ype D etermination (previously named ITT for Initial Type Test)”
RtF	is R eaction to F ire
ThIBEII	is T hermal I nsulation for B uilding E quipment and I ndustrial I nstallations
VCP	is V erification of C onstancy of P erformance (previously named evaluation of conformity)

4 Requirements

4.1 General

Product properties shall be assessed in accordance with Clause 5. To comply with this standard, products shall meet the requirements of 4.2 and the requirements of 4.3 as appropriate.

NOTE Information on additional properties is given in Annex D.

One test result for a product property is the average of the measured values on the number of the test specimens given in Table 6.

4.2 For all applications

4.2.1 Thermal conductivity

For flat specimens, the thermal conductivity shall be based upon measurements carried out in accordance with EN 12667 or EN 12939 for thick products. For cylindrical specimens, EN ISO 8497 shall be used as specified in 5.3.2.

In both cases, the thermal conductivity values shall be determined by the manufacturer and verified in accordance with EN ISO 13787 and Annex B of this product standard. They shall be declared by the manufacturer according to the measuring standards mentioned above covering the product service temperature range. The following conditions apply:

- the measured values shall be expressed with three significant figures;
- the declared thermal conductivity curve shall be given as a limit curve, defined in EN ISO 13787;
- the value of the declared thermal conductivity, λ_D , shall be rounded upwards to the nearest 0,001 W/(m·K);
- the lowest reference mean test temperature required is - 170 °C.

The declared equation/limit curve is the “declared reference” with three significant figures, that is to 0,000 1 W/(m·K) for λ values below 0,1 W/(m·K) and in 0,001 W/(m·K) for λ values above 0,1 W/(m·K). This shall be used as a reference for the verification of the declaration.

When thermal conductivity is declared as a table derived from the formula, rounding upwards to the next 0,001 W/(m·K) has to be done for the full range of the thermal conductivity.

NOTE Determinations of the declared thermal conductivity of pipe sections, following EN ISO 8497, having joints in the metering area, include the effects of these joints as defined in EN ISO 23993.

4.2.2 Dimensions and tolerances

4.2.2.1 Linear dimensions

The length, l , width, b , and thickness, d , of boards shall be determined in accordance with EN 822 and EN 823. The length, l , thickness, d , and inside diameter, D_i , of pipe sections, segments and prefabricated ware shall be determined in accordance with EN 13467. No test result shall deviate from the declared value or class by more than the tolerances given in Tables 1 and 2.

Products with a surface facing or natural skin shall be tested without removing them.