



SLOVENSKI STANDARD
kSIST FprEN 12390-11:2015
01-februar-2015

Preskušanje strjenega betona - 11. del: Ugotavljanje odpornosti betona proti kloridom, enosmerna difuzija

Testing hardened concrete - Part 11: Determination of the chloride resistance of concrete, unidirectional diffusion

Prüfung von Festbeton - Teil 11: Bestimmung des Chloridwiderstandes von Beton - Einseitig gerichtete Diffusion

Essais pour béton durci - Partie 11: Détermination de la résistance du béton à la pénétration des chlorures, diffusion unidirectionnelle

Ta slovenski standard je istoveten z: FprEN 12390-11

<https://standards.iteh.ai/catalog/standards/sist/b6082521-3c35-4bf0-ad0f-81deb3ad02b1/sist-en-12390-11-2015>

ICS:

91.100.30	Beton in betonski izdelki	Concrete and concrete products
-----------	---------------------------	--------------------------------

kSIST FprEN 12390-11:2015

en,fr,de

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

FINAL DRAFT
FprEN 12390-11

December 2014

ICS 91.100.30

Will supersede CEN/TS 12390-11:2010

English Version

Testing hardened concrete - Part 11: Determination of the chloride resistance of concrete, unidirectional diffusion

Essais pour béton durci - Partie 11: Détermination de la résistance du béton à la pénétration des chlorures, diffusion unidirectionnelle

Prüfung von Festbeton - Teil 11: Bestimmung des Chloridwiderstandes von Beton - Einseitig gerichtete Diffusion

This draft European Standard is submitted to CEN members for unique acceptance procedure. It has been drawn up by the Technical Committee CEN/TC 104.

If this draft becomes a European Standard, CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

This draft European Standard was established by CEN in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

Recipients of this draft are invited to submit, with their comments, notification of any relevant patent rights of which they are aware and to provide supporting documentation.

Warning : This document is not a European Standard. It is distributed for review and comments. It is subject to change without notice and shall not be referred to as a European Standard.

<https://standards.iteh.ai/catalog/standards/sist/b6082521-3c35-4bf0-ad0f-81deb3ad02b1/sist-en-12390-11-2015>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

	Page
Foreword.....	4
Introduction	6
1 Scope	7
2 Normative references	7
3 Terms and definitions	7
4 Principle	8
5 Reagents and apparatus	9
5.1 Reagents	9
5.2 Apparatus	9
6 Preparation of specimens	10
6.1 Preparing sub-specimens	10
6.2 Conditioning and preparation of profile specimen for chloride testing	11
7 Procedure	13
7.1 Exposure conditions	13
7.2 Exposure method.....	14
7.3 Exposure period.....	14
7.4 Determination of initial chloride content (C_i)	14
7.5 Profile grinding	15
7.6 Chloride analysis	16
8 Regression procedure and expression of results	16
9 Test report	19
10 Precision	19
Annex A (informative) Diffusion coefficients.....	21
Annex B (informative) Core test specimen	22
Annex C (informative) Typical equipment and procedure for vacuum saturation.....	23
C.1 Apparatus	23
C.2 Procedure	24
Annex D (normative) Immersion method for large specimens	25
Annex E (informative) Guidance on the test procedure	26
E.1 Guidance on suitable concretes types	26
E.2 Explanation of why water is used for saturation and curing	26
E.3 Guidance on the selection of the exposure solution	26
E.4 Curve-fitting to the error-function solution to Fick's 2 nd law	26
Annex F (informative) Examples for calibration of the calculation procedure for regression analysis.....	28
F.1 Introduction	28
F.2 Chloride profile 1	29
F.3 Chloride profile 2	30

F.4 Chloride profile 331
Bibliography33

iTeh Standards
(<https://standards.itih.ai>)
Document Preview

[SIST EN 12390-11:2015](https://standards.itih.ai/catalog/standards/sist/b6082521-3c35-4bf0-ad0f-81deb3ad02b1/sist-en-12390-11-2015)

<https://standards.itih.ai/catalog/standards/sist/b6082521-3c35-4bf0-ad0f-81deb3ad02b1/sist-en-12390-11-2015>

FprEN 12390-11:2014 (E)**Foreword**

This document (FprEN 12390-11:2014) has been prepared by Technical Committee CEN/TC 104 "Concrete and related products", the secretariat of which is held by DIN.

This document is currently submitted to the Unique Acceptance Procedure.

This document will supersede CEN/TS 12390-11:2010.

In comparison to CEN/TS 12390-11:2010, the following changes have been made:

- In Clause 2, the normative references have been updated;
- In Clause 8, a minimum value of the correlation coefficient has been added and further guidance on the calculations has been added;
- In Clause 9, a graph and details of points included and excluded plus the correlation coefficient have been added;
- In Clause 10, Table 3 has been added.
- A new Annex E (informative) "Guidance on test procedure" has been added;
- A new Annex F (informative) "Examples for calibration of the calculation procedure for regression analysis" has been added;
- The Bibliography has been reviewed;
- The standard has been revised editorially.

The drafting of this European Standard was delegated to CEN/TC 51(CEN/TC104)/JWG12/TG5.

This test method is one of a series concerned with testing concrete. At the behest of CEN, RILEM reviewed chloride testing methods [1] and this European Standard is based on their recommendations. In addition this European Standard draws on recommendations from the EU-project "Chlortest" 5th Framework Programme (GRD1-2002-71808/G6RD-CT-2002-00855) [2] immersion test recommendation as well as the Nordtest Method NT Build 443 Concrete, hardened: Accelerated Chloride penetration [3].

The series EN 12390 *Testing hardened concrete* includes the following parts:

- *Part 1: Shape, dimensions and other requirements of specimens and moulds*
- *Part 2: Making and curing specimens for strength tests*
- *Part 3: Compressive strength testing of specimens*
- *Part 4: Compressive strength – Specification of testing machines*
- *Part 5: Flexural strength of test specimens*
- *Part 6: Tensile splitting strength of test specimens*
- *Part 7: Density of hardened concrete*
- *Part 8: Depth of penetration of water under pressure*

- *Part 9: Freeze-thaw resistance – Scaling (Technical Specification)*
- *Part 10: Determination of the relative carbonation resistance of concrete (Technical Specification)*
- *Part 11: Determination of the chloride resistance of concrete, unidirectional diffusion*
- *Part 13: Determination of the secant modulus of elasticity in compression*

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[SIST EN 12390-11:2015](https://standards.iteh.ai/catalog/standards/sist/b6082521-3c35-4bf0-ad0f-81deb3ad02b1/sist-en-12390-11-2015)

<https://standards.iteh.ai/catalog/standards/sist/b6082521-3c35-4bf0-ad0f-81deb3ad02b1/sist-en-12390-11-2015>

FprEN 12390-11:2014 (E)**Introduction**

Steel reinforced concrete structures exposed to the ingress of chloride, either from seawater or other sources, need to be durable for at least the intended working life. The possibility of reinforcement corrosion is significantly increased as the chloride level at the embedded reinforcement increases. For this reason the chloride diffusivity or penetrability of the concrete is an important property to measure and this European Standard sets out a test method that may be applied to specimens cast to assess the potential chloride resistance properties of a concrete mix.

NOTE This test method takes a minimum of 119 days comprising a minimum age of the specimen prior to testing of 28 days, a minimum of one day to prepare and condition the specimen and then 90 days to expose the specimen to the chloride solution.

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[SIST EN 12390-11:2015](https://standards.iteh.ai/catalog/standards/sist/b6082521-3c35-4bf0-ad0f-81deb3ad02b1/sist-en-12390-11-2015)

<https://standards.iteh.ai/catalog/standards/sist/b6082521-3c35-4bf0-ad0f-81deb3ad02b1/sist-en-12390-11-2015>

1 Scope

This European Standard is a method for determining the unidirectional non-steady state chloride diffusion and surface concentration of conditioned specimens of hardened concrete. The test method enables the determination of the chloride penetration at a specified age, e.g. for ranking of concrete quality by comparative testing. Since resistance to chloride penetration depends on the ageing, including the effects of continual hydration, then the ranking may also change with age.

The test procedure does not apply to concrete with surface treatments such as silanes and it may not apply to concrete containing fibres, see E.1.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 12390-2, *Testing hardened concrete - Part 2: Making and curing specimens for strength tests*

EN 14629, *Products and systems for the protection and repair of concrete structures - Test methods - Determination of chloride content in hardened concrete*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

as-cast surface

surface of a concrete element exposed in the construction works to a chloride environment

3.2

chloride content

amount of acid-soluble chloride expressed in percent by mass of concrete

3.3

chloride penetration

ingress of chlorides into concrete due to exposure to external chloride sources

3.4

diffusion

movement of molecules or ions under a concentration gradient, that is movement from a zone of high concentration to a zone with a lower concentration

3.5

diffusion coefficient

proportionality between the molecular flux (e.g. rate of flow of chloride ions) and the concentration gradient in the diffusion equation

Note 1 to entry: In this European Standard Fick's Law is adopted.

Note 2 to entry: See Annex A.

3.6

initial chloride content (C_i)

chloride content at a distance sufficiently remote from the exposed surface as to not have been influenced by penetration of the chloride exposure solution

FprEN 12390-11:2014 (E)

Note 1 to entry: It reflects the initial chloride content that came from the constituents when the concrete was mixed.

3.7**non-steady state diffusion coefficient (D_{nss})**

diffusion coefficient that takes into account simultaneous chloride binding

Note 1 to entry: The steady-state chloride diffusion coefficient is measured on water saturated specimens where chloride diffuses through a thin specimen between two reservoirs of chloride solution, where one reservoir is at a higher concentration than the other. This steady state chloride diffusion is not covered by this test method. The steady-state chloride diffusion coefficient only reflects the ionic transport diffusion through concrete, as the concrete is unable to bind any more chloride ion.

Note 2 to entry: See Annex A.

3.8**profile grinding**

dry process grinding a concrete specimen in thin successive layers

3.9**vacuum saturated condition**

specimen that is vacuum saturated with water

4 Principle

A specimen, either a cylinder or cube, shall be cast and cured in accordance with EN 12390-2, with a curing period of not less than 28 days.

Annex B gives guidance on the testing of core specimens, where the core may be sampled from a test element, a precast concrete element or a structure.

The specimen is divided into two sub-specimens, a 'profile specimen' that is used to determine the chloride profile after exposure to unidirectional chloride ingress, and an initial chloride sub-specimen that is used to determine the initial chloride level, C_i . This initial figure is taken as the chloride level of the cast concrete.

The profile specimen is vacuum saturated with distilled or demineralised water, coated on all sides but one and then the uncoated face is exposed to a chloride exposure solution. The exposure is achieved by either complete immersion, ponding the uncoated face or inverting the specimen and having the uncoated face immersed in the chloride exposure solution. The reference solution is a 3 % by mass sodium chloride (NaCl) solution, for a period of 90 days (other concentrations or solutions e.g. artificial seawater, are permitted as are different exposure periods). The use of large fully immersed specimens is described in Annex D.

After 90 days of exposure, at least 8 parallel layers of the chloride exposed surface are ground off the profile specimen. The acid-soluble chloride content of each layer and the average depth of the layer from the surface of the concrete exposed to the chloride solution are determined. The initial chloride content is determined by grinding a sample from the other sub-specimen and the acid-soluble chloride content determined.

By non-linear regression analysis by least squares curve fitting, the surface chloride content (C_s) and the non-steady state chloride diffusion coefficient (D_{nss}) are determined.

Because of the high coefficient of variation, ~ 15 – 30 % for D_{nss} for the test, the number of specimens should be increased until the required precision is achieved. The results shall be reported separately and the average value.

NOTE 1 The chloride diffusion coefficient varies with the age of the concrete and the period of exposure.

NOTE 2 The diffusion test described in this European Standard is only valid for a constant initial chloride content.

5 Reagents and apparatus

5.1 Reagents

Reagents of analytical quality shall be used.

NOTE Unless otherwise stated 'percent' means percent by mass.

5.1.1 Calcium hydroxide, $\text{Ca}(\text{OH})_2$

5.1.2 Chloride Exposure Solution

5.1.2.1 Reference solution

Dissolve 30 g of analytical quality NaCl in 970 g of distilled or demineralised water having an electrical conductivity $\leq 0,5 \text{ mSm}^{-1}$ at 20 °C to produce a 3 % by mass NaCl solution. Store it in a clean container.

NOTE This NaCl solution has a similar chloride concentration to that of Atlantic seawater.

5.1.2.2 Other exposure solutions

Where the concentration of the chloride exposure solution is other than that in 5.1.2.1, the concentration shall be recorded and reported. Where a different solution is used the composition of the solution shall be recorded and reported.

NOTE 1 Natural and artificial seawater have been used to reflect the exposure of the construction works.

NOTE 2 Higher concentrations of NaCl, such as 16,5 %, and shorter exposure periods (e.g. 35 days) have been used to accelerate the development of a chloride profile.

5.1.3 Chloride ion diffusion proof two-component polyurethane or epoxy-based paint or other equivalent barrier system

5.1.4 Chemicals for chloride analysis, to EN 14629.

5.1.5 Distilled or demineralised water, having an electrical conductivity $\leq 0,5 \text{ mSm}^{-1}$.

5.2 Apparatus

5.2.1 Water cooled diamond saw

5.2.2 Balance for weighing NaCl and water, capable of weighing to an accuracy of $\pm 0,1 \text{ g}$.

5.2.3 Thermometer, capable of measuring to an accuracy of $\pm 1 \text{ }^\circ\text{C}$.

5.2.4 Temperature controlled chamber capable of keeping a temperature of $20 \text{ }^\circ\text{C} \pm 2 \text{ }^\circ\text{C}$.

5.2.5 Where used, a polyethylene container with airtight lid for immersion of the profile specimen.

The volume of the exposure solution shall exceed the volume of the specimen by not less than $12,5 \text{ ml per cm}^2$ of exposed surface. A container may contain more than one specimen provided at least the minimum ratio of exposure solution to exposed surface is achieved. The ratio of exposure solution to exposed surface shall be recorded and reported.

During the test, the chloride concentration of the chloride exposure solution reduces and if the ratio of the volume of chloride exposure solution to exposure surface varies, the rate of reduction will vary with nominally