



Designation: ~~C503-05~~ Designation: C 503 – 08

## Standard Specification for Marble Dimension Stone<sup>1</sup>

This standard is issued under the fixed designation C 503; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

### 1. Scope

~~1.1 This specification covers the material characteristics, physical requirements, and sampling appropriate to the selection of marble for general building and structural purposes.~~

1.1 This specification covers the material characteristics, physical requirements, and sampling appropriate to the selection of marble for general building and structural purposes. Refer to Guides C 1242 and C 1528 for the appropriate selection and use of marble dimension stone.

1.2 Dimension marble shall include stone that is sawed, cut, split, or otherwise finished or shaped into blocks, slabs or tiles, and shall specifically exclude molded, cast and artificially aggregated units composed of fragments, and also crushed and broken stone.

### 2. Referenced Documents

#### 2.1 ASTM Standards:<sup>2</sup>

C 97 Test Methods for Absorption and Bulk Specific Gravity of Dimension Stone

C 99 Test Method for Modulus of Rupture of Dimension Stone

C 119 Terminology Relating to Dimension Stone

C 170 Test Method for Compressive Strength of Dimension Stone

C 241 Test Method for Abrasion Resistance of Stone Subjected to Foot Traffic

C 880 Test Method for Flexural Strength of Dimension Stone

C 1242 Guide for Selection, Design, and Installation of Dimension Stone Anchoring Systems

~~C1353 Test Method Using the Taber Abraser for Abrasion Resistance of Dimension Stone Subjected to Foot Traffic~~ 1353 Test Method Using the Taber Abraser for Abrasion Resistance of Dimension Stone Subjected to Foot Traffic

C 1528 Guide for Selection of Dimension Stone for Exterior Use

### 3. Terminology

3.1 *Definitions*—All definitions are in accordance with Terminology C 119.

3.1.1 *marble, n*—a crystalline rock composed predominantly of one or more of the following minerals: calcite and dolomite capable of taking a polish (see Terminology C 119).

### 4. Classification

4.1 Dimension marble is classified as follows:

4.1.1 *I Calcite.*

4.1.2 *II Dolomite.*

NOTE 1—See Terminology C 119 for definitions of calcite and dolomite.

### 5. Soundness

~~5.1 Marbles are further classified into four “Soundness” groups. The basis of this classification is the characteristics encountered in fabrication and has no reference whatsoever to comparative merit or value. The classifications merely indicate what method of fabrication is considered necessary and acceptable in each instance, as based on standard trade practice. Marble is classified by its producer.~~

5.1 Marbles are further classified into four “Soundness” groups: A, B, C, and D. Classifications are based on the properties encountered in fabrication and has no reference whatsoever to comparative merit or value. Marble is classified by its producer.

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee C18 on Dimension Stone and is the direct responsibility of Subcommittee C18.03 on Material Specifications.

~~Current edition approved June 1, 2005. Published July 2005. Originally approved in 1962. Last previous edition approved in 2003 as C503-03.~~

~~Current edition approved Jan. 15, 2008. Published February 2008. Originally approved in 1962. Last previous edition approved in 2005 as C 503 – 05.~~

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard’s Document Summary page on the ASTM website.