



# DRAFT INTERNATIONAL STANDARD ISO/DIS 12891-2

ISO/TC 150

Secretariat: DIN

Voting begins on  
2013-02-14

Voting terminates on  
2013-05-14

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION • МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ • ORGANISATION INTERNATIONALE DE NORMALISATION

## Retrieval and analysis of surgical implants —

### Part 2: Analysis of retrieved surgical implants

*Retrait et analyse des implants chirurgicaux —*

*Partie 2: Analyse des implants chirurgicaux métalliques retirés*

[Revision of first edition (ISO 12891-2:2000)]

ICS 11.040.40

To expedite distribution, this document is circulated as received from the committee secretariat. ISO Central Secretariat work of editing and text composition will be undertaken at publication stage.

Pour accélérer la distribution, le présent document est distribué tel qu'il est parvenu du secrétariat du comité. Le travail de rédaction et de composition de texte sera effectué au Secrétariat central de l'ISO au stade de publication.

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

**iTeh STANDARD PREVIEW**  
(standards.iteh.ai)  
Full standard:  
<https://standards.iteh.ai/catalog/standards/sist/0c1ebb24-7982-4743-bcdf-f304a6a472ff/iso-12891-2-2014>

### Copyright notice

This ISO document is a Draft International Standard and is copyright-protected by ISO. Except as permitted under the applicable laws of the user's country, neither this ISO draft nor any extract from it may be reproduced, stored in a retrieval system or transmitted in any form or by any means, electronic, photocopying, recording or otherwise, without prior written permission being secured.

Requests for permission to reproduce should be addressed to either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Reproduction may be subject to royalty payments or a licensing agreement.

Violators may be prosecuted.

# Contents

Page

Foreword .....	iv
Introduction.....	v
<b>1</b> <b>Scope</b> .....	<b>1</b>
<b>2</b> <b>Normative references</b> .....	<b>1</b>
<b>3</b> <b>Terms and definitions</b> .....	<b>1</b>
<b>4</b> <b>Procedures for retrieval, handling and packaging</b> .....	<b>1</b>
<b>5</b> <b>Analysis of the implant interfaces</b> .....	<b>2</b>
<b>5.1</b> <b>Implant/tissue interface</b> .....	<b>2</b>
<b>5.2</b> <b>Implant/implant interfaces</b> .....	<b>2</b>
<b>6</b> <b>Analysis of the implant</b> .....	<b>2</b>
<b>6.1</b> <b>General</b> .....	<b>2</b>
<b>6.2</b> <b>Forms for recording the results of the analyses</b> .....	<b>2</b>
<b>6.3</b> <b>Stage I investigation (macroscopic examination — non-destructive)</b> .....	<b>3</b>
<b>6.3.1</b> <b>Identification/photography</b> .....	<b>3</b>
<b>6.3.2</b> <b>Visual examination</b> .....	<b>3</b>
<b>6.3.3</b> <b>Low-power optical examination</b> .....	<b>3</b>
<b>6.3.4</b> <b>Further evaluation</b> .....	<b>3</b>
<b>6.4</b> <b>Stage II investigation (microscopic examination — mostly non-destructive)</b> .....	<b>3</b>
<b>6.4.1</b> <b>General</b> .....	<b>3</b>
<b>6.4.2</b> <b>Microscopic examination</b> .....	<b>3</b>
<b>6.4.3</b> <b>Fractographic examination</b> .....	<b>3</b>
<b>6.4.4</b> <b>Surface topography</b> .....	<b>4</b>
<b>6.5</b> <b>Stage III investigation (material investigation — mostly destructive)</b> .....	<b>4</b>
<b>6.5.1</b> <b>General</b> .....	<b>4</b>
<b>6.5.2</b> <b>Material composition</b> .....	<b>4</b>
<b>6.5.3</b> <b>Microstructure</b> .....	<b>5</b>
<b>6.5.4</b> <b>Mechanical properties</b> .....	<b>5</b>
<b>6.6</b> <b>Surface-treated or coated implants</b> .....	<b>6</b>
<b>6.7</b> <b>Biodegradable implants</b> .....	<b>6</b>
<b>7</b> <b>Implant performance</b> .....	<b>6</b>
<b>Annex A</b> (normative) <b>Standard forms for the analysis of retrieved surgical implants</b> .....	<b>7</b>
<b>A.1</b> <b>General</b> .....	<b>7</b>
<b>A.2</b> <b>Form for examination of retrieved metallic surgical implant</b> .....	<b>8</b>
<b>A.3</b> <b>Form for examination of retrieved polymeric surgical implant</b> .....	<b>11</b>
<b>A.4</b> <b>Form for examination of retrieved ceramic surgical implant</b> .....	<b>15</b>
<b>Annex B</b> (informative) <b>Applicable International Standards for the evaluation of materials</b> .....	<b>18</b>
<b>B.1</b> <b>Metallic materials</b> .....	<b>18</b>
<b>B.1.1</b> <b>Chemical, microstructural and mechanical properties</b> .....	<b>18</b>
<b>B.1.2</b> <b>Microstructural testing</b> .....	<b>18</b>
<b>B.1.3</b> <b>Mechanical testing</b> .....	<b>18</b>
<b>B.2</b> <b>Polymeric materials</b> .....	<b>19</b>
<b>B.2.1</b> <b>Chemical, physicochemical, thermal and mechanical properties</b> .....	<b>19</b>
<b>B.2.2</b> <b>Physicochemical testing</b> .....	<b>19</b>
<b>B.2.3</b> <b>Mechanical testing</b> .....	<b>20</b>
<b>B.3</b> <b>Ceramic materials</b> .....	<b>20</b>
<b>B.3.1</b> <b>Chemical, microstructural and mechanical properties</b> .....	<b>20</b>
<b>B.3.2</b> <b>Physical testing</b> .....	<b>21</b>
<b>B.3.3</b> <b>Mechanical testing</b> .....	<b>21</b>
<b>Bibliography</b> .....	<b>22</b>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 12891-2 was prepared by Technical Committee ISO/TC 150, *Implants for surgery*, Subcommittee SC , .

This second edition cancels and replaces the first editions (ISO 12891-2:2000, ISO 12891-3:2000, ISO 12891-4:2000), which have been merged and technically revised.

ISO 12891 consists of the following parts, under the general title *Implants for surgery — Retrieval and analysis of surgical implants*:

- *Part 1: Retrieval and handling*
- *Part 2: Analysis of retrieved surgical implants*

!TECHNICAL STANDARD DRAFT!  
(standards.iteh.ai)  
Full standard:  
<https://standards.iteh.ai/catalog/standards/sis/0c1eb7b1-7982-4743-bcdf-f304a6a472ff/iso-12891-2-2014>

D  
R  
A  
F  
T

## Introduction

The investigation of retrieved implantable medical devices and adjacent tissues can be of diagnostic value in the event of clinical complications, can deepen our knowledge of clinical implant performance and safety and can improve our understanding of the interactions between implants and the body, thus furthering the development of implants with improved biocompatibility and functional longevity.

This part of ISO 12891 specifies methods for the retrieval, handling and analysis of surgical implants and associated specimens which are retrieved from patients, during revision surgery or post-mortem. The aim is to provide guidance in preventing damage to the specimens which could obscure the investigation results, and in gathering data at the proper time and under the proper circumstances. Part 1 deals with retrieval and handling. This part of ISO 12891 concerns the analysis of implants of specific materials, and includes protocols for reporting the data collected. For particular investigation programmes, additional, more specific, protocols can be required. If special analytical techniques are employed, the procedures used should be specified.

This part of ISO 12891 specifies methods for the analysis of retrieved surgical implants to ensure they are not damaged, to indicate typical investigation techniques, and to allow comparisons between investigation results from different sources. These methods may be useful for retrieval and analysis studies in animals.

ISO 12891-1 specifies methods for retrieval and handling and applies to this part of ISO 12891. Annex A and C of ISO 12891-1 include examples of protocols for reporting data concerning the retrieval process. These protocols are not repeated in this part of ISO 12891. They may be reduced or expanded depending on the retrieved surgical implant, the presence of any attached or accompanying biological material, and the purpose of the retrieval and analysis.

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

Full standard:  
<https://standards.iteh.ai/catalog/standards/sist/0c1ebb24-7982-4743-bcdf-f304a6a472ff/iso-12891-2-2014>

# Retrieval and analysis of surgical implants —

## Part 2: Analysis of retrieved surgical implants

### 1 Scope

This part of ISO 12891 specifies methods for the analysis of retrieved surgical implants.

This part of ISO 12891 describes the analysis of retrieved metallic, polymeric and ceramic implants. The analysis is divided into 3 stages which are increasingly destructive.

This part of ISO 12891 can also be applied to other materials, e.g. animal tissue implants.

This part of ISO 12891 can be applied in accordance with national regulations or legal requirements regarding the handling and analysis of retrieved implants and tissues and associated biological material.

### 2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 12891-1:2011, *Retrieval and analysis of surgical implants — Part 1: Retrieval and handling*

### 3 Terms and definitions

For the purposes of this document, the following term and definition apply.

#### 3.1

##### **surgical implant**

medical device intended to be inserted into the body by surgical techniques

NOTE 1 to entry: This part of ISO 12891 applies in particular to metallic, polymeric and ceramic implants.

NOTE 2 to entry: The medical device is hereafter referred to as an "implant".

NOTE 3 to entry: The implant may be a component of a modular or multicomponent implant.

### 4 Procedures for retrieval, handling and packaging

Procedures for retrieval, handling, packaging and protection of the personnel involved shall be in accordance with ISO 12891-1.

As a precautionary measure, retrieved implants shall be decontaminated by an appropriate means that does not adversely affect the implant or the planned investigation. Appropriate methods are given in 3.8 of ISO 12891-1:2011.

Any difficulty on implant retrieval procedure leading to unavoidable implant damage during it shall be reported together with a description of the produced damage.

Cleaning solutions (see ISO 12891-1, Table 1) can interact with the material e.g. corrosion or dissolution and should be chosen to minimize this risk.

Photographic records of the surgical field should be done before the implant retrieval, if appropriate.

## 5 Analysis of the implant interfaces

### 5.1 Implant/tissue interface

A significant part of the information associated with a retrieved surgical implant is often at the implant/tissue interface. Attention shall be given to the interface and to the peri-implant tissue and its contents. Where required, analyses of the chemistry and nature of the byproducts of degradation of the implant and a study of the cellular response to the implant shall be considered.

In cases where implant surfaces are designed to promote tissue ingrowth or ongrowth, a study of the implant tissue interface can be of particular interest, and the findings shall be recorded. If residues are adherent to the surface of the implant, this shall be recorded.

Since the appearance of the tissue can vary rapidly with the distance from the implant surface, it is important that the tissue is analysed in its context with the implant. Where possible, tissue, fluid, and particulate samples should be collected for further analysis (see e.g. 3.4 of ISO 12891-1).

### 5.2 Implant/implant interfaces

Where implants articulate on or are in contact with other implant components, the condition of the contacting surface areas of the implant may be of particular interest. Their study shall be considered in the context of the opposing surface, and that part of ISO 12891 which concerns the material of this opposite component may be consulted.

In addition to studying the condition of contacting surfaces, the surrounding area shall also be studied to determine whether wear debris is present.

## 6 Analysis of the implant

### 6.1 General

This clause describes the different degrees of characterization to be considered when a retrieved implant is under investigation.

The analyses of the retrieved implant are divided into three stages, with the degree of characterization and destruction increasing from stage I to stage III. The implant characterizations may include macroscopic and microscopic examinations, chemical analyses and the determination of physical and mechanical properties.

Because of the complexity of the materials that may be used for implants, and because of the large number of potential analyses and tests suggested in this part of ISO 12891, the stage and type of analysis to be performed shall be chosen as a function of the type of implant and the purpose of the investigation.

The examinations selected to be performed shall depend upon the reason for removal and examination of the implant, and possible restrictions in destructive testing. Perform a minimum number of investigations for routine removals where the implant is not suspected to have malfunctioned, more examinations for implants suspected of having a functional impairment, and extensive investigations for implants retrieved because of their poor performance or behaviour or because of a malfunction.

Each component of an implant shall be analysed separately, if possible and necessary.

### 6.2 Forms for recording the results of the analyses

Standard forms for metallic (see A.2), polymeric (see A.3) and ceramic (see A.4) implants, indicating the information to be recorded at each stage of the investigation are given as a framework. Further information regarding the use of the forms is given in A.1.



For other materials, e.g. animal tissue implants, a form based on A.2 to A.4 may be used for the preparation of a relevant list.

NOTE A standard form for the recording of clinical and implant-related information is given in Annex A of ISO 12891-1

### 6.3 Stage I investigation (macroscopic examination — non-destructive)

#### 6.3.1 Identification/photography

Markings found on the implant such as logos, article numbers, lot numbers, dimensions etc., shall be recorded. Photographic records shall be made of relevant findings, where useful.

#### 6.3.2 Visual examination

The implant surface shall be observed by suitable techniques to ascertain the mode of failure, destruction or surface alteration, if any such appears.

In no event shall any surface of a failed implant be destructively evaluated at this stage.

#### 6.3.3 Low-power optical examination

An overall examination shall be performed under a low-power optical stereomicroscope.

#### 6.3.4 Further evaluation

If at the conclusion of stage I further investigation is required to clarify any observations made, or to evaluate other characteristics or the failure mode of the implant, it shall be carried out subsequently in stage II.

### 6.4 Stage II investigation (microscopic examination — mostly non-destructive)

#### 6.4.1 General

Stage II investigation shall be carried out after stage I investigation, if deemed necessary, to further investigate or identify the characteristics and/or failure mode of the implant.

The primary aim of this stage of the investigation is to assess the mode of failure and the deterioration of the implant in the most non-destructive manner possible (see Annex A).

#### 6.4.2 Microscopic examination

Optical or scanning electron microscopic examination techniques suitable for the material under investigation shall be used.

Normal incidence of transmission optical microscopy or polarizing, interference, phase-contrast or other optical microscopic techniques may be used, when applicable to the implant.

When scanning electron microscopy is used, special preparation techniques can be required to obtain the necessary conditions for imaging and analyses.

X-ray methods or micro-CT systems may be used, when applicable.

#### 6.4.3 Fractographic examination

If the implant is fractured, analysis of the fracture surface by suitable techniques may help to ascertain the mode of fracture or to detect defects in the material. It may be necessary to excise a portion of the implant to conduct the examination. Destructive evaluation of the fracture surface shall be avoided. If the implant has

suffered mechanical failure, it is important to remember that it can become legal evidence and so the necessary precautions need to be taken.

#### 6.4.4 Surface topography

Where worn and unworn areas of the surfaces of retrieved implants are of interest, surface topography tests may be carried out in addition to the morphological assessment (see items 3 and 4 of A.2, A.3 and A.4 and B.1.2, B.2.3 and B.3.2).

### 6.5 Stage III investigation (material investigation — mostly destructive)

#### 6.5.1 General

If further investigation is necessary to assess the properties of the implant, the tests listed under stage III in Annex A shall be carried out as deemed necessary to further characterize the implant and its history.

NOTE 1 Applicable ISO Standards are given in Annex B for information.

NOTE 2 Additional national standards are given in the bibliography for information.

#### 6.5.2 Material composition

##### 6.5.2.1 General

Determine the physical and chemical composition and identity of the material and report the technique employed with the results. The type of material may be characterized by means of material standards listed in Annex B.

It can be sufficient in the study of a given retrieved implant to verify that the type of material corresponds to the information provided by the manufacturer. If more details are required or the nature of the material is unknown, appropriate techniques shall be used to determine the required physical and chemical properties (see Annex B).

The location of the area or portion of the implant that has been analysed shall be identified in relation to the full implant and reported with the result. The method of analysis shall be clearly identified.

##### 6.5.2.2 Metals

Where necessary, analysis of the composition shall be carried out by appropriate methods (e.g. electron diffraction X-ray analysis, X-ray fluorescence analysis, atomic absorption spectroscopy, or recognized chemical analysis techniques).

##### 6.5.2.3 Polymers

Differential thermal analysis, gel permeation chromatography or other applicable molecular weight methods, infrared analysis as well as other spectrographic techniques can be useful to further characterize the implant material.

If applicable, the thermal properties of polymers, e.g. transition temperature, heat of fusion and heat of crystallization, shall be determined in accordance with applicable test methods. The fractions extractable from the polymer shall be determined in accordance with suitable test methods (see B.2.)

Depending on the polymer, certain structural characteristics can be determined by optical or electron microscopy. For the determination of inclusions and particulate constituents, similar methods should be used.

Considering that bulk properties may differ considerably from surface properties (texture, strengths, etc.) due to processing characteristics (flow in moulds, differences in solidification rate, etc.), representative samples shall be provided from different portions of the implant, if possible.

#### 6.5.2.4 Ceramics

Recognized analytical methods shall be used to determine the chemical composition of the ceramic implant. The method of analysis shall be specified, such as X-ray fluorescence analysis and EDX analysis, and highly quantitative and specific techniques such as atomic absorption spectroscopy and spectrophotometric analysis.

Where of interest, the degree of crystallinity and the atomic structure can be determined by X-ray diffraction techniques.

#### 6.5.3 Microstructure

Standard preparation and evaluation techniques suitable for the material under investigation shall be used (see Annex B).

The grain size, in accordance with the applicable material standard and method shall be determined.

The inclusion content, in accordance with the applicable material standard, shall be determined, if appropriate.

The process condition of the material (annealed, recrystallized, work-strengthened, hot-forged, cold-forged, moulded, extruded, etc.), and other relevant features shall be indicated, where possible.

Evidence of corrosion or cracking shall be noted and recorded (see Annex A).

To check for voids and defects, scanning electron micro-analysis may be employed.

If a porous material is under investigation, the porosity shall be characterized.

#### 6.5.4 Mechanical properties

**IMPORTANT —Except for hardness measurements which can be carried out on the implant surface, the mechanical tests are destructive. The performance of such tests can be restricted or inhibited by the size and/or shape of the implant or by legal conditions.**

The types of measurement to be carried out at this stage of characterization depend upon the implant and its application. Some modern materials (e.g. shape memory alloys, degradable metals, certain polycarbonate urethanes or polydimethylsiloxanes) have unique mechanical considerations that shall also be addressed. For the assessment of mechanical properties, use section 9 in A.2, A.3 or A.4 (see also Annex B for applicable methods).

Where applicable, the density and hardness shall be determined in accordance with suitable material standards (see B.1.3 and B.3.3).

Where required and possible, the mechanical properties (tensile, flexural, compressive, etc.), shall be determined in accordance with applicable material specifications and test methods. Other tests may also be performed as appropriate to the test specimen.

Where dimensions allow, test specimen shall be fabricated from the implant. Deviation from the test specimen dimensions specified in standard methods may be made necessary by the shape and size of the implant under investigation. This shall be taken into account when evaluating the test results.

In performing hardness tests, results can vary depending on the method, the area, the direction of the measurements (surface, centre, longitudinal, transverse, etc.), deformation, etc. This shall be taken into account when evaluating the test results.

Shape memory materials can have a different set of properties to report (e.g. plateau stresses, austenite finish strain, elastic modulus, etc) that are not covered in Annex A