



DRAFT INTERNATIONAL STANDARD ISO/DIS 1887

ISO/TC 61/SC 13

Secretariat: JISC

Voting begins on
2011-04-29

Voting terminates on
2011-09-29

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION • МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ • ORGANISATION INTERNATIONALE DE NORMALISATION

Textile glass — Determination of combustible-matter content

Verre textile — Détermination de la teneur en matières combustibles

[Revision of third edition (ISO 1887:1995)]

ICS 59.100.10

In accordance with the provisions of Council Resolution 15/1993 this document is circulated in the English language only.

Conformément aux dispositions de la Résolution du Conseil 15/1993, ce document est distribué en version anglaise seulement.

To expedite distribution, this document is circulated as received from the committee secretariat. ISO Central Secretariat work of editing and text composition will be undertaken at publication stage.

Pour accélérer la distribution, le présent document est distribué tel qu'il est parvenu du secrétariat du comité. Le travail de rédaction et de composition de texte sera effectué au Secrétariat central de l'ISO au stade de publication.

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

Full standard:
<https://standards.iteh.ai/catalog/standards/sist/5e0f603d-fade-479b-8a84-9c1e6be90cb6/iso-1887-2014>

Copyright notice

This ISO document is a Draft International Standard and is copyright-protected by ISO. Except as permitted under the applicable laws of the user's country, neither this ISO draft nor any extract from it may be reproduced, stored in a retrieval system or transmitted in any form or by any means, electronic, photocopying, recording or otherwise, without prior written permission being secured.

Requests for permission to reproduce should be addressed to either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Reproduction may be subject to royalty payments or a licensing agreement.

Violators may be prosecuted.

7 contents

Page

Foreword	iv
1 Scope	1
2 Terms and definitions	1
3 Principle	1
4 Apparatus	1
5 Test specimens.....	2
5.1 Selection of test specimens	2
5.2 Number of test specimens.....	3
6 Procedure	3
6.1 Precautions to be taken during test	3
6.2 Weighing the specimen holder	3
6.3 Weighing the dried test specimen plus holder	4
6.4 Weighing the calcinated test specimen plus holder.....	4
7 Expression of results	4
8 Precision	5
9 Test report.....	5

iTeh STANDARD PREVIEW
 (standards.iteh.ai)
 Full standard:
<https://standards.iteh.ai/catalog/standards/sist/5c01603d-fade-479b-8a84-9c1e6be90cb6/iso-1887-2014>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 1887 was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 13, *Composites and reinforcement fibres*.

This fourth edition cancels and replaces the third edition (ISO 1887:1995), of which has been technically revised.

PREVIEW
iTech STANDARD
(standard.itech.ai)
Full standard
https://standards.itech.ai/catalog/standards/sist/40f603d-
fade-479b-8a84-9c1e6be90cb6/iso-1887-2011

Textile glass — Determination of combustible-matter content

1 Scope

This International Standard specifies a method for the determination of the combustible-matter content of products made from textile glass, such as continuous-filament yarns, staple-fibre yarns, rovings, chopped Strands, milled fibres, fabrics, chopped-Strand and continuous-filament mats and other glass reinforcements.

2 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

2.1

combustible-matter content

The ratio of the mass of material removed on calcination from a dried textile glass product to the mass of the dried product.

NOTE This ratio is expressed as a percentage in this International Standard. It is equal to the content of size or finish on the textile glass product when the size or finish is completely combustible without significant residue (i.e. primarily organic products).

3 Principle

Test specimens, dried under prescribed conditions, are weighed before and after calcination at a temperature of $625\text{ °C} \pm 20\text{ °C}$ or, with types of glass which are unstable at this temperature, at a temperature between 500 °C and 600 °C , also kept constant to within 20 °C .

4 Apparatus

4.1 Air-circulation oven, for drying specimens, capable of being maintained at $105\text{ °C} + 5\text{ °C}$ or the chosen drying temperature $\pm 5\text{ °C}$ (see 6.3).

4.2 Muffle furnace, capable of being maintained, with a tolerance of $\pm 20\text{ °C}$, at any desired temperature up to 625 °C , the temperature being measured at the centre of the muffle furnace with the door closed.

4.3 Desiccator, containing a suitable desiccant, for example silica gel, Calcium chloride, phosphorous(V) Oxide.

4.4 Specimen holder, made from a material stable at the test temperature, allowing the best possible air circulation around the test specimen and designed to prevent loss of material. The holder may be a porcelain crucible, a basket made of stainless-steel gauze, etc.

4.5 Stainless-steel tongs, for handling test specimens and holders.

4.6 Balance, accurate to 0,1 mg.

4.7 Polished-metal templates, for the preparation of test specimens.

4.8 **Suitable cutting tool**, for cutting mat or fabric, for example a knife, scissors, a cutting disc or a punch.

4.9 **Suitable wrap-reel**, for taking yarn and roving test specimens.

5 Test specimens

5.1 Selection of test specimens

Unless stated to the contrary in the product specification or by the person requesting the test, the test specimens shall be selected as specified in 5.1.1 to 5.1.4.

5.1.1 Yarns and rovings

Table 1 gives the length of yarn to be taken as a function of the linear density of the yarn. The test specimen shall not be unduly compressed, in order to ensure that the air will circulate as freely as possible and that drying and calcination will therefore be complete.

Table 1 — Length of yarn

Linear density, Tt tex	Length of yarn m
Tt ≤ 25	500
25 < Tt ≤ 45	200
45 < Tt ≤ 280	100
280 < Tt ≤ 650	50
650 < Tt ≤ 2 000	10
2 000 < Tt	5

5.1.2 Chopped Strands and milled fibres

Each specimen shall have a mass of not less than 5 g, but preferably between 15 g et 30 g.

5.1.3 Fabrics

Take a piece of fabric of sufficient size to allow specimens of area 100 cm² to be obtained. If the mass of the specimen is less than 5 g, either take larger specimens or use several adjacent 100 cm² specimens.

Specimens may have the same dimensions as those used for the determination of the mass per unit area.

Do not take specimens at a distance of less than 10 mm from the edges or selvages of the fabric. If the specimen has to be folded, this shall not impede good air circulation round the whole specimen. It is recommended that specimens be cut out using a template (4.7) and cutting tool or with a punch (4.8), so as to avoid losing material.

5.1.4 Mats

The test specimen shall have a mass of at least 5 g. The recommended specimen shape is a square measuring 316 mm x 316 mm (0,1 m²). However, other shapes may be used provided that the area is approximately 0,1 m². In this case, it is necessary to modify slightly the preparation procedure described below.

If it is necessary to use more than one square to achieve the required minimum specimen mass, these shall be taken along the length of the roll, in the same lane.

Cut a Strip of width at least 316 mm from across the whole width of the mat. Using the template (4.7) and the cutting tool (4.8), cut from this Strip:

- a) at each end (in the case of mats with trimmed edges, at least 10 mm inside the edges), a test specimen measuring 316 mm x 316 mm;
- b) between these end specimens, as many test specimens measuring 316 mm x 316 mm as the remaining width allows (these test specimens shall be evenly distributed).

5.2 Number of test specimens

Unless stated to the contrary or in more detail (i.e. number and location) in the specification or by the person requesting the test, the number of test specimens taken per elementary unit shall be as specified in table 2.

Table 2

Type of product	Number of test specimens
Yarns, roving	1
Chopped Strands, milled fibres	1
Fabrics, mats	3 for each metre of width, repeated regularly across the full width

NOTE The number of test specimens used for each determination of the combustible-matter content may be modified depending on the type of elementary unit, which may come in very different forms. In addition, a determination may have to be repeated at one or more locations in the elementary unit depending on the mass (chopped strands, milled fibre) or the length (fabrics, mats) of the elementary unit being tested. The additional information concerning the number and location of these specimens may be given in the product specification or by the person requesting the test.

6 Procedure

6.1 Precautions to be taken during test

- 6.1.1 Ensure that the test specimen does not come into contact with the furnace during the carbonization stage.
- 6.1.2 Always transfer the test specimen plus holder with care to prevent loss of material.
- 6.1.3 Never touch the test specimen with the bare hands.

6.2 Weighing the specimen holder

Stabilize the mass of the specimen holder (4.4) by placing it in the muffle furnace (4.2), maintained at 625 °C \pm 20 °C or, if the type of glass being tested is unstable at this temperature, at a temperature between 500 °C and 600 °C, also maintained to within \pm 20 °C. The temperature between 500 °C and 600 °C shall be chosen either on the basis of the specification for the glass or by agreement between the interested parties.

Allow the holder to cool in the desiccator (4.3), to ambient temperature.

Weigh the holder and note the mass to the nearest 0,1 mg (m_0).

Repeat the heating, cooling and weighing operations until constant mass is reached (See, however, note 6).

6.3 Weighing the dried test specimen plus holder

Place the holder with a specimen in the oven (4.1), maintained at $105\text{ °C} \pm 5\text{ °C}$ or, in the case of products containing components which are volatile, or susceptible to change, at this temperature, a lower temperature chosen by agreement between the interested parties and also maintained to within $\pm 5\text{ °C}$.

NOTE For fabrics and mats, the specimens may be cut and stacked rather than folded, in order to put them in a holder which fits into the apparatus (muffle furnace, balance).

Heat the specimen for at least 30 min.

Remove the holder plus specimen from the drying oven and allow to cool in the desiccator (4.3) for 30 min.

Weigh the holder plus dried specimen and note the mass to the nearest 0,1 mg (m_1).

Repeat the heating, cooling and weighing operations until constant mass is reached (See, however, note 6).

6.4 Weighing the calcinated test specimen plus holder

Place the holder plus dried specimen in the muffle furnace (4.2), maintained at $625\text{ °C} \pm 20\text{ °C}$ or at the chosen temperature between 500 °C and 600 °C (see 6.2).

Allow the specimen to burn for 5 min with the door of the furnace open (see NOTES 1 and 2). Then close the door of the furnace and heat for a further more than 10 min or, if a temperature lowers than 625 °C is used, for at least a further 1 h.

Remove the holder plus specimen from the furnace and transfer to the desiccator (4.3). Allow to cool to ambient temperature.

Weigh the holder plus calcinated specimen and note the mass to the nearest 0,1 mg (m_2).

Repeat the heating, cooling and weighing operations until constant mass is reached (See, however, NOTE 3).

NOTE 1 The door is left open to allow volatile products to escape from the furnace, thus preventing condensable materials being redeposited on the specimen or on the holder.

NOTE 2 If a ventilated furnace is used, this open-door time is not necessary.

NOTE 3 The test method requires that all weighings be confirmed to be to constant mass by repetition of the drying and calcination stages. In cases in which known materials are being tested regularly, the user of this International Standard is permitted to define, by experimentation, a minimum time for the drying and calcination stages to ensure that constant mass has been obtained.

7 Expression of results

The combustible-matter content of a test specimen, expressed as a percentage by mass of the dried product, is given by the formula:

$$H_1 = \frac{m_1 - m_2}{m_1 - m_0} \times 100$$

where