# INTERNATIONAL STANDARD

Second edition 2015-10-01

# Austenitic manganese steel castings

Pièces moulées en acier austénitique au manganèse

# iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 13521:2015 https://standards.iteh.ai/catalog/standards/sist/2cfbce91-cba6-4a55-89bbbd3daa29da9f/iso-13521-2015



Reference number ISO 13521:2015(E)

# iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 13521:2015 https://standards.iteh.ai/catalog/standards/sist/2cfbce91-cba6-4a55-89bbbd3daa29da9ffiso-13521-2015



© ISO 2015, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office Ch. de Blandonnet 8 • CP 401 CH-1214 Vernier, Geneva, Switzerland Tel. +41 22 749 01 11 Fax +41 22 749 09 47 copyright@iso.org www.iso.org

Page

## Contents

Forew	ord	iv						
1	Scope	1						
2	Normative references	1						
3	General conditions of delivery	1						
4	Heat treatment	1						
5	Chemical composition	1						
6	Mechanical tests   6.1 General   6.2 Bend test   6.3 Hardness test	<b>2</b> 2 2 2						
7	Microstructure	2						
8	Supplementary requirements	3						
Bibliography								

# iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 13521:2015 https://standards.iteh.ai/catalog/standards/sist/2cfbce91-cba6-4a55-89bbbd3daa29da9ffiso-13521-2015

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see <a href="https://www.iso.org/directives">www.iso.org/directives</a>).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see <a href="https://www.iso.org/patents">www.iso.org/patents</a>).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ASO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: Foreword - Supplementary information

The committee responsible for this document is ISO/TC 17, *Steel*, Subcommittee SC 11, *Steel castings*.

This second edition cancels and replaces the first edition (ISO 13521:1999), which has been technically revised with the following changes: ards.iteh.ai/catalog/standards/sist/2cfbce91-cba6-4a55-89bb-bd3daa29da9ffiso-13521-2015

- <u>6.3</u> was revised;
- <u>Clause 8</u> was revised;
- <u>Table 1</u>, grade number was added.

## Austenitic manganese steel castings

#### Scope 1

This International Standard specifies austenitic manganese cast steels for wear-resistant service. The grades covered by this International Standard will experience maximum service life in applications where the surface of the casting is subject to impact.

#### 2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 4990, Steel castings — General technical delivery requirements

ISO 7438, Metallic materials — Bend test

ISO 6506 (all parts), Metallic materials — Brinell hardness test

#### **RD PREVIEW** General conditions of delivery 3

Materials furnished according to this International Standard shall conform to the applicable requirements of ISO 4990, including the supplementary requirements that are agreed in the inquiry and purchase order. https://standards.iteh.ai/catalog/standards/sist/2cfbce91-cba6-4a55-89bb-

bd3daa29da9f/iso-13521-2015

#### 4 Heat treatment

Grade GX90MnMo14 can be supplied without heat treatment if the casting thickness is less than 45 mm and the carbon content is less than 0,8 %.

Where the thickness is 45 mm or greater and the carbon content is 0,8 % or greater, grade GX90MnMo14, and all other grades, shall be solution treated at temperatures not lower than 1 040 °C and quenched in water.

#### 5 **Chemical composition**

The steel shall conform to the requirements for chemical composition specified in Table 1.

Grade designation		C	Si	Mn	Р	S	Cr	Мо	Ni
Name	Number				max.	max.			
GX120MnMo7–1	1.3415	1,05	0,3	6,0	0,060	0,045		0,9	
		1,35	0,9	8,0				1,2	
GX110MnMo13-1	1.3416	0,75	0.3	11,0	0,060	0,045		0,9	
		1,35	0,9	14,0				1,2	
GX100Mn13 <sup>a</sup>	1.3406	0,90	0,3	11,0	0,060	0,045			
		1,05	0,9	14,0					
GX120Mn13 <sup>a</sup>	1.3802	1,05	0,3	11,0	0,060	0,045			
		1,35	0,9	14,0					
GX120MnCr13-2	1.3410	1,05	0,3	11,0	0,060	0,045	1,5		
		1,35	0,9	14,0			2,5		
GX120MnNi13-3	1.3425	1,05	0,3	11,0	0,060	0,045			3,0
		1,35	0,9	14,0					4,0
GX120Mn18 <sup>a</sup>	1.3407	1,05	0,3	16,0	0,060	0,045			
		1,35	0,9	19,0					
GX90MnMo14	1.3417	-0,70	<b>C - 0,3</b>	13,0	-0,070 -	0,045	TW	1,0	
	1	1,00	0,6	15,0				1,8	
GX120MnCr18-2	1.3411	1,05	<b>(S</b> ,31	<b>d 16,0</b>	0,060	<b>a</b> <sub>0,045</sub>	1,5		
		1,35	0,9	19,0	-2015		2,5		

Table 1 — Chemical composition, in % by mass

These grades are sometimes used for non-magnetic service and the service dards/sist/2cfbce91-cba6-4a55-89bb-

bd3daa29da9f/iso-13521-2015

## 6 Mechanical tests

## 6.1 General

Mechanical tests at room temperature shall be performed when agreed upon between the purchaser and manufacturer.

## 6.2 Bend test

Bend tests shall be carried out in accordance with ISO 7438. The type and location of bend test pieces shall be agreed between the manufacturer and purchaser. The test specimen shall withstand bending at room temperature (18 °C to 28 °C) through 150 °C without breaking into two or more pieces. Surface cracks produced by bending are not considered as failure if the test specimen remains in one piece.

## 6.3 Hardness test

Hardness tests shall be carried out in accordance with ISO 6506. The hardness shall be a maximum of 300 HBW, unless otherwise agreed between the manufacturer and purchaser. When machining of castings is required, it might be necessary to control hardness. In this case, hardness tests shall be carried out after heat treatment and prior to machining.

## 7 Microstructure

Metallographic examination shall be performed when agreed upon between the manufacturer and purchaser. Standard microstructure charts can be agreed between the manufacturer and purchaser.

## 8 Supplementary requirements

A list of normative supplementary requirements for use at the discretion of the purchaser is included in ISO 4990.

Others, whether or not in ISO 4990, can be used with this specification upon agreement between the manufacturer and purchaser.

## iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 13521:2015 https://standards.iteh.ai/catalog/standards/sist/2cfbce91-cba6-4a55-89bbbd3daa29da9f/iso-13521-2015

## Bibliography

[1] EN 10349:2009, Steel castings — Austenitic manganese steel castings

# iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 13521:2015 https://standards.iteh.ai/catalog/standards/sist/2cfbce91-cba6-4a55-89bbbd3daa29da9f/iso-13521-2015

# iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 13521:2015 https://standards.iteh.ai/catalog/standards/sist/2cfbce91-cba6-4a55-89bbbd3daa29da9f/iso-13521-2015