



Designation: A 759 – 00

## Standard Specification for Carbon Steel Crane Rails<sup>1</sup>

This standard is issued under the fixed designation A 759; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last approval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

### 1. Scope

1.1 This specification covers carbon steel crane rails of special designs only, and nominal weights of 104 lb/yd (51.6 kg/m) through 175 lb/yd (86.8 kg/m) for crane runway use.

1.2 When standard tee rail sections are desired, they shall be ordered in accordance with Specification A 1.

1.3 Supplementary Requirements S1 through S4 of an optional nature are provided. They shall apply only when specified by the purchaser in the order.

1.4 The values stated in inch-pound units are to be regarded as the standard.

### 2. Referenced Documents

#### 2.1 ASTM Standards:

A 1 Specification for Carbon Steel Tee Rails<sup>2</sup>

A 700 Practices for Packaging, Marking, and Loading Methods for Steel Products for Domestic Shipment<sup>3</sup>

2.2 Design details for the special crane rails are indicated in the crane rail catalogs of individual manufacturers, and referred to in the following documents:

American Institute of Steel Construction, Inc. (AISC), Manual of Steel Construction, Seventh Edition, pp. 1–136 and 1–137<sup>4</sup>

Association of Iron and Steel Engineers (AISE), Standard No. 6, May 1, 1969, pp. MD-22 through MD-25<sup>5</sup>

Crane Manufacturers Association, Inc. (CMAA), Specification No. 70, 1971, pp. 20 and 34<sup>6</sup>

### 3. Ordering Information

3.1 Orders for crane rails under this specification shall include the following information as appropriate:

3.1.1 Quantity (tons or pieces),

3.1.2 ASTM designation and year of issue,

3.1.3 Complete identification of section with dimensional drawing if required (see 2.1 and 2.2),

3.1.4 Length of rails or length of runway as required, (see 6.3),

3.1.5 Arrangement of drilled bolt holes with dimensional drawing if required,

3.1.6 Supplementary requirements that shall apply (see S1 through S4), and

3.1.7 Certification and Test Report Requirements (see Section 10).

### 4. Manufacture

4.1 *Melting Practice*:—The steel shall be made by any of the following processes: basic-oxygen or electric-furnace.

4.1.1 The steel may be cast by a continuous process, or in ingots.

4.2 *Discard*:—A sufficient discard shall be made to secure freedom from injurious segregation and piping.

#### 4.3 Control Cooling:

4.3.1 Rails shall be control cooled in accordance with the following procedure, except when produced from vacuum-degassed steel or control cooled blooms, in which case the rails may be air cooled and 4.3.2 through 4.3.6 are not applicable.

4.3.2 All rails shall be cooled on hot beds or runways until full transformation is accomplished, and then charge immediately into the containers. In no case should the rail be charged below 725°F (386°C).

4.3.3 The temperature of the rails before charging shall be determined with reliable equipment at the head of the rail at least 12 in. (305 mm) from the end.

4.3.4 The cover shall be placed on the container immediately after completion of the charge and shall remain in place for at least 10 h. After the removal or raising of the lid of the container, no rails shall be removed until the temperature of the top layer of rails has fallen to 300°F (149°C) or lower.

4.3.5 The temperature between an outside rail and the adjacent rail in the bottom tier of the container at a point not less than 12 in. (305 mm), nor more than 36 in. (914 mm), from the rail end shall be recorded. This temperature shall be the control for judging rate of cooling.

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.01 on Steel Rails and Accessories.

Current edition approved Nov 10, 2000. Published January 2001. Originally published as A 759 – 78. Last previous edition A 759 – 85 (1992).

<sup>2</sup> *Annual Book of ASTM Standards*, Vol 01.04.

<sup>3</sup> *Annual Book of ASTM Standards*, Vol 01.05.

<sup>4</sup> Available from the American Institute of Steel Construction, Inc., 8720 Red Oak Blvd., Ste. 201, Charlotte, NC 28217.

<sup>5</sup> Available from the Association of Iron and Steel Engineers, 3 Gateway Center, Pittsburgh, PA 15222.

<sup>6</sup> Available from the Crane Manufacturers Association of America, Inc., 8720 Red Oak Blvd., Ste. 201, Charlotte, NC 28217.

4.3.6 The container shall be so protected and insulated that the control temperature shall not drop below 300°F (149°C) in 7 h from the time that the bottom tier is placed in the container. If this cooling requirement is not met, the rails shall be considered control cooled provided the temperature at a location not less than 12 in. (305 mm) from the end of a rail at approximately the center of the middle tier does not drop below 300°F (149°C) in less than 15 h.

4.4 *End Hardening*—When specified in accordance with Supplementary Requirement S1, certain section crane rails shall be end hardened.

4.5 *High Strength Rails*—When specified in accordance with Supplementary Requirement S2, all or a portion of the quantity of rails ordered shall be high strength.

4.6 *Chamfering*—When specified in accordance with Supplementary Requirement S3, the ends of rails shall be chamfered.

4.7 *Ends Prepared for Electric Arc Welding*—When rails are to be joined by electric arc welding, special end preparation may be available from individual manufacturers as may be developed in accordance with Supplementary Requirement S4.

## 5. Chemical Requirements

5.1 *Heat or Cast Analysis*—An analysis for each heat or cast of steel shall be made by the manufacturer to determine the percentage of the elements specified in Table 1. The analysis shall be made from a test sample taken preferably during the pouring of the heat or cast and shall conform to the requirements in Table 1.

5.2 When ladle tests are not available, finished material representing the heat may be product tested. The product analysis allowance beyond the limits of the specified ladle analysis shall be within the limits for product analyses specified in Table 2.

## 6. Permissible Variations of Dimension, Weight, and Other Physical Attributes

### 6.1 Section:

6.1.1 The section of the rail shall conform to the design specified by the purchaser.

6.1.2 A variation of  $\frac{1}{32}$  in. (0.8 mm) less or  $\frac{1}{32}$  in. greater than the specified height will be permitted.

6.1.3 A variation of  $\frac{1}{16}$  in. (1.6 mm) in the width of either flange will be permitted for sections other than 175 lb/yd (86.8 kg/m), but the variation in total width of base shall not exceed  $\frac{1}{16}$  in. (1.6 mm). For 175-lb/yd (86.8-kg/m) sections a variation of  $\frac{3}{32}$  in. (2.4 mm) in the width of either flange will be permitted but the variation in total width of base shall not exceed  $\frac{3}{32}$  in.

6.2 *Weight*—A variation of 1 % from the calculated weight of section as applied to the entire order will be permitted.

**TABLE 1 Chemical Requirements, %**

Carbon	0.67 to 0.84
Manganese	0.70 to 1.10
Phosphorus, max	0.04
Sulfur, max	0.05
Silicon	0.10 to 0.50

**TABLE 2 Product Analysis Allowance Beyond Limits of Specified Chemical Analysis**

	Under Minimum Limit, %	Over Maximum Limit, %
Carbon	0.04	0.04
Manganese	0.06	0.06
Phosphorus	...	0.008
Sulfur	...	0.008
Silicon	0.02	0.02 <sup>A</sup>

<sup>A</sup> Continuously cast allowances shall be 0.05 % over maximum limit for silicon.

### 6.3 Length:

6.3.1 The standard length of rail shall be 80 ft (24.4 m) or 39 ft (11.9 m) when measured at a temperature of 60°F (15.5°C).

6.3.2 Up to 9% for 39 ft rail or 15% for 80 ft rail of the entire order will be accepted in lengths shorter than standard varying by 1 ft (0.3 M) as follows: 79, 78, 77, 75, 70, 65, 60, 39, 38, 37, 36, 33, 30, 27, and 25 ft.

6.3.3 Special cut lengths to complete an overall runway length may be specified.

6.3.4 A variation of  $\frac{7}{16}$  in. (11.1 mm) for 39 ft rails or  $\frac{7}{8}$  in. (22 mm) for 80 ft rails from the specified length of individual rails will be permitted.

### 6.4 End Finish:

6.4.1 Rails shall be milled, abrasive wheel cut, or ground to length, with a variation in end squareness of not more than  $\frac{1}{32}$  in. (0.8 mm) allowed.

6.4.2 Harmful burrs on the ends shall be removed.

### 6.5 Drilling:

6.5.1 Circular holes for joint bolts, when specified, shall be drilled to conform to the specified drawings and dimensions.

6.5.2 A variation of  $\frac{1}{16}$  in. (1.6 mm) over and nothing under in the size of the bolt holes shall be permitted.

6.5.3 A variation of  $\frac{1}{32}$  in. (0.8 mm) in the location of the holes will be permitted.

## 7. Workmanship, Finish, and Appearance

7.1 All rails shall have a workmanlike finish and be free of various imperfections that may detrimentally affect their suitability for the service for which they are intended.

7.2 Rails shall be straightened cold in a press or roller machine to be commercially straight, as determined by visual inspection.

7.3 Deviations in the vertical and horizontal alignment throughout the length of the rail shall be uniform. Sharp deviations in either direction shall not be acceptable.

7.4 Deviations of the lateral (horizontal) line in either direction at the rail ends shall not exceed a maximum ordinate of 0.040 in. (1 mm) in 3 ft (0.9 m).

7.5 All ordinate determinations shall be made on the concave side, between the rail surface and the straightedge.

7.6 Rails presented for inspection that do not conform to the requirements of 7.1 through 7.4 may be reconditioned by the manufacturer.

## 8. Inspection

8.1 The manufacturer shall afford the purchaser's inspector all reasonable facilities necessary to satisfy that the material is