

---

**Aeronavtika - Električni kabli za splošno uporabo - Delovne temperature med  $-55^{\circ}\text{C}$  in  $200^{\circ}\text{C}$  - 008. del: Družina DRP (dvožilni), DRT (trižilni), DRQ (štirižilni), večžilni, oplaščeni, z možnostjo UV-laserskega tiskanja**

Aerospace series - Cables, electrical, for general purpose - Operating temperatures between  $-55^{\circ}\text{C}$  and  $200^{\circ}\text{C}$  - Part 008: DRP (pair) DRT (3 cores) DRQ (4 cores) family, multicore UV laser printable jacketed cable - Product standard

Luft- und Raumfahrt - Leitungen, elektrisch, für allgemeine Verwendung - Betriebstemperaturen zwischen  $-55^{\circ}\text{C}$  und  $200^{\circ}\text{C}$  - Teil 008: DRP- (zweiadrig), DRT- (dreiadrig), DRQ- (vieradrig) Leitungsfamilie, mehradrige, UV-Laser-bedruckbare, ummantelte Leitungen - Produktnorm **SIST EN 2266-008:2015**

<https://standards.iteh.ai/catalog/standards/sist/5be1f515-c4e3-4735-847f-1663f264a21f/sist-en-2266-008-2015>

Série aérospatiale - Câbles, électriques, d'usage général - Températures de fonctionnement comprises entre  $-55^{\circ}\text{C}$  et  $200^{\circ}\text{C}$  - Partie 008: DRP (paire) DRT (tierce) DRQ (quarte) multiconducteurs gainés marquables au laser UV - Norme de produit

**Ta slovenski standard je istoveten z: EN 2266-008:2015**

---

**ICS:**

29.060.20	Kabli	Cables
49.060	Letalska in vesoljska električna oprema in sistemi	Aerospace electric equipment and systems

**SIST EN 2266-008:2015**

**en,fr,de**

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[SIST EN 2266-008:2015](#)

<https://standards.iteh.ai/catalog/standards/sist/5be1f515-c4e3-4735-847f-1663f264a21f/sist-en-2266-008-2015>

EUROPEAN STANDARD

EN 2266-008

NORME EUROPÉENNE

EUROPÄISCHE NORM

July 2015

ICS 49.060

English Version

**Aerospace series - Cables, electrical, for general purpose -  
Operating temperatures between -55 °C and 200 °C - Part 008:  
DRP (pair) DRT (3 cores) DRQ (4 cores) family, multicore UV  
laser printable jacketed cable - Product standard**

Série aérospatiale - Câbles, électriques, d'usage général -  
Températures de fonctionnement comprises entre -55 °C et  
200 °C - Partie 008: DRP (paire) DRT (tierce) DRQ (quarte)  
multiconducteurs gainés marquables au laser UV - Norme  
de produit

Luft- und Raumfahrt - Leitungen, elektrisch, für allgemeine  
Verwendung - Betriebstemperaturen zwischen -55 °C und  
200 °C - Teil 008: DRP- (zweiadrig), DRT- (dreiadrig), DRQ-  
(vieradrig) Leitungsfamilie, mehradrige, UV-Laser-  
bedruckbare, ummantelte Leitungen - Produktnorm

This European Standard was approved by CEN on 7 February 2015.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels**

## Contents

	Page
European foreword .....	3
1 Scope .....	4
2 Normative references .....	4
3 Terms, definitions and symbols .....	5
4 Materials and construction .....	5
5 Required characteristics .....	7
6 Quality assurance .....	8
7 Designation .....	9
8 Identification and marking .....	9
9 Packaging, labelling and delivery lengths .....	9
10 Technical specification .....	9

## iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN 2266-008:2015](https://standards.iteh.ai/catalog/standards/sist/5be1f515-c4e3-4735-847f-1663f264a21f/sist-en-2266-008-2015)

<https://standards.iteh.ai/catalog/standards/sist/5be1f515-c4e3-4735-847f-1663f264a21f/sist-en-2266-008-2015>

## European foreword

This document (EN 2266-008:2015) has been prepared by the Aerospace and Defence Industries Association of Europe - Standardization (ASD-STAN).

After enquiries and votes carried out in accordance with the rules of this Association, this European Standard has received the approval of the National Associations and the Official Services of the member countries of ASD, prior to its presentation to CEN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by January 2016, and conflicting national standards shall be withdrawn at the latest by January 2016.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[SIST EN 2266-008:2015](https://standards.iteh.ai/catalog/standards/sist/5be1f515-c4e3-4735-847f-1663f264a21f/sist-en-2266-008-2015)

<https://standards.iteh.ai/catalog/standards/sist/5be1f515-c4e3-4735-847f-1663f264a21f/sist-en-2266-008-2015>

**EN 2266-008:2015 (E)****1 Scope**

This European Standard specifies the characteristics of UV laser printable multicore jacketed electrical cables for use in the on-board electrical systems of aircraft at operating temperatures between  $-55\text{ °C}$  and  $200\text{ °C}$ .

It shall also be possible to mark these cables by qualified compatible marking. These markings shall be in accordance with EN 3838.

**2 Normative references**

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 2083, *Aerospace series — Copper and copper alloys conductors for electrical cables — Product standard*

EN 2235, *Aerospace series — Single and multicore electrical cables, screened and jacketed*

EN 2267-002, *Aerospace series — Cables, electrical, for general purpose — Operating temperatures between  $-55\text{ °C}$  and  $260\text{ °C}$  — Part 002: General*

EN 2267-009, *Aerospace series — Cables, electrical, for general purpose — Operating temperatures between  $-55\text{ °C}$  and  $260\text{ °C}$  — Part 009: DRA family, single and multicore assembly — Product standard*

EN 3475-100, *Aerospace series — Cables, electrical, aircraft use — Test methods — Part 100: General*

EN 3475-201, *Aerospace series — Cables, electrical, aircraft use — Test methods — Part 201: Visual examination*

EN 3475-202, *Aerospace series — Cables, electrical, aircraft use — Test methods — Part 202: Mass*

EN 3475-203, *Aerospace series — Cables, electrical, aircraft use — Test methods — Part 203: Dimensions*

EN 3475-301, *Aerospace series — Cables, electrical, aircraft use — Test methods — Part 301: Ohmic resistance per unit length*

EN 3475-302, *Aerospace series — Cable, electrical, aircraft use — Test methods — Part 302: Voltage proof test*

EN 3475-303, *Aerospace series — Cables, electrical, aircraft use — Test methods — Part 303: Insulation resistance*

EN 3475-304, *Aerospace series — Cables, electrical, aircraft use — Test methods — Part 304: Surface resistance*

EN 3475-306, *Aerospace series — Cables, electrical, aircraft use — Test methods — Part 306: Continuity of conductors*

EN 3475-401, *Aerospace series — Cables, electrical, aircraft use — Test Methods — Part 401: Accelerated ageing*

EN 3475-402, *Aerospace series — Cables, electrical, aircraft use — Test methods — Part 402: Shrinkage and delamination*

EN 3475-403, *Aerospace series — Cables, electrical, aircraft use — Test methods — Part 403: Delamination and blocking*

EN 3475-404, *Aerospace series — Cables, electrical, aircraft use — Test methods — Part 404: Thermal shock*

EN 3475-405, *Aerospace series — Cables, electrical, aircraft use — Test methods — Part 405: Bending at ambient temperature*

- EN 3475-406, *Aerospace series — Cables, electrical, aircraft use — Test methods — Part 406: Cold bend test*
- EN 3475-407, *Aerospace series — Cables, electrical, aircraft use — Test methods — Part 407 : Flammability*
- EN 3475-411, *Aerospace series — Cables, electrical, aircraft use — Test methods — Part 411: Resistance to fluids*
- EN 3475-412, *Aerospace series — Cables, electrical, aircraft use — Test methods — Part 412: Humidity resistance*
- EN 3475-505, *Aerospace series — Cables, electrical, aircraft use — Test methods — Part 505: Tensile test on conductors and strands*
- EN 3475-506, *Aerospace series — Cables, electrical, aircraft use — Test methods — Part 506: Plating continuity*
- EN 3475-507, *Aerospace series — Cables, electrical, aircraft use — Test methods — Part 507: Adherence of plating*
- EN 3475-508, *Aerospace series — Cables, electrical, aircraft use — Test methods — Part 508: Plating thickness*
- EN 3475-601, *Aerospace series — Cables, electrical, aircraft use — Test methods — Part 601: Smoke density*
- EN 3475-602, *Aerospace series — Cables, electrical, aircraft use — Test methods — Part 602: Toxicity*
- EN 3475-701, *Aerospace series — Cables, electrical, aircraft use — Test methods — Part 701: Strippability and adherence of insulation to the conductor*
- EN 3475-703, *Aerospace series — Cables, electrical, aircraft use — Test methods — Part 703: Permanence of manufacturer's marking*
- EN 3475-705, *Aerospace series — Cables, electrical, aircraft use — Test methods — Part 705: Contrast measurement*
- EN 3475-706, *Aerospace series — Cables, electrical, aircraft use — Test methods — Part 706: Laser markability*
- EN 3838, *Aerospace series — Requirements and tests on user-applied markings on aircraft electrical cables*
- EN 4434, *Aerospace series — Copper or copper alloy lightweight conductors for electrical cables — Product standard (Normal and tight tolerances)*
- EN 9133, *Aerospace series — Quality management systems — Qualification procedure for aerospace standard parts*

### 3 Terms, definitions and symbols

For the purposes of this document, the terms, definitions and symbols given in EN 3475-100 apply.

### 4 Materials and construction

#### 4.1 Materials

These cables shall consist of the following:

- cores according to EN 2267-009,
- number of cores 2 to 4.

## EN 2266-008:2015 (E)

2 to 4 core cables shall be twisted together according to EN 2235.

Outer jacket:

— shall be defined to satisfy all required characteristics of Clause 5.

## 4.2 Construction

See EN 4434, EN 2083 and Table 1.

Table 1

Number of cores	Code for nominal section	Nominal section	AWG <sup>a</sup>	Linear resistance at 20 °C	External diameter	Mass
		mm <sup>2</sup>		Ω/km max.		
2	001	0,15	26	165	1,86	5,01
	002	0,25	24	117	2,10	6,54
	004	0,4	22	61,7	2,39	9,47
	006	0,6	20	34,1	2,91	15,28
	010	1	18	21,7	3,44	22,90
	012	1,2	16	14,9	4,02	31,78
	020	2	14	11,2	4,67	42,61
3	001	0,15	26	165	1,99	7,28
	002	0,25	24	117	2,24	9,50
	004	0,4	22	61,7	2,55	13,91
	006	0,6	20	34,1	3,12	22,55
	010	1	18	21,7	3,68	33,91
	012	1,2	16	14,9	4,30	47,15
	020	2	14	11,2	5,01	63,34
	030	3	12	6,99	5,98	99,57
4	001	0,15	26	165	2,22	9,56
	002	0,25	24	117	2,49	12,48
	004	0,4	22	61,7	2,87	18,34
	006	0,6	20	34,1	3,50	29,82
	010	1	18	21,7	4,15	44,92
	012	1,2	16	14,9	4,80	62,52
	020	2	14	11,2	5,48	84,06

<sup>a</sup> AWG = Closest American Wire Gage.



### 4.3 Colours coding of cores

See EN 2267-002.

See EN 2235, 4.3.2 for cabling.

## 5 Required characteristics

Tests according to EN 3475-100.

See Table 2.

Table 2 (1 of 2)

EN 3475-	Designation of the test	Details
201	Visual examination	Applicable
202	Mass	Applicable, see Table 1.
203	Dimensions	Applicable, see Table 1.
301	Ohmic resistance per unit length	Applicable, see Table 1.
302	Voltage proof test	Applicable
303	Insulation resistance	Applicable
304	Surface resistance	Applicable
305	Overload resistance	Not applicable
306	Continuity of conductors	Applicable
401	Accelerated ageing	Applicable Temperature (250 ± 5) °C
402	Shrinkage and delamination	Applicable Temperature (250 ± 5) °C Maximum shrinkage at each end of cable: — for jacket: not applicable, — for core insulation: see EN 2267-009.
403	Delamination and blocking	Applicable Temperature (250 ± 5) °C
404	Thermal shock	Applicable Temperature (250 ± 5) °C Maximum shrinkage at each end of cable: — for jacket: not applicable, — for core insulation: see EN 2267-009.
405	Bending at ambient temperature	Applicable
406	Cold bend test	Applicable
407	Flammability	Applicable Extinguishing time: max. 3 s