



SLOVENSKI STANDARD
SIST EN 62788-1-2:2016

01-september-2016

**Merilni postopki za materiale, uporabljene v fotonapetostnih modulih - 1-2. del:
Enkapsulanti - Merjenje prostorninske upornosti fotonapetostnih enkapsulacij in
materialov nosilne plasti**

Measurement procedures for materials used in photovoltaic modules - Part 1-2:
Encapsulants - Measurement of volume resistivity of photovoltaic encapsulation and
backsheet materials

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN 62788-1-2:2016](https://standards.iteh.ai/catalog/standards/sist/89e3ecb2-cdbf-4005-b91e-510091e12f42/sist-en-62788-1-2-2016)

[https://standards.iteh.ai/catalog/standards/sist/89e3ecb2-cdbf-4005-b91e-
510091e12f42/sist-en-62788-1-2-2016](https://standards.iteh.ai/catalog/standards/sist/89e3ecb2-cdbf-4005-b91e-510091e12f42/sist-en-62788-1-2-2016)

Ta slovenski standard je istoveten z: EN 62788-1-2:2016

ICS:

27.160

Sončna energija

Solar energy engineering

SIST EN 62788-1-2:2016

en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 62788-1-2:2016

<https://standards.iteh.ai/catalog/standards/sist/89e3ecb2-cdbf-4005-b91e-510091e12f42/sist-en-62788-1-2-2016>

EUROPEAN STANDARD

EN 62788-1-2

NORME EUROPÉENNE

EUROPÄISCHE NORM

June 2016

ICS 27.160

English Version

Measurement procedures for materials used in photovoltaic modules - Part 1-2: Encapsulants - Measurement of volume resistivity of photovoltaic encapsulants and other polymeric materials
(IEC 62788-1-2:2016)

Procédures de mesure des matériaux utilisés dans les modules photovoltaïques - Partie 1-2: Encapsulants - Mesurage de la résistivité transversale des encapsulants photovoltaïques et autres matériaux polymères
(IEC 62788-1-2:2016)

Messverfahren für Werkstoffe, die in Photovoltaikmodulen verwendet werden - Teil 1-2: Verkapselungsstoffe - Messung des spezifischen Durchgangswiderstandes von Verkapselungsstoffen und Rückseitenfolien von Photovoltaikmodulen
(IEC 62788-1-2:2016)

iTeh STANDARD PREVIEW
(standards.iteh.ai)

This European Standard was approved by CENELEC on 2016-06-16. CENELEC members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CENELEC member [SIST EN 62788-1-2:2016](https://standards.iteh.ai/catalog/standards/sist/89e3ecb2-cdbf-4005-b91e-62788-1-2)

<https://standards.iteh.ai/catalog/standards/sist/89e3ecb2-cdbf-4005-b91e-62788-1-2>

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CENELEC member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CENELEC members are the national electrotechnical committees of Austria, Belgium, Bulgaria, Croatia, Cyprus, the Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, the Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.



European Committee for Electrotechnical Standardization
Comité Européen de Normalisation Electrotechnique
Europäisches Komitee für Elektrotechnische Normung

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

EN 62788-1-2:2016**European foreword**

The text of document 82/1085/FDIS, future edition 1 of IEC 62788-1-2, prepared by IEC/TC 82 "Solar photovoltaic energy systems" was submitted to the IEC-CENELEC parallel vote and approved by CENELEC as EN 62788-1-2:2016.

The following dates are fixed:

- latest date by which the document has to be implemented at national level by publication of an identical national standard or by endorsement (dop) 2017-03-16
- latest date by which the national standards conflicting with the document have to be withdrawn (dow) 2019-06-16

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CENELEC [and/or CEN] shall not be held responsible for identifying any or all such patent rights.

Endorsement notice

The text of the International Standard IEC 62788-1-2:2016 was approved by CENELEC as a European Standard without any modification.

ITEH STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN 62788-1-2:2016](https://standards.iteh.ai/catalog/standards/sist/89e3ecb2-cdbf-4005-b91e-510091e12f42/sist-en-62788-1-2-2016)

<https://standards.iteh.ai/catalog/standards/sist/89e3ecb2-cdbf-4005-b91e-510091e12f42/sist-en-62788-1-2-2016>

Annex ZA (normative)

Normative references to international publications with their corresponding European publications

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

NOTE 1 When an International Publication has been modified by common modifications, indicated by (mod), the relevant EN/HD applies.

NOTE 2 Up-to-date information on the latest versions of the European Standards listed in this annex is available here: www.cenelec.eu.

<u>Publication</u>	<u>Year</u>	<u>Title</u>	<u>EN/HD</u>	<u>Year</u>
IEC 61340-2-3	2000	Electrostatics -- Part 2-3: Methods of test for determining the resistance and resistivity of solid planar materials used to avoid electrostatic charge accumulation	EN 61340-2-3	2000
IEC 62631-3-2	2015	Dielectric and resistive properties of solid insulating materials - Part 3-2 Determination of resistive properties (DC Methods) - Surface resistance and surface resistivity	EN 62631-3-2	2016
ISO/IEC 17025	-	General requirements for the competence of testing and calibration laboratories	-	-
ASTM D 257-14	-	Standard Test Methods for DC Resistance or Conductance of Insulating Materials	-	-

ITeH STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN 62788-1-2:2016](https://standards.iteh.ai/catalog/standards/sist/89e3ecb2-cdbf-4005-b91e-510091e12f42/sist-en-62788-1-2-2016)

<https://standards.iteh.ai/catalog/standards/sist/89e3ecb2-cdbf-4005-b91e-510091e12f42/sist-en-62788-1-2-2016>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 62788-1-2:2016

<https://standards.iteh.ai/catalog/standards/sist/89e3ecb2-cdbf-4005-b91e-510091e12f42/sist-en-62788-1-2-2016>



IEC 62788-1-2

Edition 1.0 2016-05

INTERNATIONAL STANDARD

NORME INTERNATIONALE

**Measurement procedures for materials used in photovoltaic modules –
Part 1-2: Encapsulants – Measurement of volume resistivity of photovoltaic
encapsulants and other polymeric materials**

**Procédures de mesure des matériaux utilisés dans les modules
photovoltaïques –
Partie 1-2: Encapsulants – Mesurage de la résistivité transversale des
encapsulants photovoltaïques et autres matériaux polymères**

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

COMMISSION
ELECTROTECHNIQUE
INTERNATIONALE

ICS 27.160

ISBN 978-2-8322-3349-8

**Warning! Make sure that you obtained this publication from an authorized distributor.
Attention! Veuillez vous assurer que vous avez obtenu cette publication via un distributeur agréé.**

CONTENTS

FOREWORD.....	3
1 Scope.....	5
2 Normative references.....	6
3 Sampling.....	6
4 Apparatus.....	6
5 Procedure.....	7
5.1 Preconditioning.....	7
5.2 Test conditions.....	8
5.2.1 Room temperature.....	8
5.2.2 Elevated temperatures.....	8
5.3 Measurement voltage.....	8
5.3.1 Method A voltage.....	8
5.3.2 Method B voltage.....	9
5.4 Measurement cycle.....	9
5.4.1 Method A cycle.....	9
5.4.2 Method B cycle.....	9
5.5 Results.....	9
6 Test report.....	10
Annex A (informative) Historical studies of the volume resistivity of encapsulation materials.....	12
Annex B (informative) Example data.....	13
Bibliography.....	14
Figure 1 – Schematic of electrode apparatus for resistivity measurements.....	7
Figure B.1 – Example data showing current and voltage as a function of time for Method A measurement.....	13
Table B.1 – End of cycle current measurements and values used for calculation of volume resistivity according to Method A.....	13

INTERNATIONAL ELECTROTECHNICAL COMMISSION

**MEASUREMENT PROCEDURES FOR MATERIALS
USED IN PHOTOVOLTAIC MODULES –**
**Part 1-2: Encapsulants –
Measurement of volume resistivity of
photovoltaic encapsulants and other polymeric materials**
FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 62788-1-2 has been prepared by IEC technical committee 82: Solar photovoltaic energy systems.

The text of this standard is based on the following documents:

FDIS	Report on voting
82/1085/FDIS	82/1105/RVD

Full information on the voting for the approval of this standard can be found in the report on voting indicated in the above table.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all parts in the IEC 62788 series, published under the general title *Measurement procedures for materials used in photovoltaic modules*, can be found on the IEC website.

The committee has decided that the contents of this publication will remain unchanged until the stability date indicated on the IEC website under "<http://webstore.iec.ch>" in the data related to the specific publication. At this date, the publication will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN 62788-1-2:2016](https://standards.iteh.ai/catalog/standards/sist/89e3ecb2-cdbf-4005-b91e-510091e12f42/sist-en-62788-1-2-2016)

<https://standards.iteh.ai/catalog/standards/sist/89e3ecb2-cdbf-4005-b91e-510091e12f42/sist-en-62788-1-2-2016>

MEASUREMENT PROCEDURES FOR MATERIALS USED IN PHOTOVOLTAIC MODULES –

Part 1-2: Encapsulants – Measurement of volume resistivity of photovoltaic encapsulants and other polymeric materials

1 Scope

This part of IEC 62788 provides a method and guidelines for measuring the volume resistivity of materials used as encapsulation, edge seals, front-sheets, backsheets, or any other insulating material in a photovoltaic (PV) module. The test is performed on dry, humid or wet preconditioned samples. In the case of frontsheets and backsheets comprised of multiple layers, the measured resistivity is an effective value. This test is designed for room temperature measurement, but can also be utilized at higher temperatures.

Degradation of PV modules is known to occur in part by electrochemical corrosion, and other potential induced degradation processes. These processes may be dependent upon the resistivity of a polymeric component. Therefore, the DC resistivity of polymeric components is relevant to module design and durability in the field. The resistivity may depend on cure state, temperature, water content, and voltage history. A number of options are included to allow the measurement to be performed in a manner consistent with representative fielded module conditions.

Most resistivity measurement methods and equipment typically become inaccurate and variable for materials with volume resistivity above $10^{16} \Omega \cdot \text{cm}$ [5]. Therefore, this standard is used for measurements less than $10^{17} \Omega \cdot \text{cm}$.

Both monolithic and multilayer materials (e.g. frontsheets and backsheets) are suitable for measurement. Methods are described for room temperature measurement, with guidelines included for testing at elevated temperatures.

Results will vary with moisture content, therefore materials should be tested in a manner anticipatory of usage. Preconditioning procedures for dry, humid and wet environments are included.

Depending on the material, voltage history will affect the measured result. The rate of change of current, and time to equilibrium varies with material often taking hours or days to come to a static level. For this reason, long and short duration methods are included (Methods A and B). The specified short-duration alternating polarity Method B is intended for qualitative comparison. Method A, long-duration on/off polarity, is recommended for characterization with regard to PID resistance.

Measurements obtained using either method may be used by material manufacturers for the purpose of quality control of their electrical insulating material as well as for reporting in product datasheets. PV module manufacturers may use these methods for the purpose of material acceptance, material selection, process development, design analysis, or failure analysis.

¹ Numbers in square brackets refer to the Bibliography.