



Designation: ~~F468-05a~~ Designation: F 468 - 06^{ε1}

Standard Specification for Nonferrous Bolts, Hex Cap Screws, and Studs for General Use¹

This standard is issued under the fixed designation F 468; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

^{ε1} NOTE—Table 1, Nickel and Nickel-Base Alloys was editorially corrected in February 2008.

1. Scope*

1.1 This specification covers the requirements for commercial wrought nonferrous bolts, hex cap screws, and studs 0.250 to 1.500 in. inclusive in diameter manufactured from a number of alloys in common use and intended for general service applications.

1.2 Applicable nuts for use with bolts, cap screws, and studs covered by this specification are covered by Specification F 467.

NOTE 1—A complete metric companion to Specification F 468 has been developed—F 468M; therefore no metric equivalents are presented in this specification.

2. Referenced Documents

2.1 ASTM Standards:²

B 154 Test Method for Mercurous Nitrate Test for Copper and Copper Alloys

B 193 Test Method for Resistivity of Electrical Conductor Materials

B 211 Specification for Aluminum and Aluminum-Alloy Bar, Rod, and Wire

B 565 Test Method for Shear Testing of Aluminum and Aluminum-Alloy Rivets and Cold-Heading Wire and Rods

B 574 Specification for Low-Carbon Nickel-Chromium-Molybdenum, Low-Carbon Nickel-Molybdenum-Chromium-Tantalum, Low-Carbon Nickel-Chromium-Molybdenum-Copper, and Low-Carbon Nickel-Chromium-Molybdenum-Tungsten Alloy Rod

D 3951 Practice for Commercial Packaging

E 8 Test Methods for Tension Testing of Metallic Materials

~~E 18 Test Methods for Rockwell Hardness and Rockwell Superficial Hardness of Metallic Materials~~ Test Methods for Rockwell Hardness of Metallic Materials

E 29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications ~~stm-f468-06e1~~

E 34 Test Methods for Chemical Analysis of Aluminum and Aluminum-Base Alloys

E 38 Methods for Chemical Analysis of Nickel-Chromium and Nickel-Chromium-Iron Alloys³

~~E 53 Test Methods~~ Method for Determination of Copper in Unalloyed Copper by Gravimetry

E 54 Test Methods for Chemical Analysis of Special Brasses and Bronzes

E 55 Practice for Sampling Wrought Nonferrous Metals and Alloys for Determination of Chemical Composition

E 62 Test Methods for Chemical Analysis of Copper and Copper Alloys (Photometric Methods)

E 75 Test Methods for Chemical Analysis of Copper-Nickel and Copper-Nickel-Zinc Alloys

E 76 Test Methods for Chemical Analysis of Nickel-Copper Alloys

E 92 Test Method for Vickers Hardness of Metallic Materials

E 101 Test Method for Spectrographic Analysis of Aluminum and Aluminum Alloys by the Point-to-Plane Technique⁰

E 120 Test Methods for Chemical Analysis of Titanium and Titanium Alloys

~~E 165 Practice for Liquid Penetrant Examination~~ Test Method for Liquid Penetrant Examination

E 227 Test Method for Optical Emission Spectrometric Analysis of Aluminum and Aluminum Alloys by the Point-to-Plane Technique

¹ This specification is under the jurisdiction of ASTM Committee F16 on Fasteners and is the direct responsibility of Subcommittee F16.04 on Nonferrous Fasteners. Current edition approved Nov./May 1, 2005-2006. Published November 2005/May 2006. Originally approved in 1976. Last previous edition approved in 2005 as F 468 - 05a.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Withdrawn.

*A Summary of Changes section appears at the end of this standard.

E 354 Test Methods for Chemical Analysis of High-Temperature, Electrical, Magnetic, and Other Similar Iron, Nickel, and Cobalt Alloys

E 478 Test Methods for Chemical Analysis of Copper Alloys

E 1409 Test Method for Determination of Oxygen and Nitrogen in Titanium and Titanium Alloys by the Inert Gas Fusion Technique

F 467 Specification for Nonferrous Nuts for General Use

F 606 Test Methods for Determining the Mechanical Properties of Externally and Internally Threaded Fasteners, Washers, Direct Tension Indicators, and Rivets

F 1470 Guide for Fastener Sampling for Specified Mechanical Properties and Performance Inspection

2.2 *ASME Standards*:⁴

ASME B1.1 Unified Inch Screw Threads (UN and UNR Thread Form)

ASME B18.2.1 Square and Hex Bolts and Screws, Including Hex Cap Screws

ASME H35.1 Alloy and Temper Designation Systems for Aluminum

3. Ordering Information

3.1 Orders for fasteners under this specification shall include the following information:

3.1.1 Quantity (number of pieces of each item and size),

3.1.2 Name of item. For silicon bronze alloy 651, state if hex cap screw dimensions or roll thread body diameter are required (see 7.1.2);

3.1.3 Size (diameter, threads per inch, length);

3.1.4 Alloy number (Table 1). For Ti5, state Class A or Class B (Table 1, 6.5, and 6.5.1);

3.1.5 Stress relieving, if required (see 4.2.3);

3.1.6 Shipment lot testing, as required (see Section 10);

3.1.7 Source inspection, if required (see Section 14);

3.1.8 Certificate of compliance or test report, if required (see Section 16);

3.1.9 Additional requirements, if any, to be specified on the purchase order (see 4.2.1, 4.2.4, 7.3.1, 8.2, 11.1, and 12.1);

3.1.10 Supplementary Requirements, if any; and

3.1.11 ASTM designation and date of issue.

NOTE 2— *Example*

10 000 pieces, Hex Cap Screw, 0.250 in.-20 × 3.00 in., Alloy 270. Furnish Certificate of Compliance, Supplementary Requirement S1, ASTM F 468-XX.

4. Materials and Manufacture

4.1 *Materials*:

4.1.1 The bolts, cap screws, and studs shall be manufactured from material having a chemical composition conforming to the requirements in Table 1 and capable of developing the required mechanical properties for the specified alloy in the finished fastener. See Specification B 574 for nickel alloys.

4.1.2 The starting condition of the raw material shall be at the discretion of the fastener manufacturer but shall be such that the finished products conform to all of the specified requirements.

4.2 *Manufacture*:

4.2.1 *Forming*—Unless otherwise specified, the fasteners shall be cold formed, hot formed, or machined from suitable material, at the option of the manufacturer.

4.2.2 *Condition*—Except as provided in 4.2.3, the fasteners shall be furnished in the following conditions:

Alloy	Condition
Copper (all alloys)	As formed or stress relieved at manufacturer's option
Nickel alloys: 400 and 405	As formed or stress relieved at manufacturer's option
500	Solution annealed and aged
625	Annealed
Aluminum alloys: 2024-T4	Solution treated and naturally aged
6061-T6	Solution treated and artificially aged
7075-T73	Solution treated and stabilized
Titanium	As formed

4.2.3 *Stress Relieving*—When required, stress relieving shall be specified by the purchaser for nickel alloys 400 and 405 and all copper alloys.

⁴ Available from Global Engineering Documents, 15 Inverness Way, East Englewood, CO 80112-5704.

4.2.4 *Threads*—Unless otherwise specified, the threads shall be rolled or cut at the option of the manufacturer.

5. Chemical Composition

5.1 *Chemical Composition*—The fasteners shall conform to the requirements as to chemical composition prescribed in Table 1 for the specified alloy.

5.2 *Manufacturer's Analysis:*

5.2.1 When test reports are required on the inquiry or purchase order (see 3.1.8), the manufacturer shall make individual analyses of randomly selected finished fasteners from the product to be shipped and report the results to the purchaser, except as provided in 5.2.2. Alternatively, if heat and lot identities have been maintained, the analysis of the raw material from which the fasteners have been manufactured may be reported instead of product analysis.

5.2.2 For aluminum fasteners, the manufacturer may furnish instead a certificate of conformance certifying compliance with the chemical composition specified in Table 1.

5.3 *Product Analysis:*

5.3.1 Product analyses may be made by the purchaser from finished products representing each lot. The chemical composition thus determined shall conform to the requirements in Table 1.

5.3.2 In the event of disagreement, a referee chemical analysis of samples from each lot shall be made in accordance with 11.1 and 12.1.

iTeh Standards (<https://standards.iteh.ai>) Document Preview

[ASTM F468-06e1](#)

<https://standards.iteh.ai/catalog/standards/sist/099e676f-e157-4d1d-bd70-0996b2dbe8e3/astm-f468-06e1>

TABLE 1 Chemical Requirements

UNS Designation Number	Alloy	General Name	Composition, %														
			Aluminum	Copper, min	Iron, max	Manganese, max	Nickel, max	Phosphorus	Silicon	Zinc, max ^A	Lead, max	Tin	Arsenic, max				
C11000	110	ETP copper	...	99.9
C26000	260	brass	...	68.5-71.5	0.05	balance	0.07
C27000	270	brass	...	63.0-68.5	0.07	balance	0.10
C46200	462	naval brass	...	62.0-65.0	0.10	balance	0.20	0.5-1.0
C46400	464	naval brass	...	59.0-62.0	0.10	balance	0.20	0.5-1.0
C51000	510	phosphor bronze	...	balance ^A	0.10	0.03-0.35	0.30	0.05	4.2-5.8
C61300	613	aluminum bronze	...	6.0-7.5	2.0-3.0	0.10	...	0.15 ^C	...	0.015	...	0.10	0.05	0.01	0.20-0.50
C61400	614	aluminum bronze	...	6.0-8.0	1.5-3.5	1.0
C63000	630	aluminum bronze	...	9.0-11.0	2.0-4.0	1.5	...	4.0-5.5	0.20 max
C64200	642	aluminum silicon bronze	...	6.3-7.6	0.30	0.10	...	0.25	0.50	0.05	0.20 max
C65100	651	silicon bronze	0.8	0.7	1.5	0.05
C65500	655	silicon bronze	0.8	1.5	...	0.6	1.5	0.05
C66100	661	silicon bronze	...	0.25 max	0.25	0.05-0.5	1.5	0.05
C67500	675	manganese bronze	0.8-2.0	1.00	...	19.0-23.0 ^C	balance	0.20	0.5-1.5
C71000	710	cupro-nickel	0.60	1.00	1.00	0.05
C71500	715	cupro-nickel	0.40-0.7	1.00	...	29.0-33.0 ^C	1.00	0.05

^A Elements shown as balance shall be arithmetically computed by deducting the sum of the other named elements from 100.

^B Copper plus specified elements = 99.8 min; copper plus silver = 88.5-91.5.

^C Cobalt is to be counted as nickel.

^D Minimum content of copper plus all other elements with specified limits shall be 99.5 %.

^E An alloy containing as high as 2.6 % silicon is acceptable provided the sum of all the elements other than copper, silicon, and iron does not exceed 0.30 %.

TABLE 1 Continued

Nickel and Nickel-Base Alloys																		
UNS Designation Number	Alloy	General Name	Aluminum	Carbon, max	Chromium	Copper ^A	Iron, max	Manganese, max	Nickel ^A	Phosphorus, max	Silicon, max	Titanium	Cobalt, max	Molybdenum	Sulfur, max	Vanadium	Tungsten	Niobium [†]
N10001	335	Ni-Mo	...	0.05	1.0 max	...	4.0–6.0	1.0	balance	0.025	1.00	...	2.50	26.0–30.0	0.030	0.2–0.4
N10276	276	Ni-Mo-Cr	...	0.02	14.5–16.5	...	4.0–7.0	1.00	balance	0.040	0.08	...	2.50	15.0–17.0	0.030	0.35 max	3.0–4.5	...
N04400	400	Ni-Cu Class A	...	0.3	...	balance	2.5	2.0	63.0–70.0	...	0.5	...	^B	...	0.024
N04405	405	Ni-Cu Class B	...	0.3	...	balance	2.5	2.0	63.0–70.0	...	0.5	...	^B	...	0.025–0.060
N05500	500	Ni-Cu-Al	2.30–3.15	0.25	...	balance	2.0	1.5	63.0–70.0	...	0.5	0.35–0.85	0.3	...	0.01
N06059	59	Ni-Cr-Mo	0.1–0.4	0.010	22.0–24.0	0.5 max	max	0.5	balance	0.015	0.10	..	max	15.0–16.5	0.010 max
N06625	625	Ni-Cr-Mo-Cb	0.40 max	0.040	20.0–23.0	...	5.0 max	0.50	56.0 min	0.015	0.50	0.40 max	1.00 max	8.0–10.0	0.015	3.2–4.2
N06625	625	Ni-Cr-Mo-Cb	0.40 max	0.10 [†]	20.0–23.0	...	5.0 max	0.50	58.0 min	0.015	0.50	0.40 max	1.00 max	8.0–10.0	0.015	3.2–4.2
N06686	686	Ni-Cr-Mo-W	...	0.010 max	19.0–23.0	...	5.0 max	0.75 max	balance	0.04 max	0.08 max	0.02–0.25	max	15.0–17.0	0.02 max	...	3.0–4.4	...

^A Elements shown as balance shall be arithmetically computed by deducting the sum of the other named elements from 100.

^B Cobalt is to be counted as nickel.

^C Alloy 625 material shall be refined using the electroslag remelting process (ESR), or the vacuum arc remelting process (VAR).

[†] Editorially corrected in January 2008.



TABLE 1 Continued

UNS Designation Number	Alloy	General Name	Aluminum ^B	Composition, %									
				Chromium	Copper	Iron, max	Manganese, max	Silicon, max	Titanium, max	Zinc, max	Magnesium	Other Elements, max	
												Each	Total
A92024	2024	Aluminum 2024	balance	0.10 max	3.8–4.9	0.50	0.30–0.9	0.50	0.15 ^C	0.25	1.2–1.8	0.05	0.15
A96061	6061	Aluminum 6061	balance	0.04–0.35	0.15–0.40	0.7	0.15	0.40–0.8	0.15	0.25	0.8–1.2	0.05	0.15
A97075	7075	Aluminum 7075	balance	0.18–0.35	1.2–2.0	0.50	0.30	0.40	0.20 ^D	5.1–6.1	2.1–2.9	0.05	0.15

^A Analysis shall regularly be made only for the elements specified in this table. If, however, the presence of other elements is suspected or indicated in amounts greater than the specified limits, further analysis shall be made to determine that these elements are not present in excess of the specified limits.

^B Elements shown as balance shall be arithmetically computed by deducting the sum of the other named elements from 100.

^C Titanium + zirconium 0.20 %, max.

^D Titanium + zirconium 0.25 %, max.