

# SLOVENSKI STANDARD

## SIST EN 1762:2017

01-maj-2017

Nadomešča:

SIST EN 1762:2004

SIST EN 1762:2004/AC:2008

---

### Gumene cevi in cevni priključki za utekočinjeni naftni plin, LPG (tekoča ali plinska faza) in zemeljski plin do 25 barov (2,5 MPa) - Specifikacija

Rubber hoses and hose assemblies for liquefied petroleum gas, LPG (liquid or gaseous phase), and natural gas up to 25 bar (2,5 MPa) - Specification

**iTeh STANDARD PREVIEW**

Gummischläuche und -schlauchleitungen für Flüssiggas LPG (flüssig oder gasförmig) und Erdgas bis 25 bar (2,5 MPa) - Spezifikation

[SIST EN 1762:2017](https://standards.itih.ai/catalog/standard/sist/084117-e6f1-4911-b1b7-649893e24467/sist-en-1762-2017)

Tuyaux et flexibles en caoutchouc pour le gaz de pétrole liquéfié GPL (en phase liquide ou gazeuse) et le gaz naturel jusqu'à 25 bar (2,5 MPa) - Spécification

**Ta slovenski standard je istoveten z: EN 1762:2017**

---

#### **ICS:**

75.200	Oprema za skladiščenje nafte, naftnih proizvodov in zemeljskega plina	Petroleum products and natural gas handling equipment
83.140.40	Gumene cevi	Hoses

**SIST EN 1762:2017**

**en,fr,de**

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

SIST EN 1762:2017

<https://standards.iteh.ai/catalog/standards/sist/cf984d17-e6fd-4911-94e7-e49593e24467/sist-en-1762-2017>

EUROPEAN STANDARD  
NORME EUROPÉENNE  
EUROPÄISCHE NORM

# EN 1762

March 2017

ICS 23.040.70

Supersedes EN 1762:2003

English Version

## Rubber hoses and hose assemblies for liquefied petroleum gas, LPG (liquid or gaseous phase), and natural gas up to 25 bar (2,5 MPa) - Specification

Tuyaux et flexibles en caoutchouc pour le gaz de pétrole liquéfié GPL (en phase liquide ou gazeuse) et le gaz naturel jusqu'à 25 bar (2,5 MPa) - Spécification

Gummischläuche und -schlauchleitungen für Flüssiggas LPG (flüssig oder gasförmig) und Erdgas bis 25 bar (2,5 MPa) - Spezifikation

This European Standard was approved by CEN on 11 December 2016.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

**iTeh STANDARD PREVIEW**

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels**

<b>Contents</b>	<b>Page</b>
European foreword.....	4
<b>1 Scope</b> .....	<b>5</b>
<b>2 Normative references</b> .....	<b>5</b>
<b>3 Terms and definitions</b> .....	<b>6</b>
<b>4 Classification</b> .....	<b>6</b>
<b>5 Materials and construction</b> .....	<b>7</b>
5.1 Hose.....	7
5.2 Hose assemblies.....	7
<b>6 Dimensions</b> .....	<b>7</b>
6.1 Nominal bore, internal diameters, outside diameters, tolerances, and minimum bend radius.....	7
<b>Table 1 — Dimensions and tolerances of hoses of types D and D-LT</b> .....	<b>8</b>
<b>Table 2 — Dimensions and tolerances of hoses of types SD, SD-LTS and SD-LTR</b> .....	<b>9</b>
6.2 Minimum thickness of lining and cover.....	9
6.3 Concentricity.....	9
6.4 Tolerances on length.....	9
<b>7 Physical properties</b> .....	<b>10</b>
7.1 Rubber Compounds.....	10
<b>Table 3 — Physical properties of compounds</b> .....	<b>10</b>
7.2 Finished hose and hose assemblies.....	11
<b>Table 4 — Physical properties of finished hose and hose assemblies</b> .....	<b>11</b>
<b>8 Electrical properties</b> .....	<b>12</b>
8.1 General.....	12
8.2 Textile reinforced hoses with bonding wires.....	12
8.3 Textile reinforced hoses with conducting materials.....	13
8.4 Wire helix reinforced hoses.....	13
8.4.1 Grade M-hoses (see 8.2).....	13
8.4.2 Grade Ω-hoses (see 8.3).....	13
8.5 Hose assemblies that are required to be discontinuous.....	13
<b>9 Type testing</b> .....	<b>13</b>
<b>10 Frequency of testing</b> .....	<b>13</b>
<b>11 Marking</b> .....	<b>14</b>
11.1 Hoses.....	14
11.2 Hose assemblies.....	14
<b>Annex A (normative) Flammability test</b> .....	<b>15</b>
A.1 Method.....	15
A.2 Assessment.....	15

<b>Figure A.1 — Arrangement for flammability test.....</b>	<b>16</b>
<b>Annex B (normative) Test frequency.....</b>	<b>17</b>
<b>Table B.1 — Type and routine tests .....</b>	<b>17</b>
<b>Annex C (informative) Test frequency .....</b>	<b>19</b>
<b>Table C.1 — Recommended test frequency (Production acceptance tests) .....</b>	<b>19</b>

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[SIST EN 1762:2017](https://standards.iteh.ai/catalog/standards/sist/cf984d17-e6fd-4911-94e7-e49593e24467/sist-en-1762-2017)

<https://standards.iteh.ai/catalog/standards/sist/cf984d17-e6fd-4911-94e7-e49593e24467/sist-en-1762-2017>

**EN 1762:2017 (E)****European foreword**

This document (EN 1762:2017) has been prepared by Technical Committee CEN/TC 218 “Rubber and plastic hoses and hose assemblies”, the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by September 2017, and conflicting national standards shall be withdrawn at the latest by September 2017.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 1762:2003.

Compared to EN 1762:2003 the following changes have been made:

- a) Clause 2: The normative references have been updated;
- b) Table 3 has been technically amended (property no. 5); in accordance with corrigendum EN 1762:2003/AC of November 2007.
- c) Clause 8.4 has been divided into 8.4.1 and 8.4.2 to clarify the requirements for the 2 different grades of M and  $\Omega$  hoses
- d) Clause 9: The text has been amended editorially;
- e) Clause 10: The text has been amended editorially;
- f) Clause 11.1: The text has been amended editorially.

Annex A and B are normative. Annex C is informative.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

## 1 Scope

This European Standard specifies the requirements for rubber hoses and rubber hose assemblies used for the transfer of liquefied petroleum gas (LPG) in liquid or gaseous phase and natural gas with a maximum working pressure of 25 bar (2,5 MPa) and vacuum within the temperature range of  $-30\text{ °C}$  to  $+70\text{ °C}$  and, when designated -LT,  $-50\text{ °C}$  to  $+70\text{ °C}$ .

## 2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 1360, *Rubber and plastic hoses and hose assemblies for measured fuel dispensing systems - Specification*

EN ISO 8033, *Rubber and plastics hoses - Determination of adhesion between components (ISO 8033)*

EN ISO 1402, *Rubber and plastics hoses and hose assemblies - Hydrostatic testing (ISO 1402)*

EN ISO 10619-1, *Rubber and plastics hoses and tubing - Measurement of flexibility and stiffness - Part 1: Bending tests at ambient temperature (ISO 10619-1)*

EN ISO 4671, *Rubber and plastics hoses and hose assemblies - Methods of measurement of the dimensions of hoses and the lengths of hose assemblies (ISO 4671)*

EN ISO 10619-2, *Rubber and plastics hoses and tubing - Measurement of flexibility and stiffness - Part 2: Bending tests at sub-ambient temperatures (ISO 10619-2)*

EN ISO 7233, *Rubber and plastics hoses and hose assemblies - Determination of resistance to vacuum (ISO 7233)*

EN ISO 7326, *Rubber and plastics hoses - Assessment of ozone resistance under static conditions (ISO 7326)*

EN ISO 8031, *Rubber and plastics hoses and hose assemblies - Determination of electrical resistance and conductivity (ISO 8031)*

EN ISO 8330, *Rubber and plastics hoses and hose assemblies - Vocabulary (ISO 8330)*

ISO 37, *Rubber, vulcanized or thermoplastic — Determination of tensile stress-strain properties*

ISO 188, *Rubber, vulcanized or thermoplastic — Accelerated ageing and heat resistance tests*

ISO 1817, *Rubber, vulcanized or thermoplastic — Determination of the effect of liquids*

ISO 4649, *Rubber, vulcanized or thermoplastic — Determination of abrasion resistance using a rotating cylindrical drum device*

### 3 Terms and definitions

For the purposes of this document, the terms and definitions given in EN ISO 8330 and the following apply.

- 3.1 electrically bonded hose/hose assembly**  
hose/hose assembly that uses a metallic wire connection to conduct static electricity
- 3.2 electrically conductive hose/hose assembly**  
hose/hose assembly that is capable of conducting static electrical charges, using a conductive rubber layer, without the use of a metallic wire
- 3.3 electrically discontinuous hose/hose assembly**  
hose /hose assembly that incorporates a metallic wire connection to one end coupling of the assembly only or is electrically insulated from both end-couplings

### 4 Classification

Hoses/hose assemblies for this application are classified into 5 types and 3 grades according to their use, construction, and electrical properties. The maximum WP for all hoses/hose assemblies is 25 bar.

Type	Application
D	delivery hose
D-LT	delivery hose, low temperature,
SD	suction and delivery hose, helix reinforced
SD-LTS	suction and delivery hose "smooth hose", helix reinforced, low temperature
SD-LTR	suction and delivery hose, rough bore (having an internal, non-embedded helical wire of stainless steel), low temperature

Hoses for this application are divided into 3 grades according to their electrical properties:

Grade designation	Electrical property
M	Electrically bonded
Ω	Electrically conductive using a conductive rubber layer
Discontinuous	Electrically discontinuous



## 5 Materials and construction

### 5.1 Hose

The hose shall consist of the following:

- a lining of synthetic rubber resistant to n-pentane;
- a reinforcement of layers of woven, braided or spirally wound textile material or braided or spirally wound stainless steel wire,
- an embedded stainless steel metallic helix reinforcement (types SD, SD-LTS and SD-LTR only);
- two or more low resistance electrical bonding wires (grade “M” only);
- an outer cover of black or coloured synthetic rubber, resistant to abrasion and outdoor exposure, the cover being pricked to allow gas permeation;
- an internal, non-embedded stainless steel helical wire, suitable for use at  $-50\text{ °C}$  (type SD-LTR only).

### 5.2 Hose assemblies

Hose assemblies shall incorporate metallic couplings attached to the hose by the assembler or built in by the manufacturer. In order to produce the required electrical properties, the couplings should be attached in accordance with Clause 8.

Chlorinated materials shall not be used in contact with any stainless steel materials.

## 6 Dimensions

### 6.1 Nominal bore, internal diameters, outside diameters, tolerances, and minimum bend radius

For hoses without built-in couplings, and when measured in accordance with method A of EN ISO 4671, the internal diameter and outside diameter and their tolerances shall conform to Table 1 or Table 2, depending on the type.

For hoses with built-in couplings, the outside diameters in Tables 1 and 2 do not apply.

When tested by the method described in EN ISO 10619-1, the value of the minimum bend radius shall be as given in Table 1 or Table 2, depending on the type.

Table 1 — Dimensions and tolerances of hoses of types D and D-LT

Nominal bore	Internal diameter mm	Tolerance mm	Outside diameter mm	Tolerance mm	Design minimum bend radius* mm
12	12,7	±0,5	22,7	±1,0	100
15	15	±0,5	25	±1,0	120
16	15,9	±0,5	25,9	±1,0	125
19	19	±0,5	31	±1,0	160
25	25	±0,5	38	±1,0	200
32	32	±0,5	45	±1,0	250
38	38	±0,5	52	±1,0	320
50	50	±0,6	66	±1,2	400
51	51	±0,6	67	±1,2	400
63	63	±0,6	81	±1,2	550
75	75	±0,6	93	±1,2	650
76	76	±0,6	94	±1,2	650
80	80	±0,6	98	±1,2	725
100	100	±1,6	120	±1,6	800
150	150	±2,0	174	±2,0	1200
200	200	±2,0	224	±2,0	1600
250	254	±2,0	—	—	2000
300	305	±2,0	—	—	2500

\*) The design minimum bend radius is measured to the surface of the hose on the inside of the bend.

Table 2 — Dimensions and tolerances of hoses of types SD, SD-LTS and SD-LTR

Nominal bore	Internal diameter mm	Tolerance mm	Outside diameter mm	Tolerance mm	Design minimum bend radius* mm
12	12,7	±0,5	22,7	±1,0	90
15	15	±0,5	25	±1,0	95
16	15,9	±0,5	25,9	±1,0	95
19	19	±0,5	31	±1,0	100
25	25	±0,5	38	±1,0	150
32	32	±0,5	45	±1,0	200
38	38	±0,5	52	±1,0	280
50	50	±0,6	66	±1,2	350
51	51	±0,6	67	±1,2	350
63	63	±0,6	81	±1,2	480
75	75	±0,6	93	±1,2	550
76	76	±0,6	94	±1,2	550
80	80	±0,6	98	±1,2	680
100	100	±1,6	120	±1,6	720
150	150	±2,0	174	±2,0	1000
200	200	±2,0	224	±2,0	1400
250	254	±2,0	—	—	1750
300	305	±2,0	—	—	2100

\*) The design minimum bend radius is measured to the surface of the hose on the inside of the bend.

NOTE Nominal bores 250 and 300 apply to hoses with built-in couplings only.

## 6.2 Minimum thickness of lining and cover

When measured in accordance with EN ISO 4671, the minimum thickness of both the lining and cover of all hoses shall be 1,6 mm.

Not applicable to hose assemblies with built-in couplings

## 6.3 Concentricity

When measured in accordance with EN ISO 4671, the concentricity based on a total indicator reading shall be 1,0 mm for hoses of nominal bore 12–76 and 1,5 mm for hoses of nominal bore 80–200.

Not applicable to hose assemblies with built-in couplings

## 6.4 Tolerances on length

The tolerances on the measured length of hoses and hose assemblies shall be ± 1 %.