
**Welding — Micro joining of 2nd
generation high temperature
superconductors —**

**Part 1:
General requirements for the
procedure**

*Soudage — Micro-assemblage des supraconducteurs à haute
température de 2ème génération —*

Partie 1: Exigences générales pour la procédure

ISO 17279-1:2018

<https://standards.iteh.ai/catalog/standards/iso/ed23901f-04c4-407d-acf7-9a64da6e08e1/iso-17279-1-2018>



iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[ISO 17279-1:2018](https://standards.iteh.ai/catalog/standards/iso/ed23901f-04c4-407d-ae77-9a64da6e08e1/iso-17279-1-2018)

<https://standards.iteh.ai/catalog/standards/iso/ed23901f-04c4-407d-ae77-9a64da6e08e1/iso-17279-1-2018>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2018

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Symbols and abbreviated terms	2
5 Requirements	2
5.1 Joint design.....	2
5.1.1 General.....	2
5.1.2 Lap joint.....	3
5.1.3 Bridge joint.....	3
5.2 Equipment.....	4
5.3 Welding procedure qualification.....	5
5.4 Micro-joining and oxygenation-annealing process.....	5
5.4.1 General.....	5
5.4.2 Technical content of a pWPS and WPS.....	8
5.5 Qualification based on standard test joint specimen.....	9
5.5.1 General.....	9
5.5.2 Test specimens.....	9
5.5.3 Micro-joining and oxygenation-annealing procedure of test specimens.....	9
5.5.4 Testing of test specimens.....	13
5.5.5 Re-testing.....	16
5.5.6 Test record.....	16
5.6 Range of qualification.....	16
5.6.1 General.....	16
5.6.2 Related to the manufacturer.....	16
5.6.3 Essential variables.....	16
5.6.4 Other variables.....	17
5.7 Micro-joining and oxygenation-annealing procedure specification and procedure qualification record.....	17
5.8 Final treatment of production run joints.....	17
5.9 Acceptance criteria.....	18
5.10 Identification and traceability.....	19
6 Third-party check	19
Annex A (informative) Micro-joining and oxygenation-annealing procedure	20
Annex B (informative) Preliminary Welding Procedure Specification (pWPS)	24
Annex C (informative) Procedure qualification for micro-joining and oxygenation annealing and Welding Procedure Qualification Record (WPQR)	27
Annex D (informative) Welding Procedure Specification (WPS)	33
Annex E (informative) Check list for micro-joining and oxygenation-annealing procedure qualification	36
Bibliography	39

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 44, *Welding and allied processes*, Subcommittee SC 10, *Quality management in the field of welding*.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

A list of all parts in the ISO 17279 series can be found on the ISO website.


Introduction

The increasing use of 2nd generation high temperature superconductors (2G HTSs) and invention of resistance-free joining on 2G HTSs have created the need for this document in order to ensure that joining is carried out in the most effective way and that appropriate control is exercised over all aspects of the operation. ISO standards for micro-joining and joint evaluation procedure are accordingly essential to get the best and uniform quality of 2G HTS joint.

The technique in this document regarding resistance-free micro-joining is patent-registered and was reported to patent.statements@iso.org using the "Patent Statement and Licensing Declaration Form".

A superconductor is a material that conducts electricity without resistance and has diamagnetism below critical temperature, T_c , critical magnetic field, B_c , and critical current density, J_c . Once set in motion, electrical current flows forever in a closed loop of superconducting material under diamagnetism.

A 2G HTS consists of multi-layers and its total thickness is around between 60 μm and 100 μm with or without surrounding copper stabilizer. The superconducting layer made from $\text{ReBa}_2\text{Cu}_3\text{O}_{7-x}$ (ReBCO, abbreviated term of $\text{ReBa}_2\text{Cu}_3\text{O}_{7-x}$) is only between 1 μm and 2 μm thick depending on manufacturer's specifications. Re stands for Rare Earth materials, of which gadolinium, yttrium and samarium are used for 2nd generation high temperature superconducting materials. [Figure 1](#) shows schematic drawing of typical multiple layers with surrounded copper stabilizer, and the constituents and thicknesses of each layer in the 2G HTS. The two layers of No. 1 in [Figure 1](#) does not exist in stabilizer-free 2G HTS.




Key

- | | | | |
|---|--|---|--------------------------------------|
| 1 | 20 μm Cu stabilizer | 4 | 5 buffing layers (total 160 nm) |
| 2 | 2 μm Ag overlayer | 5 | 50 μm hastelloy substrate |
| 3 | between 1 μm and 2 μm ReBCO super-conducting layer | | |

NOTE Not to scale.

Figure 1 — Typical 2G HTS multi-layers, and the constituents and thicknesses of each layer


Currently soldering, brazing or any filler is applied in superconducting industry as shown in [Figure 2](#), which shows high electrical resistance at the joint providing fatal flaw in the superconductor.



Key
 1 superconducting layer
 2 solder

Figure 2 — Soldering to join 2G HTS

However, this document focuses on the direct autogenous joining of between 1 μm and 2 μm -thick superconducting layers of 2G HTSs as shown in [Figure 3](#) without filler metals and recovery of superconducting properties by oxygenation annealing process, which shows almost no electrical resistance at the joint.



Key
 1 superconducting layer

(<https://standards.iteh.ai>)
 Document Preview

ISO 17279-1:2018

<https://standards.iteh.ai> **Figure 3 — Direct autogenous joining of two superconducting layers of 2G HTSs for superconducting joint** <https://standards.iteh.ai> /279-1-2018

The International Organization for Standardization (ISO) draws attention to the fact that it is claimed that compliance with this document may involve the use of patents concerning 2G HTS resistance-free joining. ISO takes no position concerning the evidence, validity and scope of this patent right. The holders of these patent rights have assured ISO that they are willing to negotiate licenses under reasonable and non-discriminatory terms and conditions with applicants throughout the world. In this respect, the statement of the holders of these patent rights is registered with ISO. Information may be obtained from:

KJoins, Inc.
913C, H-1, KIST Venture Town
Korea Institute of Science and Technology
14-1 Hwarang ro, Seongbuk gu
SEOUL 136-791
REP. OF KOREA

Tel.: +82 2 921 6966

Contact: Dr HeeSung ANN
E-mail: andy@kjoins.com

Contact: Dr YoungKun OH
Email: ykoh@kjoins.com

Contact: Dr MyungWhon LEE
E-mail: mwlee@kjoins.com

Dae-A International IP & Law Firm
3F Hanyang B/D
830-71 Yeoksam dong, Gangnam gu
SEOUL 135-936
REP. OF KOREA

Tel.: +82 2 565 2500

Fax: +82 2 565 2511

Contact: Patent Attorney Mr. BoHyun KIM
E-mail: bohkim@ipdraju.com

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights other than those identified above. ISO shall not be held responsible for identifying any or all such patents.

iTeh Standards

Document Preview

[ISO 17279-1:2018](https://standards.iteh.ai/catalog/standards/iso/ed23901f-04c4-407d-acf7-9a64da6e08e1/iso-17279-1-2018)

<https://standards.iteh.ai/catalog/standards/iso/ed23901f-04c4-407d-acf7-9a64da6e08e1/iso-17279-1-2018>

Welding — Micro joining of 2nd generation high temperature superconductors —

Part 1: General requirements for the procedure

1 Scope

This document provides concepts, specification and qualification of 2G HTS joining procedure. A welding procedure specification (WPS) is needed to provide a basis for planning joining operations and for quality control during joining. Joining is considered as a special process in the terminology of standards for quality systems. Standards for quality systems usually require that special processes be carried out in accordance with written procedure specifications. This has resulted in the establishment of a set of rules for qualification of the joining procedure prior to the release of the WPS to actual production. This document defines these rules.

This document does not cover soldering, brazing or any fillers, which are currently available in the industry. It can be applied for joining of all kinds of 2G HTSs.

This document does not apply to 1st Generation Bismuth Strontium Calcium Copper Oxide (1G BSCCO) type HTS and Low Temperature Superconductor (LTS) Joining.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 15607:2003, *Specification and qualification of welding procedures for metallic materials — General rules*

ISO 17279-2, *Welding — Micro-joining of 2nd generation high temperature superconductors — Part 2: Personnel qualification for micro-joining and testing*

ISO/TR 25901 (all parts), *Welding and related processes — Vocabulary*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO/TR 25901 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

3.1 high temperature superconductor HTS

superconducting material with critical temperature higher than liquid nitrogen boiling point

3.2
low temperature superconductor
LTS

superconducting material with critical temperature lower than liquid nitrogen boiling point

3.3
2nd generation high temperature superconductor
2G HTS

superconducting material with critical temperature higher than liquid nitrogen boiling point, made of rare earth and other elements like barium, copper and their oxides

Note 1 to entry: A first generation high temperature superconductor (1G HTS) is a superconducting material with critical temperature higher than liquid nitrogen boiling point, made of bismuth strontium calcium copper oxides.

3.4
pressurized partial micro-melting diffusion

partial micro-melting of the two faying surfaces of 1 µm- to 3 µm-thick superconducting layers and atoms diffusion in partially micro-molten pool and solid state of the superconducting layers by pressurized force

3.5
oxygenation annealing

process to restore the oxygen stoichiometry in an oxygen-rich environment and to recover superconducting properties

Note 1 to entry: Structure and superconducting properties of 2G HTS are strongly affected by the oxygen stoichiometry. Joining of 2G HTS at high temperature induces oxygen out-diffusion causing a phase change from a superconducting orthorhombic phase to a non-superconducting tetragonal phase.

3.6
pressurized solid-state diffusion

atoms diffusion in solid state of the two faying surfaces of 1 µm- to 3 µm-thick superconducting layers with pressurized force

3.7
bridge joint

joint with a third 2G HTS piece overlapped as a bridge on top of two 2G HTS pieces

Note 1 to entry: See [Figure 3](#) and [Figure 5](#).

4 Symbols and abbreviated terms

The abbreviated terms listed in ISO 15607:2003, Table 1, relevant to joining procedure for 2G HTS, shall apply.

5 Requirements

5.1 Joint design


5.1.1 General

The joint shall be designed in accordance with defined requirements that support the end use of the product. Documentation shall clearly define the essential information of the joint and any special requirements, e.g. fracture critical, durability critical, mission critical, or safety critical, that are imposed over and above the general requirements. Essential process controls shall be defined to substantiate that all design requirements can be met by the joints that were produced in accordance with welding procedure specification (WPS) and testing and inspection requirements.

The joint design shall take into account the necessary material property data. There are basically two types of joint alignments (lap and bridge) and the suitable alignment can be selected depending on user's convenience. The two types of joint alignments for joining of 2G HTS are shown in [Figure 3](#).

5.1.2 Lap joint

[Figure 4](#) shows schematic sketch of lap joint design for welding procedure qualification as described in [5.3](#). All lengths, l_0 , and l_1 , should be specified in the procedure qualification report (PQR). As joint length, l_1 , is increased, effective contact surface areas between two superconducting layers are increased, probabilities of atoms inter-diffusion between the two layers for the joining are increased, and accordingly joint strengths (tensile and bending) are increased. The Cu stabilizers, if included, and Ag overlayers on top of the superconducting layers shall be perfectly removed for direct contact of two superconducting layers and micro-joining. This process is for not contaminating superconducting layers during micro-joining.



Key

- 1 superconducting layer
- l_0 60 mm; length of two parts
- l_1 40 mm; overlap (joint length)


ISO 17279-1:2018

<https://standards.iteh.ai/catalog/standards/iso/ed23901f-04c4-407d-acf7-9a64da6e08e1/iso-17279-1-2018>

Figure 4 — Lap joint

5.1.3 Bridge joint

[Figure 5](#) illustrates the joint design for welding procedure qualification as described in [5.3](#). The distance, l_2 , between two 2G HTS parts in [Figure 5](#) may be ranged from "0" to over 10 cm depending on joint design. The lengths of l_0 in [Figure 5](#) should be the same. All lengths, l_0 , l_1 , l_2 , and l_3 , should be specified in the procedure qualification report (PQR). As joint lengths, l_3 , are increased, effective contact surface areas between two superconducting layers are increased, probabilities of atoms inter-diffusion between the two layers for the joining are increased, and accordingly joint strengths (tensile and bending) and superconductivity are increased. The Cu stabilizers, if included, and Ag overlayers on top of the superconducting layers shall be perfectly removed for direct contact of two superconducting layers and joining. This process is to avoid contaminating the superconducting layers during joining.



Key

- 1 superconducting layer
- l_0 50 mm; length of two parts at bottom
- l_1 40 mm to 50 mm; length of bridge part
- l_2 0 mm to 10 mm; distance between parts to join
- l_3 20 mm; overlap (joint length)

Figure 5 — Bridge joint

5.2 Equipment

The equipment shall be adequate for the application concerned. Joining equipment shall be capable of producing joints that meet the acceptance criteria specified in 5.9. Joining equipment shall be maintained in good condition and shall be repaired or adjusted when a joining operator, inspector or joining coordinator is concerned about the capability of the equipment to operate satisfactorily.

After installation of new or refurbished equipment or developing the new equipment, appropriate tests shall be performed. Such tests shall verify the equipment functions correctly.

Reproducibility tests shall be performed to demonstrate that the joining equipment can repeatedly produce joints that meet the acceptance levels in 5.9. The reproducibility test shall be performed in accordance with a WPS that is used in production for that machine. A minimum of three test joints shall be made and found satisfactory. Reproducibility tests shall be carried out when any of the following occurs:

- critical component(s) of the equipment is (are) damaged, repaired, or replaced;
- equipment is dislodged or moved in a manner for which it was not designed;
- stationary equipment is moved from one location to another.

The manufacturer shall have a documented plan for equipment maintenance. The plan shall ensure that maintenance checks are performed on the equipment that controls variables listed in the relevant WPS. The maintenance plan may be limited to those items that are essential for producing joints that meet the quality requirements of this document.

The joining tools, if any, that are used in production shall be permanently marked for identification prior to use. Before joining, the joining tools, if any, shall be clean and sufficiently free of contaminants (e.g. oil, grease or dirt) that can have a detrimental effect on joint quality. The correct tool geometry is critical for producing a quality joint. Because the joining tool wears with use, it shall be inspected for wear at appropriate intervals and in accordance with a written procedure. Before joining, parts and pieces that contact the joining part shall be clean and sufficiently free of contaminants (e.g. oil, grease, and dirt) that can have a detrimental effect on the joint.