



Designation: D2944 – 71 (Reapproved 2008)

Standard Test Method of Sampling Processed Peat Materials¹

This standard is issued under the fixed designation D2944; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers procedures for obtaining samples for use in the determination of moisture, ash, and organic matter; volume; pH; volume weights, water-holding capacity, and air capacity of water-saturated peat materials; total nitrogen; particle size range; and sand content of processed peat materials.²

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Significance and Use

2.1 This test method provides a uniform procedure for obtaining relatively homogeneous samples when obtained from a multiplicity of sources.

3. Apparatus

3.1 *Slotted Tube*, single or double, or slotted tube and rod, all with pointed ends and a minimum 1-in. (25-mm) diameter. The Pennsylvania State Forage Sampler is a satisfactory core sampler.

4. Procedure

4.1 Take a representative sample from the lot or shipment as follows:

¹ This test method is under the jurisdiction of ASTM Committee D18 on Soil and Rock and is the direct responsibility of Subcommittee D18.22 on Soil as a Medium for Plant Growth.

Current edition approved Jan. 1, 2008. Published February 2008. Originally approved in 1971. Last previous edition approved in 1998 as D2944 – 71 (1998). DOI: 10.1520/D2944-71R08.

² Standards for the sampling of undisturbed peats in situ are presently being prepared by ASTM Committee D18.

4.1.1 *Packaged or Baled Peats*—Lay the bag or bale horizontally and remove the core diagonally from end to end. Determine the number of cores as follows: from lots of 1 to 10 bags, sample all bags; from lots of 11 or more, sample 10 bags. Take 1 core from each bag sampled except for lots of 1 to 4 bags, take enough diagonal cores from each bag to total at least 5 cores.

4.1.2 *Bulk Samples*—Draw at least 10 cores from different regions.

4.1.3 *Small Containers* (10 lb (4.5 kg) or less)—Take the entire package. Working rapidly to prevent moisture losses, reduce the composite sample to not less than 500 g by weight or 2 L by volume by mixing on a clean oilcloth or paper and quartering. Place sample in an airtight container.

4.2 Sampling by random “grab” procedure is necessary if the particle size range is to be determined or if representative sample cannot be taken with a core sampler.

5. Precision and Bias

5.1 *Precision*—Due to the nature of the soil or rock materials tested by this test method it is either not feasible or too costly at this time to produce multiple specimens which have uniform physical properties. Any variation observed in the data is just as likely to be due to specimen variation as to operator or laboratory testing variation. Subcommittee D18.18 welcomes proposals that would allow for development of a valid precision statement.

5.2 *Bias*—There is no accepted reference value for this test method, therefore, bias cannot be determined.

6. Keywords

6.1 peat; samples; sampling

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the ASTM website (www.astm.org/COPYRIGHT/).

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[ASTM D2944-71\(2008\)](#)

[/catalog/standards/astm/2244d32f-9bdf-4ec6-8083-95258e1afba3/astm-d2944-71-2008](#)