

### SLOVENSKI STANDARD SIST EN 14243-3:2019

01-april-2019

Nadomešča: SIST-TS CEN/TS 14243:2010

# Snovi iz izrabljenih avtomobilskih gum - 3. del: Drobci, odrezki in lističi - Metode za ugotavljanje njihovih mer, vključno z merami štrlečih vlaken

Materials obtained from end of life tyres - Part 3: Shreds, cuts and chips - Methods for determining their dimension(s) including protruding filaments dimensions

Materialien aus Altreifen - Teil 3: Reifenschnitzel, Abschnitte und Chips - Methode zur Bestimmung der Abmessungen und Verunreinigungen einschließlich vorstehender Fasern

#### SIST EN 14243-3:2019

Matériaux produits à partir de pnéus usagés non réutilisables (RUNR) - Partie 3 : Broyats, coupes et chips - Méthodes de détermination de leur(s) dimension(s) y compris les dimensions des barbules

Ta slovenski standard je istoveten z: EN 14243-3:2019

#### <u>ICS:</u>

13.030.50RecikliranjeRecycling83.160.01Avtomobilske pnevmatike na<br/>splošnoTyres in general

SIST EN 14243-3:2019

en,fr,de



## iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>SIST EN 14243-3:2019</u> https://standards.iteh.ai/catalog/standards/sist/8c822b8c-ce2b-4d55-8e7c-58b833ed7eb7/sist-en-14243-3-2019

#### SIST EN 14243-3:2019

# EUROPEAN STANDARD NORME EUROPÉENNE EUROPÄISCHE NORM

### EN 14243-3

February 2019

ICS 83.160.01

Supersedes CEN/TS 14243:2010

**English Version** 

### Materials obtained from end of life tyres - Part 3: Shreds, cuts and chips - Methods for determining their dimension(s) including protruding filaments dimensions

Matériaux produits à partir de pneus usagés non réutilisables (PUNR) - Partie 3: Broyats, coupes et chips - Méthodes de détermination de leur(s) dimension(s) y compris les dimensions des barbules

This European Standard was approved by CEN on 19 November 2018.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION COMITÉ EUROPÉEN DE NORMALISATION EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

#### SIST EN 14243-3:2019

#### EN 14243-3:2019 (E)

### Contents

Europ	ean foreword	3
Introd	uction	ł
1	Scope	5
2	Normative references	5
3	Terms, definitions, symbols and abbreviated terms	5
4	Categories of products obtained from end-of-life tyres based mainly on thei dimensions	r 5
5	Determination of dimensions for shreds, cuts and chips	5
Annex A (normative) Evaluation of protruding filaments for shreds, cuts and chips		
A.1	General13	3
A.2	Principle of the evaluation13	3
A.3	Sampling13	3
A.4	Principle for determining dimension(s) by image analysis	3
A.5	Equipment	3
A.6	Procedure	ł
A.7	Metrological characteristics <u>SISTEN 14243-3:2019</u>	ŀ
A.8	Measurement report	ł
Annex	B (informative) Example of scoop10	5
Annex	C (informative) Positioning of shreds when using image analysis12	7
<b>C.1</b>	General12	7
<b>C.2</b>	Position on the image12	7
<b>C.3</b>	Curvature12	7
Annex	D (informative) Removal of loose metal wires19	)
Bibliography		

#### **European foreword**

This document (EN 14243-3:2019) has been prepared by Technical Committee CEN/TC 366 "Materials obtained from End-of-Life Tyres (ELT)", the secretariat of which is held by UNI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by August 2019, and conflicting national standards shall be withdrawn at the latest by August 2019.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document together with EN 14243-1 and EN 14243-2 supersedes CEN/TS 14243:2010.

EN 14243, Materials obtained from End-of-Life Tyres (ELTs), consists of the following parts:

- Part 1: General definitions related to the methods for determining their dimension(s) and impurities
- Part 2: Granulates and powders Methods for determining the particle size distribution and impurities, including free steel and free textile content
- Part 3: Shreds cuts and chips Methods for determining their dimension(s) including protruding filaments dimensions
  Filaments dimensions
  Filaments dimensions

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

#### EN 14243-3:2019 (E)

#### Introduction

This standard is used in conjunction with the other parts of EN 14243 series. Such series is intended to cover the testing programs needed to characterize each product category as shown on the figure below.



Figure 1 — Typical scheme for a testing programme concerning several characteristics with testing steps in the field and in the laboratory

End-of-life tyres consist mainly of passenger and commercial vehicle tyres, truck, earthmover and agricultural tyres manufactured for distribution in the European market that are no longer suitable for their original purpose. Products from end-of-life tyres are used as a secondary raw material finding a wide range of applications. The principal categories of materials from end-of-life tyres are defined on the basis of their dimension(s) according to EN 14243-1.

#### 1 Scope

This document provides test methods for the determination of the dimension(s) of shreds, cuts and chips (including protruding filaments) produced from all categories of end-of-life tyres at all steps of the treatment processes.

The methods described in this document include sample collection and the preparation of a representative sample based on a sampling plan for the purpose of determining dimensions.

#### 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 14243-1:2019, Materials obtained from end of life tyres — Part 1: General definitions related to the methods for determining their dimension(s) and impurities

EN 14243-2, Materials obtained from end of life tyres — Part 2: Granulates and powders — Methods for determining the particle size distribution and impurities, including free steel and free textile content

ISO 565, Test sieves — Metal wire cloth, perforated metal plate and electroformed sheet — Nominal sizes of openings

ISO 3310-1, Test sieves - Technical requirements and testing - Part 1: Test sieves of metal wire cloth

ISO 5725-5, Accuracy (trueness and precision) of measurement methods and results — Part 5: Alternative methods for the determination of the precision of a standard measurement method <u>SIST EN 14243-32019</u>

#### 3 Terms, definitions, symbols and abbreviated terms 155-8e7c-

58b833ed7eb7/sist-en-14243-3-2019

#### **3.1 Terms and definitions**

For the purposes of this document, the terms and definitions given in EN 14243-1:2019 apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at http://www.electropedia.org/
- ISO Online browsing platform: available at http://www.iso.org/obp

#### 3.2 Symbols and abbreviated terms

For the purposes of this document, the following symbols apply.

- *ANPF* Average Number per Piece of Filaments longer than *MLF1*
- *HDF* Higher Dimension of the Format (millimetres)
- *L* Maximum projected Length (millimetres)
- *LDF* Lower Dimension of the Format (millimetres)
- *MF* Mass of the Fine pieces (grams)
- *MLF* Minimum length of a filament (in millimetres)

- *MLF1* Minimum length of a filament (in millimetres) for the criterion average number of filaments per piece
- *MLF2* Minimum length of a filament (in millimetres) for the criterion number percentage of pieces having at least one filament;
- *MLM* Mass of the Loose Metal wires (grams)
- *MPC* Mass Percentage of the *NCC* Central Classes (optional)
- *MPF* Mass Percentage of the Fine pieces
- *MPL* Mass Percentage of Large pieces (optional)
- MPM Mass Percentage of the loose Metal wires
- *MS* Mass of the laboratory Sample (grams)
- *NCC* Number of Central Classes
- *NCR* Number of Classes in the Range LDF HDF
- *NPC* Number Percentage of the NCC Central Classes
- *NPF* Number Percentage of pieces having at least one Filament longer than MLF2
- *NPL* Number Percentage of Large pieces
- *TNP* Total Number of Pieces in the sample not including the fine pieces (standards.iteh.ai)

## 4 Categories of products obtained from end-of-life tyres based mainly on their dimensions https://standards.iteh.ai/catalog/standards/sist/8c822b8c-ce2b-4d55-8e7c-

https://standards.iteh.ai/catalog/standards/sist/8c822b8c-ce2b-4d55-8e7c-58b833ed7eb7/sist-en-14243-3-2019

For categories and testing program refer to EN 14243-1:2019, Clause 4.

#### 5 Determination of dimensions for shreds, cuts and chips

#### **5.1 General**

Shreds, cuts and chips are materials produced from end-of-life tyres by primary shredding. Primary shredding corresponds to the processing of end-of-life tyres by shredding, crushing or fragmenting, while maintaining in the obtained output material an average global composition similar to that of the end-of-life tyres.

Depending on the agreed test programme between the producer and the customer, or at the producer's own will, the determination of dimensions specified in this clause for shreds, cuts and chips if required shall be followed by the additional determination of filaments as specified in Annex A.

Producer and customer may also agree to determine the dimensions of chips considered as large granulates, using the methods described in EN 14243-2.

#### 5.2 Sampling plan

#### 5.2.1 Principles of sampling

The main principle of sampling is to obtain a representative sample(s) from a whole lot (of defined material) from which a characteristic is to be determined. If the lot is to be represented by a sample, then every particle in the lot shall have an equal probability of being included in the sample (i.e. probabilistic

sampling). When these principles cannot be applied in practice, the sampler shall define a procedure as close as possible to probabilistic sampling in his judgement (i.e. judgemental sampling) and note the limitations in the sampling plan and sampling report.

To take samples in a way that is truly representative of the material produced is easier when the material is moving (to be avoided for example in a stockpile, big bag or silo). Regarding shreds, it is necessary to take samples when the material is in movement.

NOTE The determination of other properties than dimensions may result in different sampling requirements. This is the case for the determination of physical properties (such as apparent density) or chemical composition.

#### 5.2.2 Preparation of the sampling plan for determining dimensions

The first step is to identify the properties required in the testing programme and the lot in relation to which they are defined, for instance "maximum projected length on a shreds production of 300 t".

The lot size is based on production quality management decisions or specific customer requirements. The lot size may be defined by the producer as a fixed quantity produced between machine settings or a fixed quantity in a production day/shift/week or a fixed quantity. With regards to certain pieces exhibiting large dimensions, the tools for taking an increment shall be sufficiently large in order that the large pieces are equally sampled. For shreds, this typically results in increments of more than 200 pieces (about 3 kg to 15 kg).

NOTE 1 Larger increments would slightly improve the sampling quality, while increasing the size of the field sample, therefore complicating the size reduction into laboratory sample(s). It is preferable to increase the number of increments, thus increasing directly the representativeness.

For reference testing (contractual or pre-contractual) concerning shreds dimension(s) the field sample is a composite sample constituted of three increments taken at dates selected randomly along the period of time during which the lot is produced. When at one date there are no shreds at the sampling location, the increment is taken at another date preselected prior to sampling, unless this is caused by a major change in the production process (see below) sist-en-14243-3-2019

For routine testing concerning the dimension(s) of shreds the field sample consists of one increment taken at a date selected randomly along the period of time during which the lot is produced. When at this date there are no shreds at the sampling location, the increment is taken at another date preselected prior to sampling, unless this is caused by a major change in the production process (see below).

During a sampling step the production process may be interrupted by a major change. Such a major change would induce in the sample two different subpopulations, before and after the major change. Therefore, it is necessary to consider a lot before and a lot after the major change. Major changes may occur on the feed and on the production process.

NOTE 2 The random taking of three increments allows having a first approximation of the variability inside the considered lot. The random taking of one increment in routine testing allows also another evaluation of the variability when considering the lots obtained under comparable conditions.

#### 5.3 Procedure for taking the field sample and producing the laboratory sample(s)

Taking increment(s) at the output of the conveyer in the falling zone. The used tool is typically a rectangular open scoop, i.e. without an edge on one of the long side capable of "cutting" the entire flow. Such a scoop (see Annex B) shall have:

- a) a width L at least 1,5 times the width of the falling flow;
- b) a depth P at least 2/3 of the width L and at least 2,5 times the higher dimension HDF;
- c) an edge height H equal at least to 1/3 of the width L and at least two times the higher dimension HDF.

This scoop is moved for instance with a loader according to a detailed procedure adapted to the site condition. This scoop can be the bucket of a loader, provided that its cleanliness is compatible with the requirement of the dimension measurement, i.e. the absence of deposit. The taken increment is considered as valid if both criteria are fulfilled:

- the increment consists of at least 200 pieces for shreds (after sieving of fines);
- the mass of the increment does not exceed 15 kg for shreds.

NOTE The minimum size of the increment is specified as a minimum number of pieces in view of the statistical evaluation of the measurements of the maximum projected length of each piece. A specification in mass would result in significant differences depending on the size of the pieces.

For the determination of dimension(s), each increment constitutes a laboratory sample for such determination. If there are several increments, the dimension of each increment is determined and the average is calculated. This is easier than reducing the size of the field sample prior to measurement of the dimension.

#### 5.4 Principle of determining the dimension(s)

A laboratory sample of at least TNP > 200 that do not pass through the LDF mm sieve is taken for the test. The MS mass (in grams) of this laboratory sample is weighed to within  $\pm$  0,01 kg. Any elements consisting solely of metal wires released from the pieces of end-of-life tyre are not counted in the TNP pieces. They are collected and weighed together (MLM g).

After passing through a LDF mm sieve, the mass (in grams) of the fine pieces (MF) is weighed to within  $\pm$  0,01 kg. The pieces that do not pass through the sieve (without loose metal wires) are used to determine the maximum lengths and constitute the test portion for determination purposes.

Each piece of this test portion is treated individually. As these pieces are not usually flat, the largest length is defined as the largest length projected onto a plane on which the piece in question lies. This length is measured to within ± 5 mm, without deforming the piece and excluding filaments.

The measurements of the different maximum projected lengths L are used to build a histogram (see Figure 2) that is characteristic of the distribution of the pieces of the test portion, i.e. the laboratory sample without the fine pieces and without the loose metal wires. This histogram consists of the large pieces class (larger than the HDF threshold dimension of the large pieces) and NCR = 7 classes of the same width between the LDF and HDF dimensions.

Three characteristics of the histogram are extracted from these measurements:

- a) the number percentage of large pieces (NPL) (%) (and optionally, the mass percentage of large pieces (MPL) (%)) corresponding to the pieces larger than the higher dimension of the HDF format (HDF is one of the characteristics of the format of the product under consideration, for example 350 mm);
- b) the mass percentage of the fine pieces (MPF) (%) = 100 × MF/MS (mass percentage of the pieces passing through the sieve with a mesh of LDF mm) (LDF is one of the characteristics of the product format under consideration, for example 25 mm);
- c) the number percentage (NPC) (%) (and optionally the mass percentage (MPC) (%)) of the pieces in the number of NCC central classes (2-3-4-5-6) amongst the NCR = 7 classes between the lower and higher dimensions of the format (LDF and HDF).



Figure 2 — Example of a histogram

#### **5.5 Equipment**

- a) Vessel large enough to contain at least 200 pieces;
- b) Illuminated measurement plane with a ruler graduated in mm that can measure lengths up to 500 mm (1000 mm for cuts) on this measurement plane;

iTeh STANDARD PREVIEW

- c) Scales to within 0,01 kg;
- d) Circular mesh sieve in accordance with ISO 565 or ISO 3310-1 with a mesh of *LDF* (in millimetres). https://standards.iteh.ai/catalog/standards/sist/8c822b8c-ce2b-4d55-8e7c-

(standards.iteh.ai)

#### 5.6 Procedure for quantification of maximum projected length (manual)

Identify the LDF and HDF dimensions in the test specifications and calculate the limits of the seven classes of the same width. Deduce the limits of the central range defined by NCC classes 2-3-4-5-6.

HDF and LDF should be different enough in order to define in practice the seven classes.

Take a laboratory sample of the shredded material, in accordance with the sampling scheme (a vessel can be used to check that for the site in question, the TNP criterion > 200 elements after sieving at LDF mm is satisfied).

Weigh the laboratory sample (MS) (in grams).

Sieve the laboratory sample at LDF mm.

Remove the loose metal wires.

NOTE 1 To make the sieving easier, the coarsest fractions can be removed manually, ensuring that they do not contain any fines.

NOTE 2 For the removal of loose metal wires to be easier, a magnet can be used at the end of the procedure, ensuring that they do not contain ant rubber particles (see Annex D).

Weigh the undersized material, i.e. the MF fine pieces (in grams) small enough to pass through the LDF mm sieve.

The elements that do not pass through the sieve are used to determine the maximum lengths as follows: place each element not passing through the sieve on the flat measurement surface and use the ruler to