

DRAFT INTERNATIONAL STANDARD

ISO/DIS 22674.2

ISO/TC 106/SC 2

Secretariat: ANSI

Voting begins on:
2014-01-16

Voting terminates on:
2014-03-16

Dentistry — Metallic materials for fixed and removable restorations and appliances

Médecine bucco-dentaire — Matériaux métalliques pour les restaurations fixes et amovibles et les appareillages

[Revision of first edition (ISO 22674:2003)]

ICS: 11.060.10

ITeH STANDARD PREVIEW
(standards.iteh.ai)
Full standard:
<https://standards.iteh.ai/catalog/standards/sist/17403ee3-3966-422b-a3ba-a52cd418451d/iso-22674-2016>

ISO/CEN PARALLEL PROCESSING

This draft has been developed within the International Organization for Standardization (ISO), and processed under the **ISO lead** mode of collaboration as defined in the Vienna Agreement.

This draft is hereby submitted to the ISO member bodies and to the CEN member bodies for a parallel five month enquiry.

Should this draft be accepted, a final draft, established on the basis of comments received, will be submitted to a parallel two-month approval vote in ISO and formal vote in CEN.

To expedite distribution, this document is circulated as received from the committee secretariat. ISO Central Secretariat work of editing and text composition will be undertaken at publication stage.

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.



Reference number
ISO/DIS 22674.2:2013(E)

© ISO 2013

ITeH STANDARD PREVIEW
(standards.iteh.ai)
Full standard:
<https://standards.iteh.ai/catalog/standards/sist/17403ee3-3966-422b-a3ba-a52cd418451d/iso-22674-2016>

Copyright notice

This ISO document is a Draft International Standard and is copyright-protected by ISO. Except as permitted under the applicable laws of the user's country, neither this ISO draft nor any extract from it may be reproduced, stored in a retrieval system or transmitted in any form or by any means, electronic, photocopying, recording or otherwise, without prior written permission being secured.

Requests for permission to reproduce should be addressed to either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Reproduction may be subject to royalty payments or a licensing agreement.

Violators may be prosecuted.

Contents

Page

1	Scope	1
2	Normative references	1
3	Terms and definitions	1
4	Classification	3
5	Requirements.....	3
5.1	Chemical composition	3
Table 1 — Permitted deviation from the reported composition for elements.....		4
5.2	Hazardous elements.....	4
5.3	Biocompatibility.....	4
5.4	Mechanical properties.....	5
Table 2 — Mechanical properties		5
5.5	Elastic modulus	7
5.6	Density.....	7
5.7	Corrosion resistance for material integrity.....	7
5.8	Tarnish resistance.....	7
5.9	Solidus and liquidus temperatures (alloy) or melting point (commercially pure metal)	8
5.10	Thermal expansion coefficient.....	8
5.11	Information, instructions and marking.....	8
6	Sampling	8
7	Preparation of test specimens.....	8
7.1	General	8
7.2	Heat treatment	8
7.3	Proof stress of 0,2 % non-proportional extension and the elongation after fracture: Metallic materials for which production of conventional specimens is possible	9
7.4	Type 0 metallic materials for which the production of conventional specimens is not possible	10
7.5	Elastic moduli	10
7.6	Density measurement	12
7.7	Corrosion resistance.....	12
7.8	Tarnish resistance and colour	12
7.9	Linear thermal expansion.....	12
8	Test methods	12
8.1	Information, instructions and marking.....	12
8.2	Chemical composition	12
8.3	Mechanical testing	13
8.4	Proof stress of 0,2 % non-proportional extension.....	14
8.5	Percentage elongation after fracture.....	14
8.6	Elastic modulus measurement	14
8.7	Calculation of elasticity parameters from acoustic measurement	18
8.8	Density.....	19
8.9	Corrosion resistance by the static immersion procedure of ISO10271:2011	20
8.10	Sulfide tarnish test (cyclic immersion)	21
8.11	Sulfide tarnish test (static immersion).....	21
8.12	Solidus and liquidus temperatures (dental casting alloys) or melting point (commercially pure metals)	21
8.13	Linear thermal expansion.....	22
9	Information and instructions for use.....	22

9.1	Information	22
9.2	Processing instructions	23
10	Marking and labelling	23
10.1	Marking	23
10.2	Labelling of the package	24
Annex A (informative) Tensile testing of a non-cast Type 0 metallic material that is intended for use in a thickness between 0,1 mm and 0,5 mm		
A.1	Preparation of test specimen	25
A.2	Specimen numbers	26
A.3	Testing	26
A.4	Test report	27
Annex B (normative) Calculation of uncertainty for elasticity measurement		
B.1	Representation of uncertainty for elasticity measurement	28
B.2	Tensile strain method	29
B.3	Flexure method	30
B.4	Acoustic resonance	31
Annex C (informative) Measurement of Poisson ratio		
C.1	Purpose	33
C.2	Terms and definitions	33
C.3	Measurement methods	33

iTeh STANDARD PREVIEW
 (standards.iteh.ai)
 Full standard:
<https://standards.iteh.ai/catalog/standards/sist/17403e3-3966-422b-a3ba-a52cd418451d/iso-22674-2016>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 22674 was prepared by Technical Committee ISO/TC 106, *Dentistry*, Subcommittee SC 2, *Prosthetic materials*.

This second edition cancels and replaces the first edition (ISO 22674:2006), which has been technically revised. The following changes were made:

- a) Corrosion resistance measurement was referred to the recent standard ISO 10271: 2011;
- b) A second tarnish test was included, referring provisions of ISO 20271: 2011;
- c) Clarification of the term “free of “ was added to the requirements of composition and labelling;
- d) Lead was added as a hazardous element;
- e) Measurement of elasticity was revised. Beside the method of calculation of elastic modulus using an extensometer, other alternative methods were added, namely, the flexure method in three- and four-point bending and the acoustic resonance method;
- f) Informative Annex A was added, dealing with tensile testing of non-cast Type 0 metallic materials intended for use in a thickness between 0,1 and 0,5 mm;
- g) Normative Annex B was added, giving information on calculation of uncertainty for elastic measurement;
- h) Informative Annex C was added, giving information for measurement of Poisson ratio.

Introduction

Specific qualitative and quantitative requirements for freedom from biological hazard are not included in this International Standard but it is recommended that, in assessing possible biological hazards, reference should be made to ISO 10993-1 and ISO 7405.

Requirements for the performance of metals and alloys used for the metallic component of a metal-ceramic restoration contained in this International Standard supersede such requirements formerly contained in ISO 9693. The requirements for the performance of ceramic material and the metal-ceramic bond in metal-ceramic restorative systems continue to be specified in ISO 9693-1.

Requirements for the proof stress and minimum elongation after fracture for Type 0 metallic materials are not included in this International Standard, but it is recommended to adopt the test procedure given in Annex A when measuring these properties. Requirements will be included in a revision of this International Standard when information becomes available to Technical Committee ISO/TC106 Subcommittee 2.

iTeh STANDARD PREVIEW
(standards.iteh.ai)
Full standard:
<https://standards.iteh.ai/catalog/standards/sist/17403ee3-3966-422b-a3ba-a52cd418451d/iso-22674-2016>

Dentistry — Metallic materials for fixed and removable restorations and appliances

1 Scope

This International Standard classifies metallic materials that are suitable for the fabrication of dental appliances and restorations, including metallic materials recommended for use either with or without a ceramic veneer, or recommended for both uses, and specifies their requirements. It further specifies requirements with respect to packaging and marking the products and to the instructions to be supplied for the use of these materials, including products delivered for sale to a third party.

This International Standard does not apply to alloys for dental amalgam (ISO 24234), dental brazing materials (ISO 9333), or metallic materials for orthodontic appliances (ISO 15841) (e.g., wire, bracket, band and screw).

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1942, *Dentistry — Vocabulary*

ISO 3585, *Borosilicate glass 3.3 — Properties*

ISO 3696, *Water for analytical laboratory use — Specification and test methods*

ISO 6344-1:2001, *Coated abrasives — Grain size analysis — Part 1: Grain size distribution test*

ISO 7183: 2007, *Compressed-air dryers — Specifications and testing*

ISO 9693-1, *Dentistry — Compatibility testing — Part 1: Metal-ceramic systems*

ISO 10271: 2011, *Dentistry — Corrosion test methods for metallic materials*

ISO 12781-1:2011, *Geometrical product specifications (GPS) — Flatness — Part 1: Vocabulary and parameters of flatness*

ISO 15223-1: 2012, *Medical devices — Symbols to be used with medical device labels, labelling and information to be supplied — Part 1: General requirements*

3 Terms and definitions

For the purposes of this document, the terms and definitions of ISO 1942 and the following apply.

3.1

base metal

any metallic element with the exception of noble metals (i. e. gold and metals of the platinum group) and silver

**3.2
hazardous element**

element that is known for its potential to produce an adverse biological effect

Note 1 to entry: The presence of such an element (as an alloying addition or as an impurity) in a dental alloy does not imply that the alloy, in itself, is hazardous.

**3.3
metallic material**

material having the properties that are associated with an alloy, noble metal or base metal

Note 1 to entry: This may be a pure element, commercially pure metal or an alloy.

**3.4
casting alloy**

metallic material designed for casting into an investment mould

**3.5
ceramic veneer**

thin ceramic surface layer present on a metallic material restoration to provide an aesthetic effect

**3.6
metal-ceramic restoration**

dental restoration in which a ceramic veneer is bonded to a metallic material substructure by firing

Note 1 to entry This can apply also to the metallic material used for such a restoration. In this context metal-ceramic alloy is a synonym.

Note 2 to entry If recommended, such a metallic material may be used without a ceramic veneer.

**3.7
metallic base**

noble metal or base metal with highest concentration by mass fraction in the alloy

Note 1 to entry: The name of this element shall precede the words “-based metallic material for dental restoration” or “-based dental casting alloy” or “-based dental metal-ceramic material”, as is appropriate.

**3.8
base-metal alloy**

alloy having a base metal as the principal element

**3.9
as-cast condition**

metallurgical condition of the metallic material in its solid state when removed from the casting machine

Note 1 to entry This condition is dependent upon the manufacturer’s recommended cooling procedure (e. g. bench cooling).

**3.10
bench-cooling**

process whereby a casting is retained in its investment with exposed metal uppermost and placed on a flat, insulating surface at ambient temperature in freely circulating air until its temperature falls to ambient

**3.11
hardening**

heat-treatment of a metallic material producing a condition which provides a higher 0,2 % proof stress than the “as-cast” state

Note 1 to entry: if recommended by the manufacturer, explicit instructions shall be given in the instructions for use.

3.12**softening**

heat-treatment of a metallic material producing a condition which provides a lower 0,2 % proof stress than the "as-cast" state

Note 1 to entry: If recommended by the manufacturer, explicit instructions shall be given in the instructions for use.

3.13**one-surface inlay**

an inlay restoration that is exposed to the oral environment on one and no more of the surfaces that are used to define the tooth for the purposes of charting

4 Classification

For the purposes of this International Standard a metallic material is classified, according to its mechanical properties as a Type number, of which there are six.

Examples of the applications for which these Types are intended are as follows:

- **Type 0:** intended for low stress bearing single-tooth fixed prostheses, e. g. small veneered one-surface inlays, veneered crowns.
NOTE Metallic materials for metal-ceramic crowns produced by electroforming or sintering belong to Type 0.
- **Type 1:** for low stress bearing single-tooth fixed prostheses, e. g. veneered or unveneered one-surface inlays, veneered crowns.
- **Type 2:** for single tooth fixed restorations, e. g. crowns or inlays without restriction on the number of surfaces.
- **Type 3:** for multiple unit fixed prostheses.
- **Type 4:** for appliances with thin sections that are subject to very high forces, e. g. removable partial dentures, clasps, thin veneered single crowns, full arch fixed dental prostheses or those with small cross-sections, bars, attachments, implant retained superstructures.
- **Type 5:** for appliances in which parts require the combination of high stiffness and proof stress, e. g. thin removable partial dentures, parts with thin cross-sections, clasps.

NOTE 1: The higher application type may include lower application types.

NOTE 2: Multiple-unit and full-arch, fixed dental prostheses are also referred to as bridges.

5 Requirements**5.1 Chemical composition****5.1.1 Reported composition**

For all elements that are present in excess of 1,0 % (mass fraction), each constituent element shall be declared by the manufacturer and shall be reported [see 9.1 a)] to a precision of 0,1 % (mass fraction).

Any element that is present in excess of 0,1 % (mass fraction), but not of 1,0 % (mass fraction), shall be identified in [see 9.1 a)] either by name or symbol.

NOTE For example: If a constituent element is present with 0,6 % (m/m), it shall be identified [9.1 a)] either by name or symbol, if a constituent element is present with 22,06 % (m/m), it shall be reported [9.1 a)] as 22,1 % (precision of 0,1 % (mass fraction)).

If the metallic material contains less than 0,1% (mass fraction) of a specified element (other than one named in 5.2), it may be named as “free of “ this specified element. This limit has to be adhered to by natural impurities in the material.

5.1.2 Permitted deviation from the reported composition for elements

The permitted deviation of the reported composition for elements from the value stated on the package or label or insert [see 9.1 a)]. is given in Table 1.

Table 1 — Permitted deviation from the reported composition for elements

Alloy	Range of element content	
	1,0% < mass fraction ≤ 20%	mass fraction >20 %
Base metal alloy	max. 1,0 %	max. 2,0 %
Silver-based and noble metal alloy	max. 0,5 %	max. 0,5 %

5.2 Hazardous elements

5.2.1 Recognized hazardous elements

For the purposes of this International Standard the elements nickel, cadmium, beryllium and lead are designated to be hazardous elements.

5.2.2 Permitted limits for the hazardous elements cadmium and beryllium

The metallic material shall not contain more than 0,02 % (mass fraction) cadmium or beryllium.

5.2.3 Permitted limit for lead

The metallic material shall not contain more than 0,1% (mass fraction) lead.

5.2.4 Nickel

5.2.4.1 Manufacturer's reported nickel content and permitted deviation

If the metallic material contains more than 0,1 % (mass fraction) nickel, this content shall be given to an accuracy of 0,1 % (mass fraction) in the literature which accompanies the package [see 9.1 n)] and on the package, label or insert [see 10.2 f)].

The mass fraction shall not exceed the value stated in 9.1 n) and 10.2 f).

5.2.4.2 Nickel free products

For the purposes of this International Standard, alloys with max. 0,1 % (mass fraction) nickel may be labelled “nickel free” [see 9.1 o) and 10.2 g)].

If nickel is not declared, it must be limited to max. 0.1%. This limit has to be adhered to nickel is a natural impurity in a component of the alloy.

5.3 Biocompatibility

See the introduction for guidance on biocompatibility.

5.4 Mechanical properties

5.4.1 General

This requirement (see Table 2) shall be met by the metallic material after the recommended processing techniques (e. g. casting, bench-cooling, machining) and after the ceramic firing schedule (if appropriate) have been applied. A metallic material recommended for use either with or without a ceramic veneer shall meet this requirement in both metallurgical conditions.

If a heat-treatment is recommended by the manufacturer [see 9.2 c)] this requirement shall be met by the material in the heat-treated condition, applied in accordance with the manufacturer's instructions for use.

For a metallic material, the Type may be classified differently (according to Table 2) if it is recommended for use in more than one metallurgical condition (produced by alternative processing schedules). The highest applicable Type shall be specified for each condition.

Table 2 — Mechanical properties

Type	Proof stress of 0,2 % non-proportional extension $R_{p0.2}$ MPa minimum	Elongation after fracture %	Young's modulus GPa minimum
0	—	—	—
1	80	18	—
2	180	10	—
3	270	5	—
4	360	2	—
5	500	2	150

Testing shall be done according to 8.3.

5.4.2 Proof stress of 0,2 % non-proportional extension

5.4.2.1 Determination of compliance

Refer to the classification Type stated in 9.1 b).

If four, five or six of the results for the set of six specimens in the first test series meet the requirement for proof stress of 0,2 % non-proportional extension, the metallic material complies with the requirement.

If two or fewer of the results for the set of six specimens in the first test series meet the requirement for proof stress of 0.2 % non-proportional extension, the metallic material fails to comply with the requirement.

NOTE 1 Two lots of six specimens are produced (see 7.). One of these lots is tested in the first test series. If required, replacement specimens are drawn from the second lot and used in the first test series. The remaining specimens in the second lot form the second test series.

NOTE 2 In this context, the number six is reached to complete the set in the first test series when the number of specimens tested less those rejected after post fracture examination (8.3.2) is six, (i. e. replacement specimens are included in the total).

If three or four specimens in the first lot of six specimens are rejected on the basis of 8.3.2 and replaced with specimens from the second lot, all twelve specimens shall be tested. If at least eight results meet the

requirement for proof stress of 0,2 % non-proportional extension the metallic material complies with the requirement.

If three of the results for the set of six specimens in the first test series meet the requirement for proof stress of 0,2 % non-proportional extension, all remaining specimens shall be tested in a second test series. If five or six of the results for the specimens in the second test series meet the requirement for proof stress of 0,2 % non-proportional extension, the metallic material complies with the requirement.

NOTE 3 Under this compliance criterion, if one specimen from the first lot has been rejected on the basis of inspection after fracture (8.3.2) during the first test series and a specimen from the second lot of six used as its replacement, then all five remaining specimens in the second series must meet the requirement. Only one replacement is possible for a borderline metallic material.

If three of the results for the first set of six specimens in the first test series meet the requirement for proof stress of 0,2 % non-proportional extension and four or fewer of the results from the specimens in the test second series meet the requirement for proof stress of 0,2 % non-proportional extension, the metallic material fails to comply with the requirement.

Testing shall be done according to 8.3.2.

5.4.2.2 Mean value

The mean value for the proof stress of 0,2 % non-proportional extension shall not differ by more than 10 % from the value given in the literature accompanying the package [see 9.1 c)].

5.4.3 Elongation after fracture

5.4.3.1 Determination of compliance with the requirement

Refer to the classification Type stated in 9.1 b).

If the four, five or six of the results for the set of six specimens in the first test series that meet the requirement for proof stress of 0,2 % non-proportional extension also meet the requirement for elongation after fracture, the metallic material complies with the requirement for elongation after fracture.

If two or fewer of the results for the set of six specimens in the first test series meet the requirement for elongation after fracture, the metallic material fails to comply with the requirement for elongation after fracture.

NOTE 1 Two lots of six specimens are produced (see 7.). One of these lots is tested in the first test series. If required, replacement specimens are drawn from the second lot and used in the first test series. The remaining specimens in the second lot form the second test series.

NOTE 2 In this context, the number six is reached to complete the set in the first test series when the number of specimens tested less those rejected after post fracture examination (8.3.2) is six, (i. e. replacement specimens are included in the total).

If three or four specimens in the first lot of six specimens are rejected on the basis of 8.3.2 and replaced with specimens from the second lot, all twelve specimens shall be tested. If at least eight results of the specimens that meet the requirement for proof stress of 0,2 % non-proportional extension also meet the requirement for elongation after fracture, the metallic material complies with the requirement.

If three of the results for the first set of six specimens in the first test series that meet the requirement for proof stress of 0,2 % non-proportional extension also have an elongation after fracture that meets the requirement for elongation after fracture, all remaining specimens shall be tested in a second test series. If five or six of the results for the specimens in the second test series have both an elongation after fracture and a proof stress of 0,2 % non-proportional extension that meet both requirements, the metallic material complies with the requirement for the percentage elongation after fracture. If the results for the five or six specimens in the second series meet the requirement for elongation after fracture, but not the requirement for proof stress of 0,2 % non-proportional extension, the metallic material fails to comply with requirement for elongation after fracture.

NOTE 3 Under this compliance criterion, if one specimen in the first lot has been rejected on the basis of inspection after fracture (8.3.2) during the first test series and a specimen from the second lot of six used as its replacement, then all