

# SLOVENSKI STANDARD

## SIST EN ISO 4829-1:2018

01-julij-2018

Nadomešča:

SIST EN 24829-1:1997

SIST EN 24829-1:1997/AC:1997

---

**Jeklo in lito železo - Določevanje celotnega silicija - Spektrofotometrična metoda z reduciranim molibdo-silikatom - 1. del: Deleži silicija med 0,05 % in 1 % (ISO 4829-1:2018)**

Steel and cast iron - Determination of total silicon contents - Reduced molybdosilicate spectrophotometric method - Part 1: Silicon contents between 0,05 % and 1,0 % (ISO 4829-1:2018)

[https://standards.iteh.ai](https://standards.iteh.ai/catalog/standards/sist/89d78a15-1e14-4cd1-91bc-9865266e8043/sist-en-iso-4829-1-2018)  
(standards.iteh.ai)

Stahl- und Gusseisen - Bestimmung des Gesamtsiliciumanteils - Spektrophotometrische Methode mit reduziertem Molybdatosilicat - Teil 1: Siliciumanteile zwischen 0,05 % und 1,0 % (ISO 4829-1:2018)

Aciers et fontes - Détermination du silicium total - Méthode spectrophotométrique au silicomolybdate réduit - Partie 1: Teneurs en silicium comprises entre 0,05 % et 1,0 % (ISO 4829-1:2018)

**Ta slovenski standard je istoveten z: EN ISO 4829-1:2018**

---

**ICS:**

77.040.30	Kemijska analiza kovin	Chemical analysis of metals
77.080.01	Železne kovine na splošno	Ferrous metals in general

**SIST EN ISO 4829-1:2018**

**en**

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[SIST EN ISO 4829-1:2018](https://standards.iteh.ai/catalog/standards/sist/89d78a13-1ef4-4cd1-91bc-9865266e8043/sist-en-iso-4829-1-2018)

<https://standards.iteh.ai/catalog/standards/sist/89d78a13-1ef4-4cd1-91bc-9865266e8043/sist-en-iso-4829-1-2018>

EUROPEAN STANDARD

EN ISO 4829-1

NORME EUROPÉENNE

EUROPÄISCHE NORM

May 2018

ICS 77.080.01

Supersedes EN 24829-1:1990

English Version

Steel and cast iron - Determination of total silicon contents  
 - Reduced molybdosilicate spectrophotometric method -  
 Part 1: Silicon contents between 0,05 % and 1,0 % (ISO  
 4829-1:2018)

Aciers et fontes - Détermination du silicium total -  
 Méthode spectrophotométrique au silicomolybdate  
 réduit - Partie 1: Teneurs en silicium comprises entre  
 0,05 % et 1,0 % (ISO 4829-1:2018)

Stahl- und Gusseisen - Bestimmung des  
 Gesamtsiliciumanteils - Spektrophotometrische  
 Methode mit reduziertem Molybdatosilicat - Teil 1:  
 Siliciumanteile zwischen 0,05 % und 1,0 % (ISO 4829-  
 1:2018)

This European Standard was approved by CEN on 6 March 2018.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
 COMITÉ EUROPÉEN DE NORMALISATION  
 EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

<b>Contents</b>	<b>Page</b>
<b>European foreword.....</b>	<b>3</b>

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[SIST EN ISO 4829-1:2018](https://standards.iteh.ai/catalog/standards/sist/89d78a13-1ef4-4cd1-91bc-9865266e8043/sist-en-iso-4829-1-2018)  
<https://standards.iteh.ai/catalog/standards/sist/89d78a13-1ef4-4cd1-91bc-9865266e8043/sist-en-iso-4829-1-2018>

## European foreword

This document (EN ISO 4829-1:2018) has been prepared by Technical Committee ISO/TC 17 "Steel" in collaboration with Technical Committee ECISS/TC 102 "Methods of chemical analysis for iron and steel" the secretariat of which is held by SIS.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by November 2018, and conflicting national standards shall be withdrawn at the latest by November 2018.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 24829-1:1990.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

**iTeh STANDARD PREVIEW**  
**Endorsement notice**  
**(standards.iteh.ai)**

The text of ISO 4829-1:2018 has been approved by CEN as EN ISO 4829-1:2018 without any modification.

<https://standards.iteh.ai/catalog/standards/sist/89d78a13-1ef4-4cd1-91bc-9865266e8043/sist-en-iso-4829-1-2018>

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[SIST EN ISO 4829-1:2018](https://standards.iteh.ai/catalog/standards/sist/89d78a13-1ef4-4cd1-91bc-9865266e8043/sist-en-iso-4829-1-2018)

<https://standards.iteh.ai/catalog/standards/sist/89d78a13-1ef4-4cd1-91bc-9865266e8043/sist-en-iso-4829-1-2018>

INTERNATIONAL  
STANDARDISO  
4829-1Second edition  
2018-03

---

---

**Steel and cast iron — Determination  
of total silicon contents — Reduced  
molybdosilicate spectrophotometric  
method —**

Part 1:

**Silicon contents between 0,05 % and  
1,0 %****(standards.iteh.ai)***Aciers et fontes — Détermination du silicium total — Méthode  
spectrophotométrique au silicomolybdate réduit —*

<https://standards.iteh.ai/catalog/standards/sist/89d78a13-1ef1-4cd1-91bc-9865266e8043/sist-en-iso-4829-1-2018>  
**Partie 1: Teneurs en silicium comprises entre 0,05 % et 1,0 %**

Reference number  
ISO 4829-1:2018(E)

© ISO 2018

## iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN ISO 4829-1:2018

<https://standards.iteh.ai/catalog/standards/sist/89d78a13-1ef4-4cd1-91bc-9865266e8043/sist-en-iso-4829-1-2018>



### **COPYRIGHT PROTECTED DOCUMENT**

© ISO 2018

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
CP 401 • Ch. de Blandonnet 8  
CH-1214 Vernier, Geneva  
Phone: +41 22 749 01 11  
Fax: +41 22 749 09 47  
Email: [copyright@iso.org](mailto:copyright@iso.org)  
Website: [www.iso.org](http://www.iso.org)

Published in Switzerland



# Contents

	Page
Foreword.....	iv
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 Terms and definitions</b> .....	<b>1</b>
<b>4 Principle</b> .....	<b>1</b>
<b>5 Reagents</b> .....	<b>2</b>
<b>6 Apparatus</b> .....	<b>3</b>
<b>7 Sampling</b> .....	<b>4</b>
<b>8 Procedure</b> .....	<b>4</b>
8.1 Test portion.....	4
8.2 Blank test.....	4
8.3 Determination.....	4
8.3.1 Dissolution of the test portion.....	4
8.3.2 Treatment of insoluble residue.....	5
8.3.3 Preparation of the test solution.....	5
8.3.4 Development of the colour.....	5
8.3.5 Spectrophotometric measurements.....	6
8.4 Establishment of the calibration curve.....	6
8.4.1 Preparation of the calibration solutions.....	6
8.4.2 Spectrophotometric measurements.....	6
8.4.3 Plotting of the calibration curves.....	6
<b>9 Expression of results</b> .....	<b>7</b>
9.1 Method of calculation.....	7
9.2 Precision.....	8
<b>10 Test report</b> .....	<b>8</b>
<b>Annex A (informative) Additional information on the international interlaboratory test</b> .....	<b>9</b>
<b>Annex B (informative) Graphical representation of precision data</b> .....	<b>10</b>
<b>Bibliography</b> .....	<b>11</b>

## ISO 4829-1:2018(E)

### Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html). (standards.iteh.ai)

This document was prepared by Technical Committee ISO/TC 17, *Steel*, Subcommittee SC 1, *Methods of determination of chemical composition*. SIST EN ISO 4829-1:2018

This second edition cancels and replaces the first edition (ISO 4829-1:1986), which has been technically revised. https://standards.iteh.ai/catalog/standards/sist/89d78a13-1ef4-4cd1-91bc-881536f80437/iso-4829-1:2018

A list of all the parts in the ISO 4829 series can be found on the ISO website.

# Steel and cast iron — Determination of total silicon contents — Reduced molybdosilicate spectrophotometric method —

## Part 1:

## Silicon contents between 0,05 % and 1,0 %

### 1 Scope

This document specifies a spectrophotometric method for the determination of total silicon in steel and cast iron using reduced molybdosilicate.

The method is applicable to the determination of silicon mass fraction between 0,05 % and 1,0 %.

### 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 648, *Laboratory glassware — Single-volume pipettes*

ISO 1042, *Laboratory glassware — One-mark volumetric flasks*

ISO 3696, *Water for analytical laboratory use — Specification and test methods*

ISO 14284, *Steel and iron — Sampling and preparation of samples for the determination of chemical composition*

### 3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <https://www.iso.org/obp>

### 4 Principle

Dissolution of a test portion in an acid mixture appropriate to the alloy composition.

Fusion of the acid-insoluble residue with sodium peroxide. Formation of the oxidized molybdosilicate (yellow) complex in weak acid solution.

Selective reduction of the molybdosilicate complex to a blue complex with ascorbic acid, after increasing the sulphuric acid concentration and adding oxalic acid to prevent the interference of phosphorus, arsenic and vanadium.

Spectrophotometric measurement of the reduced blue complex at a wavelength of about 810 nm.