

SLOVENSKI STANDARD

SIST EN 46-2:2016

01-september-2016

Nadomešča:
SIST EN 46-2:2010

Biocidni proizvodi za zaščito lesa - Ugotavljanje preventivnega delovanja proti hišnemu kozličku *Hylotrupes bajulus* (Linnaeus) - 2. del: Ugotavljanje učinkovitosti proti jajčecem (laboratorijska metoda)

Wood preservatives - Determination of the preventive action against recently hatched larvae of *Hylotrupes bajulus* (Linnaeus) - Part 2: Ovicidal effect (laboratory method)

iTeh STANDARD PREVIEW

Holzschutzmittel - Bestimmung der vorbeugenden Wirkung gegenüber frisch geschlüpften Larven von *Hylotrupes bajulus* (Linnaeus) - Teil 2: Ovizide Wirkung (Laboratoriumsverfahren)

[SIST EN 46-2:2016](https://standards.iteh.ai/catalog/standards/sist/f7cbf28b-1af6-4be3-84d6-8d761293-1a41-en-46-2-2016)

[https://standards.iteh.ai/catalog/standards/sist/f7cbf28b-1af6-4be3-84d6-](https://standards.iteh.ai/catalog/standards/sist/f7cbf28b-1af6-4be3-84d6-8d761293-1a41-en-46-2-2016)

Produits de préservation du bois - Détermination de l'action préventive contre les larves récemment écloses d'*Hylotrupes bajulus* (Linnaeus) - Partie 2 : Effet ovicide (Méthode de laboratoire)

Ta slovenski standard je istoveten z: EN 46-2:2016

ICS:

71.100.50 Kemikalije za zaščito lesa Wood-protecting chemicals

SIST EN 46-2:2016

en,fr,de

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 46-2:2016

<https://standards.iteh.ai/catalog/standards/sist/f7cbf28b-1af6-4be3-84d6-891bb3f13cbd/sist-en-46-2-2016>

EUROPEAN STANDARD

EN 46-2

NORME EUROPÉENNE

EUROPÄISCHE NORM

June 2016

ICS 71.100.50

Supersedes EN 46-2:2009

English Version

Wood preservatives - Determination of the preventive action against recently hatched larvae of *Hylotrupes bajulus* (Linnaeus) - Part 2: Ovicidal effect (laboratory method)

Produits de préservation du bois - Détermination de l'action préventive contre les larves récemment écloses d'*Hylotrupes bajulus* (Linnaeus) - Partie 2: Effet ovicide (Méthode de laboratoire)

Holzschutzmittel - Bestimmung der vorbeugenden Wirkung gegenüber frisch geschlüpften Larven von *Hylotrupes bajulus* (Linnaeus) - Teil 2: Ovizide Wirkung (Laboratoriumsverfahren)

This European Standard was approved by CEN on 5 January 2017.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents	Page
European foreword	4
Introduction	5
1 Scope	6
2 Normative references	6
3 Terms and definitions	6
4 Principle	7
5 Test materials	7
5.1 Biological material	7
5.2 Products and reagents	7
5.3 Apparatus	7
6 Sampling	8
7 Test specimens	8
7.1 Species of wood	8
7.2 Wood quality	8
7.3 Provision of test specimens	9
7.4 Dimensions of test specimens	9
7.5 Number of test specimens	9
7.5.1 Test specimens for egg-laying	9
7.5.2 Test specimens for checking the tunnelling ability and the mortality of the larvae	10
8 Procedure	10
8.1 Preparation of the test specimens	10
8.1.1 Conditioning of the test specimens prior to sealing	10
8.1.2 Sealing of block faces	10
8.1.3 Treatment of the test specimens	10
8.1.4 Drying and conditioning of the test specimens after treatment	12
8.2 Exposure of the test specimens to the insects (ovicidal action)	12
8.3 Validity of the test	13
9 Expression of results	13
9.1 Ovicidal test	13
9.2 Tunnelling control	13
9.3 Total mortality	14
10 Test report	14
Annex A (informative) Example of a test report	16
Annex B (informative) Technique for culturing <i>Hylotrupes bajulus</i> (Linnaeus)	18
B.1 General	18
B.2 Obtaining parent beetles	18
B.3 Mating	18

B.4	Egg-laying	18
B.5	Hatching of eggs	19
B.6	Larval development	19
B.7	Enemies and parasites	20
Annex C (informative) Differentiation of heartwood and sapwood in <i>Pinus</i> species		21
C.1	Principle	21
C.2	Reagents	21
C.3	Apparatus	21
C.4	Procedure	21
Annex D (informative) Environmental, health and safety precautions within chemical/biological laboratory		22
Bibliography		23

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN 46-2:2016](https://standards.iteh.ai/catalog/standards/sist/f7cbf28b-1af6-4be3-84d6-891bb3f13cbd/sist-en-46-2-2016)

<https://standards.iteh.ai/catalog/standards/sist/f7cbf28b-1af6-4be3-84d6-891bb3f13cbd/sist-en-46-2-2016>

EN 46-2:2016 (E)**European foreword**

This document (EN 46-2:2016) has been prepared by Technical Committee CEN/TC 38 “Durability of wood and wood-based products”, the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by December 2016, and conflicting national standards shall be withdrawn at the latest by December 2016.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 46-2:2009.

Significant technical differences between this document and EN 46-2:2009 are as follows:

- a) introduction of new harmonised specifications for wood quality;
- b) option to omit control test specimens treated with the solvent or diluents only when the solvent or diluents is water of drinking quality.

The standard EN 46 is composed of two parts:

- EN 46-1, *Wood preservatives – Determination of the preventive action against recently hatched larvae of *Hylotrupes bajulus* (Linnaeus) – Part 1: Application by surface treatment (laboratory method)*
SIST EN 46-2:2016
<https://standards.iteh.ai/catalog/standards/sist/f7cbf28b-1af6-4be3-84d6-891bb3f13cbd/sist-en-46-2-2016>
- EN 46-2, *Wood preservatives – Determination of the preventive action against recently hatched larvae of *Hylotrupes bajulus* (Linnaeus) – Part 2: Ovicidal effect (laboratory method)*

EN 46 consists of two parts to enable preventive action of wood preservatives, against recently hatched larvae of *Hylotrupes bajulus*, which are intended to be applied by surface treatment; Part 1 is required to determine the larvicidal effect of preservatives and Part 2 is required to determine the ovicidal action of the preservatives after egg-laying of young females.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Introduction

This test method describes a laboratory method of test which gives a basis for the assessment of the preventive action of a wood preservative, when applied as a surface treatment for timber, against eggs of *Hylotrupes bajulus*.

In combination with EN 46-1 it provides a means of checking whether larvae may hatch from eggs laid on the treated wood surface and whether they are capable of boring through the treated surface and of surviving in the untreated part of the wood.

This standard provides information for the sealing of all but one lateral face when specimens are to be treated by dipping.

When products which are very active at very low concentration are used, it is very important to take suitable precautions to isolate and separate, as far as possible, operations involving chemical products, other products, treated wood, laboratory apparatus and clothing. Suitable precautions should include the use of separate rooms, areas within rooms, extraction facilities, conditioning chambers and special training for personnel (see also Annex D for environmental, health and safety precautions).

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN 46-2:2016](https://standards.iteh.ai/catalog/standards/sist/f7cbf28b-1af6-4be3-84d6-891bb3f13cbd/sist-en-46-2-2016)

<https://standards.iteh.ai/catalog/standards/sist/f7cbf28b-1af6-4be3-84d6-891bb3f13cbd/sist-en-46-2-2016>

EN 46-2:2016 (E)**1 Scope**

This European Standard specifies a method for the determination of the preventive action of a wood preservative against eggs of *Hylotrupes bajulus* (Linnaeus) when the preservative is applied as a surface treatment to wood.

This method is applicable to:

- water-insoluble chemicals which are being studied as active insecticides;
- organic formulations, as supplied or as prepared in the laboratory by dilution of concentrates;
- organic water-dispersible formulations as supplied or as prepared in the laboratory by dilution of concentrates; or
- water-soluble materials, for example salts.

The method is applicable whether or not the test specimens have been subjected to appropriate ageing procedures.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 46-1, *Wood preservatives — Determination of the preventive action against recently hatched larvae of Hylotrupes bajulus (Linnaeus) — Part 1: Application by surface treatment (laboratory method)*

EN 73, *Wood preservatives — Accelerated ageing of treated wood prior to biological testing — Evaporative ageing procedure*

EN 84, *Wood preservatives — Accelerated ageing of treated wood prior to biological testing — Leaching procedure*

EN ISO 3696, *Water for analytical laboratory use — Specification and test methods (ISO 3696)*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1**representative sample**

sample having its physical and/or chemical characteristics identical to the volumetric average characteristics of the total volume being sampled

[SOURCE: EN 1001-2:2005, 4.71]

3.2

supplier

sponsor of the test (person or company providing the sample of wood preservative to be tested)

Note 1 to entry: Adapted from EN 1001-2:2005, 4.83.

4 Principle

In this laboratory method treated wood panels are offered to freshly mated *Hylotrupes bajulus* females. The hatching ability of the larvae on the treated timber is examined. When the ovicidal action is insufficient, the mortality of the hatched larvae on and/or in wood treated with the same formulation is also established according to EN 46-1.

5 Test materials

5.1 Biological material

5.1.1 *Hylotrupes bajulus* (Linnaeus) females.

5.1.2 Source of females

The insects shall preferably be obtained from cultures reared as e.g. described in Annex B. Use only sound and lively insects.

5.2 Products and reagents

5.2.1 **Paraffin wax**, for fixing the glass plate in all cases and for sealing the end faces of test specimens to be treated with solutions in all cases in which water is the continuous phase.

NOTE Paraffin wax with a setting point of 52 °C to 54 °C has been found to be suitable.

5.2.2 **Gelatine**, for sealing the end faces of test specimens to be treated with solutions in which an organic solvent is the continuous phase.

5.2.3 **Water**, complying with grade 3 of EN ISO 3696.

5.2.4 **Solvent or diluent**, a volatile liquid that will dissolve or dilute the preservative but does not leave a residue in the wood at the end of the post-treatment conditioning period that has a toxic effect on the insects.

CAUTION — Do not use benzene or other solvents which pose a health risk.

5.3 Apparatus

5.3.1 **Culturing chamber**, with air circulation, and controlled at (28 ± 2) °C and at relative humidity (70 ± 5) %.

5.3.2 **Conditioning chamber**, well ventilated and controlled at (20 ± 2) °C and at relative humidity (65 ± 5) %.

The conditioning of test specimens may be carried out in the laboratory work area (see 5.3.3) provided that this has the conditions specified for the conditioning chamber (see 5.3.2).

EN 46-2:2016 (E)

5.3.3 Laboratory work area, well ventilated, where treatment of the test specimens is carried out.

CAUTION — It is essential to follow safety procedures for handling flammable and toxic materials. Avoid excessive exposure of operators to solvents or their vapours.

5.3.4 Testing chamber, ventilated and air-conditioned, controlled at (22 ± 2) °C and at relative humidity between (70 ± 5) %.

5.3.5 Petri dishes of glass or polyvinylchloride (PVC), diameter ca. 9 cm for mating the insects and for egg-laying.

5.3.6 Weights, to provide ballast for the test specimens.

The weights shall not react with any materials with which they come into contact during the test.

5.3.7 Safety equipment, protective clothing, appropriate for the test product and the test solvent, to ensure the safety of the operator.

5.3.8 Glass plates, (48 ± 1) mm long and (25 ± 1) mm wide, intended to provide a lateral slit on the test specimens.

5.3.9 Ordinary laboratory equipment, including a balance capable of weighing to an accuracy of 0,01 g and equipment for applying a liquid product by brushing or by pipette.

5.3.10 Protective gloves

ITeH STANDARD PREVIEW
(standards.iteh.ai)

6 Sampling

SIST EN 46-2:2016

<https://standards.iteh.ai/catalog/standards/sist/f7cbf28b-1af6-4be3-84d6-991e57350057/en-46-2:2016>

The sample of preservative shall be representative of the product to be tested. Samples shall be stored and handled in accordance with any written recommendations from the supplier.

For the sampling of preservatives from bulk supplies, the procedure given in EN 212 should be used.

7 Test specimens

7.1 Species of wood

The reference species is Scots pine (*Pinus sylvestris* Linnaeus)¹⁾.

Additional tests may be carried out using other species but, if so, this shall be stated in the test report.

7.2 Wood quality

The wood shall be free from visible cracks, stain, decay, insect damage and other defects. The wood shall not have been water-stored, floated, chemically treated or steamed. The wood shall originate from trees preferably felled in winter. The trees shall be cut immediately after felling

¹⁾ In southern European countries the pine species most frequently infested by *Hylotrupes bajulus* may be used as an alternative, provided that the suitability of the species for use in the tests specified in this standard has been demonstrated in all aspects (development of larvae, resistance of impregnation, etc.).

and the timber rapidly air dried or kiln dried at temperatures below 60 °C. The wood shall not have been stored for more than five years.

The wood shall be exclusively sapwood containing little resin and having between 2,5 annual rings per 10 mm and eight annual rings per 10 mm. The proportion of latewood in the annual rings shall not exceed 30 % of the whole.

It is recommended to use test specimens of similar growth rate within a single test.

7.3 Provision of test specimens²⁾

Prepare planed strips having a cross-section of $(25 \pm 0,5)$ mm \times $(15 \pm 0,5)$ mm removing a minimum of 2 mm from any surfaces exposed during drying. The longitudinal faces shall be parallel to the direction of the grain. The annual rings shall have a contact angle of $45^\circ \pm 15^\circ$ to the broad faces. Make transverse cuts, neatly to give sharp edges and a fine-sawn finish to the end-grain surfaces, to give test specimens $(50 \pm 0,5)$ mm long.

The test specimens shall originate from a minimum of three trees or shall be taken at random from a stock originally of more than 500 test specimens.

7.4 Dimensions of test specimens

The dimensions of each test specimen after reaching equilibrium in the conditioning chamber (5.3.2) shall be $(50 \pm 0,5)$ mm \times $(25 \pm 0,5)$ mm \times $(15 \pm 0,5)$ mm.

Mark each test specimen so that it can be identified throughout the test.

7.5 Number of test specimens

7.5.1 Test specimens for egg-laying

- a) Six treated test specimens (no more than two originating from the same tree unless taken at random from a stock of more than 500) for each preservative, each concentration and each duration of treatment;
- b) three untreated control test specimens (each originating from a different tree unless taken at random from a stock of more than 500) for a complete test of any given preservative;
- c) three control test specimens treated with the solvent or diluent (5.2.3 or 5.2.4) (each originating from a different tree unless taken at random from a stock of more than 500) if a solvent or diluent (including water) is used.

Control test specimens under c) may be omitted if the solvent or diluents is water of drinking quality

When dipping is to be used (8.1.3.3) it is advisable to treat more than the specified number of test specimens so that, after weighing, any test specimens with abnormally high or low retentions can be rejected from the batch.

NOTE To gain further information on a formulation, the manufacturer may find it useful to test a version of the preservative where the active ingredient(s) has been removed.

²⁾ For special tests, test specimens may be obtained according to a given series. As a result, it may be preferable to take test specimens from pretreated strips. Where pretreated strips are used details should be included in the test report.