



Designation: D2394-83 (Reapproved 1999)

Standard Methods for Designation: D 2394 – 05^{ε1}

Standard Test Methods for Simulated Service Testing of Wood and Wood-Base Finish Flooring¹

This standard is issued under the fixed designation D 2394; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

^{ε1} NOTE—Editorial corrections were made in Section 32 and Section 33 in March 2008.

1. Scope

1.1 These test methods cover procedures for measuring the performance of finish flooring under the following service loadings and conditions:

	Section
Loading Tests	
Concentrated Loading	7
Floor Surface Indentation from Small Area Loads	12
Falling-Ball Indentation	18
Rolling Load	23
Mechanical Tests	
Abrasion Resistance	28
Coefficient of Friction	33
Moisture Tests	
Surface Wetting	38

2. Referenced Documents

2.1 *ASTM Standards:*²

D 1037 Test Methods for Evaluating Properties of Wood-Base Fiber and Particle Panel Materials

E 72 Test Methods of Conducting Strength Tests of Panels for Building Construction

3. Significance and Use

3.1 The test methods presented herein are intended to provide both a factual and comparative means of appraising the suitability of finish flooring. The procedures developed simulate some conditions of use that may require either maintenance beyond that considered normal or replacement of the floor surface material.

3.2 It is important for some of the evaluations that the substrate to be used beneath the finish flooring be duplicated because the kind/type and degree of support will have a direct influence on the value obtained from test. For example, in some present-day construction, low-density materials are used for sound-deadening immediately below the finish flooring. The way this substrate distributes loading and absorbs energy will have an influence on evaluations such as those in rolling and concentrated loads.

3.3 The test methods presented herein may be used to compare different finish floorings as to their resistance to severe and ordinary service loads and also may serve as the means to set specification limits. The properties obtained by these test methods are needed in addition to such basic material properties as stiffness, strength, hardness, and dimensional stability.

3.4 Not all test may be required for any specific investigation. There may be an interrelation between two tests, and when it has been demonstrated what the interrelation is, a complete evaluation will only be required as a final stage of a study. In each instance,

¹ These methods are under the jurisdiction of ASTM Committee D-7 on Wood and are the direct responsibility of Subcommittee D07.01 on Fundamental Test Methods and Properties.

Current edition approved Feb. 25, 1983. Published April 1983. Originally published as D2394-65T. Last previous edition D2394-69(1977).

² These test methods are under the jurisdiction of ASTM Committee D07 on Wood and are the direct responsibility of Subcommittee D07.01 on Fundamental Test Methods and Properties.

Current edition approved Oct. 1, 2005. Published October 2005. Originally approved in 1965. Last previous edition approved in 1999 as D 2394 – 83 (1999).

³ Annual Book of ASTM Standards, Vol 04.10.

⁴ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For Annual Book of ASTM Standards volume information, refer to the standard's Document Summary page on the ASTM website.

therefore, it will be necessary to determine which evaluations should be made to fulfill the objectives.

4. Test Specimens

4.1 The number of specimens to be chosen for test and the method of their selection depend on the variability of the finish flooring material and on the purpose of the particular tests under consideration, so no general rule can be given to cover all instances. It is recommended that, whenever possible, sufficient replications be made to establish reliable mean values. Even for the most simple evaluation, a replication of three tests for each property is recommended.

5. Control of Moisture Content and Temperature

5.1 Wood and wood-base materials are hygroscopic. The moisture content at time of test will influence values obtained from tests. Therefore, material for test shall be conditioned to essentially constant weight at a condition of $65 \pm 1\%$ relative humidity and a temperature of $68 \pm 6^\circ\text{F}$ ($20 \pm 3^\circ\text{C}$) (Note 1 and Note 2). If there is any departure from this recommended condition, it shall be so stated in the report. No tests shall be made on any material when it is not essentially stable in moisture content.

NOTE 1—In following the recommendation that the temperature be controlled to $68 \pm 6^\circ\text{F}$ ($20 \pm 3^\circ\text{C}$) it should be understood that it is desirable to maintain the temperature as nearly constant as possible at some temperature within this range.

NOTE 2—Requirements for temperature and relative humidity vary for different materials and different conditions of use. The condition above meets the standard condition for wood and wood-base materials, and for finish flooring represents the near-maximum seasonal condition for most locations. The amount of damage from the various loadings is usually greater at higher moisture contents than at lower ones.

6. Report

6.1 The data recorded shall include, in addition to the actual test results and data required specifically from each test, a complete description of the material, sampling procedure, and record of any special treatment or conditioning of the flooring material. Any special details concerning the material under test that may have a bearing on the results shall also be recorded.

CONCENTRATED LOADING

7. Scope

7.1 Specimens shall be subjected to the concentrated loading test to obtain a measure of the resistance of the finish flooring to heavy loads produced by such articles of furniture as chests and pianos. This test procedure uses the same equipment and is essentially the same as the one described in Test Methods E 72.


8. Test Specimen

8.1 The size of the test specimen will depend on the size of components making up the finish flooring, but should be at least 18 in. (457 mm) square. When the finish flooring is prefabricated in parquet or tile form, the specimen shall consist of at least four such tiles attached to an underlayment, subfloor, or other substrate, using the same construction and technique as will be used in the finished construction. When the flooring is manufactured in strip form, the flooring shall be laid in courses over the subfloor and substrate so that end joints occur in the same manner as in actual construction. At least two such end joints shall occur near midwidth in the center one-half of the specimen. Fig. 1 shows the orientation for typical specimens using square and strip configurations of flooring.

9. Apparatus

9.1 The apparatus shall be assembled as shown in Fig. 2 and shall conform in the requirements for component parts as described in 9.1.1-9.1.4.

9.1.1 *Steel Disk Loading Tool*—The steel disk loading tool shall be 1 in. (25 mm) in diameter with the circumference of the end rounded to a radius of 0.05 in. (1.3 mm). The loading tool shall be provided with a collar to engage the movable tip of the micrometer dial for measuring deformation under load, and shall be fabricated with a means of fastening it to the platen of the testing machine or loading device.



NOTE 1—One in. equals 25.4 mm.

FIG. 1 Layout of Specimens for Concentrated Load Test




FIG. 2 Assembly for Concentrated Loading Test of Finish Flooring

9.1.2 *Deformation Gage*—The deformation gage shall consist of a dial micrometer mounted on the three-point supported bridge. The dial micrometer shall be of the kind with divisions of 0.001 in. (0.025 mm). The bridge shall be of sufficient length so that the distance between the single-point support and a line between the pair of point supports is at least 12 in. (305 mm). The bridge support shall have a slot in the center of its span of sufficient opening to clear the loading tool to permit placing the micrometer directly adjacent to the disk loading tool with the stem end in contact with the collar.

9.1.3 *Loading Device*—A testing machine with a platen area sufficiently large to accommodate the 18-in. (457-mm) square or other suitable loading device convenient for loading and measuring the amount of loading to 1000 lb (or 4.45 kN) at the prescribed rate shall be provided.

9.1.4 An indentation measuring tool, as required for the falling-ball indentation test (see 20.1.4) shall be provided for determining the residual indentation from the loading to 1000 lb (4.45 kN) 1 h after removal of load.

10. Procedure

10.1 *Loading Points*—Load points 1 and 2, for both square or rectangular parquet or tile form finish flooring, are illustrated in Fig. 1. Load point 1 for the tile form of flooring is near the corner, so that deformation under load at a corner can be determined. Load point 2 is provided to obtain an index of resistance to concentrated load at a point where the finish flooring can distribute the load because of its inherent stiffness. Load point 2 should be at the approximate center of the tile area, and when using a 12-in. (305-mm) deformation bridge, the bridge can be placed along the diagonal. Load point 1 for strip flooring is to simulate the loading condition possible when the concentrated load comes at or near an end joint. Load point 2 simulates the condition that exists when loading is on a continuous strip of flooring but there is a joint in the adjacent course of flooring. When strip flooring is less than 2 in. (51 mm) wide, the point of load 2 shall be centered on the strip. For other configurations of finish flooring, load point 1 should correspond to the one producing maximum deformation under load and point 2 the more average condition. In each instance, the 1-in. (25-mm) diameter loading disk shall be centered over the dimensioned point.

10.2 *Loading*—Apply the load continuously at a uniform rate of movement of the loading tool of 0.10 in. (2.5 mm)/min (Note 3) to 1000 lb (4.45 kN) (Note 4). After the load of 1000 lb (4.45 kN) has been applied, it shall be removed immediately so that residual deformation can be determined. Record any observed behavior of either the finish flooring or the substrate during test.

NOTE 3—The testing machine speed used shall not vary by more than $\pm 50\%$ from that specified for a given test. The testing machine speed shall mean the free-running, or no load, crosshead speed for testing machines of the mechanical-drive type and the loaded crosshead speed for testing machines of the hydraulic-loading type.

NOTE 4—For some evaluations of finish flooring where possible use is in commercial buildings, concentrated load evaluations may be desirable for loads greater than 1000 lb (4.45 kN). When this is so, the material shall be loaded first as specified and then, after residual deformation has been obtained, reloaded to the higher maximum load or failure.

10.3 *Residual Deformation*—One h after the load has been removed, measure the depth of residual indentation to the nearest 0.01 in. (0.25 mm), using the falling-ball indentation measuring tool described in 20.1.4.

11. Report

11.1 The report shall include typical load-deformation curves for load points 1 and 2. Each deformation value for 1000 lb (4.45 kN) loading, and residual after loading was removed, shall be presented. Any observations of behavior of either finish flooring or substrate or failures shall also be reported. Photographs showing nature of residual indentation after loading will be beneficial and should be included.

FLOOR SURFACE INDENTATION
FROM SMALL AREA LOADS

12. Scope

12.1 Specimens shall be subjected to the “indentation damage from small area load test” to obtain a measure of the resistance to sharp-edged small area loadings, such as women’s “stiletto” heels, protruding nailheads on other shoes, and indentation damage from small, hard objects on the surface either being stepped on or indented into the floor from rolling loads. In some of these “point” loadings, unit stresses are almost infinite. Some damage to the surface usually is going to occur.occurs. The purpose of this evaluation is to compare by observing the damage from this kind of loading, new finish flooring systems with those of established service performance, or two or more floorings to determine which may have better service possibilities. Results obtained are qualitative rather than quantitative.

13. Test Specimen

13.1 The test specimen shall be a composite of the various floorings being evaluated. When the number of materials being evaluated exceeds the number that can be fabricated in a single specimen, the different materials shall be distributed so that a representative number are included in each sample. Fig. 3 shows the specimen in position for test and the apparatus used for imposing the concentrated loads on the specimen. Specimens shall be approximately 9 in. (229 mm) wide and of any convenient length, so that the number of finish floorings being evaluated can be accommodated. Specimens shall be fabricated with the same substrate and in the same manner as is to be used in the application of the finished floor. When strip floorings are being evaluated, two sets of specimens shall be fabricated; one with the long dimension of the pieces of flooring parallel to, and one with the long direction of the flooring across the direction of movement of the studded roller. Cleats shall be provided to prevent sliding of the specimens.

14. Apparatus

14.1 The apparatus shall be assembled as shown in Fig. 3 and shall conform in the requirements for component parts as described in 14.1.1-14.1.3.

14.1.1 *Base*—The base shall be a rigid supported unit that will not deflect measurably under the rolling load. The surface of the base shall be slightly wider than the surface of the specimen, as is shown in Fig. 3.

14.1.2 *Roller*—The roller shall be a hard maple (or equivalent) cylinder 3¹³/₁₆ in. (97 mm) in diameter and approximately 18 in. (457 mm) long. The roller shall be studded with boot caulks (approximately 0.15 in. (4 mm) in diameter and projecting approximately 0.2 in. (5 mm), including collar, from surface of roller) 1 in. (25 mm) on center around the circumference for an 8-in. (203-mm) width. Alternate rows of studs shall be staggered. The ends of the roller shall be provided with arms for rolling it along the specimen and, either through trunnions or an axle with bearings and straps, provide a means for attaching the superimposed load on the specimen.

ASTM D2394-05e1

<https://standards.iteh.ai/catalog/standards/sist/05ae6e2e-07b2-43df-bdde-6992e02d2bb4/astm-d2394-05e1>



FIG. 3 Assembly for Tests of Floor-Surface Indentation from Small-Area Loads, Showing Loaded Maple Roller Studded with Boot Caulks and Specimens Firmly Supported on Heavy Beam

14.1.3 *Superimposed Load*—The superimposed load shall total 200 lb (890 N). This shall be in addition to the weight of roller, straps, and bearings and shall be divided equally on both ends of roller.

15. Procedure

15.1 Move the roller over the surface by rotation (force applied to arms) for 100 trips. A trip is defined as a single pass from one end of the specimen to the other. Forward and back are two trips.

16. Interpretation of Results

16.1 At the end of 100 trips, the damage to the different finish flooring samples shall be compared. The amounts of damage shall be classified as none to minor, moderate, severe, and complete. The complete classification would be, in the judgment of the investigator, so severe that replacement would be necessary if that kind of damage occurred in an actual installation.

17. Report

17.1 The report shall include a complete description of the finish flooring, substrate, and method of attaching the finish flooring to the substrate. Any slivering or other disintegration of the flooring surface beyond just denting shall be noted and the classification of the damage shall be reported. Photographs of actual tested specimens (Fig. 4) are desirable and shall be considered in reporting. In Fig. 4, material G can be considered typical of a specimen showing “~~none~~ to minor” damage; J is “moderate,” moderate, H “severe,” severe, and material I probably would be considered to be “complete.” complete.

FALLING-BALL INDENTATION

18. Scope

18.1 Specimens shall be subjected to the falling-ball indentation test to obtain a measure of the resistance of a finish flooring to impacts from dropped objects. In this procedure, the indentation-heights of drop data are plotted and a line drawn through the plotted points. The slope of this line, amount of indentation for a prescribed height of drop, and damage to the surface beyond indentation are values used as criteria. Each drop is made at a different location on the surface.

19. Test Specimen

19.1 The specimen shall be of any convenient size, in the same thickness as is to be used in the finished floor, but large enough (Note 5) so that twelve drops of the falling ball may be made without the value for indentation for one height of drop being influenced by another, or by being too close to the edge of the specimen. This means that a minimum area of about 100 in.² (0.065 m²) is required. In this test, the specimens are not backed by the underlayment or other substrate. The indentation is obtained with a minimum of energy absorption by any other component than the finished flooring.

[ASTM D2394-05e1](https://standards.iteh.ai/ASTM-D2394-05e1)

<https://standards.iteh.ai/catalog/standards/sist/05ae6e2e-07b2-43df-bdde-6992e02d2bb4/astm-d2394-05e1>




FIG. 4 Appearance of Finish Flooring Specimens After 100 Trips with Caulk-Studded Roller

NOTE 5—These impact points should be approximately 2 in. (51 mm) apart. When flooring is in strip form or in small tile, it may be necessary to use two or more pieces to satisfy that requirement. If so, they should be selected to be as nearly alike as possible.

20. Apparatus

20.1 The equipment suitable for measuring the falling-ball impact resistance is shown in Fig. 5. Essential parts are described in 20.1.1-20.1.4.

20.1.1 *Ball*—The impacting unit is a 2-in. (51-mm) diameter steel ball weighing 1.18 lb (535 g).

NOTE 6—A suitable ball may be a bearing ball of that diameter.

20.1.2 *Base*—The base shall be flat and smooth, of heavy mass, rigidly supported, oriented so the top surface is horizontal, and preferably of steel.

20.1.3 *Holding and Release Mechanism*— The mechanism for positioning and holding the steel ball until released at desired height of drop shall be such that at release of the ball no horizontal motion is imparted. The free fall of the ball must be vertical. Shown in Fig. 5 is an electromagnetic unit with an electric switch that releases when the magnetic head unit reaches a preset height. If such a unit is not provided, some means must be provided to accurately measure and set the distance from the surface of the specimen to the bottom of the ball at the desired increments of 6 in. (152 mm).

20.1.4 *Indentation Measuring Device*—The indentation measuring device should be as shown in Fig. 5 or its equivalent. The measuring device shall be assembled from the components listed in 20.1.4.1-20.1.4.3.

20.1.4.1 A hollow cylinder with approximately the following dimensions: outside diameter of barrel 1⁵/₁₆ in. (49 mm), base 1¹/₁₆ in. (43 mm), height of base, outside 1/2 in. (12 mm), inside 1/4 in. (6 mm); inside diameter of barrel 3/8 in. (9.5 mm) (to accommodate collar of micrometer), base 1³/₁₆ in. (30 mm); and ~~over-all~~ overall height 2¹/₈ in. (54 mm).

20.1.4.2 A dial micrometer of the type with graduations of 0.001 in. (0.025 mm), with a stem of sufficient length so indentations of about 1/4 in. (6 mm) can be measured.

20.1.4.3 The tip (anvil) of the micrometer shall be the standard rounded one, 1³/₄ in (5 mm) diameter, with the spherical end surface of 1¹/₆₄ in. (4.4 mm) radius.

21. Procedure

21.1 *Increments of Drop*—The height of the drops shall progress in increments of 6 in. (152 mm). Make the initial drop from 6 in. (measured from the surface of the specimen to the bottom of the steel ball). Make each drop at a fresh, undisturbed location on the surface of the specimen at least 2 in. (51 mm) from any previous indentation. Catch the steel ball on the rebound after each drop, so that each indentation is the result of a single impact. Make drops up to a height of 6 ft (1.8 m).

21.2 *Indentation Measurements*—Set the dial of the indentation measuring tool at zero by placing it at about five different places on the surface of the specimen and averaging the differences in surface irregularity as indicated by the readings of the dial. Measure the depth of indentation after each drop by placing the center of the indentation-measuring device over the center of the impact area.



FIG. 5 Apparatus for Falling-Ball Indentation Test for Wood or Wood-Base Finish Flooring