



SLOVENSKI STANDARD

SIST EN 1011-8:2018

01-julij-2018

Nadomešča:
SIST EN 1011-8:2005

Varjenje - Priporočila za varjenje kovinskih materialov - 8. del: Varjenje železove litine

Welding - Recommendations for welding of metallic materials - Part 8: Welding of cast irons

Schweißen - Empfehlungen zum Schweißen metallischer Werkstoffe - Teil 8: Schweißen von Gusseisen

(standards.iteh.ai)

Soudage - Recommandations pour le soudage des matériaux métalliques - Partie 8 : Soudage des fontes

<https://standards.iteh.ai/catalog/standards/sist/1787402a-3273-4ccf-91c4-3eb1a154244d/sist-en-1011-8-2018>

Ta slovenski standard je istoveten z: EN 1011-8:2018

ICS:

25.160.10	Varilni postopki in varjenje	Welding processes
77.140.80	Železni in jekleni ulitki	Iron and steel castings

SIST EN 1011-8:2018

en,fr,de

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 1011-8:2018

<https://standards.iteh.ai/catalog/standards/sist/1787402a-3273-4ccf-91c4-3eb1a154244d/sist-en-1011-8-2018>

EUROPEAN STANDARD

EN 1011-8

NORME EUROPÉENNE

EUROPÄISCHE NORM

May 2018

ICS 25.160.10

Supersedes EN 1011-8:2004

English Version

Welding - Recommendations for welding of metallic materials - Part 8: Welding of cast irons

Soudage - Recommandations pour le soudage des matériaux métalliques - Partie 8 : Soudage des fontes

Schweißen - Empfehlungen zum Schweißen metallischer Werkstoffe - Teil 8: Schweißen von Gusseisen

This European Standard was approved by CEN on 22 January 2018.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents	Page
European foreword.....	4
1 Scope	6
2 Normative references	6
3 Terms and definitions	6
4 Abbreviations and symbols	7
5 Provision for quality assurance requirements	7
6 Storage, handling and identification of parent metal	7
7 Fusion welding processes	7
8 Welding consumables	8
8.1 General	8
8.2 Storage and handling	8
9 Equipment	8
9.1 General	8
9.2 Ancillary equipment	8
10 Fabrication	9
11 Weld preparation	9
11.1 Assembly for welding	9
11.2 Finishing welds and repair welds	10
12 Fabrication and inspection feasibility	10
13 Pre-heat temperature and interpass temperature	10
14 Tack welds	10
15 Temporary attachments	10
16 Run-on plates and run-off plates	10
17 Arc strikes	10
18 Weld run sequence	10
19 Heat input	10
20 Welding procedure specification (WPS)	11
21 Traceability	11
22 Elimination of distortion or inherent stresses	11
23 Inspection and testing	11
24 Quality requirements	11
25 Non-conformance and corrective actions	11
26 Distortion	11
27 Post weld heat treatment	11
28 Surface cleaning and treatment	11

Annex A (normative) Quality requirements	12
A.1 General	12
A.2 Requirements for fusion welding	12
Annex B (informative) Welding technology for cast iron castings	20
B.1 General	20
B.2 Preparation for welding.....	20
B.3 Backing bar	20
B.4 Heat and temperature distribution	20
Bibliography	24

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN 1011-8:2018](https://standards.iteh.ai/catalog/standards/sist/1787402a-3273-4ccf-91c4-3eb1a154244d/sist-en-1011-8-2018)

<https://standards.iteh.ai/catalog/standards/sist/1787402a-3273-4ccf-91c4-3eb1a154244d/sist-en-1011-8-2018>

EN 1011-8:2018 (E)**European foreword**

This document (EN 1011-8:2018) has been prepared by Technical Committee CEN/TC 190 “Foundry Technology”, the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by November 2018 and conflicting national standards shall be withdrawn at the latest by November 2018.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 1011-8:2004.

Within its programme of work, Technical Committee CEN/TC 190 requested CEN/TC 190/WG 13 “Welding of cast iron” to prepare the following revision of the standard:

EN 1011-8:2004, *Welding — Recommendations for welding of metallic materials — Part 8: Welding of cast irons*.

The following modifications were made:

- iTeh STANDARD PREVIEW**
(standards.iteh.ai)
- “Normative references”: revised;
 - Clause 7: Process designations brought in accordance with EN ISO 4063 and reference number “143” added;
 - Subclause 8.2: Title modified in “**Storage and handling**”;
 - Title of Subclause 10.1 removed;
 - Subclauses 10.2 and 10.3 removed;
 - Title of Subclause 11.1 changed in “Assembly for welding” and Subclause revised;
 - Title of Clause 12 changed in “Fabrication and inspection feasibility”;
 - Title of Clause 17 changed in “Arc strikes” and clause revised;
 - Title of Clause 18 changed in “Weld run sequence”;
 - List in Clause 20 extended;
 - Title of Clause 22 changed in “Elimination of distortion or inherent stresses” and clause revised;
 - Title of Clause 25 changed in “Non-conformance and corrective actions”;
 - Clause 27 revised;
 - Title of Clause 28 changed in “Surface cleaning and treatment” and clause revised;
 - Annex A, Table A.2, No. 7, 3rd column: standard text “Smooth edge rounding is not an undercut.” added as footnote c;

- Annex A, A.2.2, below 2nd paragraph: heading inserted "Numbers and types of external imperfections with reference to Table A.2" and the text "Types of imperfections 1, 2, 3, 4, 5 and 6 especially for joint welding." added as NOTE in Table A.2;
- Table B.1, "Column: Method", "row: Oxy acetylene welding (311)", last cell, entry changed in "Welding rods OII EN 12536";
- Bibliography revised.

This is one of a series of European Standards for requirements for fusion welding of metallic materials with the general title *Welding — Recommendations for welding of metallic materials*.

This series of European Standards is composed of the following parts:

- *Part 1: General guidance for arc welding;*
- *Part 2: Arc welding of ferritic steels;*
- *Part 3: Arc welding of stainless steels;*
- *Part 4: Arc welding of aluminium and aluminium alloys;*
- *Part 5: Welding of clad steel;*
- *Part 6: Laser beam welding;*
- *Part 7: Electron beam welding;*
- *Part 8: Welding of cast irons.*

iTeH STANDARD PREVIEW
(standards.iteh.ai)
SIST EN 1011-8:2018
<https://standards.iteh.ai/catalog/standards/sist/1787402a-3273-4ccf-91c4-3eb1a154244d/sist-en-1011-8-2018>

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

EN 1011-8:2018 (E)**1 Scope**

This document specifies the requirements for fusion welding of unalloyed and low-alloy cast iron castings produced in accordance with:

- EN 1561, *Founding — Grey cast irons*;
- EN 1562, *Founding — Malleable cast irons*;
- EN 1563, *Founding — Spheroidal graphite cast irons*.

This document does not apply to the joint welding of cast iron castings to other materials.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 1011-1:2009, *Welding - Recommendations for welding of metallic materials - Part 1: General guidance for arc welding*

EN ISO 4063, *Welding and allied processes - Nomenclature of processes and reference numbers (ISO 4063)*

EN ISO 15609-1, *Specification and qualification of welding procedures for metallic materials - Welding procedure specification - Part 1: Arc welding (ISO 15609-1)*

EN ISO 15609-2, *Specification and qualification of welding procedures for metallic materials - Welding procedure specification - Part 2: Gas welding (ISO 15609-2)*-8:2018

<https://standards.iteh.ai/catalog/standards/sist/1787402a-3273-4ccf-91c4-3eb1a154244d/sist-en-1011-8-2018>

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

3.1 production welding

welding carried out during manufacturing before final delivery to the end user

Note 1 to entry: It includes joint welding and finishing welding (see 3.2 and 3.3).

3.2 joint welding

production welding used to assemble components together to obtain an integral unit

3.3 finishing welding

production welding carried out in order to ensure the agreed quality of the casting

3.4**repair welding**

welding carried out after final delivery of the casting to the end user

3.5**homogeneous filler metal**

filler metal which results in a deposited metal with the same type of microstructure as the parent metal

3.6**semi-homogeneous filler metal**

filler metal which results in a deposited metal with a steel-type microstructure

3.7**non-homogeneous filler metal**

filler metal which results in a deposited metal with a microstructure that differs from the parent metal

3.8**cast welding**

welding by pouring liquid metal into a specially prepared groove in a casting

3.9**liquid metal welding**

cast welding with additional use of a metal arc welding process

4 Abbreviations and symbols

For the purposes of this document, the abbreviations and symbols given in EN 1011-1:2009 shall apply.

5 Provision for quality assurance requirements

For the purposes of this document, the provisions for quality assurance requirements given in Annex A shall apply.

6 Storage, handling and identification of parent metal

Storage and handling shall be carried out in such a manner that the parent metal is not adversely affected. Provision shall be made for correct identification, e.g. grade and storage.

7 Fusion welding processes

Fusion welding processes shall be either one or a combination of the following welding processes with their reference number in accordance with EN ISO 4063:

- 111 Manual metal arc welding (metal arc welding with covered electrode);
- 114 Self-shielded tubular cored arc welding;
- 12 Submerged arc welding;
- 13 Gas-shielded metal arc welding;
- 141 TIG welding with solid filler material (wire/rod);

EN 1011-8:2018 (E)

- 143 TIG welding with tubular cored filler material (wire/rod);
- 15 Plasma arc welding;
- 185 Magnetically impelled arc welding;
- 24 Flash welding;
- 311 Oxy acetylene welding;
- 42 Friction welding;
- 71 Aluminothermic welding;

and additionally:

- cast welding;
- liquid metal welding.

Other fusion welding processes shall be agreed between the manufacturer and the purchaser by the time of acceptance of the order.

8 Welding consumables

ITeH STANDARD PREVIEW
(standards.iteh.ai)

8.1 General

An appropriate filler metal (see 3.5, 3.6 and 3.7) shall be selected in accordance with the requirements of the weld and the welding process.

Any special recommendations given by the manufacturer and/or supplier of the welding consumables shall be taken into account.

Welding consumables (e.g. filler metals, gases and fluxes) shall conform to the appropriate European and/or International Standards, as applicable (see Annex B, Tables B.1 and B.2).

It can be necessary to manufacture appropriate filler metals, especially for oxy acetylene and liquid metal welding. To avoid confusion, such products shall be identified.

8.2 Storage and handling

For the purposes of this European Standard the storage and handling requirements given in EN 1011-1:2009 shall apply.

9 Equipment**9.1 General**

For the purposes of this European Standard, the equipment requirements given in EN 1011-1:2009 shall apply.

9.2 Ancillary equipment

If applicable, the ancillary equipment shall include:

- a) power source for welding equipment and additional machinery;
- b) facilities for joint preparation;

- c) facilities for preheating and post-weld heat treatment including temperature measurement equipment;
- d) cranes and other handling equipment;
- e) peening equipment;
- f) electrode baking ovens, electrode bags, etc. for handling filler metals;
- g) cleaning equipment;
- h) equipment for destructive and non-destructive testing;
- i) fixtures and welding jigs;
- j) personal protection equipment directly connected with welding.

10 Fabrication

When welding cast iron castings, consideration shall be given to the:

- need for trained and approved welders;
- need for a responsible welding co-ordinator;
- casting geometry;
- temperature control;
- stress conditions caused by welding;
- material behaviour;
- working conditions;
- inspection requirements.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN 1011-8:2018](#)

standards.iteh.ai/catalog/standards/sist/1787402a-3273-4ccf-91c4-3eb1a154244d/sist-en-1011-8-2018

Selection of the requirement category (see EN ISO 3834-1) is recommended and should be carried out with due consideration of any special operating conditions and joint strains together with any economic factors.

Prior to welding, there shall be an agreement made between the parties concerned which includes the requirements for finishing welding, joint welding and repair welding, as applicable.

If applicable, finishing and/or repair welding methods to correct casting non-conformities shall be carefully planned and prepared.

The casting surface to be welded shall be checked by a suitable non-destructive test method, in order to ensure sound material after complete removal of any casting non-conformity.

11 Weld preparation

11.1 Assembly for welding

Assembly shall be carried out in accordance with EN 1011-1:2009.

In addition, weld preparation should meet the recommendations given in Table B.1 and Table B.2.